MILITARY SPECIFICATION

SACK, SHIPPING, PAPER, EMESIS

1. SCOPE

1.1 This specification covers a disposable sack (airsick bag) of the self-opening style.

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

SPECIFICATIONS

Federal

UU-B-36	Bags, Paper (Grocers).
PPP-B-585	Boxes, Wood, Wirebound.
PPP-B-601	Boxes, Wood, Cleated-Plywood.
PPP-B-621	Boxes, Wood, Nailed and Lock-Corner.
PPP-B-636	Box, Fiberboard.
PPP-T-76	Tape, Pressure-Sensitive Adhesive Paper, (For Carton Sealing).

Military

MIL-L-10547	Liners, Case, and Sheet, Overwrap, Water-Vaporproof or Waterproof, Flexible.

FSC 8105

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:10Z
Check the source to verify that this is the current version before use.

STANDARDS

Military

MIL-STD-105	Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129	Marking for Shipment and Storage.

(Copies of specifications and standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

TECHNICAL ASSOCIATION OF THE PULP AND PAPER INDUSTRY

T 401 M-53	Fiber Analysis of Paper and Paperboard.
T 402 M-49	Conditioning Paper and Paperboard for Testing.
T 403 M-53	Bursting Strength of Paper.
T 404 OS-61	Tensile Breaking Strength of Paper and Paperboard.
T 408 OS-61	Rosin in Paper and Paperboard.
T 410 OS-61	Basis Weight of Paper and Paperboard.
T 414 M-49	Internal Tearing Resistance of Paper.
T 630 M-61	Melting Point (Plateau of Petroleum Wax.)

(Application for copies should be addressed to the Technical Association of the Pulp and Paper Industry, 155 East 44th Street, New York 17, N. Y.)

3. REQUIREMENTS

3.1 Material.

3.1.1 Paper. Paper for both the inner and outer walls of the bag shall be rosin-sized, natural-brown kraft paper composed of 100 percent unbleached sulfate fibers. The inner wall shall be waxed employing a pure paraffin wax having a minimum melting point of 124° Fahrenheit (F.) and a maximum melting point of 132° F. Paper shall be tested for presence of rosin size and 100 percent unbleached sulfate fibers as specified in 4.4.1.

Source: https://assist.dla.mil -- Downloaded: 202610-21T08:10Z
Check the source to verify that this is the current version before use.

3.1.1.1 Physical and mechanical requirements. The paper for the inner and outer walls of the bag shall conform to the following physical and mechanical requirements. The properties listed for the paper for the inner wall are for the finished paper after waxing, unless otherwise specified. The tolerance for basis weight is plus or minus 5 percent. All other values are minimum. Tests shall be conducted as specified in 4.4.1.

Property	Outer wall	Inner wall
Basis weight (grams per square meter)	81.4	56.9 (before waxing) 66.7 (after waxing)
Tearing resistance, machine direction, grams	74	40
Tearing resistance, cross direction, grams	81	48
Tensile strength, machine direction, kilograms/15 mm width	7.28	5.39
Tensile strength, cross direction, kilograms/15 mm width	3.77	3.23
Bursting strength, Mullen points	35	28

3.1.2 Adhesive. The adhesive used for joining the seams of the bags shall be water-resistant and shall meet the test requirements specified in 4.4.2.

3.2 Construction. Bags shall be of double-wall construction, of the self-opening or automatic type. Construction shall conform to figure 1 of Specification UU-B-36, except that the bottom shall be to the front or back of the bag.

3.2.1 Seams. Seams shall be made with a water-resistant adhesive as specified in 3.1.2. All seams shall be joined with a continuous line of adhesive throughout their area. The minimum amount of overlap shall be 3/4 inch. The seams shall be staggered.

3.3 Dimensions. Bag shall be 11 inches in height by 7-3/4 inches in width by 5-1/4 inches in depth. Tolerances on these dimensions shall be plus or minus 1/8 inch.

3.4 Workmanship. The sacks shall be uniformly constructed and shall be free from holes, tears, cuts, splits, or other defects which might impair their usefullness, and shall conform to the levels of quality established herein.

Source: https://assist.dla.mil -- Downloaded: 202610-21T08:10Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Inspection. Inspection, as used in this specification, is defined as both examination (such as visual, auditory, etc., investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

4.1.2 Certificates of quality. When available, certificates of quality supplied by the manufacturer of the component or material, listing the specified test method and test results obtained, may be furnished in lieu of actual performance of such testing by the contractor.

4.2.1 Sampling for inspection and acceptance. Sampling for inspection and acceptance shall be performed in accordance with the provisions set forth in Standard MIL-STD-105, except where otherwise indicated. For purposes of sampling, an inspection lot for examination and tests shall consist of all material of the same size and construction submitted for delivery at one time.

4.2.2 Sampling for chemical and physical tests. Sufficient samples shall be selected from each roll of paper used in the manufacture of the sacks or from the sample sacks to perform the tests specified herein. No test results shall fall below the values specified. Melting point of the wax shall be determined on the wax used in the fabrication of the paper.

4.2.3 Inspection of materials and components. In accordance with the above, the supplier is responsible for insuring that materials and components used were manufactured, tested, and inspected in accordance with the requirements of referenced subsidiary specifications and standards to the extent specified, or, if none, in accordance with this specification. In the event of conflict, this specification shall govern.

4.3 Inspection of the end item.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:10Z
Check the source to verify that this is the current version before use.

4.3.1 Examination of the end item. Examination of the end item shall be made in accordance with the classification of defects, inspection levels, and acceptable quality levels (AQLs) set forth below. For purposes of determining sample size in accordance with Standard MIL-STD-105, the lot size for examinations under 4.3.1.1 and 4.3.1.2 shall be expressed in units of sacks, for examination under 4.3.1.3 in units of packages, and for examination under 4.3.1.4 in units of shipping containers.

4.3.1.1 Examination of the end item for defects in appearance, construction, and workmanship. The sample unit for this examination shall be one sack. No more than 5 sacks shall be drawn from any one package.

EXAMINE	DEFECT
Appearance	Surface not clean; presence of foreign or undigested matter, dirt spots, discoloration, grease, or oil spots.
	Tear, cut, puncture, split, holes (including pinholes), slits, breaks, wrinkles, or sharp creases; chafed spot or scuff mark.
	Inner wall not smoothly and uniformly waxed on both sides; evidence of bare spots, lumps, blister, flaking, or streaked wax; presence of foreign matter embedded in wax.
Construction	Construction not in accordance with contractual requirements; not a double wall construction.
	Seams poorly glued, do not adhere securely throughout their entire area; glue line not continuous throughout any joined area.
	Position of seams not as specified, not staggered.
	Folded edges not parallel or perpendicular to unfolded edges of bag.
	Sacks stick together to the extent that opening causes tearing or injury to any surface.

Source: https://assist.dla.mil -- Downloaded: 20260-21T08:10Z
Check the source to verify that this is the current version before use.

4.3.1.2 Examination of the end item for dimensional defects. The sample unit for this examination shall be one sack.

EXAMINE	DEFECT
Dimensions	Length, face width, or tuck width (as applicable) varies by more than plus or minus 1/8 inch from dimensions specified.
	Overlap less than 3/4 inch.

4.3.1.3 Examination of the end item for count. The sample unit for this examination shall be one package of sacks. The average count of sacks per package shall be not less than the specified or indicated quantity.

4.3.1.4 Examination of preparation for delivery. An examination shall be made to determine that packaging, packing, and markings comply with the requirements of section 5 of this specification. The sample unit shall be one shipping container, fully packed, selected just prior to the closing operation. Shipping containers fully prepared for delivery shall be examined for closure defects.

EXAMINE	DEFECT
Packing (as applicable)	Not level specified; not in accordance with contract requirements.
	Packaging material not as specified.
Packing	Not level specified; not in accordance with contract requirements.
	Liner material (as applicable) omitted, damaged, or not type material specified.
	Interior or exterior container material, as applicable, not as specified; closures not accomplished by specified or required methods or materials.
Strapping(steel or tape) (as applicable)	Not properly placed lengthwise, girthwise, or horizontally, or not applied in manner specified.
	Interior or exterior markings(as applicable) illegible, incorrect, incomplete, omitted, or not in accordance with contract requirements.

Source: https://assist.dla.mil -- Downloaded: 202610-21T08:10Z
Check the source to verify that this is the current version before use.

4.3.1.5 Inspection levels and acceptable quality levels (AQLs) for examinations. The inspection levels for determining the sample size, and the acceptable quality levels (AQLs) expressed in defects per 100 units, shall be as follows:

Examination Paragraph	Inspection Level
4.3.1.1	S-4
4.3.1.2	S-2
4.3.1.3	S-2
4.3.1.4	S-2

4.3.2 Testing of the end item. The end item shall be tested for the applicable characteristics as indicated in table II herein for each lot presented for examination. The sample unit for tests shall consist of five (5) complete sacks. Five sample units, randomly selected throughout the lot, shall be tested with no evidence of failure to meet the specified requirements. At the discretion of the contractor, with the exception of the seam strength characteristic, testing may be performed on samples of the waxed and unwaxed paper prior to fabrication of the sacks.

4.4 Test methods.

4.4.1 The paper for the inner and outer walls of the sacks shall be tested in accordance with the following methods of the Technical Association of the Pulp and Paper Industry (TAPPI).

Taole I.

Test Method	TAPPI Method No.
Conditioning Paper and Paperboard for Testing	T 402 M-49
Basis Weight of Paper and Paperboard	T 410 OS-61
Fiber Analysis of Paper and Paperboard	T 401 M-53
Internal Tearing Resistance of Paper	T 414 M-49
Tensile Breaking Strength of Paper and Paperboard	T 404 OS-61
Bursting Strength of Paper	T 403 M-53
Rosin in Paper and Paperboard	T 408 OS-61

Source: https://assist.dla.mil -- Downloaded: 20260-21T08:10Z
Check the source to verify that this is the current version before use.

4.4.2 Water-resistance of adhesive (seam strength). The adhesive shall be tested for resistance to water as follows: Cut strip 1 inch wide across the longitudinal seam, adjusting the length so that both sheetings will extend approximately 1-1/2 inches beyond one edge of the cemented joints. Immerse the test specimens in 1 to 2 inches of distilled water at 73° plus or minus 3.5° for 24 hours. Remove one specimen at a time, blot off the excess water with blotting paper, and test before removing the next strip. To test, grasp the projecting ends of the sheetings with one thickness between the thumb and forefinger of each hand, the forefinger resting against the cemented joint, one on each side. Separate the joint, noting the percent of separation that occurs without fiber failure of the paper surface. Test not less than 10 strips for each determination. Separation of the adhesive from more than 25 percent of the surface of either ply without visible fiber failure shall be judged as failure of a specimen, and failure of more than 10 percent of the specimens shall be reported as failure of the adhesive.

Source: https://assist.dla.mil -- Downloaded: 20260-21T08:10Z
Check the source to verify that this is the current version before use.

Table II - Test Procedures

Outer wall:	Requirement paragraph	(1)	(2)	(3)	(4)
Stock (sulfate content)	3.1.1	4.4.1	Avg of 2	-	percent
Sizing	3.1.1	4.4.1	1	X	
Basis weight	3.1.1.1	4.4.1	1 (Avg of 5 sheets)	-	grams/square meter
Bursting strength	3.1.1.1	4.4.1	6 (3 on each side)	-	points
Tearing resistance:	3.1.1.1	4.4.1			
Machine direction			Avg of 5	-	grams
Cross direction			Avg of 5	-	grams
Tensile strength:	3.1.1.1	4.4.1			
Machine direction			Avg of 10	-	kilograms/15 mm width
Cross direction			Avg of 10	-	kilograms/15 mm width
Seam strength	3.1.2	4.4.2	10	X	

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:10Z
Check the source to verify that this is the current version before use.

Table II - Test Procedure (Cont'd)

Inner wall:	Requirement paragraph	(1)	(2)	(3)	(4)
Stock					
Sulfate content(before waxing)	3.1.1	4.4.1	Avg of 2	-	percent
Sizing (before waxing)	3.1.1	4.4.1	1	X	-
Basis weight:	3.1.1.1	4.4.1	Avg of 2	-	grams/square meter
(before waxing)					
Waxed			Avg of 5 sheets		grams/square meter
Bursting strength	3.1.1.1	4.4.1	6 (3 on each side)	-	points
Tearing resistance:	3.1.1.1	4.4.1			
Machine direction			Avg of 5	-	grams
Cross direction			Avg of 5	-	grams
Tensile strength:	3.1.1.1	4.4.1			
Machine direction			Avg of 10	-	kilograms/15 mm width
Cross direction			Avg of 10	-	kilograms/15 mm width
Melting point of wax	3.1.1	4.4.3	Avg of 3	-	To within 0.1°F.
Seam strength	3.1.2	4.4.2	10	X	-

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:10Z
Check the source to verify that this is the current version before use.

NOTE: (1) Test methods, as referenced, shall be performed in accordance with procedures referenced in the applicable TAPPI Standards, except that the stipulation as to the number of specimens to test, number of determinations to perform, or number of results to report shall be as indicated in this table. All testing shall be performed under atmospheric conditions as described in TAPPI Standard T402 M-49.

(2) The average result shall consist of the representative result obtained from each sample unit and combined into a single result.

(3) If failure is indicated, report either description of failure or numerical point of failure, as applicable

(4) Test reports shall include all values on which results are based.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:10Z
Check the source to verify that this is the current version before use.

4.4.3 Test for melting point. The melting point of the wax used for the inner wall shall be determined in accordance with Technical Association of the Pulp and Paper Industries (TAPPI) Method T 630 M-61, Melting Point (Plateau) of Petroleum Wax.

5. PREPARATION FOR DELIVERY

5.1 Packaging.

5.1.1 Unit of issue. One (1) sack, as specified, constitutes one unit of issue.

5.1.2 Unit packaging. Unit packaging shall not be required.

5.2 Packing.

5.2.1 Level B.

5.2.1.1 Exterior container. Five hundred (500) units shall be packed in a carton constructed in accordance with Specification PPP-B-636, type 1, class 1. Closure of carton shall be in accordance with appendix of box specification.

5.2.2 Level A.

5.2.2.1 Exterior container. Five hundred (500) units packed for the degree of protection specified for Level B in 5.2.1.1 shall be overpacked in an exterior container designed for type 2 load, and constructed in accordance with Specification PPP-B-585, style 3, for class 3 use; PPP-B-601, table II, using type III, class 1 plywood; PPP-B-621, table III; or PPP-B-636, type I, class 2.

5.2.2.2. Case liner. Each level A wood box shall be lined with a waterproof case liner conforming to Specification MIL-L-10547. Closure and sealing shall conform to applicable paragraphs of appendix thereto.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:10Z
Check the source to verify that this is the current version before use.

5.2.2.3 Closure. Closure of each level A fiberboard box shall be as specified in the appendix of Specification PPP-B-636. In addition, all seams, including manufacturer's joint, shall be closed by tape conforming with the requirements of Specification PPP-T-76. The tape shall be not less than 2 inches wide. Three strips shall be applied to both top and bottom so that all seams and joints are covered their full length. Tape applied over the lengthwise seams shall extend a minimum of 2 inches onto each of the end panels. Tape applied over the end edge seams shall extend a minimum of 2 inches along the side and top, and side and bottom panels.

5.2.2.4 Strapping. Strapping, when required, shall be in accordance with applicable paragraphs of appendix thereto.

NOTE: Strapping will not be required for shipment forwarded to a receiving activity within the continental limits of the United States for storage and redistribution.

5.2.3 Packing variation permitted. If the required number of units to be shipped is less than the number of units specified to be overpacked in an exterior container, such units shall be packed in an exterior container of suitable size and design, acceptable to a common carrier, which will insure safe delivery to destination.

5.3 Marking.

5.3.1 Exterior container. Exterior container shall be marked in accordance with Standard MIL-STD-129. In addition, the letter "L" shall precede the Federal stock number. One space shall be allowed between the letter "L" and the first digit of the stock number. The terms "Stock number" or "FSN" shall not be indicated.

6. NOTES

6.1 Ordering data. Procurement documents should specify the following:

(a) Number and date of the specification.

(b) Selection of applicable levels of packing required (see 5.2).

6.2 This specification does not include all types, classes, grades, sizes, etc., of the commodity indicated by the title of this specification, or which are commercially available, but is intended to cover the types, etc., which are normally procured to meet Military requirements.

Source: https://assist.dla.mil -- Downloaded: 20260-21T08:10Z
Check the source to verify that this is the current version before use.

6.3 Transportation. The transportation description applicable to this item is:

Bags, Paper, NOI, in boxes.

Carload minimum weight 36,000 pounds per Uniform Freight Classification.

Truckload minimum weight 36,000 pounds per National Motor Freight Classification.

Custodians:
Army. - MD
Navy. - BuMed
Air Force. - AFMSG
Defense Supply Agency. - DM

Review activities:
Army. - Md
Navy. - BuMed
Air Force. - AFMSG
Defense Supply Agency. - DM

Preparing activity:
Defense Supply Agency. - DM

Review information is current as of the date of this document. For future coordination of changes to this document, draft circulation should be based on the information in the current DODISS

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:10Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers/vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?
   A. GIVE PARAGRAPH NUMBER AND WORDING.

   B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?

   ☐ YES ☐ NO *(If "Yes", in what way?)*

4. REMARKS

SUBMITTED BY *(Printed or typed name and address - Optional)*

TELEPHONE NO.

DATE

DD FORM 1 JAN 72 1426 REPLACES EDITION OF 1 JAN 66 WHICH MAY BE USED

S/N 0102-014-1802

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:10Z
Check the source to verify that this is the current version before use.

FOLD

POSTAGE AND FEES PAID



OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

Commander
Defense Personnel Support Center
ATTN: DPSC-ATTS
2800 South 20th Street
Philadelphia, Pennsylvania 19101

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:10Z
Check the source to verify that this is the current version before use.