UU-C-201G
November 30, 1972
SUPERSEDING
Fed. Spec. UU-C-201F
June 7, 1963

FEDERAL SPECIFICATION

CARDBOARD AND RAILROAD BOARD

(MANILA AND WOOD)

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers manila board, railroad board, white and colored; wood cardboard, colored; and chemical wood board, colored, and reflects item requirements parallel to the specifications of the Joint Committee on Printing (JCP).

1.2 Classification.

1.2.1 Types. Cardboard and railroad board shall be of the following types, as specified (see 6.2):

Type I. Manila board (JCP Q10).
Type II. Railroad board, white and colored (JCP Q20).
Type III. Wood cardboard, colored (JCP Q40).
Type IV. Chemical wood board, colored (JCP Q50).

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

Federal Specification:

PPP-P-25 - Printing and Stationery Paper, Packaging and Packing of.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specification, Standards, and Handbooks and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington, DC 20402.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Washington, DC, Atlanta, Chicago, Kansas City, MO, Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, Wash.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications, Standards, and Handbooks from established distribution points in their agencies.)

Military Standard:

MIL-STD-105-Sampling Procedures and Tables for Inspection by Attributes.

(Copies of Military Specifications and Standards required by contractor in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

2.2 Other publications. The following document forms a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply.

Joint Committee on Printing Publication:
Government Paper Specification Standards.

(Copies may be obtained from the Superintendent of Documents, U. S. Government Printing Office, Washington, DC 20402.)

3. REQUIREMENTS

3.1 Standard sample. The color, finish and cleanliness, as applicable, shall conform to the standard sample as adopted by the Joint Committee on Printing and as furnished by the contracting officer.

3.2 Material. Types of board shall conform to the requirements for the applicable items set forth in the Government Paper Specification Standards.

3.2.1 Type I. Type I shall conform to JCP Q10, "Manila Board".

3.2.2 Type II. Type II shall conform to JCP Q20, "Railroad Board, White and Colored" for the applicable thickness (see 6.2).

3.2.3 Type III. Type III shall conform to JCP Q40, "Wood, Cardboard, Colored".

3.2.4 Type IV. Type IV shall conform to JCP Q50, "Chemical Wood Board, Colored."

3.3 Sheets. Paper shall be furnished in the size(s) ordered (see 6.2) and must be flat, trimmed square on four sides with clean, smooth edges, and evenly jogged. Size and trim tolerance shall conform to the requirements set forth in the Government Paper Specification Standards.

3.4 Grain. Direction of grain on flat paper shall be as ordered (see 6.2).

3.5 Color. The color of the board shall be as specified and shall conform to the standard sample for the applicable type (see 3.1).

3.5.1 Type I shall be manila.

3.5.2 Type II shall be ash gray, blue, green, orange, or red, as specified (see 6.2).

3.5.3 Type III shall be blue, buff, green, melon, or pink, as specified (see 6.2).

3.5.4 Type IV shall be blue or tan, as specified (see 6.2).

3.6 Workmanship. All types of board covered by this specification shall be clean, free from dirt spots, oil spots, shives, foreign matter and shall be uniform in color.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may use his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspection set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.1.1 Sampling for inspection and test. Sampling for inspection and test shall be performed in accordance with MIL-STD-105, except where otherwise indicated. For sampling purposes, a lot shall consist of the same type, color, and thickness of board offered for inspection at one time.

4.2 Inspection of components and materials. In accordance with 4.1 above, the supplier is responsible for insuring that components and materials used were manufactured, examined and tested in accordance with this specification or reference subsidiary specifications and standards.

4.3 Inspection of the end item.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:20Z
Check the source to verify that this is the current version before use.

4.3.1 Examination of the end item. Examination of the end item shall be made for the defects set forth in the applicable subparagraphs at the inspection levels and acceptable quality levels (AQL's) set forth therein.

4.3.1.1 Examination of preparation for delivery. An examination shall be made to determine whether the packaging, packing, and marking requirements comply with PPP-P-25. The inspection level and acceptable quality level (AQL) shall be as stated in PPP-P-25.

4.3.1.2 Examination of the end item for average count. The lot size for the purpose of determining the sample size shall be expressed in units of packages or 500 sheets when skid packed. The average number of sheets per package or between markers when skid packed, of all sample units examined, shall be not less than specified. The inspection level shall be S-2.

4.3.1.3 Examination of the end item for dimensional defects. The sample unit for this examination shall be one sheet and the lot size for purposes of determining the sample size shall be expressed in units of sheets. The inspection level shall be S-3 and the acceptable quality level (AQL) shall be 2.5 percent defective.

Examine	Defect
Sheet size	Less than specified in length or width. Oversize by more than 1/8 inch along any edge from size specified.
Squareness	Diagonal variation exceed 1/32 inch for sheets 32 inches or less in length or exceed 1/16 inch for sheets over 32 inches in length.

4.3.1.4 Examination of the end item for visual defects.

4.3.1.4.1 Packages or reams. An examination shall be made for the defects listed below, applicable to reams or packages. The lot size for this examination shall be expressed in units of packages or reams of board and the sample size shall be selected in accordance with level S-2. The sample unit shall be one package or ream, as applicable, and the acceptable quality level (AQL) shall be 2.5 percent defective. Approximately an equal number of sample units shall be taken from each of the shipping containers selected in accordance with 4.3.1.1.

4.3.1.4.2 Skids. An examination shall be made for the defects listed below, applicable to skids. The lot size shall be expressed in units of skids and the sample size shall be selected in accordance with level S-2. The sample unit shall be one skid and the acceptable quality level (AQL) shall be 2.5 percent defective.

4.3.1.4.3 Sheets. An examination shall be made for the defects listed below applicable to sheets. The lot size for this examination shall be expressed in units of sheets and the sample size shall be selected in accordance with level S-4. The sample unit shall be one sheet and the sample size shall be accumulated by taking approximately an equal number of sheets, in consecutive order from each of the reams or packages selected in accordance with 4.3.1.4.1. The acceptable quality level (AQL) shall be 2.5 defects per hundred sheets for major defects, and the AQL for minor defects shall be 25 defects per hundred sheets.

Examine	Defect
Packages, reams, or skids, as applicable	
Color and finish	Variation within ream, skid, or package. Variation between reams, skids, or packages.
Workmanship, packages, reams and skid only	Wavy edges, uneven, ragged or crushed edges. Torn or partial sheet; spliced sheets.
Sheets	
Major	
Appearance	Presence of creases, wrinkles, tears, or holes larger than 1.5 mm in area.
Color and finish, as applicable	Does not compare favorably with the standard

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

Table cont.

Minor	
Cleanliness	Does not compare favorably with the standard sample with respect to: dirt specks larger than 0.5 mm in area; oil, size, color, or slime spots; foreign matter; lumps; fuzz or loose particles, scabs or scale.

4.3.2 Testing of the end item. The end item shall be tested for the applicable characteristics specified in section 3 for each lot presented for examination for each type, thickness, size or color of paperboard. The characteristics tested and methods of testing shall be as specified in the Government Paper Specification Standards. The lot size shall be expressed in units of shipping containers and the inspection level for determining the sample size shall be S-2. The sample unit shall consist of not less than 3000 square inches of paperboard and not more than one sample unit shall be taken from any one ream, package, or skid. The test report shall include all values upon which the results are based and there shall be no failure to meet the lot average, sample unit, or composite average.

5. PREPARATION FOR DELIVERY

5.1 The cardboard and the railroad board shall be prepared for delivery in accordance with PPP-P-25, as specified (see 6.2).

6. NOTES

6.1 Intended use. The intended use for each type shall be as specified in the Government Paper Specification Standards for the applicable type.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

(a) Title, number and date of this specification.
(b) Type and size required (1.2.1 and 3.3).
(c) Thickness required (3.2.2).
(d) Color (3.5).
(e) Grain direction (3.4).
(f) Selection of applicable levels of packaging and packing (see 5.1).

6.3 When paper will be used in air conditioned pressrooms, the level of temperature and relative humidity should be stated in the invitation for bids.

6.4 The Department of Defense has waived coordination of this document.

MILITARY INTEREST	Preparing Activity
Army-GL	GSA-FSS

☆U. S. GOVERNMENT PRINTING OFFICE : 1973 O - 514-175 (249)

Orders for this publication are to be placed with the General Services Administration, acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents referenced herein. Price 10 cents each.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:20Z
Check the source to verify that this is the current version before use.