INTERIM FEDERAL SPECIFICATION

PAPER, CORRECTION

This Interim Federal Specification was developed by the Standardization Division, Federal Supply Service, General Services Administration, Washington, D. C. 20406, based upon currently available technical information. It is recommended that Federal agencies use it in procurement and forward recommendations for changes to the preparing activity at the address shown above.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers pressure-sensitive correction paper with liner.

1.2 Classification.

1.2.1 Type and grade. The correction paper shall be of one type and one grade.

1.2.2 Form and size. The paper shall be furnished in sheets or rolls, as specified, and shall be of the size specified. (See 3.6 and 6.2)

2. APPLICABLE SPECIFICATIONS AND STANDARDS

2.1 The following specifications and standards, of the issues in effect on date of invitation for bids, form a part of this specification to the extent specified herein:

Federal Specifications:

GG-B-60 -- Ball Point Pen, Single Cartridge.
TT-I-528 -- Ink, Drawing, Waterproof, Black.
TT-I-544 -- Ink, Marker, Felt Tip.
UU-P-31 -- Paper, General Specifications and Methods of Testing.
UU-P-121 -- Paper, Bond and Writing, White and Colored.
UU-P-268 -- Paper, Kraft, Untreated, Wrapping.
PPP-B-636 -- Box, Fiberboard.
DDD-R-311 -- Ribbons, Typewriter.

Federal Standards:

Fed. Std. No. 102 -- Preservation, Packaging and Packing Levels.
Fed. Std. No. 123 -- Marking for Domestic Shipment (Civilian Agencies).

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, D.C., 20402.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Washington, D.C., Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, Los Angeles, and Seattle, Wash.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standards:

MIL-STD-105 -- Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 -- Marking for Shipment and Storage.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

3. REQUIREMENTS

3.1 Material. The correction paper shall be made from such material as to insure compliance with the requirements of this specification.

3.1.1 Paper stock. At least 90 percent of the pulp content shall be bleached fiber; the remainder may be unbleached fiber. The paper shall be uniform in texture and suitably sized. The paper shall conform to the physical requirements of table I. (See 4.4.1.)

TABLE I. Physical requirements of paper stock without adhesive.

Property	Value	UU-P-31 Method No.
Basic weight, 25x38-500, lbs, minimum	42	110
Brightness, average, percent, minimum	80	111
Bursting strength, average, points, minimum	20	112
Finish (smoothness), felt side, average, seconds	100-150	130
Opacity, average, percent, minimum	87	151
Tensile breaking strength, average, minimum:		171
Machine direction, lbs./inch width.	20	
Cross direction, lbs./inch width.	10	

3.1.2 Adhesive. The adhesive shall be pressure sensitive and shall require no moisture, heat, or other preparation prior to application. The adhesive shall cause the paper to adhere immediately and firmly to paper without wrinkling, curling, breaking, or lifting. There shall be no separation of the adhesive from the paper upon removal of the liner from the paper.

3.1.3 Liner. The liner shall be of such material as to permit easy removal of the liner from the paper without breakage or delamination of the paper or liner.

3.2 Design. The correction paper shall consist of paper stock, adhesive and liner. The paper stock shall be coated on the wire side with adhesive which shall be covered with three strips of liner running parallel to the longer dimension. The liner strips shall not overlap each other. Alternatively, the adhesive may be applied in three strips running parallel to the longer dimension and the outer edges of the paper stock may be uncoated. If applied in three strips and without a coating on the outer edges, the adhesive shall cover not less than 9-3/4 inches of the overall width dimension.

3.3 Adhesion. When tested in accordance with method 100 of UU-P-31, the average initial tack of the adhesive shall be not less than 60.0 ounces per inch width; and the average tack of the adhesive after aging for ten days at 140°F shall be not less than 70.0 ounces per inch width. (See 4.4.2.1.)

3.4 Color. The working surface of the paper shall be white and shall show no discoloration after aging for 10 days at 140° F. (See 4.4.2.2)

3.5 Performance.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

3.5.1 Ruling and writing qualities. The working surface of the paper shall accept without spreading, feathering, bleeding, skipping, or ragged edges, ink from the following:

Ball point pen
Drawing ink
Typewriter ribbons

There shall be no appreciable spreading or feathering of lines made with felt tip marker ink. (See 4.4.2.3.)

3.5.2 Erasing qualities. The working surface shall have good erasing qualities. After an erasure there shall be no appreciable spreading or feathering of lines made with drawing ink. (See 4.4.2.4.)

3.6 Form and size. The correction paper shall be furnished in sheets or rolls as specified (see 1.2.2 and 6.2).

3.6.1 Sheets. Sheets shall be 16 inches ± 1/8 inch long by 10-1/2 inches ± 1/8 inch wide.

3.6.2 Rolls. The paper shall be furnished in continuous lengths without joining or splicing. The paper shall be wound on cores to form rolls not exceeding 4 inches in diameter. The liner shall be on the outside of the roll. The wall thickness of the core shall be not less than 0.130 inch. The minimum length of the paper shall be 25 feet. The width of the paper shall be 10-1/2 inches ± 1/8 inch.

3.8 Workmanship. The adhesive shall be a smooth uniform coating. Edges of the correction paper shall be straight, true and unbroken. The correction paper shall be free from spots, wrinkles, pinholes, and any other defects which affect appearance or which might impair satisfactory performance.

4. SAMPLING, INSPECTION, AND TEST PROCEDURES

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.2 Sampling.

4.2.1 Lot. For purposes of sampling, a lot shall consist of all correction paper of the same form and size offered for inspection at one time.

4.2.2 Sampling for visual and dimensional examination. A random sample of paper shall be taken from each lot in accordance with MIL-STD-105, inspection level I, Acceptable Quality Level (AQL) 6.5 percent defective. The sample unit shall be one package or one roll of paper.

4.2.3 Sampling for test.

4.2.3.1 Paper stock. A sample of the paper stock, of sufficient size to perform the tests specified in 4.4.1, shall be furnished by the supplier with each delivery.

4.2.3.2 Correction paper. A random sample of packages and rolls shall be taken from each lot in accordance with MIL-STD-105, inspection level S-1, Acceptable Quality Level (AQL) 6.5 percent defective. The sample unit shall be one package or one roll of paper.

4.2.4 Sampling for preparation for delivery. Sampling shall be in accordance with MIL-STD-105. For examination of interior packaging the sample unit shall be one shipping container fully prepared for delivery, and selected at random just prior to the closing operations. Defects of closure listed shall be examined on shipping containers fully prepared for delivery. The lot size shall be the number of shipping containers in the end item inspection lot. The inspection level shall be II and the Acceptable Quality Level (AQL) shall be 4.0 defects per hundred units.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

4.3 Visual and dimensional examination. Samples taken in accordance with 4.2.2 shall be examined for defects listed in table II. Any sample containing one or more defects shall be rejected.

TABLE II. Classification of defects

Examine	Defects
Material:	
Paper stock:	Not uniform in texture. Not suitably sized.
Adhesive:	Not in conformance with 3.1.2.
Liner:	Not in conformance with 3.1.3.
Design:	Correction paper does not consist of paper stock, adhesive and liner. Wire side of paper stock not coated with adhesive. Adhesive not covered with three liner strips running parallel to the longer dimension. Liner strips overlap each other. When applied in three strips, the adhesive covers less than 9-3/4 inches of the overall width dimension.
Form and size:	Not furnished in sheets or rolls, as specified.
Sheets:	Do not conform with size and tolerance.
Rolls:	Not in continuous lengths. Not wound on cores to form rolls. Rolls exceed 4 inches in diameter. Liner not on outside of rolls. Wall thickness of core less than 0.130 inch. Do not conform with size and tolerance.
Workmanship:	Adhesive coating not smooth and uniform. Edges of correction paper not straight, true, and unbroken. Correction paper not free from spots, wrinkles, pinholes, and other defects affecting appearance or impairing satisfactory performance.

4.4 Tests.

4.4.1 Paper stock tests. Samples taken in accordance with 4.2.3.1, shall be subjected to the following tests described in UU-P-31. Failure of any sample to pass any of the tests shall be cause for rejection of the lot.

TEST	METHOD
Atmospheric conditions	102
Basis weight	110
Brightness	111
Bursting strength	112

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

TEST	METHOD
Finish (smoothness)	130
Opacity	151
Tensile breaking strength	171
Fiber identification and quantitive determination	300

4.4.2 Correction paper tests. Samples taken in accordance with 4.2.3.2, shall be subjected to the following tests under the atmospheric conditions described in method 102 of UU-P-31. Any sample failing one or more tests shall be considered defective.

4.4.2.1 Adhesion. The initial tack of the adhesive shall be determined as described in method 100 of UU-P-31. Next, the samples shall be placed in a circulating air oven maintained at a temperature of $140^{\circ} \pm 3.6^{\circ}$ F. for a period of ten days. Then the tack of the adhesive shall be determined as described in method 100.

4.4.2.2 Color. After completion of test described in 4.4.2.1, compare the color of the working surface of the exposed samples with the color of the working surface of unexposed paper (see 3.4).

4.4.2.3 Ruling and writing qualities. This test shall be conducted on the working surface of the correction paper without removing the liner. Draw five parallel lines, each six inches long and 1/2-inch apart with a drawing pen set at an opening of 0.003 inch $\pm$ 0.001 inch and black drawing ink conforming to TT-I-528. Draw five lines, each six inches long and 1/2-inch apart with blue felt tip marker ink conforming to TT-I-544. Write six five-letter words with dark blue ink from a ball point pen conforming to GG-B-60. Thoroughly clean the type faces of an electric typewriter equipped with a medium-inked black nylon ribbon conforming to grade A of DDD-R-311. The typewriter shall be equipped with a platen having a hardness of approximately 93 when measured with a Shore durometer, Type A. Type the entire keyboard, small letters, capitals, numerals, and other characters twice in unrelated order. Examine the lines and writing for the requirements of 3.5.1.

4.4.2.4 Erasing qualities. This test shall be conducted on the working surface of the correction paper with black drawing ink conforming to TT-I-526, a drawing pen, and an electric erasing machine (capacity 7,500 RPM) equipped with an eraser of medium abrasive texture. Remove the liner and apply the correction paper to chemical wood bond, 40 pound paper (Basis weight: 17 X 22 inches - 1,000 sheets) conforming to type IV of UU-P-121. Set the drawing pen at an opening of 0.003 inch $\pm$ 0.001 inch and draw three parallel lines, each six inches long and 1/2-inch apart. After an interval of not less than five minutes erase the lines. Redraw lines over the erased area. Examine the lines for the requirements of 3.5.2.

4.5 Inspection of preparation for delivery requirements. An inspection shall be made to determine that packaging, packing and marking comply with the requirements in section 5 of this specification. Defects shall be scored in accordance with table III.

TABLE III. Classification of preparation for delivery defects.

Examine	Defects
Markings (exterior and interior)	Omitted; incorrect; illegible; improper size, location, sequence, or method of application.
Materials	Any component missing, or damaged.
Workmanship	Inadequate application of components such as incomplete closure of container flaps, loose strapping. Distortion of container.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

5. PREPARATION FOR DELIVERY

For civil agency procurement the definitions and application of the levels of packaging and packing shall be in accordance with Fed. Std. No. 102.

5.1 Packaging. Packaging shall be level A, B, or C as specified (see 6.2).

5.1.1 Levels A and B.

5.1.1.1 Sheets. One hundred (100) sheets of paper shall be compactly wrapped in kraft paper conforming to UU-P-268, grade B, having a minimum basis weight of 60 pounds per ream (24 x 36 - 500). The wrapper shall be sealed with an adhesive or gummed paper tape. Adhesive shall be applied in such a manner that no contact of adhesive is made with the paper being packaged.

5.1.1.2 Rolls. Each roll shall be compactly wrapped in kraft paper conforming to UU-P-268, grade B, having a minimum basis weight of 60 pounds per ream (24 x 36 - 500). The wrapper shall be sealed with an adhesive or gummed paper tape. Adhesive shall be applied in such a manner that no contact of adhesive is made with the paper being packaged.

5.1.2 Level C. The sheets or rolls shall be packaged in accordance with the suppliers commercial practice.

5.2 Packing. Packing shall be level A, B, or C as specified (see 6.2).

5.2.1 Level A.

5.2.1.1 Sheets. Sheets of correction paper, packaged as specified in 5.1, shall be packed in a box conforming to PPP-B-636, V3c. Each box shall be closed, waterproof sealed with tape, and reinforced with bands of filament tape in accordance with the appendix to the box specification.

5.2.1.2 Rolls. Rolls of correction paper, packaged as specified in 5.1, shall be packed as specified in 5.2.1.1.

5.2.2 Level B.

5.2.2.1 Sheets. Ten unit packages of correction paper (1000 sheets), packaged as specified in 5.1, shall be packed in a box conforming to PPP-B-636, class domestic. Closure shall be in accordance with method I of the appendix to the box specification.

5.2.2.2 Rolls. Twenty-four (24) rolls of correction paper, packaged as specified in 5.1, shall be packed in a box conforming to PPP-B-636, class domestic. Closure shall be in accordance with method I of the appendix to the box specification.

5.2.3 Level C. The sheets or rolls shall be packed to insure carrier acceptance and safe delivery at destination in containers complying with the rules and regulations applicable to the mode of transportation.

5.3 Marking.

5.3.1 Civil agencies. In addition to markings required by the contract or order, the interior packages and shipping containers shall be marked in accordance with Fed. Std. No. 123.

5.3.2 Military activities. In addition to markings required by the contract or order, the interior packages and shipping containers shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 Intended use. The correction paper is intended for use in masking unwanted information on duplicating masters and graphic presentations, and in the preparation of printed labels.

6.2 Ordering data. Purchasers should exercise any desired options offered herein and procurement documents should specify the following:

(a) Title, number, and date of this specification.
(b) Form and size required (see 1.2.2 and 3.6).
(c) Levels of packaging and packing required (see 5.1 and 5.2).

GSA DC 66-2895

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.