UU-P-121N
February 14, 1973
SUPERSEDING
Int. Fed. Spec. UU-P-00121M
March 2, 1970 and
Fed. Spec. UU-P-121L
December 2, 1965

FEDERAL SPECIFICATION

PAPER, BOND AND WRITING; WHITE AND COLORED

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers cotton or linen and chemical wood and writing paper, and reflects item requirements parallel to the specifications of the Joint Committee on Printing (JCP).

1.2 Classification.

1.2.1 Types. Bond and writing paper, in accordance with this specification, shall be furnished in the following types, as specified (see 6.2).

Types:

I - 100 percent, white bond (JCP-G80).
II - 50 percent, white bond (JCP-G70).
III - 25 percent, bond white and colored (JCP-G40).
IV - Chemical wood, white bond (JCP-G10).
V - Writing, white and colored (JCP-D10 and JCP-D20).
VI - White translucent bond (JCPG20).
VII - 25 percent white translucent bond (JCP-G50).
VIII - 25 percent opacified bond, white and colored (JCP-G60).

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of the specification to the extent specified herein.

Federal Specifications:

UU-P-268 - Paper, Kraft, Untreated, Wrapping.
PPP-P-25 - Printing and Stationery Paper, Packaging and Packing of.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, DC, Atlanta, Chicago, Kansas City, MO, Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, WA.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:19Z
Check the source to verify that this is the current version before use.

Military Standards:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.

(Copies of Military Specifications and Standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply.

Joint Committee on Printing Publications

Government Paper Specification Standards

(Applications for copies should be addressed to the Superintendent of Documents, U.S. Government Printing Office, Washington, D.C. 20402.)

National Motor Freight Traffic Association, Inc., Agent:

National Motor Freight Classification.

(Application for copies should be addressed to the American Trucking Associations, Inc., Tariff Order Section, 1616 P Street, N.W., Washington, DC 20036.)

Uniform Classification Committee, Agent:

Uniform Freight Classification.

(Application for copies should be addressed to the Uniform Classification Committee, Room 1106, 222 South Riverside Plaza, Chicago, IL 606066.)

3. REQUIREMENTS

3.1 Standard sample. The color, formation, finish and cleanliness, as applicable, shall conform to the standard sample as adopted by the Joint Committee on Printing and as furnished by the contracting officer.

3.2 Material.

3.2.1 Type I. Type I bond paper shall conform to the requirements of G80, "100 percent White Bond" set forth in the Government Paper Specification Standards for the applicable basis weight.

3.2.2 Type II. Type II bond paper shall conform to the requirements of G70, "50 percent White Bond" set forth in the Government Paper Specification Standards for the applicable basis weight.

3.2.3 Type III. Type III bond paper shall conform to the requirements of G40, "25 percent Bond, White and Colored" set forth in the Government Paper Specification Standards for the applicable basis weight.

3.2.4 Type IV. Type IV bond paper shall conform to the requirement of G10, "Chemical Wood White Bond" set forth in the Government Paper Specification Standards.

3.2.5 Type V. Type V writing paper shall conform to the requirements of D10, "Writing, White and Colored" set forth in the Government Paper Specification Standards for the applicable basis weight.

3.2.5.1 The requirements of D20 are the same as for D10.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:19Z
Check the source to verify that this is the current version before use.

3.2.6 Type VI. Type VII translucent bond paper shall conform to the requirements of G50, "25 percent White Translucent Bond" set forth in the Government Paper Specification Standards.

3.2.7 Type VII. Type VII translucent bond paper shall conform to the requirements of G50, "25 percent White Translucent Bond" set forth in the Government Paper Specification Standards.

3.2.8 Type VIII. Type VIII opacified bond paper shall conform to the requirements of G60, "25 percent Opacified Bond, White and Colored" set forth in the Government Paper Specification Standards.

3.3 Basis weight. The basis weight (or substance) of bond or writing papers in accordance with this specification shall be expressed in pounds per 1000 sheets of a 17 by 22 inch basic size.

3.3.1 Types I and II papers shall be 32 or 40 pounds as specified (see 6.2).

3.3.2 Type III paper shall be 24, 32, or 40 pounds as specified (see 6.2).

3.3.3 Type IV paper shall be 40 pounds.

3.3.4 Type V paper shall be 24, 32, 36, or 40 pounds as specified (see 6.2).

3.3.5 Type VI paper shall be 26 pounds.

3.3.6 Types VII and VIII shall be 32 pounds.

3.4 Size and trim.

3.4.1 Sheets. Paper shall be furnished in the size(s) ordered (see 6.2) and must be flat, trimmed square on four sides with clean, smooth edges, and evenly jogged. Size and trim tolerance shall conform to the requirements set forth in the Government Paper Specification Standards.

3.4.2 Rolls. Roll width shall be not less than specified (see 6.2) and not more than 1/8 inch oversize and shall have clean trimmed edges. Roll diameter shall be as specified with a tolerance of minus 1 inch or plus 1/2 inch (see 6.2). Roll assembly shall conform to the requirements set forth in the Government Paper Specification Standards.

3.5 Grain. Direction of the grain on flat paper shall be as ordered (see 6.2).

3.6 Color. All types of paper in accordance with this specification shall be furnished in white. Type III paper shall also be yellow in substance 24 and blue, buff, green, pink, salmon, or yellow in substance 32, as specified (see 6.2). Type V paper shall also be blue, buff, green, pink, salmon, or yellow, as specified (see 6.2). Type VIII shall also be buff, as specified (see 6.2).

3.7 Workmanship. All types of paper in accordance with this specification shall be clean, free from dirt spots, oil spots, shives, foreign matter, and shall be uniform in color. The sheets shall be free from holes, tears, cuts, folds, scuff marks, lint, fuzz, or any particles that will fluff or pile on the blanket under normal press conditions. There shall be no splices within a sheet and there shall be no partia sheets.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to insure that supplies and services conform to prescribed requirements.

4.1.1 Inspection. Sampling for inspection shall be performed in accordance with MIL-STD-105, except where otherwise indicated.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:19Z
Check the source to verify that this is the current version before use.

4.2 Component and material inspection. In accordance with 4.1 above, components and materials shall be tested in accordance with all the requirements of referenced specifications, drawings and standards unless otherwise excluded, amended, modified, or qualfified in this specification or applicable purchase documents.

4.3 Inspection of the end item.

4.3.1 Examination of the end item. The end item shall be examined for the defects set forth in the applicable subparagraphs at the inspection levels and acceptable quality level (AQLs) shown in table I. Each inspection lot sampled shall consist of one type, size, weight, and color of bond or writing paper.

TABLE I. Sampling procedure

Examination paragraph	Lot size units	Sample unit	Inspection level	AQL % defective
4.3.1.1	Shipping containers	Shipping	S-2	1/
4.3.1.1.2	Rolls	Roll	S-1 2/	2.5
4.3.1.2	Reams or rolls	Ream or roll	S-2 2/	---
4.3.1.3.1	Sheets	Sheet	S-4	1.5
4.3.1.3.2	Rolls	Roll	S-3	2.5
4.3.1.4	Rolls	Roll	S-1 2/	2.5
4.3.1.5	As specified in paragraph 4.3.1.5			

1/ Acceptable quality level shall be as specified in PPP-P-25.
2/ Rolls for these examinations shall be from those selected for examination in 4.3.1.3.2.

4.3.1.1 Examination of preparation for delivery.

4.3.1.1.1 Sheet form. An examination shall be made to determine that the packaging, packing, and marking requirements comply with PPP-P-25, except that the inspection level shall be S-2.

4.3.1.1.2 Rolls. An examination shall be made to determine that markings, materials, and workmanship comply with the requirements of section 5 applicable to rolls. The sample unit for this examination shall be one roll fully prepared for delivery.

Examine	Defect
Markings	Incorrect; incomplete; illegible; omitted; of improper size, location, sequence, or method of application.
Material	Any nonconforming component; component missing, damaged or otherwise defective.
Workmanship	Inadequate application of component such as: incomplet closure, headers missing, loose or inadequate sealing.

4.3.1.2 Examination of the end item for average count (sheets) or weight (rolls), as applicable. The average number of sheets per ream, or between markers when skid packed, of all sample units examined shall be not less than the specified quantity. The average weight per roll (including non-returnable core, plugs, and wrapper) shall be not less than the indicated weight.

4.3.1.3 Examination of the end item for dimensional defects.

4.3.1.3.1 Sheets. The sample unit for this examination shall be one sheet. The number of sheets comprising the sample size, as specified in table I for this examination shall be made up by taking two consecutive sheets from one ream or 500 sheet unit (to count as two sample units). Examine each sheet.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:19Z
Check the source to verify that this is the current version before use.

Examine	Defect
Sheet size	Less than specified in length or width.
Sheet 8-1/2 x 14 inches or less	Oversize by more than 1/16 inch along any edge, from size specified.
Sheets over 8-1/2 by 14 inches	Oversize by more than 1/8 inch along any edge, from size specified.
Squareness	Diagonal variation exceed 1/32 inch for sheets 32 inches or less in length or exceeds 1/16 inch for sheets over 32 inches in length.
Consecutive sheets 8-1/2 by 14 inches or less	Successive sheets differ from each other by more than 1/64 inch in either dimension.

4.3.1.3.2 Rolls. The sample unit for this examination shall be one roll.

Examine	Defect
Width	Less than specified, oversize by more than 1/8 inch.
Diameter	More than 1 inch less or 1/2 inch greater than specified.

4.3.1.4 Examination of the end item, in roll form, for construction and workmanship defects. The sample unit for this examination shall be one roll.

Examine	Defect
Assembly of roll	Not suitably restrained to prevent unwinding.
	Material not wound evenly and tightly on roll, causing soft or uneven edges or telescoping of the roll.
	Material not wound on a substantial core; core broken, collapse, crushed, or mutilated.
	Plugs, when specified, omitted from one or both ends; do not fit properly.
Unwinding of roll	Paper slips over core when unwinding.
	More than 3 splices per roll.
	Splice comes apart during unwinding. Splice not evenly and neatly made; not flagged, does not cover entire width of material. Splice material not as specified.
Workmanship	Not trimmed clean; ragged, torn, uneven or crushed edges.

4.3.1.5 Examination of the end item for visual defects.

4.3.1.5.1 Reams. An examination shall be made for the defects listed in table II, applicable to reams. The lot size for this examination shall be expressed in units of reams of paper and the sample size shall be selected in accordance with level S-2. The acceptable quality level (AQL) for ream defects shall be 2.5 defects per hundred reams. Approximately an equal number of sample reams shall be taken from each of the shipping containers selected in accordance with 4.3.1.1.1. Sample reams shall be selected from not less than 5 shipping containers.

4.3.1.5.2 Skids. An examination shall be made for the defects listed in table II, applicable to skids. The lot size shall be expressed in units of skids and the sample size shall be selected in accordance with level S-2. The acceptable quality level shall be 2.5 defects per hundred skids.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:19Z
Check the source to verify that this is the current version before use.

4.3.1.5.3 Rolls. An examination shall be made for the defects listed in table II, applicable to rolls and roll paper. The rolls selected for this examination shall be those selected for examination in 4.3.1.4. Not less than 10,000, plus or minus 100 square inches of roll paper shall be examined for the defects applicable to roll paper. The required area of paper shall be selected by taking equal portions of paper from each of the rolls in the sample size. The acceptable quality level shall be 2.5 defects per hundred rolls for roll defects. The lot shall be acceptable if the number of defects applicable to roll paper, does not exceed 3 defects per 10,000 square inches of paper for major defects and 40 defects per 10,000 square inches of paper for minor defects.

4.3.1.5.4 Sheets. An examination shall be made for the defects listed in table II, applicable to sheets. The lot size shall be expressed in units of sheets and the sample size shall be selected in accordance with level S-4. The sheets for this examination shall be accumulated by taking approximately an equal number of sheets in consecutive order, from each of the reams selected in accordance with 4.3.1.5.1 or the skids selected in accordance with 4.3.5.2. The acceptable quality level (AQL) shall be 2.5 defects per hundred sheets for major defects, all types of bond and writing paper and the AQL for minor defects shall be 25 defects per hundred sheets for types I, II, III, VII, and VIII paper and 40 defects per hundred sheets for types IV, V, and VI paper.

TABLE II. Classification of defects

Examination	Defects
Reams, skids, or rolls, as applicable	
Color and finish	Variation within ream, skid or roll. Variation between reams, skids, or rolls.
Workmanship, reams and skids only	Wavy edges, uneven, ragged or crushed edges. Torn or partial sheets; spliced sheets. Sheets stuck together.
Sheets or roll paper	
Major	
Appearance	Presence of creases, wrinkles, tears, or holes larger than 1.5 mm in area.
Color, finish and formation	Does not compare favorably with the standard sample.
Watermark (types I, II, III, VII and VIII)	Watermark missing; indistinct; incomplete.
Minor	
Cleanliness	Does not compare favorably with the standard sample with respect to: dirt specks larger than 0.5 mm in area; oil, size, color, or slime spots; foreign matter; lumps, fuzz or loose particles, scabs or scale.

4.3.2 Testing of the end item. The end item shall be tested for the applicable characteristics as specified in section 3 for each lot presented for examination for each type, weight, size, or color of paper. The characteristics testing and methods of testing shall be as specified in the Government Paper Specification Standards. The lot size shall be expressed in units of shipping containers and the inspection level for determining the sample size shall be S-2. The sample unit shall consist of not less than 3000 square inches of paper and not more than one sample unit shall be taken from any one ream, skid, or roll. The test report shall include all values upon which the results are based and there shall be no failure to meet the specification requirements.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A, B, or C as specified (see 6.2).

5.1.1 Level A. Sheets of bond or writing paper shall be packaged in accordance with level A, packaging requirements of PPP-P-25, for "Paper, Bond" or "Paper, Writing", of the applicable type, substance, and size.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:19Z
Check the source to verify that this is the current version before use.

5.1.2 Level B. Sheets of bond or writing paper shall be packaged in accordance with Level B, packaging requirements of PPP-P-25, for "Paper, Bond" or "Paper, Writing" of the applicable type, substance size.

5.1.3 Level C. Sheets of bond or writing paper shall be packaged in accordance with the industry's practice.

5.2 Packing. Packing shall be level A, B, or C as specified (see 6.2).

5.2.1 Level A.

5.2.1.1 Sheets. Sheets of bond or writing paper, packaged as specified in 5.1, shall be packed in accordance with the level A, packing requirements of PPP-P-25, for "Paper, Bond" or Paper, Writing" of the applicable type, substance, and size.

5.2.1.2 Rolls. Each roll of bond or writing paper (see 3.4.2) shall be wrapped overall with a repulpable wax laminated kraft paper. The wrapper shall consist of a minimum of 20 pounds of wax, contained between two sheets of not less than 75 pound kraft paper; weights based on a 500 sheet, 24 by 36 inch ream. The wrapper shall be closed at the ends by means of inside and outside headers of the same material as the wrapper. Seams and headers shall be sealed with an adhesive in accordance with the wrapper manufacturers recommendations.

5.2.2 Level B.

5.2.2.1 Sheets. Sheets of bond or writing paper, packaged as specified in 5.1, shall be packed in accordance with the level B packing requirements of PPP-P-25 for "Paper, Bond" or "Paper, Writing" of the applicable type, substance, and size.

5.2.2.2 Rolls. Each roll of bond or writing paper (see 3.4.2), shall be wrapped overall with kraft paper having minimum basis weight of 80 pounds per ream in accordance with UU-P-268. The wrapper shall be closed at the ends by means of inside and outside headers. The seams of the wrapper and the headers shall be securely sealed with an adhesive commerically used for this purpose.

5.2.3 Level C. Sheets of bond or writing paper, packaged as specified in 5.1, or rolls of bond paper (see 3.4.2), shall be packed in a manner to insure carrier acceptance and safe delivery at destination at the lowest tranportation rate for such supplies. Shipments shall be in accordance with rules or regulations of carriers applicable to the mode of tranportation.

5.3 Marking. The marking shall be in accordance with PPP-P-25.

6. NOTES.

6.1 Intended use. The intended use for each type of paper shall be as specified in the Government Paper Specification Standards for the applicable type and weight.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents.

(a) Title, number, and date of this specification.
(b) Type and size required (see 1.2.1 and 3.4).
(c) Basis weight, as specified (see 3.3).
(d) Grain direction (see 3.5).
(e) Color (see 3.6).
(f) Pressroom conditions (see 6.3).
(g) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).
(h) Special markings (see 5.3).

6.3 When paper will be used in air-conditioned pressrooms the level of temperature and relative humdity maintained shall be in the invitation to bid (see 6.2).

6.4 Copies of full size watermark design will be supplied upon request to the Joint Committe on Printing.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:19Z
Check the source to verify that this is the current version before use.

6.5 The Department of Defense has waived coordination of this specification.

MILITARY INTEREST:

User activity

Army - GL

Preparing Activity:

GSA-FSS

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See Section 2 of this specification to obtain extra copies and other documents referenced herein.

GSA DC-01903647

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:19Z
Check the source to verify that this is the current version before use.