UU-P-134E
March 19, 1974
SUPERSEDING
Fed. Spec. UU-P-134D
April 7, 1969

FEDERAL SPECIFICATION

PAPER, WRAPPING, WET-WAXED

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers wet-waxed paper suitable for use in food packaging, self-sealing application and general wrapping purposes (see 6.1).

1.2 Classification. Wet-waxed wrapping paper shall be of the following types, as specified (see 6.2).

Type I - Paraffin wax.
Type II - Wax-polyethylene blend.
Type III - General purpose.
Type IV - Light weight.

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

Federal Specification:

PPP-B-636 - Boxes, Shipping, Fiberboard.

Federal Standard:

FED-STD-123 - Marking for Domestic Shipment (Civil agencies).

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, US Government Printing Office, Washington, DC 20402.

FSC 8135

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

(Single copies of this specification and other Federal specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers, at the General Services Administration Regional Offices in Boston, New York, Washington, DC, Atlanta, Chicago, Kansas City, MO, Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, WA.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standards:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.

(Copies of specifications, standards, drawings, and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

LAWS AND REGULATIONS

21 CFR 121 - Food Additive Resulting From Contact With Containers or Equipment and Food Additives Otherwise Affecting Food.

(The Code of Federal Regulations (CFR) and the Federal Register (FR) are for sale on a subscription basis by the Superintendent of Documents, US Government Printing Office, Washington, DC 20402. When indicated, reprints of certain regulations may be obtained from the Federal agency responsible for issuance thereof.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply:

Technical Association of the Pulp and Paper Industry (TAPPI) Publications

T 401 - Fiber Analysis of Paper and Paperboard.
T 402 - Conditioning Paper and Paperboard for Testing.
T 403 - Bursting Strength of Paper.
T 404 - Tensile Breaking Strength of Paper and Paperboard.
T 405 - Wax in Paper.
T 410 - Basis Weight of Paper and Paperboard.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

T 414 - Internal Tearing Resistance of Paper.
T 460 - Air Resistance of Paper.
T 630 - Melting Point (Plateau) of Petroleum Wax.

(Application for copies of TAPPI testing methods may be obtained from the Technical Association of the Pulp and Paper Industry, 1 Dunwoody Park, Atlanta, GA 30341.)

National Motor Freight Traffic Association, Inc., Agent

National Motor Freight Classification

(Application for copies should be addressed to the American Trucking Associations, Inc., Tariff Order Section, 1616 P Street, N.W., Washington, DC 20036.)

Uniform Classification Committee, Agent

Uniform Freight Classification

(Application for copies should be addressed to the Uniform Classification Committee, Room 1106, 222 South Riverside Plaza, Chicago, IL 60606.)

(Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

3. REQUIREMENTS

3.1 Material. The paper shall consist of 100 percent bleached chemical woodpulp and shall be wet-waxed.

3.1.1 Paper. The paper before waxing shall have a basis weight of 25 pounds ± 5 percent (24 x 36 - 500), except, that for type IV, the basis weight shall be 16.75 pounds ± 5 percent (24 x 36 - 500). After waxing, the paper shall conform to the requirements of table I, when tested as specified in 4.3.2.

TABLE I - Physical characteristics after waxing

Bursting strength, points, minimum (except type IV)	12
Tearing resistance, grams, each direction, minimum (except type IV)	17
Tensile strength, pounds/inch width, each direction, minimum	5
Porosity, seconds, minimum (type IV only)	150

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:20Z
Check the source to verify that this is the currenversion before use.

3.1.2 Wax.

3.1.2.1 Type I. Type I paper shall contain not less than 10.0 and not more than 15.0 pounds (24 x 36 - 500) of fully refined paraffin wax having a melting point of not less than 132°F. The total surface wax on both sides of the paper shall be not less than 5.0 pounds (24 x 36 - 500) and neither side shall contain less than 2.5 pounds. The total wax content shall be determined as specified in 4.4.2, total surface coating as specified in 4.4.1, and the melting point of the wax determined as specified in 4.2.1.

3.1.2.2 Type II. Type II paper shall contain not less than 12.0 and not more than 16.0 pounds (24 x 36 - 500) of a coating composed of a blend of polyethylene and wax. The blend shall contain not less than 2 percent polyethylene. When specified (see 6.2), the supplier shall furnish a certificate of compliance stating that the coating contains 2% polyethylene. The coating composition shall have a melting point of not less than 132°F. The total surface coating on both sides of the paper shall be not less than 5.0 pounds (24 x 36 - 500) and neither side of the paper shall contain less than 2.5 pounds. The total content of coating shall be determined as specified in 4.4.2, the total surface coating as specified in 4.4.1.

3.1.2.3 Type III. Type III paper shall be wet-waxed on both sides with a total of not less than 8.0 pounds nor more than 12.0 pounds (24 x 36 - 500) of fully refined paraffin wax having a melting point of not less than 132°F. The total content of wax shall be determined as specified in 4.4.2, and the melting point shall be determined as specified in 4.2.1.

3.1.2.4 Type IV. Type IV paper shall contain between 3 and 5 pounds (24 x 36 - 500) of paraffin wax having a melting point of not less than 132°F. After waxing, the paper shall have a basis weight of between 18.75 and 21.75 pounds (24 x 36 - 500).

3.1.3 Material. All materials used in the manufacture of wet-waxed wrapping paper shall conform to the provisions of the Federal Food, Drug, and Cosmetic Act, and General Regulations for Its Enforcement. When specified (see 6.2), the supplier shall furnish a certificate of compliance covering this requirement.

3.2 Form. Wet-waxed wrapping paper shall be furnished in sheet or roll form, as specified (see 6.2).

3.2.1 Sheets. Sheets shall be clean-cut with dust free edges and shall be square to the extent that difference between the two diagonals does not exceed 1/8-inch. The length and width of the sheets shall be as specified (see 6.2), with a tolerance of ± 1/8-inch.

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:20Z
Check the source to verify that this is the currenversion before use.

3.2.2 Rolls. Roll width shall be as specified (see 6.2 and table II), with a tolerance of ± 1/8-inch, and shall have clean cut edges. The cores shall be protected at each end with fitted plugs having a 1-inch diameter center hole with a minus 0, plus 1/8-inch tolerance.

3.2.2.1 Types I, II and III. The diameter of the rolls shall be as specified (see 6.2 and table II), with a tolerance of ± 1/4-inch. The wrapping paper shall be tightly and smoothly wound on non-returnable cores having an inside diameter of 3 ± 1/16-inches and shall be restrained to prevent unwinding. The length of the cores shall be equal to the specified width of the roll material with a tolerance of ± 1/8-inch.

3.2.2.2 Type IV. The wrapping paper shall be uniformly and smoothly wound on paperboard cores. The core shall have sufficient rigidity to prevent distortion of the roll while in use. The roll shall be 125 feet ± 1 foot.

3.2.3 Splices. Sheets shall contain no splices. Rolls 10-inches and under in diameter shall contain not more than 2 splices; rolls over 10-inches in diameter shall contain not more than 3 splices. There shall be a minimum of 20-yards between splices. Splices shall be evenly and neatly made over the entire roll width and shall not come apart during unwinding. Splices shall be made with colored tape.

TABLE II - Roll dimensions

	Width(inches)	Weight(pounds)	Diameter(inches)
Type I	16	60	11-1/2
	18	40	9
	18	70	11-1/2
Type III	24	62	9-1/2
Type IV	11.75		

3.3 Blocking (except type IV). The finished product shall not block nor adhere to itself when tested as specified in 4.3.2.

3.4 Dispensing (type IV only). The paper shall unroll without adhering to itself when dispensed (see 4.3.1.3).

3.5 Transparency. Wet-waxed paper shall be sufficiently transparent to permit the reading of 6 point printed matter over which the wax paper is placed (see 4.3.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

3.6 Workmanship. The wet-waxed paper shall be clean, continuously coated with wax, and free from any holes, tears, cuts, creases, chafed spots, scuff marks, lumps, blisters, flaking, or streaked wax. The edges of the paper shall be clean cut. The paper shall be odorless.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Certificate of compliance. Where certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

4.1.2 Inspection. Sampling for inspection shall be performed in accordance with MIL-STD-105, except where otherwise indicated hereinafter.

4.2 Component and material inspection. In accordance with 4.1 above, components and materials shall be inspected and tested in accordance with all the requirements of referenced specifications, and standards unless otherwise excluded, amended, or qualified in this specification or applicable purchase documents.

4.2.1 Sampling and testing of components. The components materials shall be tested for the applicable characteristics in table III. The sample unit shall be 10 randomly selected 100 square-inch sheets of unwaxed paper base stock and 4-ounces of paraffin wax or polyethylene-wax blend, as applicable. The lot size for purposes of determining the sample size shall be expressed in units of rolls for the paper and in units of pounds for the paraffin wax or polyethylene wax blend. The sample size shall be drawn at inspection level S-1 of MIL-STD-105. There shall be no failure to the composite, sample unit, or lot average requirements. A composite shall consist of equal portions taken from all sample units and combined in a single sample.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

TABLE III - Instructions for testing of components

Characteristic	Specification reference		Requirements applicable to		Number determinations per sample unit	Results reported as	
	Requirement	Test method	Individ unit	Lot aver		Pass or fail	Numerically to nearest
Paper							
Stock 1/	3.1	T401	---	---	1 on composite		5 percent
Basis weight (24 x 36 -500) 1/	3.1.1	T410	---	X	1		0.1 pound
Wax melting point 1/	3.1.2.1 3.1.2.3 3.1.2.4	T630	X	---	1		0.1 degree
Wax blend							
Melting point 1/	3.1.2.2	T630	X	---	1		0.1 degree
Material 2/	3.1.3						

1/ Indicates TAPPI Test Method.

2/ When specified (see 6.2) the supplier shall furnish a certificate of compliance covering this requirement.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

4.3 Inspection of the end item.

4.3.1 Examination of the end item. The end item shall be examined in accordance with the defects set forth in the applicable subparagraphs at the inspection levels and acceptable quality levels (AQL's) in 4.3.1.5. Random samples shall be drawn from each lot of the end items for examination of visual, dimension, construction, count and preparation for delivery defects. The lot size for purposes of determining the sample size in accordance with MIL-STD-105 shall be expressed in units of rolls or 1,000 sheets of one type and form of waxed paper for examination in 4.3.1.1, 4.3.1.2 and 4.3.1.3 and in units of shipping containers of one type of waxed paper for the examination in 4.3.1.4.

4.3.1.1 Examination for visual defects. For examination of defects within rolls the sample unit shall be one yard the full width of the roll. No sample unit shall be taken from the first or last convolution of the roll. For examination of defects in sheets the sample unit shall be one sheet. Both sides of the material shall be examined.

Examine	Defect
Form	Not in rolls or sheets, as specified.
Appearance	Not clean; presence of any dirt, or foreign matter. Any hole, tear, cut, crease, chafed spot or scuff marks.
Workmanship	Not continuously wet-waxed on each side, bare spots, presence of any lump, blister, flaking or streaked wax. Not trimmed clean; ragged, torn, uneven or crushed edges. Not odorless.

4.3.1.2 Examination for defects in dimensions. The sample unit for this examination shall be one roll or one flat cut sheet, as applicable.

Examine	Defect
Sheets	Length or width varies from dimensions specified by more than ± 1/8 inch. Sheet not square, difference between two opposite corner diagonals exceeds 1/8 inch.
Rolls	
Width	Varies by more than ± 1/8 inch from width specified.
Diameter	Varies by more than ± 1/4 inch from diameter specified.
Core	Length varies by more than ± 1/8 inch from specified width of roll. Inside diameter less than 2-15/16 inches or more than 3-1/16 inches.
Core Plugs	Plug holes not centered; diameter of holes less than 1 inch or greater than 1-1/8 inch.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

4.3.1.3 Examination for defects in construction. The sample unit for this examination shall be one roll or one package of sheets, as applicable.

Examine	Defect
Assembly of sheets	Not evenly and uniformly stacked. Any splice within a sheet.
Rolls	
Assembly of roll	Not suitably restrained to prevent unwinding. Material not wound uniformly and smoothly causing soft or uneven edges, or telescoping of roll. Edges not clean cut; ragged, nicked, crushed or uneven edges. Core missing; core broken, collapsed, crushed or multilated. Plugs omitted from one or both ends; do not fit properly, too loose to the extent that plug(s) fall in or out of end openings.
Unwinding of roll	Does not unroll uniformly and evenly. Roll wound unevenly causing sharp creases, wrinkles or folds within a roll. When unwound, material sticks together to the extent that unrolling causes tearing to injury to any surface.
Splices in rolls	Splice(s) not evenly and neatly made; does not cover entire width of material; comes apart during unwinding. Splice not made with colored tape. More than 2 splices in any roll with a diameter of 10 inches or under; more than 3 splices in any roll with a diameter of over 10 inches. Less than 20 yards between splices.

4.3.1.4 Examination of preparation for delivery requirements. An examination shall be made to determine whether the packaging, packing, and marking complies with the section 5 requirements. Defects shall be scored in accordance with the list below. The sample unit for this examination shall be one shipping container fully prepared for delivery except that it shall not be closed. Defects of closure listed below shall be examined on shipping containers fully prepared for delivery. The lot size shall be the number of shipping containers in the end item inspection lot.

Examine	Defect
Markings (exterior and interior)	Incorrect; incomplete; illegible; omitted, or improper size, location, sequence or method of application.
Materials	Any nonconforming component; component missing, damaged or otherwise defective.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

Examine	Defect
Workmanship	Inadequate application of components; such as incomplete closure of container flaps, loose strapping, improper taping, or inadequate stapling. Bulged or distorted container.
Contents	Quantity of sheets per package or number of dispensers per container is less than indicated.
Weight	Weight of contents per container exceeds requirement.

4.3.1.4.1 Examination for count. The sample unit for this examination shall be one package of sheets. The lot shall be unacceptable if the average count per package for all packages examined is less than specified. Only one package of sheets shall be examined for count from a shipping container.

4.3.1.5 Inspection levels and acceptable quality levels (AQL's) for examination. The inspection levels, for the purpose of determining the sample size, and the acceptable quality levels (AQL's) expressed in defects per one hundred units shall be as follows:

Examination paragraph	Inspection level	AQL
4.3.1.1	I	4.0
4.3.1.2	S-2	2.5
4.3.1.3	S-2	2.5
4.3.1.4	S-2	4.0
4.3.1.4.1	S-2	N.A.

4.3.2 Testing of the end item. The end item shall be tested for the applicable characteristics in table IV. The sample unit shall be four (4) yards from roll of type I, II or III; one roll in dispenser box for type IV; or ten (10) sheets when lot is in sheets. The sample size shall be drawn at inspection level S-1 of MIL-STD-105. The lot size for purposes of determining the sample size shall be expressed in units of rolls or units of 1,000 sheets of one type and form of waxed paper. No more than one sample unit shall be taken from any one roll or package. There shall be no failure to meet the sample unit or lot average requirements. The paper shall be conditioned in accordance with TAPPI Method T402 prior to testing.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

TABLE IV - Instructions for testing of the end item

Characteristic	Specification reference		Requirements applicable to		Number determinations per sample unit	Results reported as	
	Requirement	Test method	Individ unit	Lot aver		Pass or fail 2/	Numerically to nearest 3/
Bursting strength (except type IV) 1/	Table I	T403	--	X	10 (5 on each side)		point
Tearing resistance (except type IV) 1/							
Machine direction 1/	Table I	T414	--	X	10		gram
Cross direction 1/	Table I	T414	--	X	10		gram
Tensile strength							
Machine direction 1/	Table I	T404	--	X	10		pound/inch width
Cross direction 1/	Table I	T404	--	X	10		pound/inch width
Wax content							
Type I							
Surface wax	3.1.2.1	4.4.1	X	--	2		0.1 pound
Total wax	3.1.2.1	4.4.2	--	X	1		0.1 pound
Type II							
Surface wax	3.1.2.2	4.4.1	X	--	2		0.1 pound
Total wax	3.1.2.2	4.4.2	--	X	1		0.1 pound
Type III							
Total wax	3.1.2.3	4.4.2	--	X	1		0.1 pound
Blocking (except type IV)	3.3	4.4.3	X	--	1	X	
Porosity (type IV only) 1/	Table I	T460		X			second
Transparency	3.5	4.4.4	X	--	1	X	

1/ Indicates TAPPI Test Method.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

2/ If failure is indicated report description of failure.

3/ Test reports shall include all values upon which results are based.

4.4 Test procedures.

4.4.1 Surface wax. The amount of surface wax shall be determined by finding the loss in weight of a measured area not less than 6 inches by 6 inches of paper after removal of the wax. Measure and record the exact area of the specimen to the nearest 0.01 square inch. Weigh the specimen to the nearest milligram. Lay the specimen on several sheets of paper, larger in size than the test specimen, and place on a smooth surface. Scrape the wax off one side with a sharp edged instrument such as a razor blade or the end of a microscope slide, continuing until all the wax appears to be removed. Avoid removal of paper fibers. Weigh the specimen. Repeat the process on the other side of the paper. Calculate and report the amount of wax removed, in pounds per ream (24 by 36 - 500 sheets), for each side of the paper in accordance with the following formula:

Surface wax, in pounds (24 by 36 - 500) per side,

$$\text{Side 1} = \frac{952 \times (W_o - W_1)}{\text{Specimen area (square inches)}}$$

$$\text{Side 2} = \frac{952 \times (W_1 - W_2)}{\text{Specimen area (square inches)}}$$

Where: W_o = Specimen weight in grams, before scraping.

W_1 = Specimen weight in grams, after scraping first side.

W_2 = Specimen weight in grams, after scraping second side.

4.4.2 Total wax. Select a specimen of waxed paper approximately 100 square inches in area and determine the area to the nearest 0.1 square inch. Determine the total wax content of the specimen in accordance with the procedure in TAPPI Method T405. Calculate the total wax content by the following formula:

$$\text{Total wax in pounds (24 x 36 - 500)} = \frac{952 \times \text{weight of wax (grams)}}{\text{specimen area (square inches)}}$$

4.4.3 Blocking.

4.4.3.1 Apparatus. The apparatus to conduct the blocking test shall consist of a constant temperature oven, a 6- to 8-inch desiccator, a bottom

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

support surface, a blocking weight and interleaving paper or foil. The bottom support surface shall be a 4- by 4-inch piece of plate glass or metal plate with a flat upper surface. The blocking weight shall be a brass weight or piece of glass with a flat base not less than 1.5 nor more than 3 square inches in area. The blocking weight shall be adjusted such that its weight in pounds is numerically equal to one half the base area of the blocking weight in square inches.

4.4.3.2 Procedure. Cut four representative specimens, each 1-3/4 by 2-1/4 inches, from the sample to be tested and condition for at least 1 hour at 73° ± 3.5°F. and 50 ± 2 percent relative humidity. Heat the desiccator containing a saturated solution of C. P. magnesium nitrate in the oven at 100° ± 2°F. At the end of this period, quickly assemble the specimens in the following sequence: the bottom support surface, interleaving paper or foil, four test specimens, interleaving paper or foil, and blocking weight. Place the assembly on the shelf on the heated desiccator and allow to remain at 100°F. and 50 ± 2 percent relative humidity for 24 hours ± 1 hour. At the end of this time, examine the specimens for blocking by slipping or peeling the sheets apart.

4.4.4 Transparency. Place a specimen of the waxed paper over a page of 6-point printed matter and observe the legibility of the printing.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A, B, or C, as specified (see 6.2).

5.1.1 Level A.

5.1.1.1 Types I, II, and III.

5.1.1.1.1 Roll form. Each roll of wet-waxed paper shall be wrapped overall with type III paper of this specification. The wrap shall be securely sealed.

5.1.1.1.2 Sheet form. Five-hundred or 1000 sheets, as specified (see 6.2), of wet-waxed paper of one type and size only, shall be evenly stacked and then completely wrapped with type III paper of this specification. The wrap shall be securely sealed.

5.1.1.2 Type IV. Each type IV roll of wet-waxed paper shall be packaged in a paperboard dispenser type box fitted with a full length metal serrated cutting edge.

5.1.2 Level B (Civil agencies). Wet-waxed paper shall be packaged as specified in 5.1.1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

5.1.3 Level C (commercial packaging). Wet-waxed paper shall be packaged to afford adequate protection against physical damage during shipment from the supplier to the first receiving activity. The package and the quantity per package shall be the same as that normally used by the supplier for retail distribution.

5.2 Packing. Packing shall be level A, B, or C, as specified (see 6.2).

5.2.1 Level A.

5.2.1.1 Types I, II, and III.

5.2.1.1.1 Roll form. Each roll of wet-waxed paper, packaged as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC, grade V2s of PPP-B-636. The weight limitation of the fiberboard container shall be waived. Each shipping container shall be closed in accordance with method III, waterproofed in accordance with method V, and reinforced as specified in the appendix of PPP-B-636.

5.2.1.1.2 Sheet form. Wet-waxed paper of one type and size only, packaged as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style FTC, grade V2s of PPP-B-636. The weight of contents of each shipping container shall not exceed 80-pounds. Each shipping container shall be closed, waterproofed, and reinforced in accordance with the applicable requirements specified in the appendix of PPP-B-636.

5.2.1.2 Type IV. Forty-eight rolls of wet-waxed paper, packaged as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC, grade V2s of PPP-B-636. Each shipping container shall be closed in accordance with method III, waterproofed in accordance with method V, and reinforced as specified in the appendix of PPP-B-636.

5.2.2 Level B.

5.2.2.1 Types I, II, and III.

5.2.2.1.1 Roll form. Each roll of wet-waxed paper, packaged as specified in 5.1, shall be wrapped overall with kraft paper having a minimum basis weight of 80-pounds per ream (24 by 36 - 500). The wrapper shall be closed at the ends by means of inside and outside headers of the same material as the wrapper. Seams and headers shall be securely sealed with an adhesive commercially used for this purpose.

5.2.2.1.2 Sheet form. Wet-waxed paper of one type and size only, packaged as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style FTC, type CF (variety SW) or SF, class domestic,

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

grade 275 of PPP-B-636. The weight of contents of each shipping container shall not exceed 80-pounds. Each shipping container shall be closed in accordance with the applicable requirements specified in the appendix of PPP-B-636.

5.2.2.2 Type IV. Forty-eight rolls of wet-waxed paper, packaged as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC, type CF (variety SW) or SF, class domestic, of PPP-B-636. Each shipping container shall be closed in accordance with method II as specified in the appendix of PPP-B-636.

5.2.2.3 When specified (see 6.2), the fiberboard shipping container specified in 5.2.2.1.2 and 5.2.2.2 shall be a grade V3c, V3s, or V4s fiberboard box fabricated in accordance with PPP-B-636 and closed in accordance with the appendix of the container specification.

5.2.3 Level C (commercial packing). Wet-waxed, packaged as specified in 5.1, shall be packed in a manner to insure carrier acceptance and safe delivery at destination at the lowest transportation rate for such supplies. The quantity per shipping container shall be the same as that normally used by the supplier for retail distribution. Containers shall comply with Uniform Freight Classification Rules or National Motor Freight Classification Rules, as applicable.

5.3 Marking.

5.3.1 Civil agencies. In addition to any special marking required by the contract or order, interior packages, wrapped rolls and shipping containers shall be marked in accordance with FED-STD-123.

5.3.2 Military requirements. In addition to any special marking required by the contract or order, interior packages, wrapped rolls, and shipping containers shall be marked in accordance with MIL-STD-129.

5.3.3 Special marking. Each interior package, wrapped roll and shipping container shall be legibly marked with the following legend:

"STORE IN A COOL PLACE"

6. NOTES

6.1 Intended use. Types I and II wet-waxed wrapping paper are intended for use in bread wrapping or similar applications requiring self-sealing. Type III wet-waxed wrapping paper is intended for general use in galleys, bakeries, commissaries and for over-wrapping wax-dipped packages. Type IV wet-waxed wrapping paper is intended for use in food packaging.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

(a) Title, number, and date of this specification.
(b) Type, form, and size required (see 1.2, 3.2, 3.2.1 and 3.2.2).
(c) Whether certificate of compliance is required for molecular weight of polyethylene and purity of material (see 3.1.2.2, 3.1.3 and table III).
(d) Selection of the applicable levels of packaging and packing (see 5.1 and 5.2).
(e) Quantity of sheets required per package (see 5.1.1.1.2).
(f) When weather-resistant grade fiberboard shipping containers are required for level B packing (see 5.2.2.3).

Custodians:

Army - GL
Navy - SA
Air Force - 69

Review activity:

Army - MD

Preparing activity:

Army - GL

CIVIL AGENCY COORDINATING ACTIVITIES:

COMMERCE - NBS
GSA-FSS

Project No. 8135-0403

☆ U. S. GOVERNMENT PRINTING OFFICE: 1974-603-109/986

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents referenced herein. Price 20 cents each.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.