UU-P-150b
AMENDMENT—2
MAY 15, 1961

SUPERSEDING
Int. Amend.—1
November 30, 1960

FEDERAL SPECIFICATION

PAPER, CARBON, DUPLICATING MACHINE, SPIRIT-PROCESS

This amendment, which forms a part of Federal Specification UU-P-150b, dated April 11, 1958, was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

Page 1, title: Delete and substitute:

"PAPER, CARBON, DUPLICATING MACHINE AND ADDRESSING MACHINE, (SPIRIT-PROCESS)".

Page 1, paragraphs 1.1 through 1.2.3: Delete and substitute:

1.1 Scope. This specification covers carbon paper in sheet and roll form for use in spirit process operations (see 6.1.3).

1.2 Classification.

1.2.1 *Types, grades, and classes.* The carbon paper shall be of the following types, grades, and classes, as specified in the invitation for bids (see 6.2):

Type I.—Sheets.

Grade A. — Smudge-resistant (carbon overcoated with protective film) (see 3.2).

Grade B.—Regular (carbon not overcoated with protective film) (see 3.2).

Class 1.—Completely covered with coating.

Class 2.—With an uncoated edge ½ inch wide across the short dimension of the coated paper.

Type II.—Rolls.

Grade A. — Smudge-resistant (carbon overcoated with protective film) (see 3.2).

Class 1.—Completely covered with coating.

1.2.2 *Sizes.* The carbon paper shall be furnished in sizes as specified in the invitation for bids (see 3.3 and 6.2).

1.2.3 *Colors.* Colors of carbon paper sheets shall be purple, red, blue, black, or green; colors of carbon paper rolls shall be purple, blue, or black, as specified in the invitation for bids (see 6.2).

Page 1, paragraph 2.1:

(*A*) Under *"Federal Specifications"* delete "UU–P–231—Paper; Duplicating, Copy and Master, Liquid Process" and substitute "UU–P–232—Paper, Duplicating, Copy, Liquid Process".

(*B*) Preceding *"Federal Standards"* insert the following:

"Interim Federal Specification:

UU–P–00233(GSA–FSS) — Paper, Duplicating, Master, Liquid Process."

Page 2, paragraph 3.2: Delete and substitute:

3.2 Coating. The base paper stock shall be coated with suitable waxes, dyes, and other necessary ingredients to insure the quality and performance requirements of this specification. The carbon-coated side of grade A

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

shall be overcoated with a protective film. This protective film shall keep the carbon surface from crystallizing, shall seal in the dye, and shall prevent smearing, smudging, soiling the hands, or discoloration of the master. Edges shall be sealed with a protective material to destroy permanently the aniline dyes. The back of the carbon paper shall be coated with a protective material so that the carbon will not bleed through the back of the sheets or rolls.

Page 3, paragraph 3.7: Delete and substitute new paragraphs as follows:

3.7 Rolls of carbon paper.

3.7.1 *Splices.* Splices, when necessary, shall be neatly and securely made, and shall be flagged with a red paper marker (50-lb. cover stock or equal) not pasted to the splice. The resulting uncoated area following the splice shall be kept to a minimum.

3.7.2 *Roll winding.* Carbon paper in rolls shall be evenly wound at uniform tension, and the rolls shall show no tendency to telescope under ordinary handling.

3.7.3 *Core diameter.* The diameter of cores shall be as specified in the invitation for bids, contract, or order (see 6.2).

3.8 Workmanship.—Carbon paper shall be free from defects which will affect the appearance or quality of the reproduction. Carbon coating shall be free of flaking, pinholes, wrinkles, streaks, puckers, and other surface blemishes.

Page 3, paragraph 4.3.2: Delete first sentence and substitute: "At least five sheets of grade A carbon paper and roll carbon paper of sufficient quantity for conducting test shall be tested for smudge resistance."

Page 3, paragraph 4.3.2.1: Delete second sentence and substitute the following: "The paper shall conform to Interim Federal Specification UU–P–00233(GSA–FSS) and shall be ¾ inch wide and at least 10½ inches long with grain running in the long direction."

Page 4, paragraph 4.3.3.2: Delete first sentence and substitute: "The carbon paper shall be placed in the typewriter with a sheet of master paper conforming to Interim Federal Specification UU–P–00233(GSA–FSS), with the coated side of the carbon paper in contact with the master sheet."

Page 4, paragraph 4.3.3.2.1: Delete first sentence and substitute: "A typed master, prepared as specified in 4.3.3.2, shall be placed on a spirit-process duplicating machine, using type II duplicating fluid conforming to Federal Specification O–D–825 together with copy paper in accordance with Federal Specification UU–P–232."

Page 4, paragraph 5.2.1: Add the following sentence: "Rolls of carbon paper shall be packaged as specified in the contract or order (see 6.2)."

Pages 4 and 5, paragraph 5.3.1: Add the following sentence: "Rolls of carbon paper shall be packed as specified in the contract or order (see 6.2)."

Page 5, paragraph 5.3.2: Add the following sentence: "Rolls of carbon paper shall be packed as specified in 5.3.3."

Page 5, paragraph 5.4.1, line 4: Following "No. 123" insert ", including specification classification, such as type; grade and class (for type I); size of sheet carbon, core diameter, and size of rolls of carbon paper, color, etc.;".

Page 5, paragraph 6.1: Add new subparagraph 6.1.3 as follows:

6.1.3 *Type I, carbon paper sheets,* covered herein, are intended for use in preparing paper masters on a typewriter. The prepared masters are used on spirit-process duplicating machines. *Type II, carbon paper rolls,* are intended for use in preparing paper masters on a typewriter equipped with a carbon roll holder (attachment). The prepared mas-

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

ters are used on spirit-process addressing machines.

Page 5, paragraph 6.2: Delete and substitute:

6.2 Ordering data.—Purchasers should exercise any desired options offered herein and should specify the type of carbon paper required, grade, class, and size of type I carbon-paper sheets required; color of carbon paper; core diameter and size of roll carbon paper (see 6.1.3); level of packaging and level of packing; packaging and packing required for carbon paper rolls (level A); and any special marking desired. (See 1.2.1, 1.2.2, 1.2.3, 5.2, 5.2.1, 5.3, 5.3.1, 5.4, 6.3, and 6.4.)

Page 5, paragraph 6.3: Following the first sentence, insert "Quantity and size of roll carbon paper, core diameter, etc., should be specified when sample rolls are required."

Page 5, paragraph 6.4, lines 2 and 3: Delete "six sheets" and substitute "samples".

Page 6, paragraph 6.6: Delete and substitute:

6.6 Transportation description.—Transportation descriptions and minimum weights applicable to this commodity are:

Rail:

Paper, carbon, not otherwise indexed by name.

Carload minimum weight 36,000 pounds.

Motor:

Paper, carbon, not otherwise indexed.

Truckload minimum weight 36,000 pounds, subject to Rule 34, National Motor Freight Classification.

MILITARY INTEREST:
Army—Q
Navy—S MC
Air Force.

☆ U. S. GOVERNMENT PRINTING OFFICE: 1961

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.