UU-P-158E
March 30, 1973
SUPERSEDING
Fed. Spec. UU-P-158D
July 25, 1961

FEDERAL SPECIFICATION

PAPER, CARBON, TYPEWRITER, BLACK

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers carbon paper for use with standard commercial typewriters of the manual and electrical types.

1.2 Classification.

1.2.1 Type and grade. The carbon paper shall be of one type and grade (see 6.9).

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

Federal Specifications:

L-R-350 - Ribbon, Typewriter and Composing Machine, Changeable Type-Plate Style, Polyethylene.
PPP-B-636 - Boxes, Shipping, Fiberboard.
PPP-B-676 - Boxes, Set-Up, Paperboard.
UU-P-121 - Paper, Bond and Writing, White and Colored.
UU-P-328 - Paper, Manifold.

Federal Standard:

Fed. Std. No. 123 - Marking for Domestic Shipment (Civil Agencies).

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, DC, Atlanta, Chicago, Kansas City, MO, Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, WA.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

FSC 7530

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:20Z
Check the source to verify that this is the current version before use.

Military Standards:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply.

Technical Association of the Pulp and Paper Industry (TAPPI) Standards:

T 401 - Fiber Analysis of Paper and Paperboard.
T 402 - Standard Conditioning and Testing Atmospheres for Paper, Board, Pulp Handsheets and Related Products.
T 410 - Weight Per Unit Area (Basis Weight or Substance) of Paper and Paperboard.

(Application for copies should be addressed to the Technical Association of the Pulp and Paper Industry, One Dunwoody Park, Atlanta GA 30341.)

American Society for Testing and Materials (ASTM) Standards:

F234-69 - Slip Resistance of Carbon Paper.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

National Motor Freight Traffic Association, Inc., Agent

National Motor Freight Classification.

(Application for copies should be addressed to the American Trucking Association, Inc., 1616 P Street, N.W., Washington, DC 20036.)

Uniform Classification Committee, Agent:

Uniform Freight Classification.

(Application for copies should be addressed to the Uniform Classification Committee, Room 1106, 222 South Riverside Plaza, Chicago, IL 60606.)

3. REQUIREMENTS

3.1 Material. Carbon paper shall consist of carbonizing paper coated on one side with suitable carbon or other materials necessary to meet the quality and performance requirements specified herein.

3.2 Appearance and color. The carbon coated side of the carbon paper shall be readily identifiable. The color of reproductions produced by the carbon paper shall be black.

3.3 Sizes. Carbon paper shall be furnished in the following sizes as specified (see 6.1 and 6.2):

3 x 5-1/2	8-1/2 x 11-1/2	5 x 8-1/2	8-1/2 x 14-1/2
10-1/2 x 16-1/2	11 x 17-1/2	8 x 11	16 x 21-1/2
8 x 13-1/2	17 x 22-1/2		

Dimensional tolerances shall be as specified in 3.3.1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

3.3.1 Size and trim sheets. Carbon must be flat, trimmed square on four sides with clean, smooth edges, and evenly jogged. Carbon paper must not be less than 1/16 inch undersize or more than 1/8 inch oversize in either direction.

3.4 Corners. Each sheet of carbon paper shall have cut corners located at diagonally opposite positions. The depth of cut shall be such that the normal copying area is not reduced.

3.5 Finished weight. The weight of the carbon paper shall be 20 pounds per ream (20 x 30-1000) maximum, when tested as specified in 4.2.

3.6 Tensile breaking strength. The average tensile breaking strength of the carbon paper in the machine direction shall be 6.0 pounds per inch, minimum, when tested as specified in 4.2.

3.7 Resistance to curl. Carbon paper shall not curl more than 20 percent when tested as specified in 4.2.

3.8 Resistance to smudging. Carbon paper shall not smudge because of the softness or poor abrasion resistance of the coating when tested as specified in 4.2.

3.9 Resistance to slippage. The average value for carbon paper should be 15° for backside and 20° for coated side as tested in 4.2.

3.10 Pinholes. Carbon paper shall be free from pinholes having a 0.006 to 0.007 inch diameter when tested as specified in 4.2 (for holes other than pinholes). For holes other than pinholes, see 4.4.3.

3.11 Serviceability (weardown). Carbon paper shall produce 12 sharp and legible impressions from the same area when tested as specified in 4.2. Carbon paper having average reflective density readings of less than 0.15 at the minimum serviceability line shall be rejected.

3.12 Finish. Carbon paper shall have an average initial reflective density of 0.37 to 0.52; when tested as specified in 4.2. Carbon paper having average initial reflective density readings outside of the above ranges shall be rejected (see 6.4).

3.13 Manifolding. The carbon paper shall produce at one time not less than 12 legible copies when tested as specified in 4.2.

3.14 Identification of product marking. Unless otherwise specified (see 5.3), the manufacturer's name or trademark of such known character that the manufacturer can be readily identified shall appear on the uncarbonized (not carbon coated) side of the carbon paper.

3.15 Workmanship. The workmanship shall be accordance with standard commercial practice. The carbon paper shall be free from uncoated areas, hard spots, wrinkles, flaking, welts, lumps, and any other defects or irregularities which affect its appearance and which might affect its serviceability.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsiblity for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilties or any commerical laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.1.1 Inspection. Sampling for inspection shall be performed in accordance with MIL-STD-105, except where otherwise indicated.

4.1.2 Inspection of components and materials. In accordance with 4.1 above, the supplier is responsible for insuring that components and materials used were manufactured, examined, and tested in accordance with this specification or referenced subsidiary specifications and standards.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

4.2 Inspection of the end item.

4.2.1 Examination of the end item. Samples of shipping containers, packages (unit boxes of carbon paper), and carbon paper shall be examined for the defects set forth in the applicable subparagraphs. The inspection levels and acceptable quality levels (AQLs) shall be as indicated in table below. For sampling purposes, the lot shall consist of all carbon paper sheets of the same size presented for inspection at one time.

Sampling procedure

Examination paragraph	Lot size units	Inspection level	AQL defects per 100 units
4.2.1.1	Shipping containers	S-2	4.0
4.2.2	Packages 1/	S-3	4.0
4.2.3	Carbon paper sheet 1/	S-3	10.0

1/ Packages and sheets sampled shall be from the shipping containers selected for examination in 4.2.1.1.

4.2.1.1 Examination of preparation for delivery. An examination shall be made to determine whether the packaging, packing, and marking comply with the requirements of section 5. Defects shall be scored as specified in table below. The sample unit shall be one shipping container fully prepared for delivery.

Examination of preparation for delivery

Examine	Defects
Containers	Not as specified.
Contents	Not as specified.
Markings (interior and exterior)	Ommitted; incorrect; illegible, improper size, location, incomplete sequence or method of application.
Materials	Component missing, damaged.
	Any nonconforming component.
Workmanship	Bulging or distortion of containers. Cushioning inadequate, improper or missing.
	Inadequate application of components, incomplete closure.
	Loose or inadequate sealing, strapping, or stapling.

4.2.1.1.1 Examination for closure and reinforcement of containers. When boxes are required to comply with PPP-B-636 or PPP-B-676 examination for defects in closure and reinforcement shall be in accordance with the appendix of the appropriate specification.

4.2.2 Sampling of packages. Packages of carbon paper to be examined for packaging and marking/labeling defects shall be taken from shipping containers selected in accordance with 4.2.1.1. The sample boxes shall be examined for the presence of packaging and marking/labeling defects listed in table below, except that one box shall be retained unopened for curl resistance test (see 4.3). The sample unit shall be one package of carbon paper.

Package defect

Examine	Defect
Unit box	Type, class, and style not in compliance with PPP-B-636.
Box top	Not perforated or scored as specified; or inadequately perforated or scored to provide end opening hinged cover.
Construction of box (if approved equivalent box is furnished in lieu of specification box).	Not constructed of materials equal in strength to specification box.
Cover-wrap of box	Box top not secured to base-box by a cover-wrap as specified.
Arrangement of folders in unit boxes	Slippage of papers and/or folders within the box. A tight fit not provided. Chipboard, paperboard, or fiberboard filler missing (if use is necessary to provide tight fit).
Count:	
Average number of sheets per box	Less than the number specified.
Number of sheets per folder	Less than required amount by more than 2.
Unit box marking/labeling	Missing, illegible, incorrect or incomplete.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

4.2.3 Sampling for sheet examination. Sample sheets of carbon paper shall be taken from the boxes examined in accordance with 4.2.2 The sample unit shall be one sheet of carbon paper. Not less than 5 sheets be taken from each box and examined for the applicable defects listed in table below, except that the total number of sheets shall not exceed 225.

Carbon paper defects

Examine	Defects
Wrinkles and waves	Any wrinkle or wave which can be felt when carbon paper is laid on a flat surface uncarbonized-side up and fingers are moved on the surface.
Appearance	Carbon-coated side not readily identifiable. Any carbon coating material on back of sheet. Any stain (coating material) on back of any sheet visible when viewed by reflected light at a distance of 18 inches.
Uniformity of coating (Hold so that bright light strikes back of sheet).	Any area coated so lightly as to be translucent. Light lines and nonuniform appearance of coating. Flaking.
Dimensions (sizes)	Varies from specified size by more than + 1/8 inch or -1/16 inch in any direction.
Holes, etc.	Any hole visible when sheet is laid out flat on a white opaque surface carbon side up. Any tear or cut; any crease.
Workmanship	Any crimped corners or side; lump, or knot of fiber grit. Corners not cut.
Identification of marking.	Missing or illegible (when required).

4.3 Testing of the end item. Carbon paper shall be tested for performance and the physical properties specified in section 3, for each lot submitted for inspection at one time. The sample unit shall consist of 50 sheets selected in consecutive order from one package. Five sample units randomly selected from the supping containers selected under 4.2.1.1.

Test results shall include all values upon which the results are based and there shall be no failures to meet the composite, sample unit, or lot average requirements. The composite sample shall consist of approximately equal amounts drawn from all the sample units combined into a single sample. Except where otherwise specified, all samples shall be conditioned and tested under uniform atmospheric conditions as specified in TAPPI method T 402.

TABLE I. Instructions for testing components

Characteristic	Specification Requirements	Reference Test Method or Paragraph	Requirement Applicable to	Results Reported to Nearest
Atmospheric conditions	4.3	TAPPI T 402	All Testing	
Finish weight	3.5	TAPPI T 410	Lot average	0.1 pound
Tensile Breaking strength	3.6	TAPPI T 404	Lot average	0.1 pound
Resistance to curl	3.7	4.4.1	Lot average	1.0 percent
Smudge Test	3.8	4.4.2	Sample unit	Pass or Fail
Slip Resistance	3.9	ASTM F 254	Lot average	1.0 degree
Pin Holes	3.10	4.4.3	Sample unit	Pass or Fail
Serviceability		4.4.4	Sample unit	Pass or Fail
Finish	3.11	4.4.5	Lot average	0.01
Manifolding	3.12	4.4.6	Sample unit	Pass or Fail

4.4 Tests.

4.4.1 Curl Resistance Test. The following tests may be conducted in conditioning rooms or in special laboratory cabinets capable of maintaining the relative humdities

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

and temperature ranges specified. Two sheets of the carbon paper to be tested shall be removed from a previously unopened box and placed on a flat surface, first sheet carbon side up and the second sheet carbon side down. The sheets shall be exposed for 1 minute at each of the following atmospheric conditions:

(a) 73.0° ± 3.5°F and 20 ± 2 percent relative humidity.
(b) 73.0° ± 3.5°F and 50 ± 2 percent relative humidity.
(c) 70° to 80°F and 90 ± 2 percent relative humidity.

The portion of each short side on each sheet which is in direct contact with the flat surface shall be measured. The percentage of curling for each sheet shall be calculated by the following equation:

$$\text{Percent curl} = \frac{2L_o - (L_1 + L_2)}{2L_o} \times 100$$

Where: L_o = Length in inches (short side) of sheet before test.
L_1 = Length in inches of short sides of first sheet remaining in contact with flat surface.
L_2 = Length in inches of short sides of second sheet remaining in contact with flat surface.

4.4.2 Smudge test. The smudge test shall be made on the same machine and under the same conditions as described in 4.3.6, using the same types of bond and manifold papers specified herein. The test shall be made with typewriter impression indicator and the multiple-copy control indicator setting appropriate for the machine being used. A first sheet of bond paper together with the number of manifold and carbon paper sheets required to produce 20 copies shall be assembled in the usual manner. Assembled sheets shall be inserted in the typewriter (advancement of the assembly to each succeeding line as well as removal from the typewriter shall be accomplished by manual turning of the platen). The following steps shall be performed in the sequence indicated:

(a) Type entire keyboard twice-both upper and lower case.
(b) Type three lines of writing-both upper and lower case.
(c) Advance platen three lines.
(d) Type left one-third of line.
(e) Advance platen five lines.
(f) Type middle third of line.
(g) Advance platen five lines.
(h) Type last third of line.
(i) Turn platen to (d) and complete the line.
(j) Turn platen to (f) and type last third of line.
(k) Turn platen to (h) and complete the line.
(l) Turn platen to (f) and type left one-third of line.

Remove the carbons from the assembled sheets by grasping the first sheet and copy sheets between the thumb and forefinger of one hand at the carbon-paper corner cut-out. Carefully pull the carbons all together at one time from the assembled sheets. Examine specimens for smudging as specified in 3.8.

4.4.3 Pinhole. Twenty-five square inches on each of twelve sheets (300 square inch) taken at random from the boxes drawn for sampling as specified in 4.3, shall be examined for freedom from pinholes. Care should be exercised if a comparison hole is made by puncturing a sheet of carbon paper with a wire 0.006 to 0.007 inch in diameter that the hole is not made larger than the diameter of the wire. Examination of carbon paper for the presence of pinholes shall be made in a dark room. Either a 20 watt frost-glass flourescent tube or a 7-1/2 watt white night-light bulb may be used to provide the light source. A template having a 5 by 5 inch opening (prepared from cardboard or other like material) 0.007 inch in diameter may be found in some multiple-strand copper electrical cords. The wire shall be measured with a micrometer to assure that it is the proper diameter. In examining the carbon paper, place the specimen with the carbon side up on the glass plate directly over the light. Place the template over the carbon paper to define the area to be examined.

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:20Z
Check the source to verify that this is the currentversion before use.

4.4.4 Serviceability (weardown test).

4.4.4.1 Equipment.

(a) Electric typewriter, IBM Model 11b, or equivalent, with the following characteristics:

1. Pica type (freshly cleaned).
2. No. 1 platen (IBM), or platen with a durometer hardness of approximately 93 when measured with a Shore durometer, type A. The ratchet shall have 55 teeth.
3. The two central pairs of feed rollers may be removed and replaced with metal brushing with outside diameters approximately 1/16 inch less than the rollers.
4. Attachment to fasten the carbon paper and permit the cover and copy writing papers to move, when required, without smearing the impressions (see 6.5).
5. Special IBM type, cross-hatch, 3 by 3 lines, to be used in a pica-type machine (see 6.7).

Note 1. The impression indicator of the test typewriter shall be adjusted so that the impression force of the cross-hatch characters and the lower case letters will just barely emboss one sheet of type V, 32-pound (17 x 22-1000) writing paper conforming to UU-P-121. The multiple-copy indicator shall be adjusted to the narrowest opening.

(b) Macbeth Reflection densitometer (see 6.8).

4.4.4.2 Materials.

(a) Carbon paper sample, 2 by 4 inches.
(b) A 4 by 8 inch strip of manifold paper conforming to type VI, 16 pound (17 x 22-1000), of UU-P-328.
(c) Two sheets of writing paper, approximately 8 by 10-1/2 inches, conforming to type V, 32-pound (17 x 22-1000), of UU-P-121.
(d) Typewriter ribbon (new) conforming to L-R-350.

4.4.4.3 Preparation of test assembly. The 2 by 4 inch sample of carbon paper to be tested shall be placed back side up, over a 4 by 8 inch strip of manifold paper so that 1/2 inch of the manifold paper is covered. The 4 inch length of carbon paper shall be parallel to the 4 inch length of manifold paper. A piece of cellulose tape shall be used to fasten the carbon paper to the manifold paper. This combination of manifold and carbon paper shall be centered between the two writing paper sheets (long dimensions parallel) and inserted into the machine as for normal collation. This assembly shall be drawn into the machine until one-half of the carbon paper is above the typing area. The manifold paper shall be secured in any suitable manner (see 6.5) so that the carbon paper does not move when the platen is turned to mmove the cover and copy writing paper sheets. The platen shall be turned to make the samples taut.

4.4.4.4 Preparation of impressions. The typed impressions shall be made on the conditioned samples with the electric typewriter, using freshly cleaned pica type and a 3 by 3 cross-hatch special type (10 per inch). The impression indicator which controls the force of the stroke shall be at the setting specified in 4.4.4.1 and the multiple-copy control indicator which controls the distance between the platen and the carriage shall be set at the position for the test assembly specified in 4.3.4.1 (note 1). A line shall be typed consisting of 25 impressions of the cross-hatch type. Two additional lines shall be typed, without spacing, to form a block three lines wide. Five blocks shall be typed. There shall be a single space between each block.

4.4.4.5 Evaluation of impressions. A Macbeth Reflection densitometer with visual filter in position shall be used for determining reflective density of the impressions. The instrument shall be standardized for using four ASA visual diffused reflection density standards, one with a value below 0.37, two with values between 0.37 and 0.72, and one with a value about 0.72. The instrument shall be acceptable for evaluation of impressions when the reflection density of all four tiles can be read within $\pm$ 0.02 units of the standard values without requiring adjustment between readings. The prepared impressions backed by four sheets of 32-pound, type V writing paper shall be inserted in the machine for evaluation. The aperture of the instrument shall be tangent to the middle line of first block of the impressions. Five readings shall be taken at various points along the middle line of each block under tests. All lines within each block having a reflective density of 0.15 or more shall be considered acceptable for weardown. The average reflective density of the minimum serviceability line shall be reported.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

4.4.5 Finish. The color intensity of the first impression shall be expressed as average initial reflective density and used to determine conformity with the requirements for finish. Report the average reflective density of the middle line of first block of the impressions prepared under the serviceability test as described in 4.3.4.

4.4.6 Manifolding test.

4.4.6.1 Equipment.

(a) Electric typewriter, IBM Model 11b or equivalent, with the following characteristics:

1. Pica type (freshly cleaned).

2. Number 1 platen (IBM), or platen with a durometer hardness of approximately 93 when measured with a Shore durometer, Type A. The ratchet shall have 55 teeth.

3. Typewriter ribbon (new) conforming to L-R-350.

Note 2. Each lower case letter shall be adjusted so that its impression force will barely emboss one sheet of type V, 32-pound (17 x 22-1000) writing paper, conforming to UU-P-121, when the impression force indicator of the typewriter is set at the middle of its range.

4.4.6.2 Materials.

(a) Bond paper conforming to type III, 32-pound (17 x 22-1000), of UU-P-121.
(b) Manifold paper conforming to type VI, 16-pound (17 x 22-1000), of UU-P-328.
(c) Standard manifolding performance sample (see 6.6).

The typewriter shall be adjusted to make 12 copies according to the manufacturer's recommendations. A first sheet of the bond paper specified in the 4.4.6.2 (a) and 12 carbon and manifold sheets specified in 4.4.6.2 (b) required for the type and grade of carbon paper being tested shall be assembled in the usual manner. The assembled sheets shall be inserted in the typewriter with a new ribbon as specified in 4.4.6.1 (3) and the entire keyboard, both upper and lower case, shall be typewritten twice in unrelated order. Additional lines may be typed. Compare copy reproductions with standard manifolding performance sample (see 6.6) giving particular attention to the legibility of the small letters a, e, i, o, u.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A, B, or C as specified (see 6.2).

5.1.1 Level A and B. Fifty sheets of one size shall be packaged in a paper folder commonly used for the purpose. Two folders (100 sheets) shall be packaged in a box conforming to PPP-B-676, type I, class A, style 4. Additional filler material as sheet of chipboard, paperboard, or fiberboard may be used to assure that no slippage of paper of folders will occur during handling or shipping. Closure of the box shall be in accordance with the box specification. Alternatively, two folders (100 sheets) shall be packaged in a box as described above with the top hinged at one end, one side or the approximate center of its longer dimension. Box tops hinged at the approximate center shall have that portion of the top above the hinge securely attached to the bottom.

5.1.2 Level C. Paper shall be packaged to afford adequate protection against damage during shipment from the supply source to the first receiving activity.

5.2 Packing. Packing shall be level A, B, or C, as specified (see 6.2).

5.2.1 Level A and B. Fifty boxes of paper with neither dimension of the individual sheets exceed 14-1/2 inches; or 25 boxes with one dimension of the individual sheets exceeds 14-1/2 inches packaged as specified in 5.1, shall be packed snuggly in a box conforming to PPP-B-636, class domestic, except that the minimum bursting strength shall be 275 p.s.i. The box shall be closed in accordance with the appendix of that specification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

5.2.2 Level C. Paper in quantities as specified (see 6.2), packaged as specified in 5.1, shall be packed in containers to assure carrier acceptance and safe arrival at destination in compliance with Uniform Freight Classification Rules or National Motor Freight Classification Rules, as applicable.

5.3 Marking. In addition to any special marking required by the procurement document, marking of interior and exterior shipping containers shall be in accordance with Fed. Std. No. 123 for civil agencies or MIL-STD-105 for military agencies, as applicable (see 6.2).

6. NOTES

6.1 Intended use for the carbon paper is to make up to 12 copies of type when used in manual or electric typewriters. For ease of extraction from manifold after typing, the carbon paper is 1/2 inch longer than the sheet size.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

(a) Title, number, and date of this specification.
(b) Size of carbon paper required (see 3.3).
(c) Selection of applicable level of protection (see 5.1 and 5.2).
(d) Any special marking and applicable marking document (see 5.3).
(e) Quantities required (see 5.2.2.).

6.3 Bid samples. When bid samples are required, they shall be examined for conformance to 3.2, 3.3, 3.4, 3.13, 3.15.

6.4 Reflective density limits. Carbon paper giving first block reflective densities below 0.37 or above 0.72 are not satisfactory for general typewriting purposes.

6.5 Typewriter attachment for testing. An attachment for fastening the carbon paper to the typewriter and for trouble-free performance of the weardown test may be devised as follows: This device consists of a 3/16 inch diameter brass rod of suitable length (approximately 17 inches) on which a piece of rubber tubing, 4 inches in length, is centered. The brass rod is bent at right angles in the same direction 3 inches from each end. A simple fitting is soldered to each end which enables the rod to be attached to the carriage and prevents it from moving. The rod is positioned directly above and in line with the back of the carriage. A 2-1/2 inch, spring-type paper clip is used to fasten the uncovered end of the manifold paper to the rod in order to hold the carbon paper in place. A 3/8 by 3 inch strip of shim brass (approximately 15 mils thick) is soldered to the paper clip vertically to prevent the bond sheet from catching on the paper clip during the testing process. Approximately 1-1/2 inches of the brass shim should extend beyond the gripping edge of the clip.

6.6 Standard manifolding performance sample. Samples of carbon paper reproductions of acceptable legibility are available from comparison purposes at the Quality Control Division Offices in all General Services Administration Regional Offices.

6.7 Special IBM cross-hatch type. This type may be purchased through any local office of the International Business Machines Corporation.

6.8 Macbeth reflection densitometer. This instrument may be purchased from the Macbeth Instrument Corporation, P.O. Box 950, Newburgh, NY 12550.

6.9 The carbon paper of this specification is the type I, light weight and Grade A, extra quality.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

Military Interest:

DOD has waived coordination

User Interest:

Navy-MC
Army-GL

Preparing Activity:

GSA-FSS

Civil Agency Coordinating Activities

HEW-SSA
GSA-FSS
Commerce-NBS
Postal-POS
GPO

☆U. S. GOVERNMENT PRINTING OFFICE : 1973 O - 514-179 (501)

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See Section 2 of this specification to obtain extra copies and other documents referenced herein. Price 15 cents each.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.