UU-P-192A
INTERIM AMENDMENT-4(GSA-FSS)
November 18, 1971
SUPERSEDING
Interim Amendment-3(GSA-FSS)
March 26, 1968

INTERIM AMENDMENT

TO

FEDERAL SPECIFICATION

PAPER, CARBONLESS TRANSFER

This Interim Amendment was developed by the Standardization Division, Federal Supply Service, General Services Administration, Washington, DC 20406, based upon currently available technical information. It is recommended that Federal agencies use it in procurement and forward recommendations for changes to the preparing activity at the address shown above.

The General Services Administration has authorized the use of this Interim Amendment as a valid exception to Federal Specification UU-P-192A, dated August 17, 1965.

PAGE 1

Paragraph 1.1, delete and substitute:

1.1 Scope. This specification describes one type of paper capable of transferring an image from one sheet to another sheet of the same paper, when arranged in the proper sequence, through chemical interaction, without the use of carbon.

Paragraph 1.2.2, delete in its entirety.

PAGE 2

Paragraph 2.2, add the following

"National Motor Freight Traffic Association, Incorporated, Agent:

National Motor Freight Classification.

(Application for copies should be addressed to the American Trucking Association Inc., Tariff Order Section, 1616 P Street, N.W., Washington, DC 20036.)

Uniform Classification Committee, Agent:

Uniform Freight Classification.

(Application for copies should be addressed to the Uniform Classification Committee, Room 202 Union Station, 516 W. Jackson Blvd., Chicago, IL 60606.)"

Paragraph 3.1.1, delete and substitute:

3.1.1 Stock. The paper shall be 100 percent chemical woodpulp and shall be free from poly-chlorinated biphenyls (PCB) when tested as specified in 4.2.1.

Paragraph 3.1.2, delete and substitute:

3.1.2 Basis weight. The paper shall have a basis weight of not less than 14 nor more than 18 pounds (17 x 22-500 sheets).

Paragraph 3.1.3, delete and substitute:

3.1.3 Thickness. The paper thickness shall be not less than 0.0027 inch nor more than 0.0042 inch.

FSC 7530

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

PAGE 2 (Con.)

Add new paragraph 3.1.5, as follows:

3.1.5 Copyability. All parts of carbonless transfer paper, original and copies shall reproduce legible copy when imaged on a Xerox copier.

Paragraph 3.3, delete and substitute:

3.3 Performance. The paper shall be coated with chemicals to effect reproduction of the image onto the underlying sheet by means of chemical interaction. The top side of the sheet (face) shall be surface treated with a receiving chemical. The bottom side of the sheet (back) shall be surface treated with a transmitting chemical capable of reacting with the chemically coated top side of the underlying sheet to produce an image. This paper shall be suitable for letterpress and offset production of multiforms requiring semipermanence.

Add new paragraph 4.2.1, as follows:

4.2.1 The contractor shall certify in writing to the contracting officer or his representative that the material offered to the Government is free from poly-chlorinated biphenyl (PCB's).

PAGE 3

Table II, opposite "Paper", add the following defect:

"Both sides of paper not white, or color specified."

PAGE 4

Add new paragraph 5.2.3, as follows:

5.2.3 Additional marking. In addition to markings required in 5.2.1 or 5.2.2, as applicable, carbonless transfer paper packaged as specified in 5.1 shall bear the following instructions on each package:

"Use only in combination with similar paper from the same manufacturer."

Paragraph 6.2, delete in its entirety.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.