UU-P-202D
September 14, 1973
SUPERSEDING
Fed. Spec. UU-P-202C
October 18, 1967

FEDERAL SPECIFICATION

PAPER, GRAPH

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers graph paper.

1.2 Classification. The graph paper covered by this specification shall be of the following types, grades, classes and styles, as specified (see 6.2).

Type I. Drawing.
  Grade A. 100 percent cotton or linen rag.
  Grade B. 50 percent cotton or linen rag.
  Grade C. Fibrous, cellulosic material.

Type II. Tracing.
  Class 1. Natural tracing paper.
    Grade A. 100 percent cotton or linen rag.
    Grade B. 50 percent cotton or linen rag.
    Grade C. Fibrous, cellulosic material.

  Class 2. Transparentized tracing paper.
    Grade A. 100 percent cotton or linen rag.
      Style 1. High translucency.
      Style 2. Medium translucency.

Type III. Ledger.

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

Federal Specifications:

TT-I-528 - Ink, Drawing, Waterproof, Black.
UU-B-356 - Binder, Looseleaf, Ring.
UU-P-288 - Paper, Ledger, Unruled.
UU-P-561 - Paper, Tracing.
PPP-B-636 - Boxes, Shipping, Fiberboard.

Federal Standard:

Fed. Std. No. 123 - Marking for Domestic Shipment (Civil Agencies).

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which included cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, D.C. 20402.

FSC 7530

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:20Z
Check the source to verify that this is the current version before use.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Washington, DC, Atlanta, Chicago, Kansas City, MO., Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, WA.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks, and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standards:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply.

National Motor Freight Traffic Association, Inc., Agent:

National Motor Freight Classification.

(Application for copies should be addressed to the American Trucking Associations, Inc., Tariff Order Section, 1616 P Street, N.W., Washington, DC 20036.)

Uniform Classification Committee, Agent:

Uniform Freight Classification.

(Application for copies should be addressed to the Uniform Classification Committee, Room 1106, 222 South Riverside Plaza, Chicago, IL 60606.)

Technical Association of the Pulp and Paper Industry (TAPPI) Standards:

T 401 - Fiber Analysis of Paper and Paperboard.
T 402 - Standard Conditioning and Testing Atmospheres for Paper, Board, Pulp Handsheets and Related Products.
T 403 - Bursting Strength of Paper.
T 410 - Weight per Unit Area (Basis Weight or Substance) of Paper and Paperboard.
T 423 - Folding Endurance of Paper (Schopper Tester).
T 425 - Opacity of Paper.
T 479 - Smoothness of Printing Paper.

(Application for copies should be addressed to the Technical Association of the Pulp and Paper Industry, One Dunwoody Park, Atlanta, GA 30341.)

(Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

3. REQUIREMENTS.

3.1 Standard sample. A standard sample (see 6.3) can be obtained from the contracting officer for comparison of the color and cleanliness of the paper and color, configuration, and spacing of lines of the material to be supplied. Graph paper shall conform to the requirements of this specification in all other respects.

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:20Z
Check the source to verify that this is the current version before use.

3.2 Material. Graph paper shall be made from the following pulps, or blends of pulps, as applicable, and additives needed to meet the requirements of this specification.

3.2.1 Grade A. Grade A graph paper shall be made from 100 percent cotton or linen textile mill wastes, linters or rags, when tested as specified in 4.2.1.

3.2.2 Grade B. Grade B graph paper shall be made from not less than 50 percent cotton or linen textile mill wastes, linters or rags, when tested as specified in 4.2.1.

3.2.3 Grade C. Grade C graph paper shall be made from cellulosic, fibrous material which may include reclaimed fibers.

3.2.4 Paper component physical requirements.

3.2.4.1 Type I. Type I drawing graph paper shall conform to the requirements of table I when tested as specified in 4.2.1.

TABLE I. Physical requirements for type I drawing paper

	Grade A	Grade B	Grade C
Basis weight (17 x 22-500 sheets), pounds 1/	36	24	16
Bursting strength, minimum, average, pounds per square inch (psi)	50	32	12
Finish (smoothness), both sides, average, seconds	50-80	30-50	20-30
Folding endurance, before aging, average each direction, minimum, Schopper double folds	250	100	
Folding endurance, after aging, minimum, average each direction, Schopper double folds	125	50	

1/ A plus or minus tolerance of 5 percent will be permitted.

3.2.4.2 Type II. Type II, class 1 tracing graph paper shall conform to the requirements of table II when tested as specified in 4.2.1.

TABLE II. Physical requirements for type II, class 1 tracing paper

	Grade A	Grade B	Grade C
Basis weight (17 x 22-500 sheets), pounds 1/	12	12	13
Bursting strength, minimum, average, pounds per square inch (psi)	28	24	15
Finish (smoothness), both sides average, seconds	30-50	30-50	30-50
Folding endurance, before aging, average each direction, minimum, Schopper double folds	250	200	50
Folding endurance, after aging, average each direction, minimum, Schopper double folds	125	75	--
Opacity, (contrast ratio method), maximum percent	60	60	65

1/ A plus or minus tolerance of 5 percent will be permitted.

3.2.4.3 Type II, class 2. Type II, class 2 transparentized graph paper shall conform to all the requirements of types III and IV of UU-P-561 for the applicable basis weight, as specified (see 6.2).

3.2.4.4 Type III. Type III ledger graph paper shall conform to the requirements applicable to 48 pound basis weight (17 x 22-1000 sheets) of type III of UU-P-288 (JCP J 10).

3.2.5 Color and cleanliness. Graph paper shall be equal to the standard sample (see 3.1) with respect to color and cleanliness.

3.3 Printing and ruling. Lines shall be produced by printing or machine ruling. The overall size of the printed or ruled area shall be as specified in the contract or order (see 6.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

3.3.1 Lines.

3.3.1.1 Configuration. Configuration of the lines on graph paper, its specific pattern such as cross section, logarithmic scale or other, shall be as in the standard sample (see 3.1).

3.3.1.2 Width and color. Each line shall be visually continuous and of uniform width and color throughout conforming to the standard sample (see 3.1). Intersections of lines shall be sharp with no blotting or feathering. When specified, lines shall be printed in nonreproducible blue ink (see 6.2).

3.3.1.3. Spacing of lines. After conditioning the graph paper and standard sample to equilibrium in accordance with TAPPI T 402, the distance between any two lines on the graph paper shall be equal to the distance between corresponding lines on the standard sample (see 3.1).

3.4 Construction.

3.4.1 Form. Graph paper shall be furnished in rolls, sheets or pads, as specified (see 6.2). Rolls or sheets of paper shall contain no splices.

3.4.1.1 Rolls. Rolls shall be uniformly and smoothly wound on nonreturnable cores. The edges of the rolls shall be clean cut, even and dust-free. The ends of the paper shall be commercially secured to prevent unwinding or slippage on the core. The width shall be as specified (see 6.2), ± 1/16 inch. The length of graph paper in a roll shall be as specified (see 6.2). The core length shall be the specified roll width, ± 1/16 inch tolerance.

3.4.1.2 Sheets. Sheets of graph paper shall be the length and width specified (see 6.2) with a ± 1/16 inch tolerance. Sheets shall be trimmed on four sides and shall have clean-cut, dust-free edges. Sheets shall lie flat and shall be square to the extent that the difference between the two diagonals shall not exceed 1/16 inch.

3.4.1.3 Pads. Unless otherwise specified, pads shall contain 20, 24, 40, 50, 60 or 100 sheets, continuously and securely padded together along a specified edge, in accordance with commercial practice (see 6.2). The length and width of pads shall be as specified (see 6.2) with a tolerance of ± 1/16 inch. Assembled pads shall have clean-cut, dust-free edges and shall be square to the extent that the diagonals of a sheet of the pad shall not vary by more than 1/16 inch.

3.4.1.3.1 Perforation. When specified (see 6.2), the pad shall be perforated 3/4 ± 1/16 inch from the bound edge. The perforation shall be parallel to the bound edge and shall extend the entire length or width, as applicable.

3.4.2 Binder holes. When specified, graph paper in sheet or pad form shall have 5 punched holes 1/4 ± 1/32 inch in diameter along a specified edge and spaced to fit a standard 2 or 3 ring binder conforming to UU-B-356 (see 6.2).

3.5 Performance characteristics.

3.5.1 Penciling and erasing. There shall be no visible change of color of the erased surfaces, no perceptible linting of the paper, no erasure of the printed lines or rulings when tested as specified in 4.3.2.

3.5.2 Inking. There shall be no visible spreading or feathering when inked after erasing as specified in 4.3.2.

3.5.3 Erasing and inking. There shall be no visible spreading or feathering, when inked afer erasing as specified in 4.3.2.

3.6 Marking. Each sheet of graph paper shall be identified in the sheet margin with the manufacturer's name or trademark and the configuration of rulings in accordance with commercial practice. Identification markings shall be spaced at intervals of not more than 36 inches in the bottom margin of roll graph paper. When the printed or ruled area is identical to the overall sheet size, identification markings shall be omitted.

3.7 Workmanship. The paper shall be free from spots, wrinkles, discolorations, and other visible defects. The edges shall be clean-cut, not ragged, crushed or uneven.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.1.1 Certificate of compliance. Where certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

4.1.2 Inspection. Sampling for inspection and tests shall be performed in accordance with the provisions set forth in MIL-STD-105, except where otherwise indicated. For purposes of sampling, a lot of graph paper shall consist of all graph paper of the same type, grade, configuration of ruling or printing, form, size, and color of ruled or printed lines offered for inspection at one time. A lot of paper component shall consist of all paper of one type, grade, and weight used in producing the graph paper.

4.2 Component and material inspection. In accordance with 4.1 above, components and materials shall be inspected and tested in accordance with all the requirements of referenced specifications, drawings, and standards unless otherwise excluded, amended, modified, or qualified in this specification or applicable purchase documents.

4.2.1 Sampling and testing of components. The paper components shall be tested for the applicable characteristics specified in table III. The sample unit shall be a minimum of 1000 square inches of paper. Five randomly selected sample units shall be tested for each lot of paper component of the same type and grade furnished by the same component supplier for use in the manufacture of printed graph paper. The methods of testing as specified in table III shall be followed. Composite samples shall consist of small pieces of all sample units combined into a single sample. There shall be no failure to meet the lot average or composite requirement. With the exception of the fiber identification test, all specimens shall be conditioned to equilibrium in accordance with TAPPI T 402.

TABLE III. Instructions for testing components

Characteristic	Spec. Ref. Rqmt. Par.	Spec. Ref. Test Method	Rqmt. applic. to Sample Unit	Rqmt. applic. to Lot Ave.	Number of determinations per sample unit	Results 1/ reported as Numer. to nearest
Atmospheric conditions	4.2.1	T 402	All testing except Stock			
Stock						
Grade A	3.2.1	T 401			1 on composite	5 percent
Grade B	3.2.2	T 401			1 on composite	5 percent
Basis weight						
Type I	Table I	T 410		X	1	0.5 pound
Type II, class 1	Table II	T 410		X	1	0.5 pound
Bursting Strength						
Type I	Table I	T 403		X	10 (5 per side)	1 psi
Type II, class 1	Table II	T 403		X	10 (5 per side)	1 psi
Smoothness						
Type I	Table I	T 479		X	10 (5 per side)	1 second
Type II, class 1	Table II	T 479		X	10 (5 per side)	1 second

(TABLE III - Continued on next page).....

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:20Z
Check the source to verify that this is the current version before use.

TABLE III. Instructions for testing components

Characteristic	Spec. Ref. Rqmt. Par.	Spec. Ref. Test Method	Rqmt. applic. to Sample Unit	Rqmt. applic. to Lot Ave.	Number of determinations per sample unit	Results reported as Numer. to nearest
Folding endurance						
Before aging						
Type I	Table I	T 423		X	20 (10 in each direction)	1 double fold
Type II class 1	Table II	T 423		X	20 (10 in each direction)	1 double fold
After aging		4.4.1				
Type I	Table I	T 423		X	20 (10 in each direction)	1 double fold
Type II, class 1	Table II	T 423		X	20 (10 in each direction)	1 double fold
Opacity	Table II	T 425	X		5	0.5 percent

1/ Test results shall include all values upon which results are based.

4.2.1.1 Evidence of compliance. In lieu of using his own facilities, the contractor may submit a report of analysis of type II, class 2, and type III materials from a laboratory acceptable to the Government, whether an independent test facility or the laboratory of the raw material supplier, as evidence of compliance with the specification requirements. The report of analysis shall include, in addition to the actual test data, the manufacturer's name and address of the testing laboratory, date of test, and quantity of material represented by the test report.

4.3 Inspection of the end item.

4.3.1 Examination of the end item. The end item shall be inspected for the defects set forth in the applicable subparagraphs at the inspection levels and acceptable quality levels (AQLs) in 4.3.1.5. The lot size for purposes of determining the sample size in accordance with MIL-STD-105 shall be expressed in units of yards for rolls, and units of sheets for paper in pad or sheet form, or packages of 100 sheets for examinations under 4.3.1.1 through 4.3.1.3, and in units of shipping containers in the end item inspection lot for examination under 4.3.1.4.

4.3.1.1 Examination of the end item for defects in appearance and workmanship. The sample unit shall be three consecutive yards, full width of the roll for the examination for defects within rolls. No sample unit shall be taken from the first or last convolution of the roll. The sample unit shall have five consecutive sheets taken from a package for examination for defects in sheets. The sample unit shall be five consecutive sheets taken from one pad for defects in pads. No more than three sample units shall be examined from any one roll and no more than one sample unit from any one package or pad. Both sides of the material shall be examined. Defects of each type shall be scored only once within each sample unit.

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:20Z
Check the source to verify that this is the current version before use.

Examine	Defects
Form	Not form specified.
Appearance and workmanship	Color and cleanliness do not compare favorably with the standard sample. Presence of any wrinkle, foreign matter, shives, lumps, spots, or slime holes. Edges not clean cut; ragged, crushed or uneven.
Lines, printed or ruled	Not continuous; not uniform in width or color. Intersections or lines blotted; not sharp, feathered.
Ink	Color does not match standard sample.

4.3.1.2 Examination of the end item for dimensional defects. The sample unit for this examination shall be one roll, one sheet, or one pad, as applicable.

Examine	Defects
Sheet or pad	Length or width varies more than 1/16 inch from dimension specified.
Squareness	Not trimmed square; difference between two diagonals exceeds 1/16 inch.
Roll width	Varies more than 1/16 inch from dimension specified.
Core length	Varies by more than 1/16 inch from width of roll.
Printing or ruling	Length and width of printed or ruled area not as specified in contract or order.

4.3.1.3 Examination of the end item for defects in construction. The sample unit for this examination shall be one roll, one package of sheets, or one pad.

Examine	Defects
Assembly of sheets	Not evenly and uniformly stacked.
Punched holes, when specified	Missing. Diameter less than 7/32 or more than 9/32 inch. Improperly spaced or located.
Pads	Not securely and continuously padded along specified edge. Chipboard backing missing. Not evenly and uniformly assembled.
Rolls	Not suitably restrained to prevent unwinding. Material not wound evenly and tightly on core causing soft or uneven edges or telescoping of the roll. Core missing, broken, or crushed. Paper slips over core when unwinding. Any splice in rolls. Markings, as applicable, missing; not spaced at 36-inch intervals along roll; not according to commercial practice or as in standard sample. Printed side not wound towards the inside of roll.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

4.3.1.3.1 Examination for length per roll or count per package or pad as applicable. The sample unit for this examination shall be one roll, one pad or one package of sheets, as applicable.

Examine	Defects
Roll Length	The lot shall be unacceptable if the average length per roll for all rolls examined varies by more than 5 percent from the length specified.
Sheets Count	The lot shall be unacceptable if the average count per pad or package for all units examined is less than the specified count.

4.3.1.4 Examination of preparation for delivery. An examination shall be made to determine whether markings, materials, workmanship, contents, and weight comply with requirements of section 5 of this specification. The sample unit shall be one shipping container, fully packed. Closed containers shall be examined for closure defects.

Examine	Defects
Markings (exterior and interior)	Incorrect; incomplete; illegible; omitted; of improper size, location, sequence, or method of application.
Materials	Any nonconforming component; component missing, damaged, or otherwise defective.
Workmanship	Inadequate application of components such as incomplete closure of case liners, container flaps, loose or inadequate sealing, strapping, or stapling. Bulged or distorted container.
Contents	Not one type, grade, color, or size.
Pads	More or less than 12 pads per package.
Weight	Net weight exceeds requirement.

4.3.1.5 Inspection levels and acceptable quality levels (AQLs). The inspection levels, for determining the sample size, and the acceptable quality levels (AQLs), expressed in defects per 100 units, shall be as follows:

Examination paragraph 1/	Inspection levels	AQLs
4.3.1.1	III	2.5
4.3.1.2	S-3	2.5
4.3.1.3	S-2	4.0
4.3.1.3.1	S-2	N.A.
4.3.1.4	S-2	2.5

1/ The same rolls, package of sheets or pads, as applicable, of the specified material shall be used for examinations under 4.3.1.2 through 4.3.1.3 inclusive and shall be within the rolls, pads or sheets randomly selected under 4.3.1.1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

4.3.2 Testing of the end item. The end item shall be tested for the applicable characteristics specified in table IV. The sample unit shall consist of one foot, full width of rolls, or one sheet taken from a pad or package of sheets. The lot size for determining the sample size shall be expressed in number of rolls, pads, or packages of sheets. No more than one sample unit shall be taken from any one roll, pad, or package of sheets. The inspection level shall be S-1 with no failure to meet any test requirement. Before testing, samples shall be conditioned according to TAPPI T 402.

TABLE IV. Instructions for testing of the end item

Characteristic	Specification reference: Requirement	Specification reference: Test Method	Requirements applicable to Sample unit	Number of determinations per sample unit	Results reported Pass or fail
Atmospheric conditions	4.3.2	T 402	X	All testing	
Color, width and spacing of lines	3.3.1.2	4.4.2	X	1	X
Writing Quality Penciling and erasing	3.5.1	4.4.3	X	1	X
Inking	3.5.2	4.4.4	X	1	X
Erasing and inking	3.5.3	4.4.5	X	1	X
Nonreproducibility (when applicable)	3.3.1.2	1/			

1/ The supplier shall furnish a certificate of compliance covering this requirement.

4.4. Test procedures.

4.4.1 Accelerated aging test. Ten specimens of the proper size for testing of folding endurance (see TAPPI T423) shall be conditioned for 72 hours ± 1/4 hour in a circulating air oven at a temperature of 100° ± 1°C. The specimens shall then be conditioned to equilibrium in accordance with TAPPI T402 and then tested for folding endurance in accordance with TAPPI T423.

4.4.2 Color, width, and spacing of lines. Cut the sample to be tested perpendicularly to the lines and spaces being checked (check both directions). Lay the cut sample on the standard sample so that the equivalent edges of the lined areas coincide. Compare the color, lines, and spacing visually. Corresponding lines on the two sheets shall touch at the junction of the sheets.

4.4.3 Penciling and erasing. Lines shall be drawn upon different portions of the sample with a 2H pencil and erased with an eraser of the Ruby type or equal. The paper shall be inspected for any changes of color of the erased surface, perceptible linting of the paper or erasure of printed lines or rulings.

4.4.4 Inking. Lines of different width shall be drawn upon different portions of the specimen with black waterproof drawing ink conforming to TT-I-528, and carefully inspected for any feathering or skips that are visible to the naked eye.

4.4.5 Erasing and inking. Not sooner than 5 minutes after the ink lines have been drawn, they shall be erased by an electrically operated rubber eraser and then redrawn (as specified in 4.4.4) in the erased area and examined for feathering.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A or C as specified (see 6.2).

5.1.1 Level A.

5.1.1.1 Sheets. One hundred sheets of graph paper of one type, grade, class, color, and size only, shall be completely wrapped in kraft paper having a minimum basis weight of 40 pounds per ream (24 x 36-500). The wrap shall be secured with an adhesive or gummed paper tape. Adhesive shall be applied in such a manner that contact of adhesive is not made with the paper being packaged. Alternatively, the graph paper may be enclosed in a sealed, plastic film.

5.1.1.2 Pads. Twelve pads of graph paper of one type, grade, class, number of sheets, color, and size only shall be completely wrapped in kraft paper and secured as specified in 5.1.1.1.

5.1.1.3 Rolls. Each roll of graph paper shall be completely wrapped in kraft paper and secured as specified in 5.1.1.1.

5.1.2 Level C. Graph paper shall be packaged to afford adequate protection against damage during shipment from the supply source to the first receiving activity.

5.2 Packing. Packing shall be level A, B, or C, as specified (see 6.2).

5.2.1 Level A. Graph paper of one type, grade, class, size, color, and form only, packaged as specified in 5.1 shall be packed in a snug-fitting fiberboard shipping container conforming to PPP-B-636, grade V2s. Closure, waterproofing by means of tape, and reinforcing with steel strapping or tape banding shall be in accordance with the appendix of the container specification. The weight of contents of each shipping container shall not exceed 65 pounds.

5.2.2 Level B. Unless otherwise specified (see 5.2.2.1), graph paper of one type, grade, class, size, color, and form only, packaged as specified in 5.1, shall be packed in quantities indicated in the procurement document in a snug-fitting fiberboard shipping container conforming to PPP-B-636, class domestic, type CF, variety SW, or type SF. Closure shall be in accordance with method II of the appendix of the container specification.

5.2.2.1 When specified (see 6.2), the shipping container shall conform to PPP-B-636, V3c or V3s.

5.2.3 Level C. Graph paper, packaged as specified in 5.1, shall be packed in a manner to insure carrier acceptance and safe delivery at destination at the lowest transportation rate for such supplies. Containers shall be in accordance with rules or regulations of carriers applicable to the mode of transportation.

5.3 Marking.

5.3.1 Civil agencies. In addition to any special marking required by the contract or order, interior packages and shipping containers shall be marked in accordance with Fed. Std. No. 123.

5.3.2 Military agencies. In addition to any special marking required by the contract or order, interior packages and shipping containers shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 Intended use. The graph papers covered by this specification are intended for both office and field use.

6.1.1 Grade A. Grade A papers are intended for use where maximum permanency and serviceability are required.

6.1.2 Grade B. Grade B papers are intended for general use where limited permanency and serviceability are required.

6.1.3 Grade C. Grade C papers are intended for uses of a temporary nature.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

6.2 Ordering data. Purchasers should exercise any desired options offered herein and procurement documents should specify the following:

a. Title, number and date of this specification.
b. Types, classes, grades and styles of paper (see 1.2).
c. Standard sample (see 3.1).
d. Width and length of sheets, pads, or rolls (see 3.4.1.1, 3.4.1.2, and 3.4.1.3).
e. Number of sheets per pad when pads are specified (see 3.4.1.3).
f. Edge of pad to be fastened (see 3.4.1.3).
g. Location of punched holes, when required (see 3.4.2).
h. Form, whether rolls, pads, or sheets (see 3.4.1).
i. When nonreproducible, blue lines are required (see 3.3.1.2).
j. Size of printed or ruled area (see 3.3).
k. Selection of applicable levels of packaging and packing (see 5.1 and 5.2).
l. Quantity per shipping container (see 5.2.2).
m. When V3c or V3s fiberboard is required for level B shipment (see 5.2.2.1).
n. Whether type II (transparentized) paper is to be supplied in high translucency or medium translucency, type III or type IV, respectively, of UU-P-561 and the basis weight required (see 3.2.4.3).
o. Whether perforation is required (see 3.4.1.3.1).

6.3 Standard sample. A sample of the graph paper illustrating required characteristics of the paper to be supplied (see 3.2.5, 3.3.1.1, 3.3.1.2, 3.3.1.3 and 3.7), may be obtained from the contracting officer.

6.4 The Department of Defense waives coordination of this specification.

MILITARY INTEREST:

User activities:

Army-GL
Navy-SA, MC

Preparing Activity:

GSA-FSS

CIVIL AGENCY COORDINATING ACTIVITIES:

COM-NBS
GSA-FSS

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See Section 2 of this specification to obtain extra copies and other documents referenced herein. Price 15 cents each.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.