UU-P-21G
September 15, 1989
SUPERSEDING
Fed. Spec. UU-P-21F
October 16, 1972

FEDERAL SPECIFICATION

PAD, WRITING PAPER

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers writing paper pads, easel or wall (lecture) pads and legal pads.

1.2 Classification. Pad paper shall be of the following types, as specified (see 6.2):

Type I - Writing paper pads.
Type II - Easel pads.
Type III - Legal pads.

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

Federal Specification:

PPP-B-1163 - Box, Corrugated Fiberboard, High Compression Strength, Weather-Resistant, Wax-Resin Impregnated.

FSC 7530

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:19Z
Check the source to verify that this is the current version before use.

Federal Standards:

Fed. Std. No. 123 - Marking for Domestic Shipment (Civil Agencies).
Fed. Std. No. 224 - Closing, Sealing and Reinforcing of Fiberboard Shipping Boxes, General Methods for.

Activities outside the Federal Government may obtain copies of Federal Specification, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, D.C. 20402.

Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, D.C., Atlanta, Chicago, Kansas City, Mo., Fort Worth, Denver, San Francisco, Los Angeles and Seattle, Washington.

Federal Government activities may obtain copies of Federal Specification, Standards and Handbooks and the Index, of Federal Specifications and Standards from established distribution points in their agencies.

Military Standards:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.

Copies of Military Specification and Standards required by suppliers in connection with specific procurement functions should by obtained from the procuring activity or as directed by the contracting officer.

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:19Z
Check the source to verify that this is the current version before use.

Technical Association of the Pulp and Paper Industry (TAPPI) Standards:

T401 - Fiber Analysis of Paper and Paperboard
T402 - Standard Conditioning and Testing Atmospheres for Paper, Board, Pulp Handsheets and Related Products.
T403 - Bursting Strength of Paper.
T410 - Weight per Unit Area (Basis Weight or Substance) of Paper and Paperboard.
T411 - Thickness (Caliper) of Paper and Paperboard.
T425 - Opacity of Paper.
T807 - Bursting Strength of Paperboard and Linerboard.

Application for copies should be addressed to the Technical Association of the Pulp and Paper Industry, Technology Park/Atlanta, P.O. Box 105113, Atlanta, GA 30348.

Technical society and technical association specifications and standards are generally available for reference from libraries.

3. REQUIREMENTS

3.1 Comparison sample. Writing pads shall conform to the comparison sample as provided by the contracting officer with respect to color, finish, and formation. The color of the paper shall be as bright or brighter than the comparison sample. As applicable, the pad ruling lines shall conform favorably to the comparison sample with respect to color, location, intensity, and clarity.

3.2 Material.

3.2.1 Paper. The writing pad paper shall be made from not less than 95 percent bleached chemical pulp, with not more than 5 percent unbleached and/or ground wood pulp, when tested as specified in 4.2. The backing shall contain reclaimed fibers (see 3.2.3.1).

3.2.1.2 Physical properties. The physical properties of the paper shall conform to the requirements specified in Table I when tested as specified in 4.2.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:19Z
Check the source to verify that this is the current version before use.

TABLE I. Physical Properties of Pad Paper

Characteristic	Type I and III	Type II
Basis Weight (17x22-500), avg., lbs. ± 5%	16	20
Bursting strength, avg., p.s.i., min.	12	20
Opacity, percent, min.	75	85
Thickness, inch, ± 0.0005 inch	0.0030	--

3.2.1.3 Writing and erasure quality. Types I, II and III pads shall be sufficiently sized to accept fountain pen ink writing without feathering or ink penetration through to the opposite side of the sheet, when tested as specified in 4.2. Both surfaces of the pad paper shall be sized or otherwise processed to provide good erasability. Good erasability of the paper surface shall be determined by the absence of paper failure when No. 2-1/2 lead pencil lines are erased, redrawn, and erased from the same area, when tested as specified in 4.2.

3.2.2 Backing. The pad backing shall be chipboard or other suitable paperboard which shall conform to the requirements of Table II for the applicable pad type. The backing shall contain reclaimed fibers (see 3.2.3.2).

TABLE II. Physical Requirements of Pad Backing

Characteristic	Type I and III	Type II
Thickness, inch, min.,	0.020	0.030
Bursting strength, avg., p.s.i., min.	50	55

3.2.3 Certification. The contractor shall certify that the product offered shall conform to the requirements of 3.2.3.1 and 3.2.3.2. The government reserves the right to require proof of such conformance prior to the first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:19Z
Check the source to verify that this is the currentversion before use.

3.2.3.1 Regulatory requirements. The paper offered shall include a minimum of 50% waste paper (see 6.5.2).

3.2.3.2 Regulatory requirements. The backing offered shall include a minimum of 90% post consumer recovered material (see 6.5.1).

3.3 Color. The color of the ruled and unruled sheets shall conform to the comparison sample (see 3.1). The sheets shall be white or yellow as specified (see 6.2). All sheets in a pad shall be the same color.

3.4 Size. The first dimension given is the horizontal dimension.

3.4.1 Type I pads. Type I pads shall be 3 by 5 inches, 5 by 8 inches, 8 1/2 by 11 inches or 8 1/2 by 14 inches as specified (see 6.2). A tolerance of ± 1/8 inch in each direction shall be permitted.

3.4.2 Type II pads. Type II pads shall have minimum overall dimensions of 27 by 34 inches and shall not exceed 27 1/2 by 35 1/2 inches.

3.4.3 Type III pads. Type III pads shall be 8 1/2 by 14 inches. A tolerance of ± 1/8 inch in each direction shall be permitted.

3.5 Rulings. Pads shall be ruled or unruled, as follows:

Type I, size 3 by 5 inches and 5 by 8 inches shall be unruled.

Type I, size 8 1/2 by 11 inches, shall be unruled, ruled one side, or ruled two sides, as specified (see 6.2).

Types I and III, size 8 1/2 by 14 inches, shall be ruled on two sides.

Type II shall be ruled or unruled, as specified (see 6.2).

3.5.1 Ruling configuration.

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:19Z
Check the source to verify that this is the currentversion before use.

3.5.1.1 Type I pads. When rulings are specified (see 6.2), they shall conform to the following spacings:

For 8 1/2 by 11 inch pads: Lines shall be spaced 5/16 inch apart with a tolerance of ± 1/16 inch. The first line shall begin 1 3/8 inches, plus 3/16 inch or minus 1/8 inch, from top edge of the paper. The unlined portion of the front and back sides of the sheet shall be located at the binding end of the sheet.

For 8 1/2 by 14 inch pads: Lines shall be spaced 5/16 inch apart with a tolerance of ± 1/16 inch. The first line shall begin not less than 1 1/4 inches nor more than 1 7/8 inches from top edge of the paper. The unlined portion of the front side of the sheet shall be located at the binding end of the sheet, and the unlined portion of the back side of the sheet shall be located at the end opposite the binding end. The vertical ruling shall be located 1 1/4 inches, ± 1/8 inch, from the left edge of the paper and shall extend the full length of the sheet.

3.5.1.2 Type II pads. When specified, type II pads shall have ruled 1 inch squares. A tolerance of ± 1/16 inch shall be permitted between rulings.

3.5.1.3 Type III pads. When specified, type III pads shall have lines rulings spaced 5/16 inch apart with a tolerance of ± 1/16 inch. The first line shall begin not less than 1 1/4 inches nor more than 1 7/8 inches from top edge of the paper. The unlined portion of the front side of the sheet shall be located at the binding end of the sheet, and the unlined portion of the back side of the sheet shall be located at the end opposite the binding end. The vertical ruling shall be located 1 1/4 inches, ± 1/8 inch, from the left edge of the paper and shall extend the full length of the sheet.

3.5.2 Ink Color. The ruling ink shall be blue except that the vertical ruling on types I and III, 8 1/2 by 14 inch pads shall be red. The ruling shall be continuous and uniform without waviness or feathering of the lines.

3.6 Assembly of pads. Paper of the size specified (see 3.4), shall be assembled to form a pad, as indicated.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:19Z
Check the source to verify that this is the current version before use.

3.6.1 Type I pads. Not less than one hundred sheets of paper (see 3.2.1) and a backing sheet (see 3.2.2), of equal size, ± 1/16 inch, shall be securely fastened together along the top edge (horizontal dimension). Type I pads shall be fastened with a hot melt plastic resin material, or a cold, water resistant, padding compound material, or an adhesive binding material with cheesecloth strip, at the option of the contractor, unless otherwise specified. The pad binding shall be of a quality which will result in conformance to the testing in 4.4.2 and 4.4.3. Pads ruled on one side only shall be assembled with the ruled side uppermost.

3.6.2 Type II pads. Each pad shall contain not less than fifty sheets of paper (see 3.2.1). The sheets shall have a backing sheet (see 3.2.2), of equal size, ± 1/16 inch, and a front reinforcing strip of the same material. The front reinforcing strip shall run the full width of the pad and shall extend 1 3/16 inches, ± 1/8 inch, from the top edge of the pad. A minimum of four staples shall fasten together the front reinforcing strip, sheets, and backing sheets.

A cloth binding strip, of the type used commercially for this purpose, shall be firmly adhered to the backing, top edge, and reinforcing strip. The cloth binding shall cover the front reinforcing strip, plus 1/32 inch, minus 1/16 inch, and shall extend and cover the full width of the backing sheet for a distance of not less than 1/2 inch from the top edge.

The cloth binding shall be attached with a suitable adhesive. The sheets shall be perforated across the width of the pad. The perforations shall be parallel to the bottom edge of the reinforcing strip and shall not fall under the strip nor be located beyond the bottom edge of the strip by more than 1/16 inch. The top assembly, as described above, shall be punched with two holes. The holes shall have a diameter of 5/16 inch, ± 1/16 inch, and shall be spaced 17 1/2 inches, plus or minus 1/16 inch, center to center, located equidistant from the nearest sides. The holes shall be placed 1/2 inch, ± 1/16 inch, hole center to top edge of the pad.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:19Z
Check the source to verify that this is the currentversion before use.

3.6.3 Type III pads. Each pad shall contain no less than the number of sheets of paper (see 3.2.1) as specified (see 6.2). The sheets shall have a backing sheet (see 3.2.2) of equal size, ± 1/16 inch, and a front reinforcing strip of the same material. The front reinforcing strip shall run the full width of the pad and shall extend 3/4 inch, ± 1/16 inch, from the top edge of the pad. A minimum of two staples shall fasten together the front reinforcing strip, sheets and backing sheet. A suitable binding strip, of the type used commercially for this purpose, shall be firmly adhered to the backing, top edge and reinforcing strip. The binding strip shall cover the front reinforcing strip, plus 1/32 inch, minus 1/16 inch, and shall extend and cover the full width of the backing sheet for a distance of not less than 1/2 inch from the top edge. The binding strip shall be attached with a suitable adhesive, used commercially for this purpose.

The sheets shall be perforated across the width of the pad. The perforations shall be parallel to the bottom edge of the reinforcing strip and shall not fall under the strip nor be located beyond the bottom edge of the strip by more than 1/16 inch.

The vertical ruling shall consist of one, two, or three lines. The width between any two lines shall not exceed 1/8 inch. The line(s) shall be located 1 1/4 inches, ± 1/8 inch, from the left edge of the paper and shall extend the full length of the sheet.

3.7 Punching. When required, type I writing pads shall be punched as specified (see 6.2).

3.8 Workmanship. All edges of writing pads shall be smoothly and evenly cut. Sheets of pad paper shall be free from dirt, foreign matter, holes, tears, or scuffs marks.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:19Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.1.1 Inspection. Sampling for examination and tests shall be performed in accordance with MIL-STD-105, except where otherwise noted. For purposes of sampling, a lot shall consist of pads of one type, size, and as applicable, ruling submitted for inspection at one time.

4.1.2 Inspection of components and materials. In accordance with 4.1, the supplier is responsible for insuring that components and material were manufactured, examined, and tested in accordance with this specification or referenced subsidiary specifications and standards.

4.1.2.1 Component testing. Each lot of paper and backing material used for the fabrication of writing paper pads shall be tested in accordance with the applicable test methods specified hereinafter, to determine compliance with the requirements of section 3. Each inspection lot shall consist of a component of a single grade manufactured by the same source, under essentially the same conditions and used in the production of the quantity of the end item submitted for inspection at one time.

4.1.2.2 Evidence of compliance. In lieu of using his own facilities, the contractor may submit a report of analysis of component materials from a laboratory acceptable to the Government, whether an independent test facility or the laboratory of the raw material supplier, as evidence of compliance with the specification requirements. The report of analysis shall include, in addition to the actual data, the manufacturer's name and address of the testing laboratory, date of test, and quantity of material represented by the test report.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:19Z
Check the source to verify that this is the current version before use.

4.2 Testing of components. All component lots must be directly traceable to specific lots of end items. The pad paper and pad backing material shall be tested for the applicable characteristics specified in table III. Tests shall be made in accordance with the indicated TAPPI method or as referenced in the table. The lot size shall be expressed in pounds of paper or backing materials, as applicable, used in the manufactured of the paper pads. The sample unit shall consist of not less than 3,000 square inches of paper or backing material, as applicable. The sample size shall be drawn in accordance with level S-1 of MIL-STD-105. Test results shall include all values upon which the results are based and there shall be no failures to meet the sample unit or lot average requirements. All samples shall be conditioned and tested under uniform atmospheric conditions as specified in TAPPI method T402.

TABLE III. Instructions for testing components

Characteristic	Requirement	Test Method	Applicable to	Results Reported Pass/Fail	Results Reported / Nearest
Atmospheric conditions	4.2	T 402	All testing		
Paper					
Fiber Analysis	3.2.1	T 401	Sample unit		5 percent
Bursting Strength	Table I	T 403	Lot average		1 psi
Basis weight	Table I	T 410	Lot average		0.5 percent
Thickness	Table I	T 411	Sample unit		0.0005 inch
Opacity	Table I	T 425	Sample unit		0.5 percent
Writing and Erasability Quality	3.2.1.2	4.4.1	Sample unit	X	
Backing					
Thickness	Table II	T 411	Lot average		0.001 inch
Bursting Strength	Table II	T 807	Lot average		1 psi

4.3 Inspection of the end item.

4.3.1 Examination of the end item. The end item shall be examined for the defects set forth in applicable subparagraphs at the inspection levels and acceptable quality levels (AQL's), in 4.3.1.1. Random samples shall be drawn from each lot for examination of visual, dimensional, and preparation for delivery defects. The lot size shall be expressed in units of pads, for examination in 4.3.1.2.1, 4.3.1.3 and 4.3.1.4 and in units of shipping containers for examination in 4.3.1.2.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:19Z
Check the source to verify that this is the current version before use.

4.3.1.1 Inspection levels and acceptable quality levels for examination. The inspection levels for determining the sample size and AQL's, expressed as defects per hundred units, shall be as follows:

Examination paragraph	Inspection levels	AQLs
4.3.1.2	S-2	2.5
4.3.1.2.1	S-1	NA
4.3.1.3	S-3	2.5
4.3.1.4	S-3	4.0
4.3.1.5	(as stated in paragraph)	

4.3.1.2 Examination of preparation for delivery. An examination shall be made to determine whether markings, materials, workmanship, and contents shall comply with requirements of section 5. The lot size shall be expressed in units of shipping containers. The sample unit shall be one shipping container fully packed. Closed containers shall be examined for closure defects.

Examine	Defects
Marking (exterior and interior)	Incorrect; incomplete; illegible, omitted; of improper size, location, sequence, or method of application.
Material	Any nonconforming component; components missing, damaged, or otherwise defective.
Workmanship	Inadequate application of components such as: incomplete closure of container flaps, loose or inadequate sealing, strapping, or stapling, bulged or distorted container.
Contents	Number of pads per shipping container more or less than specified.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:19Z
Check the source to verify that this is the current version before use.

4.3.1.2.1 Count. An examination shall be made to determine the average number of sheets per pad. The sample unit shall be one pad and the sample size shall be accumulated by drawing an approximately equal number of pads from each of the shipping containers selected under 4.3.1.2. The lot shall be unacceptable if the mean average number of sheets per pad, of all sample units examined, is less than specified. No single pad shall contain less than 95 percent of the specified number of sheets.

4.3.1.3 Examination of the end item for defects in construction. The sample unit for this examination shall be one pad.

Examine	Defects
Assembly	Pad and backing not assembled as specified; not padded on horizontal edge; backing missing. One side ruled pads not assembled with ruling uppermost. Punching, as applicable, not as specified.
Type II, only	Reinforcing strip omitted; cloth binding strip omitted. Sheets not perforated along edge of reinforcing strip; perforations not parallel to reinforcing strip; perforations fall under reinforcing strip. Not punched as specified. Sheets, backing and reinforcing strip not securely fastened together.
Type III	Same as Type II excluding "cloth binding strip omitted"

4.3.1.4 Examination of the end item for dimensional defect. The sample unit for this examination shall be one pad.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:19Z
Check the source to verify that this is the current version before use.

Examine	Defects
Sheet size	
Type I	Not size specified, within plus or minus 1/8 inch.
Type II and III	More or less than dimensions permitted.
Backing size	More or less than sheet size by 1/16 inch.

4.3.1.5 Examination of the end item for visual defects. The pads selected as specified in 4.3.1.2.1 shall be examined for the defects listed below. Applicable pads and each sheet in each pad shall be examined for the defects listed below. The acceptable quality level (AQL) for pad defects shall be 2.5 defects per hundred pads. The acceptable quality levels (AQL's) for sheet defects shall be 2.5 defects per hundred sheets for major defects and 40 defects per 100 sheets for minor defects.

Examine	Defects
Pads	Pad edges not smoothly and evenly cut. Color of sheets varies within the pad. Color of sheets varies between pads.
Sheets	Color, finish, formation do not conform to the comparison sample.
Rulings	Not uniform; partial line; not continuous; wavy. Not as specified. Location and spacing not as specified, within tolerance permitted.
Cleanliness	Presence of holes, tears, or scuff marks; dirt or slime spot; foreign matter.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:19Z
Check the source to verify that this is the current version before use.

4.3.2 Testing of the end item.

4.3.2.1 Types I and III pads. Five randomly selected pads shall be tested for padding strength and binding quality in accordance with 4.4.2. and 4.4.3 respectively. For the lot to be acceptable, there shall be no failure of any of the five pads tested to meet the specification requirements.

4.4 Test methods.

4.4.1 Writing and erasure quality. To determine writing quality of the writing pad paper, draw several lines and characters on both surfaces of the paper with a medium point (commercial type) fountain pen using a one (1) percent aqueous solution of either C.I. Acid Red 1 (Color Index No. 18050) or C.I. Acid Green 3 (Color Index No. 42085). To be considered satisfactory, the lines and characters shall not feather or penetrate through to the opposite side of the paper. To determine erasure quality, draw several lines and characters with a No. 2-1/2 lead pencil and erase with a latex rubber eraser; on the same area, redraw the pencil lines/characters and erase. To be considered satisfactory, the tested area shall not show smearing of the pencil lines, or failure of the paper fiber.

4.4.2 Padding strength. Hold the pad to be tested in a stationary, vertical position with the padded edge down. While holding the backing, allow the sheet pad to naturally fall until it hangs supported by the padding. While performing this test, do not twist or jerk the backing. Repeat the test three additional times. To be considered satisfactory, the pads of sheets shall not become detached from the pad backing nor separate for more than one inch along the padded edge.

4.4.3 Binding quality and strength. Remove five (5) sheets, one sheet at a time, from the pad. Examine the torn edge of the sheets. To be considered satisfactory, the edge shall not be ripped with ragged edges, but shall have a clean and straight edge. Sheets shall be able to be removed with reasonable effort. Next, fold at least five sheets over and under the pad and press the fold slightly. Examine the sheets and binding at the fold. To be considered satisfactory, the sheets shall not break, split, or separate from the binding of the pad.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:19Z
Check the source to verify that this is the current version before use.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A or B, as specified (see6.2).

5.1.1 Level A. Writing pads in quantities as specified in table IV, shall have fiberboard stiffeners, the size of the stacked pads, on top and bottom to prevent damage to edges and then be completely wrapped in 50 pound kraft and sealed with gummed tape or a suitable adhesive. The package will provide product protection against loss and damage during multiple shipments, handling and storage.

5.1.2 Level B. Writing pads in quantities specified in table IV shall be stacked so that the chipboard backings are on top and the bottom (e.g. half the number face up and the other half face down). The pads shall be completely wrapped with 50 pound kraft paper and sealed with tape or a suitable adhesive or shall be wrapped in a transparent plastic film or a plastic heat-shrinkable film.

5.2 Packing. The packages of pads, in quantities as specified in the contract or purchase order (see 6.2), shall be packed in a snug-fitting fiberboard box in compliance with the rules and regulations applicable to the mode of transportation.

5.2.1 Special navy pack. When specified (see 6.2), writing pads packaged as specified in 5.1, shall be packed in the quantities as specified in table IV, in unused fiberboard boxes conforming to PPP-B-1163, style RSC, type SW, grade 275. Each container shall be closed, sealed and reinforced in accordance with FED. STD. No. 224.

TABLE IV. Packaging and packing

Size	Number of pads per package	Number of packages per shipping container
3 x 5	24	18
5 x 8	12	12
8 1/2 x 11	12	6
8 1/2 x 14	12	6
17 x 22	1	20
27 x 34	—	8

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:19Z
Check the source to verify that this is the current version before use.

5.3 Marking.

5.3.1 For delivery to civil agencies. In addition to any special marking required by the contract or order, interior packages and exterior shipping containers shall be marked in accordance with Fed. Std. No. 123, including specification classification such as type, class, color, etc. Bar code marking is required, unless specified otherwise (see 6.2).

5.3.2 For delivery to military agencies. In addition to any special marking required by the contract or order, interior packages and exterior shipping containers shall be marked in accordance with MIL-STD-129. Bar code marking is required, unless specified otherwise (see 6.2).

6. NOTES

6.1 Intended use. Writing pads are used for temporary record purposes or as work sheets by accountants, engineers, clerks, statisticians, etc.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

(a) Title, number, and date of this specification.
(b) Type and size required (see 1.2 and 3.4).
(c) Rulings (see 3.5)
(c) Number of sheets (for Type III only)
(d) Punching (see 3.7)
(e) Quantities of packaging and packing required (see 5.1 and 5.2)
(f) Whether special navy pack is required (see 5.2.1).
(g) Whether Bar Code Marking is required (see 5.3)
(h) Color of sheets (see 3.3).

6.3 Comparison samples may be obtained as directed by the procuring agency issuing the invitation to bid (see 3.1).

6.4 Acid Red 1 Color Index Number 18050 may be obtained from Pylam Products, International Dyestuffs Corp., Sandoz, Incorp., Bern Colors-Poughkeepsie and Ciba-Geigy Chemical Corp. Acid Green 3 Color index Number 42085 may be obtained from Pylam Products, Warner-Jenkinson Co., Bern Colors-Poughkeepsie and International Dyestuffs Corp.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:19Z
Check the source to verify that this is the current version before use.

6.5 Definitions.

6.5.1 Postconsumer material is any of the following materials:

Paper, paperboard, and fibrous wastes from retail stores, office buildings, homes, and so forth, after they have passed through their end usage as a consumer item, including: Used corrugated boxes, old newspapers, old magazines, mixed waste paper, tabulating cards, and used cordage. All paper, paperboard, and fibrous wastes that enter and are collected from municipal solid waste.

6.5.2 Waste paper is any of the following materials:

(1) Postconsumer material and
(2) Manufacturing, forest residues, and other wastes such as:
Dry paper and paperboard waste generated after completion of the papermaking process (that is, those manufacturing operations up to and including the cutting and trimming of the paper machine reel into smaller rolls or rough sheets) including: Envelope cuttings, bindery trimmings, and other paper and paperboard waste, resulting form printing, cutting, forming, and other converting operations; bag, box, and carton manufacturing wastes; and butt rolls, mill wrappers, and rejected unused stock. And finished paper and paperboard from obsolete inventories of paper and paperboard manufacturers, merchants, wholesalers, dealers, printers, converters, or others.

MILITARY INTERESTS:

NOTE: DoD has waived coordination on revisions and amendments to this federal specification until further notice.

PREPARING ACTIVITY:

GSA - FSS

U.S. GOVERNMENT PRINTING OFFICE: 1989 O—943-799

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:19Z
Check the source to verify that this is the current version before use.