UU-P-223c
September 7, 1967
SUPERSEDING
Int. Fed. Spec. UU-P-00223b (Army-GL)
August 23, 1966 and
Fed. Spec. UU-P-223a
November 15, 1963

FEDERAL SPECIFICATION

PAPER, DRAWING

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers drawing paper for pencil, ink, and water-color work.

1.2 Classification. The drawing paper covered by this specification shall be of the following types, classes and styles, as specified (see 6.2):

Type I - 100 percent cotton or linen fibers.
Type II - 50 percent cotton or linen fibers.
Type III - 100 percent chemical wood pulp.

Class 1 - Smooth surface.
Class 2 - Slightly grained surface.

Style A - Unmounted.
Style B - Single mounted.
Style C - Double mounted.

2. APPLICABLE DOCUMENTS

2.1 The following specifications and standards, of the issues in effect on date of invitation for bids or request for proposal, form a part of the specification to the extent specified herein:

Federal Specifications:

TT-I-528 - Ink, Drawing, Waterproof, Black.
UU-P-31 - Paper; General Specifications and Methods of Testing.
CCC-T-191 - Textile Test Methods.
MMM-A-260 - Adhesive, Water-Resistant (For Sealing Water-proof Papers)
PPP-B-621 - Box, Wood, Nailed and Lock-Corner.
PPP-B-636 - Box, Fiberboard.
PPP-B-1055 - Barrier Material Waterproofed, Flexible.
PPP-T-76 - Tape: Pressure-Sensitive Adhesive Paper. (for Carton Sealing).

Federal Standard:

Fed. Std. No. 123 - Marking for Domestic Shipment (Civilian Agencies).

(Activities outside the Federal Government may obtain copies of Federal Specifications and Standards as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington, D. C., 20402)

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, Los Angeles, Seattle and Washington, D. C.)

FSC 7530

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:20Z
Check the source to verify that this is the current version before use.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Specifications:

MIL-L-10547 - Liners, Case, and Sheet, Overwrap, Water-Vaporproof or Waterproof, Flexible.

Military Standards:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

3. REQUIREMENTS

3.1 Standard sample. A standard sample shall be furnished with the contract or purchase order (see 6.3) for comparison of color, cleanliness, and when applicable, the surface finish of class 2 items.

3.2 Type I.

3.2.1 Stock. Type I paper shall be made from 100 percent cotton or linen fibers.

3.2.2 Basis weight. The basis weight of type I paper shall be 50 or 70 pounds (17 X 22-500) as specified (see 6.2). A tolerance of ± 5 percent will be allowed.

3.2.3 Color. The color of type I paper shall be white, buff or cream, as specified (see 6.2).

3.3 Type II.

3.3.1 Stock. Type II paper shall contain not less than 50 percent cotton or linen fibers. The remainder shall be free from unbleached pulp and groundwood.

3.3.2 Basis weight. The basis weight of type II paper shall be 45 pounds (17 X 22-500) with a tolerance of ± 5 percent.

3.3.3 Color. The color of type II paper shall be buff or cream, as specified (see 6.2).

3.4 Type III.

3.4.1 Stock. Type III paper shall be free from groundwood pulp.

3.4.2 Basis weight. The basis weight of type III paper shall be 27.5 pounds (17 X 22-500) with a tolerance of ± 2.5 pounds.

3.4.3 Color. Type III paper shall be white or colored, as specified (see 6.2).

3.5 Color and cleanliness. The drawing paper shall be at least equal to the standard sample (see 3.1) with respect to color and cleanliness.

3.6 Writing and erasing qualities. There shall be no spreading or feathering of the last ink line drawn, on all types of paper, when the paper is tested as specified in 4.3.2.

3.7 Surface. The surface of the paper shall be as specified (see 1.2 and 6.2). Each side of class 1 paper shall have a smooth finish with a minimum Bekk smoothness of 30 seconds when tested as specified in 4.3.2. Class 2 paper shall have a slightly grained surface equal to the standard sample (see 3.1). Single and double mounted paper shall conform to the surface requirements on the drawing surface(s) only.

3.8 Mounting. The paper shall be unmounted, single mounted or double mounted, as specified (see 1.2 and 6.2).

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:20Z
Check the source to verify that this is the current version before use.

3.8.1 Single mounted (style B). When specified, the paper shall be mounted on bleached cotton muslin having a minimum weight of 2.4 ounces per square yard. The yarn count shall be not less than 64 per inch in the warp direction and 56 per inch in the filling. The muslin mounting shall be flush with the paper or shall extend 1/2 ± 1/16 inch beyond all edges of the paper, as specified (see 6.2). The muslin and paper shall be securely and continuously adhered to each other.

3.8.2 Double mounted (style C). Double mounted paper shall be furnished in sheets only and shall have the grain of one sheet at a right angle to the grain of the other sheet. The muslin mounting stock shall be as specified in 3.8.1, laminated between the two sheets and adhered securely and continuously to each.

3.9 Form. The drawing paper shall be furnished in sheets or rolls, as specified (see 6.2).

3.9.1 Sheets. Paper furnished in sheets shall be of the dimensions specified with a tolerance of ± 1/8 inch (see 6.2). The sheet shall be square to the extent that the difference between the two diagonals does not exceed 1/8 inch. Sheets shall be trimmed square on four sides with smooth, clean-cut edges. No splice shall be permitted.

3.9.2 Rolls. The rolls shall be tightly and evenly wound on nonreturnable fiber or paperboard cores. The width of the roll shall be as specified (see 6.2) with a tolerance of ± 1/8 inch. The length of the roll shall be as specified (see 6.2). The length of the core shall be at least equal to the specified width of the roll with a plus 1/8 inch tolerance. No splice shall be permitted within the roll.

3.10 Workmanship. Drawing paper shall be clean, free from holes, tears, cuts, creases, wrinkles, or ply separations.

4. QUALITY ASSURANCE PROVISION

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections as deemed necessary to insure that supplies and services conform to prescribed requirements.

4.1.1 Certificates of compliance. Where certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

4.1.1.1 Inspection. Sampling for examination and tests shall be performed in accordance with MIL-STD-105 except where otherwise indicated.

4.2 Component and material inspection. In accordance with 4.1 above, components and materials shall be inspected and tested in accordance with all the requirements of reference specifications, drawings and standards unless otherwise excluded, amended, modified, or qualified, in this specification or applicable purchase document.

4.2.1 Testing of components. The component materials shall be tested for the applicable characteristics in table I. When unmounted paper (style A) is specified in the contract or purchase order it shall be considered a component material for purpose of stock and basis weight determinations only. The paper shall be conditioned in accordance with method 102 of UU-P-31 and the muslin conditioned in accordance with section 4 of CCC-T-191. The sample unit shall be 1,000 square inches of paper or 1/4 yard of cloth the full width of the roll, as applicable. The sample size, for paper and cloth, shall be drawn in accordance with level S-1 or MIL-STD-105. The lot size shall be expressed in units of rolls of paper or cloth, as applicable, received at one time from one source of supply for use in the manufacture of one type, class, weight, and color of drawing paper. There shall be no failure to meet the composite or lot average requirements, as applicable. Composite samples shall consist of small portions taken from all sample units and combined in a single sample.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:20Z
Check the source to verify that this is the currentversion before use.

TABLE I. Instructions for testing of components

CHARACTERISTIC	Specification Reference		Requirements Applicable To		Number Determinations Per Sample/Unit	Results Reported As 1/		Inspect Level	AQL
	Requirement	Test Method	Individual Unit	Lot Aver		Pass or Fail	Numerically to Nearest		
Paper component:									
Stock:									
Type I	3.2.1	300 *		X	Average of 2 (on composite)		5 percent		
Type II	3.3.1	300 *		X	Average of 2 (on composite)		5 percent		
Type III	3.4.1	300 *		X	Average of 2 (on composite)		5 percent		
Basis weight:									
Type I	3.2.2	110 *		X	1		0.1 pound		
Type II	3.3.2	110 *		X	1		0.1 pound		
Type III	3.4.2	110 *		X	1		0.1 pound		
Cloth component:									
Thread count:									
Warp direction	3.8.1	5050 **		X	5		whole number		
Filling direction	3.8.1	5050 **		X	5		whole number		
Weight per square yard	3.8.1	5041 **		X	5		0.1 ounce		
* Indicates test method of UU-P-31.									
** Indicates test method of CCC-T-191.									

1/ Test reports shall include all values upon which averages are based.

Source: https://assist.dla.mil -- Downloaded: 20260-26T12:20Z
Check the source to verify that this is the current version before use.

4.3 Inspection of the end item.

4.3.1 Examination of the end item. The end item shall be examined for the defects set forth in the applicable subparagraphs at the inspection levels and acceptable quality levels (AQLs) set forth in 4.3.1.6. Random samples shall be drawn from each lot of the end items for examination of visual, dimensional, roll construction, roll length, count and preparation for delivery defects, as applicable. The lot size shall be expressed in units of rolls or packages of sheets, as applicable, for examination in 4.3.1.1 thru 4.3.1.4 and in units of shipping containers for examination in 4.3.1.5.

4.3.1.1 Examination for visual defects. The sample unit for this examination shall be one yard of material the full width of the roll or one sheet, as applicable. No more than 3 sample units shall be examined in one roll or one package of sheets, as applicable.

Examine	Defect
Class, form, and style	Not as specified.
Appearance	Not clean; any mark or discoloration affecting appearance. Any dirt, hole, tear, cut, crease, wrinkle, blister, lump, or mounting separation. Warp or cockle.
Color	Not color specified. Not uniform. Does not compare favorably with the standard sample.
Workmanship	Any splice within a sheet. Surface not smooth or slightly grained, as specified. Class 2 paper not equal to standard sample. Edges not clean cut, ragged, crushed or uneven.
Mounting	Not firmly attached to sheet at all points of contact. Not flush with sheet edges, when applicable Not laminated between two sheets (when double mounted).

4.3.1.2 Examination for defects in dimensions. The sample unit shall be one roll or sheet, as applicable.

Examine	Defect
Rolls	
Width	Varies from width specified by more than ± 1/8 inch.
Core	Less than width of roll or greater by more than 1/8 inch.
Sheets	
Length or width	Varies from dimension specified by more than ± 1/8 inch.
Squareness	Difference between the two diagonals exceeds 1/8 inch.
Mounting	Muslin does not extend 1/2 ± 1/16 inch beyond all edges of sheets (when specified).

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:20Z
Check the source to verify that this is the current version before use.

4.3.1.3 Examination for defects in roll construction. The sample unit for this examination shall be one roll, when applicable.

Examine	Defect
Construction	Material not wound evenly and tightly; roll telescoped. Edges not clean cut, ragged, nicked, crushed or uneven. Material not wound on fiber or paperboard core; core broken, collapsed, crushed or mutilated. Any splice within a roll.

4.3.1.4 Examination for length per roll or count per package. The sample unit for this examination shall be one roll or one package of sheets, as applicable.

Examine	Defect
Roll:	
Length	The lot shall be unacceptable if the average length per roll for all rolls examined is less than specified.
Sheets:	
Count	The lot shall be unacceptable if the average count per package for all packages examined is less than specified.

4.3.1.5 Examination of preparation for delivery. An examination shall be made to determine that markings, material, workmanship, content, and weight comply with the requirements of section 5 of this specification. The sample unit shall be one shipping container, fully packed, selected just prior to the closing operation. Closed shipping containers shall be examined for closure defects.

Examine	Defect
Marking (exterior and interior)	Incorrect; incomplete; illegible; omitted; of improper size, location, sequence or method of application.
Material	Any nonconforming component; component missing, damaged or otherwise defective.
Workmanship	Inadequate application of components, such as: incomplete closure of container flaps; loose or inadequate sealing, strapping or stapling.
Contents	Number of intermediate packages per shipping container is less than the specified or indicated quantity.
Weight	Net weight exceeds requirement.

4.3.1.6 Inspection level and acceptable quality levels (AQLs) for examinations. The inspection levels for determining the sample size and acceptable quality levels (AQLs) expressed in defects per one hundred units shall be as follows:

Examination paragraph	Inspection level	AQLs
4.3.1.1	I	2.5 1/
4.3.1.2	S-2	2.5 2/
4.3.1.3	S-2	4.0
4.3.1.4	S-2	N.A.
4.3.1.5	S-2	2.5

1/ The amount defective shall be expressed in defects per 100 units of yards or sheets, as applicable.

2/ The amount defective shall be expressed in defects per 100 units of rolls or sheets, as applicable.

4.3.2 Testing of the end item. The end item shall be tested for the applicable characteristics in table II. The sample unit shall be two one-foot squares for rolls or one full size sheet for sheets. The sample size shall be drawn in accordance with level S-1 of MIL-STD-105. The lot size shall be expressed in units of rolls or packages of sheets, as applicable. There shall be no failure to pass the sample unit requirements.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:20Z
Check the source to verify that this is the current version before use.

TABLE II. Instruction for testing of the end item

CHARACTERISTIC	Specification Reference		Requirements Applicable To		Number Determinations Per Unit Sample	Results Reported As		Inspect Level	AQL
	Requirement	Test Method	Individual Unit	Lot or Aver		Pass or Fail	Numerically to Nearest		
Writing and erasing qualities:									
Type I	3.6	4.4.1.1		X	1	X			
Type II	3.6	4.4.1.2		X	1	X			
Type III	3.6	4.4.1.3		X	1	X			
Surface smoothness (all types, class 1 only):									
Unmounted									
Felt side	3.7	130 *	X		Average of 5		second		
Wire side	3.7	130 *	X		Average of 5		second		
Single or double mounted									
Drawing surface	3.7	130 *	X		Average of 5 (on each drawing surface)		second		
Grain direction (double mounted, only)	3.8.2	4.4.1.4							

* Indicates test method of UU-P-31.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

4.4 Test procedures.

4.4.1 Writing and erasing qualities. Lines of different widths shall be drawn upon the surface of the paper with a ruling pen using black, waterproof drawing ink conforming to TT-I-528. Ink shall be allowed to dry at least five minutes. The ink lines shall be completely erased with a soft ink electrically operated eraser or with a steel instrument or razor blade. The erased surface shall be smoothed with a soft pencil eraser. The rubber erasers shall be of the "Ruby" type. Lines of different widths shall again be drawn with the specified ink upon the surface of the paper diagonally through the erased line area.

4.4.1.1 Type I. Three successive erasures and redrawing of ink lines as specified in 4.4.1 shall be made within the same area, each set of lines being drawn in a different direction. The lines last made shall show no spreading or feathering. All erasures shall be complete and the surface shall show no damage.

4.4.1.2 Type II. Type II shall withstand two erasures and redrawing of ink lines as specified in 4.4.1. To be considered satisfactory, there shall be no spreading or feathering of the last ink line drawn and no visible surface damage.

4.4.1.3 Type III. Type III paper shall withstand one erasure and redrawing of the ink lines as specified in 4.4.1. The last ink line drawn shall not spread nor feather. There shall be no surface damage.

4.4.1.4 Grain direction. The supplier shall furnish a certificate of compliance stating that the grain of the two sheets cross at a right angle.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A or C, as specified (see 6.2).

5.1.1 Level A.

5.1.1.1 Sheets. One hundred and twenty five or two hundred and fifty sheets of drawing paper, as specified (see 6.2), of one type, class, style, basis weight, size and color only, shall be completely and compactly wrapped in waterproof barrier material conforming to PPP-B-1055, class C-1. Other barrier materials may be used that conform to the minimum physical requirements of PPP-B-1055, class C-1, except that the stiffness requirement may be deleted. The wrap shall be completely sealed with a waterproof adhesive conforming to the minimum physical requirements of MMM-A-260.

5.1.1.2 Rolls. Each roll of drawing paper shall be wrapped overall with waterproof barrier material and sealed as specified in 5.1.1.1.

5.1.2 Level C. The drawing paper shall be packaged to afford adequate protection against damage during shipment from the supply source to the first receiving activity. The supplier may use his standard practice when it meets this requirement.

5.2 Packing. Packing shall be level A, B, or C, as specified (see 6.2).

5.2.1 Level A.

5.2.1.1 Sheets. Sheets of drawing paper of one type, class, style, basis weight, size and color only, packaged as specified in 5.1, shall be packed in snug-fitting shipping containers as specified in 5.2.1.1.1, 5.2.1.1.2, or 5.2.1.1.3, as applicable. Unless otherwise specified, the supplier shall have the choice of container to be used.

5.2.1.1.1 Weight of contents up to 80 pounds. Where the net weight does not exceed 80 pounds the shipping container shall conform to PPP-B-636, style FTC, grade V2c. Each shipping container shall be closed, waterproofed by means of tape or a waterproof adhesive continuously and completely sealed around the perimeter of the two sections of the closed container. The adhesive shall conform to the minimum physical requirements of MMM-A-260. The container shall be reinforced with flat strapping or tape banding in accordance with the Appendix of PPP-B-636.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

5.2.1.1.2 Weight of contents up to 200 pounds. For net weight up to 200 pounds the fiberboard shipping container shall be as specified in 5.2.1.1.1, except that the weight and dimensional limitations shall be waived. Each shipping container shall be provided with a corrugated fiberboard liner fabricated of class domestic, variety DW fiberboard, grade not less than 600. The liner shall be fabricated and taped in accordance with PPP-B-636. In addition, a top and bottom pad of the same material as the liner and having dimensions equal to the length and width of the container inside the liner less 1/8 inch shall be provided. Each shipping container shall be closed, waterproofed and reinforced as specified in 5.2.1.1.1.

5.2.1.1.3 Nailed wood boxes. Nailed wood boxes shall conform to PPP-B-621, class 2, style 2 or 4. Each shipping container shall be provided with a case liner conforming to MIL-L-10547, type I or II, grade C. Each shipping container shall be closed and strapped in accordance with the appendix to PPP-B-621. Net weight of nailed wood boxes shall not exceed 200 pounds.

5.2.1.2 Rolls. Rolls of drawing paper of one type, class, style, basis weight, size and color only, packaged as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to PPP-B-636, style FTC, grade V2s. Each shipping container shall be closed waterproofed with tape, and reinforced as specified in 5.2.1.1.1. The weight of contents of each shipping container shall not exceed 65 pounds.

5.2.2 Level B.

5.2.2.1 Sheets. Sheets of drawing paper of one type, class, style, basis weight, size and color only, packaged as specified in 5.1, in quantities as indicated in the procurement document shall be packed in a snug-fitting container as specified in 5.2.2.1.1, 5.2.2.1.2, or 5.2.2.1.3. Unless specified otherwise, the supplier shall have the choice of container to be used.

5.2.2.1.1 Weight of contents up to 80 pounds. When the net weight does not exceed 80 pounds (see 5.2.2.3), each fiberboard shipping container shall conform to PPP-B-636, style FTC, type CF or SF. Each shipping container shall be securely sealed by applying 3-inch width pressure sensitive tape conforming to PPP-T-76, completely covering all seams of the shipping container lengthwise and widthwise. The tape shall be applied equally over the sides, ends and bottom panels and shall overlap at the corners at least 2 inches. Closures of FTC style containers may be made with adhesive around the entire perimeter of the two closed sections of the container that results in a secure closure.

5.2.2.1.2 Weight of contents up to 200 pounds. For net weights up to 200 pounds, unless otherwise specified (see 5.2.2.3), each fiberboard shipping container shall be as specified in 5.2.2.1.1, except that the grade shall be not less than 350 and the weight and dimensional limitations shall be waived. In addition, a top and bottom pad and liner shall be provided as specified in 5.2.1.1.2. Each shipping container shall be securely sealed as specified in 5.2.2.1.1 and reinforced in flat strapping or tape banding as specified in 5.2.1.1.1.

5.2.2.1.3 Nailed wood boxes. Nailed wood boxes shall conform to PPP-B-621, class 1, style 2 or 4.

5.2.2.2 Rolls. Unless otherwise specified (see 5.2.2.3), rolls of drawing paper of one type, class, style, basis weight, size and color only, packaged as specified in 5.1 in quantities specified in the procurement document, shall be packed in a snug-fitting fiberboard shipping container conforming to PPP-B-636. Closure shall be in accordance with method II of the appendix of PPP-B-636. The weight of contents of each shipping container shall not exceed 65 pounds.

5.2.2.3 When specified (see 6.2), the shipping container shall conform to PPP-B-636, grade V3c or V3s.

5.2.3 Level C. Drawing paper, packaged as specified in 5.1, shall be packed in a manner to insure carrier acceptance and safe delivery at destination at the lowest transportation rate for such supplies. Containers shall be in accordance with rules or regulations of carriers applicable to the mode of transportation.

5.3 Marking.

5.3.1 Civil agencies. In addition to any special marking required by the contract or order, shipping containers shall be marked in accordance with Fed. Std. No. 123.

5.3.2 Military agencies. In addition to any special marking required by the contract or order, shipping containers shall be marked in accordance with MIL-STD-129.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

6. NOTES

6.1 Intended use. Type I drawing papers covered by this specification are used in the preparation of permanent ink drawings of the most exact character and importance which are subject to severe and frequent handling. Type II drawing papers are used in the preparation of ink and pencil drawings which are not necessarily permanent. These papers are subject to frequent handling. Type III drawing papers are used in school work for pencil, ink and water-color work.

6.2 Ordering data. Purchasers should exercise any desired options herein and procurement documents should specify the following:

a. Title, number, and date of this specification.
b. Type, class, and style required (see 1.2).
c. Weight of type I paper required (see 3.2.2).
d. Color required (see 3.2.3, 3.3.3, and 3.4.3).
e. Form and size required (see 3.9).
f. Whether mounting is flush or extends beyond drawing surface (see 3.8.1).
g. Number of sheets per package (see 5.1.1.1).
h. Selection of applicable levels of packaging and packing (see 5.1 and 5.2).
i. When V3c or V3s fiberboard is required for level B shipment (see 5.2.2.3).
j. When a particular type of container is desired (see 5.2.1.1, and 5.2.2.2).
k. Number of packages or rolls to the shipping container (see 5.2.2.1, and 5.2.2.2).

6.3 Standard samples. Standard samples may be obtained upon application to the agency issuing the invitation to bids.

MILITARY CUSTODIANS:

Army - GL
Navy - SA
Air Force - 69

Review activities:

Army - GL
Navy - SA
Air Force - 69

User activities:

Army - SM
Navy - AS, MC, CG

Preparing activity:

Army - GL

Civil Agencies Interest:

GSA-FSS
AGR
GPO
JUS
VA

U. S. Government Printing Office: 1967 0 - 302-503 (299)

Orders for this publication are to be placed with General Services Administration acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents referenced herein. Price 10 cents each.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.