INTERIM AMENDMENT

TO

FEDERAL SPECIFICATION

TAPE, PAPER, COMPUTING MACHINE

This interim amendment was developed by the General Services Administration, Federal Supply Service, Washington, DC 20406, based upon currently available technical information. It is recommended that Federal agencies use it in procurement and forward recommendations for changes to the preparing activity at the address shown above.

The General Services Administration has authorized the use of this interim amendment as a valid exception to UU-T-110C, dated January 12, 1976.

PAGE 2

Paragraph 3.1, delete and substitute:

"3.1 Material. Materials used shall conform to the requirements specified herein. No polychlorinated biphenyls (PCB's) shall be added or used during the manufacture of the paper or in any coating operation on the base paper. As evidence of compliance, the contractor shall submit a certificate stating that no polychlorinated biphenyls have been added or used during the manufacturing or converting operations. (See 4.1.2.1.1)."

Paragraph 3.1.4, delete and substitute:

"3.1.4 Type IV. Carbonless paper tape, type IV, shall be made from fibrous cellulosic material and shall be of the chemical self-imaging type to be used without machine ribbon."

PAGE 3

Delete Table I and substitute:

TABLE I. Physical requirements

Characteristic	Type I	Type II	Types III and IV
Basis weight, pounds (17 x 22 - 500), ± 5%	16	16	12-16*
Bursting strength, pounds per square inch (min.)	16	10	12
Tear strength, grams (min.)			
Cross direction	50	28	21
Machine direction	44	23	18
Brightness, percent (min.)	75	60	72
Thickness, inches	.0029-.0039	.0033-.0043	.0025-.0040

* Tolerance does not apply.

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:19Z
Check the source to verify that this is the current version before use.

Paragraph 3.4, delete and substitute:

"3.4 Rolls. The paper tape shall be wound tightly and evenly on a core conforming to 3.4.1. Types I and II rolls shall be wound with the felt side facing out. Type III rolls shall consist of two plies of chemically-coated carbonless transfer paper. The top (outer) ply of the roll shall be coated on the back side with a transmitting chemical. The bottom ply of the roll shall be coated on the front side with a receiving chemical and shall be positioned to react with the transmitting chemical of the top ply to produce an image on the bottom ply. Type IV rolls shall be wound with the coated side facing out. The overall outside diameter for type I rolls shall be 3-1/4 inches maximum and for types II, III, and IV rolls shall be 3-1/2 inches maximum. The minimum length of tape for a type I paper shall be 160 feet, for type II the minimum length shall be 165 feet, for type III the minimum length shall be 112 feet (two-ply only) and for type IV the minimum length shall be 185 feet (one-ply only). The paper tape shall be one continuous length without splices, joints, seams or tears."

PAGE 4

Paragraph 4.2, table II. Delete the "Stiffness" line.

Paragraph 4.2.1, delete in its entirety.

PAGE 5

Paragraph 4.3.1.2, under the Defect column for "Dimension", delete "Roll contains less than 200 feet of paper." and substitute "Length of roll less than specified."

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:19Z
Check the source to verify that this is the current version before use.