MIL-W-14993B (PA)
SEPT 26 1975
SUPERSEDING
MIL-W-14993A (MU)
26 May 1972

MILITARY SPECIFICATION

WARHEAD SECTION, GUIDED MISSILE, PRACTICE: M231

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 This specification contains requirements not normally covered by the drawings and provides quality assurance provisions for the fabrication of parts, assembly and packing of one type of warhead section designated as Warhead Section, Guided Missile, Practice: M231.

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposals form a part of this specification to the extent specified herein.

SPECIFICATIONS

FEDERAL TEST METHOD STANDARD
No. 141 - Paint, Varnish, Lacquer, and Related Materials, Methods of Inspection, Sampling and Testing.

MILITARY

MIL-C-5541 - Chemical Conversion Coatings on Aluminum and Aluminum Alloys
MIL-A-48078- Ammunition, Standard Quality Assurance Provisions, General Specification For

STANDARDS

MILITARY

MIL-STD-1169 - Packaging, Packing and Marking for Shipment of Inert Ammunition Components

FSC: 1336

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T05:20Z
Check the source to verify that this is the current version before use.

DRAWINGS

PICATINNY ARSENAL

9224024 - Warhead Section, Guided Missile, Practice: M231

3. REQUIREMENTS

3.1 Materials.-Materials shall be in accordance with applicable drawings and specifications.

3.2 Components and Assemblies.-The components and assemblies shall comply with all requirements specified on drawing 9224024 and associated drawings and with all requirements of applicable standards and specifications.

3.3 Warhead to Missile Assembly Capability.-The warhead shall exhibit capabilities of assembly to the missile.

3.4 Weight of Warhead Section.-The warhead section weight shall be as required by dwg. 9224024.

3.4.1 Weight of Ballast.-The weight of the ballast shall be as specified in dwg. 9224135.

3.5 Center of Gravity.

3.5.1 Longitudinal.-The longitudinal center of gravity shall be as specified in dwg. 9224024.

3.6 Launch Shock.-The practice warhead section (dwg. 9224024) shall be capable of withstanding the launch shock when flown on a Dragon missile under normal conditions of launch without structural deformation or failure, looseness or movement of ballast, or shifting of the longitudinal center of gravity beyond the permissible tolerance.

3.6.1 Static Load Strength.-The practice warhead section final assembly (dwg. 9224024) shall withstand a static load of 5000 pounds minimum without failure. This test simulates the practice warhead section's ability to withstand launch shock in real flight.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T05:20Z
Check the source to verify that this is the current version before use.

3.6.2 Tightness and Integrity of Ballast to Warhead Body Assembly.-The practice warhead section assembly shall demonstrate complete tightness and integrity of the magneformed joint of the ballast to the warhead body.

3.7 Protective Finishes.-Test panels and test specimens of the same metal, same surface finish and coated identically to and concurrently with the manufactured parts they represent shall be subjected to and must withstand the protective finish tests outlined below without failure.

3.7.1 Corrosion Resistance.-Chemical film test specimens representing Practice Warhead Body (dwg. 9224134), Ballast (dwg. 9224135) and Angle Assembly (dwg. 9272375) shall be subjected to a 100 hour 5 percent salt spray test in accordance with MIL-C-5541 and Method 6061 of Fed. Test Method Std. No. 141. The test specimens shall meet the corrosion resistance requirements specified in MIL-C-5541.

3.7.2 Paint Adhesion.-Epoxy painted test panels representing Warhead Section, GM, Practice: M231 (dwg. 9224024) shall be subjected to paint adhesion, knife and tape tests in accordance with MIL-C-5541 and Methods 6301.1 and 6304.1 of Federal Test Method Std. 141. The paint on the test panels shall not exhibit flaking, chipping, peeling, loss of adhesion or discoloration.

3.8 Electrical Continuity.-The Angle Assembly, (dwg. 9272375) shall demonstrate electrical continuity by having an electrical resistance not to exceed 0.2 ohm between the grounded electrical contact and the body.

3.9 First Article Inspection.-This specification contains technical provisions for first article inspection. Requirements for the submission of first article samples by the contractor shall be as specified in the contract.

3.10 Workmanship.-The parts and assemblies shall be fabricated, assembled and finished in a thorough, workmanlike manner as defined in 3.10.1, 3.10.2 and 3.10.3.

3.10.1 Fabrication and Assembly.-The parts and assemblies shall be complete and shall not contain cracks, dents, gouges, holes, porous area, inclusions, blowholes, toolmarks, sharp or chipped edges, burrs, blisters, rust, corrosion, warpage or other distortion or any other undesirable characteristics, signs of damage or poor workmanship.

Source: https://assist.dla.mil -- Downloaded: 202610-18T05:20Z
Check the source to verify that this is the current version before use.

3.10.2 Finishes.-Surface coatings and finishes of parts and assemblies shall be continuous and complete and shall not have scratches, blisters, porosity, corrosion or other signs of defective finish or damage thereto except for superficial scratches that do not expose the base metal.

3.10.3 Cleanliness.-The parts shall be clean and free from dirt, corrosion, chips, grease, contaminants or other foreign matter. The cleaning method used shall not be injurious to any of the parts, nor shall the parts be contaminated by the cleaning agents.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection and Standard Quality Assurance Provisions.-Unless otherwise specified herein or in the contract, the provisions of MIL-A-48078 shall apply and are hereby made a part of this detail specification.

4.2 Classification of Inspections.-The following types of inspection shall be conducted on this item:

a. First Article Inspection

b. Quality Conformance Inspection

4.3 First Article Inspection

4.3.1 Submission.-The contractor shall submit a first article sample as designated by the Contracting Officer for evaluation in accordance with provisions of 4.3.2. The first article sample shall consist of the following items in sample quantities as indicated:

Dwg. No.	Component/Assembly	No. of Units	Test Panels
9224134	Practice Warhead Body	5	
	Chromate Film Test Specimens		15
9224135	Ballast	5	
	Ballast - Protective Finish		
	Chromate Film Test Specimens		15
9272374	Unequal Angle	5	

Source: https://assist.dla.mil -- Downloaded: 202610-18T05:20Z
Check the source to verify that this is the current version before use.

9272375	Angle Assembly	5
	Angle Assembly - Protective Finish Chromate Film Test Specimens	15
9224024	Warhead Section, Guided Missile, Practice: M231	9
	Warhead Body external protective finish test panels	15
	Complete sets of other parts not listed above, such as, screws, washers, pins, etc.	5 of each

4.3.2 Inspections to be Performed.-See MIL-A-48078 and Table I specified herein.

4.3.3 Rejection.-See MIL-A-48078.

Source: https://assist.dla.mil -- Downloaded: 202640-18T05:20Z
Check the source to verify that this is the currenversion before use.

TABLE I - FIRST ARTICLE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE		SHEET 1 OF 3		DRAWING NUMBER
	Warhead Section, Guided Missile, Practice, M231 and Components				See Below
					NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
	Body, Practice Warhead (Dwg. 9224134) Examination for Defects	5		3.2	4.4.2.1
	Ballast (Dwg. 9224135) Examination for Defects	5		3.2	4.4.2.2
	Unequal Angle (Dwg. 9272374) Examination for Defects	5		3.2	4.4.2.3
	Angle Assembly (Dwg. 9272375) Examination for Defects	5		3.2	4.4.2.4
	Warhead Section, Guided Missile, Practice: M231 (See Dwg. 9224024) Examination for Defects	9		3.2	4.4.2.5
	Center of Gravity:				
	Longitudinal	9		3.5.1	4.5.2.1
	Weight	9		3.4	4.5.3

NOTES:
All defects listed in Table I are classified as Major B, unless otherwise specified.

SARPA-QA FORM 2567 FEB 74

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T05:20Z
Check the source to verify that this is the current version before use.

TABLE I - FIRST ARTICLE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE Warhead Section, Guided Missile, Practice, M231 and Components		SHEET 2 OF 3	DRAWING NUMBER See Below NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
	Functional Examination for Assembly Capability to Missile Body:				
	Location of Missile Mounting Holes (see dwg. 9224134)	9		3.3	4.5.4
	Diameter of Missile Mounting Holes (see dwg. 9224134)	9		3.3	4.5.4
	Mounting Surface Outside Diameter (see dwg. 9224134)	9		3.3	4.5.4
	Electrical Resistance of Grounded Electrical Contact	9		3.8	4.5.5
	Paint Adhesion Tests:				
	Adhesion (knife)	13Test Panels*		3.7.2	4.5.6.1
	Adhesion (tape)	13Test Panels*		3.7.2	4.5.6.2

NOTES:
*Any defective in the test panel or test specimen shall reject the first article samples represented by the test panels or test specimens.

SARPA-QA FORM 2567 FEB 74

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T05:20Z
Check the source to verify that this is the current version before use.

TABLE I - FIRST ARTICLE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE		SHEET 3 OF 3		DRAWING NUMBER
	Warhead Section, Guided Missile, Practice, M231 and Components				See Below
					NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
	Corrosion Resistance of Components				
	Protective Finish of:				
	Practice Warhead Body	13Test Specimens*		3.7.1	4.5.9
	Ballast	13Test Specimens*		3.7.1	4.5.9
	Angle Assembly	13Test Specimens*		3.7.1	4.5.9
	Tightness of Ballast Assembly	9		3.6.2	4.5.7
	Static Load Test	9		3.6.1	4.5.8.1

NOTES:

SARPA-QA FORM 2567 FEB 74

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T05:20Z
Check the source to verify that this is the current version before use.

4.4 Quality Conformance Inspection

4.4.1 Inspection Lot Formation.-Inspection lots shall comply with the lot formation provisions of MIL-A-48078. In addition, inspection lots of Warhead Section, GM, Practice Assemblies shall contain:

a. Bodies (dwg. 9224134) from not more than one interfix lot number from one manufacturer.

b. Metal parts from not more than one interfix lot number from one manufacturer.

4.4.2 Examination.-See MIL-A-48078.

a. Sampling Plans.-Unless otherwise specified in the Classification of Defects and Test tables, sampling plans for major and minor defects shall be in accordance with MIL-STD-105, Inspection Level II.

Source: https://assist.dla.mil -- Downloaded: 202640-18T05:20Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER 9224134
4.4.2.1	Body, Practice Warhead				NEXT HIGHER ASSEMBLY 9224024
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined				
Major B					
131	Total length		0.40%	3.2	Gage
132	Distance from Missile mounting end to end of taper		0.40%	3.2	Gage
133	Inside diameter of Ballast at locating diameter (Datum A)		0.40%	3.2	Gage
134	Outside diameter of Missile mounting end		0.40%	3.2	Gage
135	Total runout of Missile mounting end		0.40%	3.2	Gage
136	Perpendicularity of base		0.40%	3.2	Gage
137	Profile of nose improper		0.40%	3.2	Gage
138	Wall thickness		0.40%	3.2	Gage
139	Location/hole pattern of Missile mounting holes		0.40%	3.2	Gage
140	Diameter of Missile mounting holes		0.40%	3.2	Gage
Minor					
201	Protective finish inadequate		0.65%	3.10.2	Visual
202	Evidence of poor workmanship		1.00%	3.10	Visual

NOTES:

SARPA-QA FORM 2567 FEB 74

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T05:20Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER 9224135
4.4.2.2	Ballast				NEXT HIGHER ASSEMBLY 9224024
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined				
Major B					
131	Outside diameter, maximum		0.40%	3.2	Gage
132	Total length, max.		0.40%	3.2	Gage
133	Spacing of channels		0.40%	3.2	Gage
134	Diameter of channels		0.40%	3.2	Gage
135	Configuration of slot		0.40%	3.2	Gage
136	Location of angle mounting hole		0.40%	3.2	Gage
137	Angle mounting hole thread size		0.40%	3.2	Gage
138	Weight of ballast		0.40%	3.4.1	Balance Scale
Minor					
201	Evidence of poor workmanship		1.00%	3.10	Visual

NOTES:

SARPA-QA FORM 2567 FEB 74

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T05:20Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER 9272374
4.4.2.3	Unequal Angle				NEXT HIGHER ASSEMBLY 9224024
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined				
Major B					
131	Diameter, small pin hole		0.40%	3.2	Gage
132	Diameter, large pin hole		0.40%	3.2	Gage
133	True position, large pin hole		0.40%	3.2	Gage
Minor					
201	Tapped hole for fastening missile battery harness		0.40%	3.2	Gage
202	True position, tapped hole		0.40%	3.2	Gage
203	Recessed hole for missile battery harness		0.40%	3.2	Gage
204	Diameter, hole for assembly to ballast		0.40%	3.2	Gage
205	Evidence of poor workmanship		1.00%	3.10	Visual

NOTES:

SARPA-QA FORM 2567 FEB 74

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T05:20Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER 9272375
4.4.2.4	Angle Assembly				NEXT HIGHER ASSEMBLY 9224024
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined				
Major B					
131	Pin height		0.40%	3.2	Gage
132	Position of pins and recessed hole		0.40%	3.2	Gage
Minor					
201	Protective finish inadequate		0.65%	3.10.2	Visual
202	Evidence of poor workmanship		1.00%	3.10	Visual

NOTES:

SARPA-QA FORM 2567 FEB 74

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T05:20Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE	SHEET 1 OF 2	DRAWING NUMBER
4.4.2.5	Warhead Section, Guided Missile, Practice, M231		9224024
			NEXT HIGHER ASSEMBLY

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined				
Major B					
131	Center of gravity - Longitudinal		0.40%	3.5.1	4.5.2.1
132	Weight		100%	3.4	4.5.3
133	Location of missile mounting holes (see Dwg. 9224134)		100%	3.2	4.5.4
134	Diameter of Missile mounting holes (see Dwg. 9224134)		100%	3.2	4.5.4
135	Mounting surface outside diameter (see Dwg. 9224134)		100%	3.2	4.5.4
136	Electrical resistance of grounded electrical contact		100%	3.8	4.5.5
137	Paint adhesion-knife test on test panels		**	3.7.2	4.5.6.1
138	Paint adhesion-tape test on test panels		**	3.7.2	4.5.6.2
139	Tightness of ballast assembly		100%	3.6.2	4.5.7
140	Parts missing, loose or improperly assembled		0.40%	3.10.1	Visual
141	Assembly weight missing		0.40%	3.2	Visual
142	Surface at mounting end free of paint		0.40%	3.2	Visual
Minor					
201	Adhesive sealant missing		0.65%	3.2	Visual
202	Marking missing or improper		0.65%	3.2	Visual

NOTES: **Acceptance testing shall be in accordance with MIL-STD-105 using a single sample plan for normal inspection (Table IIA) at general inspection Level I with lot rejection according to an AQL of 1.50%.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T05:20Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE		SHEET 2 OF 2		DRAWING NUMBER 9224024
4.4.2.5 (Cont'd)	Warhead Section, Guided Missile, Practice, M231				NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
203	Protective finish inadequate		0.65%	3.10.2	Visual
204	Evidence of poor workmanship		1.00%	3.10	Visual

NOTES:

SARPA-QA FORM 2567 FEB 74

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T05:20Z
Check the source to verify that this is the current version before use.

4.4.2.6 Other Components.-The parts and items listed below shall be subjected to the inspections that follow the list. The contractor or vendor shall supply a certificate that the materials used conform with the drawing requirements.

Dwg. No.	Document Nomenclature
9272372	Pin
9272373	Pin
MS15795-741	Washer, Flat
MS35218-40	Screw, Machine Pan Hd.

Quality Conformance Inspections

Categories	Defects	Method of Inspection
Critical:	None defined	
Major B:	AQL 0.40 Percent each	
131.	Operation missing or improperly performed	Visual
Minor:	AQL 0.65 Percent each	
201.	Protective finish inadequate or other evidence of poor workmanship (see 3.10.1, 3.10.2 or 3.10.3)	Visual

4.4.3 Testing

4.4.3.1 Testing.-Testing and examination of the samples for First Article and Quality Conformance are completely described in the First Article and Quality Conformance tables.

4.4.4 Inspection Equipment.-The inspection equipment required to perform the examinations and tests prescribed herein is described in the Paragraph Reference/Inspection Method column in the tables starting with paragraph 4.4.2.1. The contractor shall submit for approval inspection equipment designs in accordance with the terms of the contract. See Section 6 of MIL-A-48078 and 6.3 herein.

Source: https://assist.dla.mil -- Downloaded: 202610-18T05:20Z
Check the source to verify that this is the current version before use.

4.5 Test Methods and Procedures

4.5.1 Materials, Components and Processes.-Compliance with all requirements of Section 3 of this specification shall be ascertained by current and continuing examination of inspection and test data to determine that all components (parts, subassemblies and materials) have been inspected and tested and found to comply with their respective drawing and specification requirements, and that all specified manufacturing processes have been followed.

4.5.1.1 Visual, Mechanical and Electrical Inspections.-The visual, manual, mechanical and electrical inspections and tests shall verify compliance with the requirements of sections 3 and 5 of this specification in accordance with 4.4.2 herein and Table I.

4.5.2 Center of Gravity.

4.5.2.1 Longitudinal.-The practice warhead section shall be mounted to a fixture and measured for longitudinal center of gravity. Any assembly which does not satisfy the drawing requirement for longitudinal center of gravity shall be classed defective.

4.5.3 Weight of Practice Warhead Section.-The warhead section shall be weighed on a balance type scale. Any assembly not meeting the requirements shall be classed defective.

4.5.4 Functional Examination.-The warhead section shall be examined for functional compliance (dwg. 9224024) by assembly to a test fixture which simulates the mounting surface of the missile body. Any assembly which fails to satisfy all of the requirements for a functional fit shall be classed defective.

4.5.5 Resistance of Electrical Contact.-Using a milliohmmeter, the electrical resistance between the electrical contact and the body shall be measured. If the resistance of the grounded contact does not meet the requirement, the warhead section shall be classed defective.

4.5.6 Paint Adhesion

4.5.6.1 Adhesion (Knife).-The knife test for paint adhesion properties of painted test panels shall be performed in accordance with test method 4.5.3 of MIL-C-5541 and method 6304.1 of Federal Test Method Std. No. 141 using a knife as specified therein. If the paint film forming the protective finish on any of the test panels fails to meet the requirements specified, the parts represented by the test panels shall be rejected.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T05:20Z
Check the source to verify that this is the current version before use.

4.5.6.2 Adhesion (Tape).-The tape test for paint adhesion properties of painted test panels shall be performed in accordance with test method 4.5.4 of MIL-C-5541 and method 6301.1 of Federal Test Method Std. No. 141 using masking tape 1" wide and rubber covered roller as specified therein. If the paint film forming the protective finish does not meet the requirements specified, the parts represented by the test panels shall be rejected.

4.5.7 Tightness of Ballast Assembly.-The warhead section shall be inspected for tightness of the magneforming of the warhead body to the ballast grooves by performing the following manual test. Grasp the ballast at the rear within the warhead body and apply a light hand force along the longitudinal axis of the ballast in both the forward and rearward directions, and a light twisting action (torque) in both rotational directions. Any discerned motion of the ballast in any direction shall result in the warhead section being classed defective.

4.5.8 Launch Shock.-In lieu of ballistic flight testing or dynamic acceleration testing, the practice warhead section (dwg. 9224024) shall be subjected to and withstand a Static Load Test as specified in 4.5.8.1 below to satisfy the requirement of 3.6.1.

4.5.8.1 Static Load Test.-The practice warhead sections which will be subjected to this test shall first be examined for tightness of ballast with respect to the shroud end in accordance with the procedures of 4.5.7. A maximum of three (3) inches of the nose end of each warhead shall be cut off in a plane approximately perpendicular to the longitudinal axis. A .201 inch diameter hole (+.0058 - .001) (No. 7 drill bit) shall be drilled in the middle of each magneformed groove approximately .50 inch into the ballast and perpendicular to the warhead's longitudinal axis. These three (3) holes shall be equally spaced around the circumference. A static load shall then be applied through the open nose perpendicular to the forward surface of the ballast in a rearward longitudinal direction of the warhead section, using mounting fixture, gage for checking Ballast position and hydraulic steady load compression testing machine, load cell and calibrated pressure gage with capacity for generating ram forces up to 20,000 lbs. This loading shall be increased very gradually at a rate not to exceed 4000 lbs. per minute until the minimum static load requirement is reached or until structural failure, whichever occurs first. Structural failure is indicated by the fact that the load cannot be further increased without buckling,

Source: https://assist.dla.mil -- Downloaded: 202610-18T05:20Z
Check the source to verify that this is the current version before use.

tearing, or other failure in the shroud skin or in the magneformed joint holding the ballast. At point of static loading to the minimum requirement, measure and record the permanent displacement, if any, of the ballast relative to the warhead skin by measurement with an appropriate plug gage or drill blank inserted into each of the holes in the magneformed grooves in the skin and ballast to their full depth. If the displacement of the ballast does not exceed 0.03 inch in any of the holes, the magneformed joint shall be considered satisfactory. If the maximum loading recorded for a warhead is less than the specified minimum loading requirement before structural failure occurs (as defined above), the warhead shall be classed defective.

4.5.9 Corrosion Resistance.-The chemical film test specimens shall be subjected to a 5 percent salt spray test in accordance with 4.5 of MIL-C-5541 and Method 6061 of Fed. Test Method Std. 141, except the test shall be for 100 hours, using test equipment specified therein. When the chemical film protective finish on any test specimen fails to meet the requirements specified, the parts represented by the failing test specimen shall be rejected.

5. PREPARATION FOR DELIVERY

5.1 Packaging, Packing and Marking.-The parts shall be packaged, packed and marked in accordance with MIL-STD-1169.

6. NOTES

6.1 Intended Use.-The Warhead Section, GM, Practice: M231, covered by this specification, is intended for use in the DRAGON Practice GM, M47.

6.2 Ordering Data.-See MIL-A-48078.

6.3 Submission of Inspection Equipment for Design Approvals. See MIL-A-48078.-Submit equipment designs, as required, to Commander, Picatinny Arsenal, ATTN: SARPA-QA-T-T, Bldg. 92, Dover, New Jersey 07801.

Custodian:
ARMY - PA

Preparing Activity:
ARMY - PA

Project Number: 1336-A204

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T05:20Z
Check the source to verify that this is the current version before use.

FOLD

POSTAGE AND FEES PAID
DEPARTMENT OF THE ARMY
DOD – 314

U.S. MAIL

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

COMMANDER
Picatinny Arsenal
ATTN: SARPA-QA-A
Dover, New Jersey 07801

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T05:20Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers/vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?
   A. GIVE PARAGRAPH NUMBER AND WORDING.

   B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?

   ☐ YES ☐ NO *(If "Yes", in what way?)*

4. REMARKS

SUBMITTED BY *(Printed or typed name and address - Optional)*

TELEPHONE NO.

DATE

DD FORM 1 JAN 72 1426 REPLACES EDITION OF 1 JAN 66 WHICH MAY BE USED

Source: https://assist.dla.mil -- Downloaded: 202610-18T05:20Z
Check the source to verify that this is the current version before use.