A-A-2311
September 27, 1985

COMMERCIAL ITEM DESCRIPTION

PILE, HAND (AMERICAN PATTERN), FLAT

The General Services Administration has authorized the use of this commercial item description in preference to Type VII, Styles A, B, C, and D of Federal Specification GGG-F-325.

This commercial item description covers hand files used for general purpose filing.

Salient characteristics:

Material:	Carbon alloy steel.
Design:	Uniform width and thickness from heel to midpoint (approximately). Tapered in width from approximately the midpoint to point. Thickness parallel or tapered slightly from approximately the middle of the length to point. Two square single-cut edges (one set of parallel cuts on the surface). Furnished in either bastard-cut, second-cut, smooth-cut, or single-cut with chip-breaking grooves as shown in table. Bastard-cut second-cut, and smooth-cut shall be double-cut on each flat (two sets of parallel cuts on the surface, one set crossing the other) (Figure 1). Single-cut with chip-breaking grooves shall be single-cut on each flat and have from four to six chip-breaking grooves per inch, cut diagonally, and be designed for fast stock removal while producing a reasonably smooth surface (Figure 2).
Tang:	Of a conventional shape and size suitable for attachment to a wood handle. Tempered to a maximum hardness of 45 on the Rockwell C scale at a point approximately midway of its length and width.
Teeth:	Uniformly cut or etched and of uniform height throughout the fully cut portion. Cutting surfaces hardened to a uniform hardness. The distance between the heel and point of the file, excluding the tang, shall be hardened to not greater than 68 nor less than 64 on the Rockwell C scale. Free from decarburization and brittleness.
Marking:	Marked with the country of origin and the name of the manufacturer or with a trademark of such known character that the source of manufacture may be readily determined.
Workmanship:	The teeth of the file shall be well-defined, sharp, and uniform in height and form. There shall be no evidence of rust or other defect which may impair serviceability, durability, or appearance.



FIGURE 1

FSC 5110

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:21Z
Check the source to verify that this is the current version before use.




FIGURE 2

National Stock Number	Length Inches	Dimensions at largest section A Inches	B Inch	Number of teeth per inch Min.	Max.	Allowable distortion (maximum) Inch	Allowable warpage (maximum) Degrees
			Bastard-cut				
5110-00-249-2847	6	5/8	5/32	30	33	0.008	2
5110-00-249-2848	8	13/16	7/32	23	26	.010	2
5110-00-249-2849	10	1	1/4	20	23	.025	2
5110-00-234-6539	12	1-3/16	9/32	17	19	.025	2
5110-00-203-5486	14	1-3/8	5/16	16	18	.050	2
5110-00-203-5463	16	1-17/32	11/32	14	16	.060	2
5110-00-239-7707	18	1-23/32	3/8	13	15	.070	2
			Second-cut				
5110-00-234-6531	6	5/8	5/32	41	45	.008	2
5110-00-234-6534	8	13/16	7/32	33	37	.010	2
5110-00-234-6537	10	1	1/4	29	32	.025	2
5110-00-203-4855	12	1-3/16	9/32	26	28	.025	2
5110-00-203-4854	14	1-3/8	5/16	23	25	.050	2
			Smooth-cut				
5110-00-234-6532	6	5/8	5/32	52	57	.008	2
5110-00-203-4935	8	13/16	7/32	44	48	.010	2
5110-00-249-2850	10	1	1/4	37	41	.025	2
5110-00-203-4936	12	1-3/16	9/32	33	36	.025	2
5110-00-234-6544	14	1-3/8	5/16	29	32	.050	2
			Single-cut with chip-breaking grooves				
5110-00-529-3239	10	31/32	1/4	18	22	.025	2
5110-00-529-3452	14	1-11/32	5/16	16	18	.050	2

Length dimension: Measured from the point (free or front end) to the heel (junction of the tang with the body of the file) and have a tolerance of plus or minus 1/8 inch.

Tolerance: Width (A) - plus or minus 1/16 inch.
Thickness (B) - files 6 inches in length - plus or minus 1/32 inch. Files over 6 inches in length - plus or minus 1/16 inch.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:21Z
Check the source to verify that this is the current version before use.

Regulatory requirements. In accordance with the section 23.403 of the Federal Acquisition Regulations, the Government's policy is to acquire items composed of the highest percentage of recovered materials practicable, consistent with maintaining a satisfactory level of competition without adversely affecting performance requirements or exposing suppliers' employees to undue hazards from the recovered materials.

Preservation, packaging, packing, labeling, and marking. The preservation, packaging, packing, labeling, and marking shall be as specified in the contract or order.

PREPARING ACTIVITY:

GSA-PSS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:21Z
Check the source to verify that this is the current version before use.