A-A-51840A
6 June 1989
SUPERSEDING
A-A-51840(DM)
4 March 1987

COMMERCIAL ITEM DESCRIPTION

SCISSORS, EAR, SERRATED (Joseph)

The General Services Administration has authorized the use of this commercial item description.

This commercial item description covers Joseph style serrated ear scissors suitable for use in ear surgery.

Salient characteristics:

Material. The scissors shall be fabricated from Class 4 martensitic corrosion-resistant steel in accordance with American Society for Testing and Materials (ASTM) Designation F899.

Hardness. The scissors shall have a Rockwell Hardness C scale (HRC) of 48 to 53 in accordance with ASTM Designations E18 or E92 whichever is applicable. Conversion of hardness values shall be in accordance with ASTM Designation E140.

Characteristics. The scissors shall be a straight or curved ear scissors with one or both serrated blades used in eye, ear, and throat surgery procedures. The scissors shall be medium weight and 5-3/4 inches long. Both tips shall be sharp. The scissors shall be in accordance with Defense Personnel Support Center (DPSC) Drawing No. 23390.

Finish. The finish of the scissors shall be mirror or satin. The finish shall be uniform and free from cracks, grind or tool marks, burrs, and dirt or polishing materials.

Identification marking and labeling. The scissors shall be marked with the name or registered trademark of the contractor and the word "stainless". In addition, scissors of foreign manufacture shall bear the name of the country of manufacture.

Corrosion-resistance. The scissors shall show no sign of corrosion or copper plating when tested in accordance with ASTM Designation F1089.

AMSC N/A FSC 6515

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:01Z
Check the source to verify that this is the current version before use.

Performance. The scissors shall not bind or snag the test material when tested as specified herein. Each cut shall be made using the most distal seventy-five percent of the blade.

Workmanship. The scissors shall be free from defects which detract from its appearance or impair its serviceability.

Unit. Each (EA). One scissors, as specified, constitutes one unit.

Quality Assurance Provisions.

Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of three years after delivery of the supplies to which such records relate.

Inspection. Inspection, as used herein, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

Tests. Tests shall be conducted to determine compliance with specification requirements. Where feasible, the same sample shall be used for the determination of two or more test characteristics.

Performance test. The scissors shall be tested in accordance with the scissors performance test in ASTM Designation F1089. The test material shall be medium rubber dam in accordance with Federal Specification ZZ-R-690 (See Note 2).

Source: https://assist.dla.mil -- Downloaded: 202610-26T09:01Z
Check the source to verify that this is the current version before use.

Sampling for tests. Sampling for tests shall be conducted in accordance with MIL-STD-105 and as specified herein. The inspection level shall be S-2. Dimensional testing shall be at a 1.5% AQL, hardness testing at a 1.5% AQL, and corrosion and performance testing at a 1.0% AQL. The unit of product for test purposes shall be one scissors.

Metric products. Products manufactured to metric dimensions will be considered on an equal basis with those manufactured using inch-pound units, providing they fall within the tolerances specified using conversion tables contained in the latest revision of Federal Standard No. 376, and all other requirements of this document are met.

If a product is manufactured to metric dimensions and those dimensions exceed the tolerances specified in the inch/pound units, a request should be made to the contracting officer to determine if the product is acceptable.

The contracting officer has the option of accepting or rejecting the product.

Contractor certification. The contractor shall certify that the product offered meets the salient characteristics of this description and conforms to the producers' own drawings, specifications, standards, and quality assurance practices. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Regulatory requirements.

Federal Food, Drug and Cosmetic Act. If the product covered by this document has been determined by the U.S. Food and Drug Administration to be under its jurisdiction, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of the Federal Food, Drug and Cosmetic Act, as amended, and regulations promulgated thereunder. In addition, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of all other applicable Federal, State, and local statutes, ordinances, and regulations.

Recovered materials. The offeror/contractor is encouraged to use recovered material in accordance with Public Law 94-580, as amended and as implemented by Federal Acquisition Regulation Subpart 23.4 to the maximum extent practical.

Source: https://assist.dla.mil - Downloaded: 2026-10-26T09:01Z
Check the source to verify that this is the current version before use.

Preservation, packaging, packing, labeling, and marking. Unless otherwise specified, preservation, packaging, and packing shall be to a degree of protection to preclude damage to containers and/or contents thereof under normal shipping conditions, handling, etc., involving shipment from the supply source to the receiving activity, plus reshipment from receiving activity, and shall conform to applicable carrier's rules and regulations. Intermediate and exterior package quantities and labeling and marking shall be as specified in the contract and/or order.

NOTE 1: The following National Stock Number are covered by this document:

NSN	ITEM IDENTIFICATION
6515-01-111-1013	SCISSORS, EAR, SERRATED, Joseph, Curved Blades
6515-01-112-6408	SCISSORS, EAR, SERRATED, Joseph, Straight Blades

NOTE 2: The test material, medium size dental rubber dam, is commercially available from the HYGENIC CORPORATION, AKRON, OHIO.

Ordering data (Intermediate/exterior package quantities and labeling and marking must be specified in the contract and/or order).

MILITARY INTERESTS:

Custodians:

Army - MD
Navy - MS
Air Force - 03

Preparing Activity:

DoD-MB

Agent:

DLA-DM

CIVIL AGENCY COORDINATING ACTIVITIES:

VA-OSS
PHS
FDA-MPQAS

Project No. 6515-4575

Source: https://assist.dla.mil -- Downloaded: 202610-26T09:01Z
Check the source to verify that this is the current version before use.