The documentation and process conversion measures necessary to comply with this revision shall be completed by 28 January 2011.

INCH-POUND

MIL-PRF-19500/286J
28 October 2011
SUPERSEDING
MIL-PRF-19500/286H
w/AMENDMENT 1
13 August 2009

PERFORMANCE SPECIFICATION SHEET

SEMICONDUCTOR DEVICE, DIODE, SILICON, POWER RECTIFIER, TYPES 1N4245 THROUGH 1N4249, JAN, JANTX, JANTXV, AND JANHC

These devices are inactive for new design, preferred devices are 1N5614, 1N5616, 1N5618, 1N5620, 1N5622 of MIL-PRF-19500/427.

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-PRF-19500.

1. SCOPE

1.1 Scope. This specification covers the performance requirements for silicon, power rectifier, medium-recovery diodes. Four levels of product assurance are provided for each device type as specified in MIL-PRF-19500.

1.2 Physical dimensions. See figure 1 and figure 2.

1.3 Maximum ratings.

Type	V_R	V_{RWM}	I_O (1) T_A = 55°C (2)	I_{FSM} I_O = 1.0 A dc t_p = 8 ms
	V dc	V (pk)	A dc	A (pk)
1N4245	200	200	1.0	25
1N4246	400	400	1.0	25
1N4247	600	600	1.0	25
1N4248	800	800	1.0	25
1N4249	1,000	1,000	1.0	25

Types	Barometric pressure (reduced)	T_{STG} and T_J	$R_{\Theta JL}$ at L = .375 inch (9.53 mm)	$Z_{\theta JX}$	t_{rr}
	mm Hg	°C	°C/W	°C/W	µs
1N4245	8	-65 to +175	42	4.5	5.0
1N4246	8	-65 to +175	42	4.5	5.0
1N4247	8	-65 to +175	42	4.5	5.0
1N4248	33	-65 to +175	42	4.5	5.0
1N4249	33	-65 to +175	42	4.5	5.0

See notes on next page.

* Comments, suggestions, or questions on this document should be addressed to DLA Land and Maritime, ATTN: VAC, P.O. Box 3990, Columbus, OH 43218-3990, or emailed to Semiconductor@dla.mil. Since contact information can change, you may want to verify the currency of this address information using the ASSIST Online database at https://assist.daps.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:04Z
Check the source to verify that this is the current version before use.

1.3 Maximum ratings - Continued.

(1) I_O rating is independent of heat sinking, special mounting, or forced air across the body or leads of the device.
(2) Derate linearly at 8.33 mA/°C between T_A = +55°C to +175°C.

2. APPLICABLE DOCUMENTS

2.1 General. The documents listed in this section are specified in sections 3, 4, or 5 of this specification. This section does not include documents cited in other sections of this specification or recommended for additional information or as examples. While every effort has been made to ensure the completeness of this list, document users are cautioned that they must meet all specified requirements of documents cited in sections 3, 4, or 5 of this specification, whether or not they are listed.

2.2 Government documents.

2.2.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

DEPARTMENT OF DEFENSE SPECIFICATIONS

MIL-PRF-19500 - Semiconductor Devices, General Specification for.

DEPARTMENT OF DEFENSE STANDARDS

MIL-STD-750 - Test Methods for Semiconductor Devices.

* (Copies of these documents are available online at https://assist.daps.dla.mil/quicksearch/ or https://assist.daps.dla.mil. or from the Standardization Document Order Desk, 700 Robbins Avenue, Building 4D, Philadelphia, PA 19111-5094.)

2.3 Order of precedence. Unless otherwise noted herein or in the contract, in the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.


3. REQUIREMENTS

3.1 General. The individual item requirements shall be as specified in MIL-PRF-19500 and as modified herein.

3.2 Qualification. Devices furnished under this specification shall be products that are manufactured by a manufacturer authorized by the qualifying activity for listing on the applicable qualified manufacturer's list (QML) before contract award (see 4.2 and 6.3).

3.3 Abbreviations, symbols, and definitions. Abbreviations, symbols, and definitions used herein shall be as specified in MIL-PRF-19500.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:04Z
Check the source to verify that this is the current version before use.





Symbol	Dimensions				Notes
	Inches		Millimeters		
	Min	Max	Min	Max	
BD	.065	.110	1.65	2.79	3
BL	.125	.250	3.30	5.21	4
LD	.027	.032	0.66	0.84	
LL	.70	1.30	25.4	38.10	

NOTES:
1. Dimensions are in inches.
2. Millimeters are given for general information only.
3. Dimension BD shall be measured at the largest diameter.
4. The BL dimension shall include the entire body including slugs and sections of the leads over which the diameter is uncontrolled. This uncontrolled area is defined as the zone between the edge of the diode body and extending .050 inch (1.27 mm) onto the leads.
5. The shape of the body, within the bounds of the dimensions is optional.
6. In accordance with ASME Y14.5M, diameters are equivalent to ϕx symbology.

FIGURE 1. Physical dimensions.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:04Z
Check the source to verify that this is the current version before use.





A - version

Ltr	Dimensions			
	Inches		Millimeters	
	Min	Max	Min	Max
A	.047	.053	1.19	1.35
B	.007	.011	0.18	0.28
C	.033	.037	0.84	0.94

NOTES:
1. Dimensions are in inches.
2. Millimeters are given for general information only.
3. The physical characteristics of the die are:
   Top metal: Gold 10,000 Å minimum.
   Back metal: Gold 4,000 Å minimum.
4. In accordance with ASME Y14.5M, diameters are equivalent to ϕX symbology.

FIGURE 2. JANHC (A-version) die dimensions.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:04Z
Check the source to verify that this is the current version before use.

3.4 Diode construction. Except for the JANHC devices, these devices shall be constructed utilizing metallurgically bonded, thermally matched, non-cavity, double-plug construction. The metallurgical bond between the chip and the plug shall meet the category I requirement of MIL-PRF-19500, appendix A.

3.5 Interface and physical dimensions. Interface and physical dimensions shall be as specified in MIL-PRF-19500, and on figure 1 and figure 2. No lead (Pb) shall be used in the construction of the die bonds.

3.5.1 Lead finish. Lead finish shall be solderable in accordance with MIL-PRF-19500, MIL-STD-750, and herein. Where a choice of lead finish is desired, it shall be specified in the acquisition document (see 6.2).

3.6 Electrical performance characteristics. Unless otherwise specified herein, the electrical performance characteristics are as specified in 1.3 and table I.

3.7 Electrical test requirements. The electrical test requirements shall be group A as specified herein.

3.8 Marking. Marking shall be in accordance with MIL-PRF-19500. At the option of the manufacturer, marking may be omitted from the body, but shall be retained on the initial container.

3.9 Workmanship. Semiconductor devices shall be processed in such a manner as to be uniform in quality and shall be free from other defects that will affect life, serviceability, or appearance.

4. VERIFICATION

4.1 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. Qualification inspection (see 4.2).

b. Screening (see 4.3).

c. Conformance inspection (see 4.4).

4.2 Qualification inspection. Qualification inspection shall be in accordance with MIL-PRF-19500 and as specified herein.

4.2.1 Group E qualification. Group E qualification shall be performed herein for qualification or requalification only. In case qualification was awarded to a prior revision of the specification sheet that did not request the performance of table II tests, the tests specified in table II herein that were not performed in the prior revision shall be performed on the first inspection lot to this revision to maintain qualification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:04Z
Check the source to verify that this is the current version before use.

4.2.1.1 JANHC die. Qualification shall be in accordance with appendix H of MIL-PRF-19500.

* 4.3 Screening (JANTX, and JANTXV levels only). Screening shall be in accordance with appendix E, table E-IV of MIL-PRF-19500 and as specified herein. The following measurements shall be made in accordance with table I herein. Devices that exceed the limits of table I herein shall not be acceptable.

Screen (see appendix E, table E-IV of MIL-PRF-19500)	Measurement JANTX and JANTXV levels
(1) 3c	See 4.3.2
7a 7b	Not applicable Optional
9	Not applicable
10	Method 1038 of MIL-STD-750, condition A
11	I_{R1} and V_{F1}
12	See 4.3.1
(2) 13	Subgroup 2 of table I herein. $\Delta V_{F1} \leq +.1, -.2$ V dc; $\Delta I_{R1} \leq 100$ percent of initial values or ±100 nA dc, whichever is greater. Scope display evaluation (see 4.5.3)
14a (3) 14b	Not applicable Required

(1) Shall be performed anytime after temperature cycling, screen 3a, and does not need to be repeated in screening requirements.
(2) Thermal impedance is not required in screen 13, if it has already previously performed.
(3) For clear glass diodes, the hermetic seal (gross leak) may be performed at anytime after temperature cycling.

4.3.1 Power burn-in conditions. Power burn-in conditions are as follows (see 4.5.2): $I_{O(min)}$ = Rated I_O (see 1.3 herein). T_A = 55°C maximum. Test conditions in accordance with method 1038 of MIL-STD-750, condition B. Adjust I_O or T_A to achieve the required T_J. T_J = 135°C minimum. With approval of the qualifying activity and preparing activity, alternate burn-in criteria (hours, bias conditions, T_J, mounting conditions) may be used for JANTX and JANTXV quality levels. A justification demonstrating equivalence is required. In addition, the manufacturing site's burn-in data and performance history will be essential criteria for burn-in modification approval.

* 4.3.2 Thermal impedance. The thermal impedance measurements shall be performed in accordance with method 3101 or 4081 as applicable of MIL-STD-750 using the guidelines in that method for determining I_M, I_H, t_H, and K factor where appropriate. Measurement delay time (t_{MD}) = 70 μs max. See table II, subgroup 4 herein. Thermal impedance limit used by supplier shall not exceed the thermal impedance graph, see figure 3 herein.

4.4 Conformance inspection. Conformance inspection shall be in accordance with MIL-PRF-19500 and as specified herein.

4.4.1 Group A inspection. Group A inspection shall be conducted in accordance with MIL-PRF-19500 and table I.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:04Z
Check the source to verify that this is the current version before use.

4.4.2 Group B inspection. Group B inspection shall be conducted in accordance with the conditions specified for subgroup testing in appendix E, table E-VIb (JANTX, and JANTXV) of MIL-PRF-19500, and as follows. Electrical measurements (end-points) shall be in accordance with table I, group A, subgroup 2 herein.

* 4.4.2.1 Group B inspection, appendix E, table E-VIb, of MIL-PRF-19500.

Subgroup	Method	Inspection
B2	4066	I_{FSM} = 25 A (pk), ten surges of 1/120 s each at 1 minute intervals, super-imposed on I_0 = 1.0 A dc, V_R = rated V_{RWM} (see 1.3).
B3	1027	I_0 = 1.0 A dc minimum; T_A = +55°C (max.); T_J = +150°C minimum; f = 50 - 60 Hz; V_R = rated V_{RWM} (see 1.3). Adjust I_O to achieve a T_J = +150°C minimum.

4.4.3 Group C inspection. Group C inspection shall be conducted in accordance with the conditions specified for subgroup testing in appendix E, table E-VII of MIL-PRF-19500, and as follows. Electrical measurements (end-points) shall be in accordance with of table I, group A, subgroup 2 herein.

* 4.4.3.1 Group C inspection, appendix E, table E-VII, of MIL-PRF-19500.

	Subgroup	Method	Inspection
	C2	2036	Tension: Test condition A; weight = 10 pounds; t = 15 seconds. Lead fatigue: Test condition E; weight 2 pounds.
*	C5	4081	+25°C ≤ T_R ≤35°C , $R_{\Theta JL}$ ≤ 42°C/W, L = .375 inch (9.525 mm) (see 1.3 and 4.3.2).
	C6	1026	I_0 = 1.0 A dc minimum; T_A = +55°C (max.); T_J = +150°C minimum; f = 50 - 60 Hz; V_R = rated V_{RWM} (see 1.3). Adjust I_O to achieve a T_J = +150°C minimum.
*	C8	2031	n = 22, c = 0. One cycle.

4.4.4 Group E inspection. Group E inspection shall be conducted in accordance with the conditions specified for subgroup testing in appendix E, table E-IX of MIL-PRF-19500 and table II herein. Electrical measurements (end-points) shall be in accordance with the applicable inspections of table I, subgroup 2 herein.

4.5 Methods of inspection. Methods of inspection shall be as specified in the appropriate tables and as follows.

4.5.1 Inspection conditions. Unless otherwise specified, all inspections shall be conducted at T_A = room ambient as defined in the general requirements of 4.5 of MIL-STD-750.

4.5.2 Free air power burn-in and life tests. The use of a current limiting or ballast resistor is permitted provided that each DUT still sees the full P_t (minimum) and that the minimum applied voltage, where applicable, is maintained through out the burn-in period. Use method 3100 of MIL-STD-750 to measure T_J.

4.5.2.1 Mounting configurations. Any clips or heat sink mounting configurations may be utilized provided that I_O is adjusted such that the junction temperature of each diode is maintained at T_J = +135°C minimum for burn-in screening and T_J = +150°C minimum for JANTX and JANXV life testing.

4.5.3 Scope display evaluation. Scope display evaluation shall be sharp and stable in accordance with method 4023 of MIL-STD-750. Scope display may be performed on ATE (automatic test equipment) for screening only with the approval of the qualifying activity. Scope display in table I, group A, subgroup 4 shall be performed on a scope. Reverse current over the knee shall be 500 µA peak.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:04Z
Check the source to verify that this is the current version before use.

* 4.5.4 Peak reverse power test. This test shall be measured as on the figure 4 test circuit, or equivalent. A 20 microsecond half-sine waveform of current shall be used and peak reverse power shall be determined by the product of peak reverse voltage and peak reverse current.

* 4.5.5 Pulse measurements. Conditions for pulse measurement shall be as specified in section 4 of MIL-STD-750.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:04Z
Check the source to verify that this is the current version before use.

* TABLE I. Group A inspection.

Inspection 1/	MIL-STD-750		Symbol	Limits		Unit
	Method	Conditions		Min	Max	
Subgroup 1						
Visual and mechanical inspection	2071					
Subgroup 2 2/						
Thermal impedance	3101	See 4.3.2	$Z_{\theta JX}$		4.5	°C/W
Forward voltage	4011	I_F = 1 A dc (pulsed, see 4.5.5); duty cycle = 2 percent maximum	V_{F1}	0.6	1.3	V (pk)
Forward voltage	4011	I_F = 3 A (pk), duty cycle ≤ 2 percent pulsed, tp ≤ 8.3 ms	V_{F2}	0.8	1.3	V (pk)
Reverse current leakage	4016	DC method; V_R = rated (see 1.3)	I_{R1}		1.0	µA dc
Breakdown voltage	4021	I_R = 100 µA dc	$V_{(BR)}$			
1N4245				240		V
1N4246				480		V
1N4247				720		V
1N4248				960		V
1N4249				1,150		V
Subgroup 3						
High temperature operation:		T_A = +125°C				
Reverse current leakage	4016	DC method, V_R = rated (see 1.3)	I_{R2}		150	µA dc
Low temperature operation:		T_A = -55°C				
Forward voltage	4011	I_F = 3.0 A (pk), duty cycle ≤ 2 percent pulsed, tp ≤ 8.3 ms	V_{F3}		1.5	V dc

See footnotes at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:04Z
Check the source to verify that this is the current version before use.

* TABLE I. Group A inspection - Continued.

Inspection 1/	MIL-STD-750		Symbol	Limits		Unit
	Method	Conditions		Min	Max	
Subgroup 4						
Reverse recovery time	4031	Condition B, I_F = 0.5 A, I_R = 1.0 A, $I_{(REC)}$ = 0.25 A	t_{rr}		5	µs
Scope display	4023	Sharp and stable, n = 116; c = 0				
Subgroup 5						
Not applicable						
Subgroup 6						
Forward surge	4066	I_{FSM} = 25 A (pk); ten surges of 8.3 ms each at 1 minute intervals, superimposed on I_O = 1 A				
		V_{RWM} = rated (see 1.3); T_A = +55°C				
Electrical measurements		See table I, subgroup 2				
Subgroup 7						
Not applicable						

1/ For sampling plan, see MIL-PRF-19500.
2/ This test required for the following end-point measurement only:
Group B, subgroup 3, 4, and 5 (JANS).
Group B, subgroups 2 and 3 (JAN, JANTX, and JANTXV).
Group C, subgroup 2.
Group E, subgroup 1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:04Z
Check the source to verify that this is the current version before use.

* TABLE II. Group E inspection (all quality levels) for qualification and requalification only.

Inspection	MIL-STD-750		Sampling plan
	Method	Conditions	
Subgroup 1A			
Temperature cycling (air to air)	1/ 1051	20 cycles, except high temperature shall be 150°C and low temperature shall be -195°C.	45 devices c = 0
Hermetic seal 2/	1071		
Electrical measurements		See table I, subgroup 2 and table III, steps 1 and 2.	
Subgroup 1B			
Temperature cycling (air to air)	1051	500 cycles, condition C, -65°C to +175°C.	45 devices c = 0
Hermetic seal 2/	1071		
Electrical measurements		See table I, subgroup 2 and table III, steps 1 and 2.	
Subgroup 2			
Steady-state dc blocking life	1048	T_A = +150°C; t = 1,000 hours +65, -0 hours; dc = 80 - 85 percent rated V_{RWM} (see 1.3).	22 devices c=0
Electrical measurements		See table I, subgroup 2 and table III, steps 1 and 2.	
Subgroup 4			
Thermal impedance		See MIL-PRF-19500.	
Subgroup 5			
Barometric pressure (reduced)	1001	Pressure = 8 mm Hg for 1N4245, 1N4246, and 1N4247. Pressure = 33 mm Hg for 1N4248 and 1N4249.	22 devices c = 0
Subgroup 6			
ESD	1020	Test is required for non–sensitive listing to prove capability.	22 devices c = 0

See footnotes at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:04Z
Check the source to verify that this is the current version before use.

* TABLE II. Group E inspection (all quality levels) for qualification and requalification only – Continued.

Inspection	MIL-STD-750		Sampling plan
	Method	Conditions	
Subgroup 8			
Peak reverse power	4065	Peak reverse power (P_{RM}) = shall be characterized by the supplier and the data shall be available to the Government. Test shall be performed on each sublot.	45 devices c = 0
Electrical measurements		During the P_{RM} test, the voltage (V_{BR}) shall be monitored to verify it has not collapsed. Any collapse in V_{BR} during or after the P_{RM} test, or rise in leakage current (I_R) after the test, that exceeds I_{R1} in table I herein shall be considered a failure to that level of applied P_{RM}. Progressively higher levels of P_{RM} shall be applied until failure occurs on all devices within the chosen sample size.	
Subgroup 9			
Resistance to glass cracking	1057	Test condition B. Step stress to destruction by increasing cycles or up to a maximum of 25 cycles.	45 devices c = 0
Subgroup 10		I_{FSM} = rated (see 1.3); ten surges of 8.3 ms each at 1 minute intervals superimposed on I_O = 1.0 A (see 1.3); V_{RWM} = rated (see 1.3); T_A = + 55°C.	22 devices c = 0
Forward surge	4066		
Electrical measurement		See table I, subgroup 2.	

1/ Test method 1056 of MIL-STD-750, condition D, using liquid nitrogen, may be used in lieu of test method 1051.
2/ For opaque glass diodes use test method 2068 of MIL-STD-750.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:04Z
Check the source to verify that this is the current version before use.

* TABLE III. Groups A, B, C, and E delta measurements. 1/ 2/ 3/ 4/

Step	Inspection	MIL-STD-750		Symbol	Limits		Unit
		Method	Conditions		Min	Max	
1.	Forward voltage	4011	I_F = 3.0 A dc pulse width = 8.3 ms maximum, duty cycle = 2 percent maximum.	ΔV_{F2}		±0.1 V dc maximum	
2.	Reverse current	4016	DC method; V_R = rated (see 1.3).	ΔI_{R1}		±50 nA dc or ±100 percent of initial value, whichever is greater.	

1/ Devices that exceed the table I, subgroup 2 limits for this test shall not be accepted.
2/ The electrical measurements for group B inspection in appendix E, table E-VIb (JAN and JANTX) of MIL-PRF-19500 are as follows: Subgroup 3 and 6, see table III herein, steps 1 and 2.
3/ The electrical measurements for group C inspection in appendix E, table E-VII of MIL-PRF-19500 are as follows: Subgroup 6, see table III herein, steps 1 and 2.
4/ The electrical measurements for group E inspection in table E-IX of MIL-PRF-19500 are as follows:
a. Subgroup 1, see table III herein, steps 1 and 2.
b. Subgroup 2, see table III herein, steps 1 and 2.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:04Z
Check the source to verify that this is the current version before use.





FIGURE 3. Thermal impedance graph $R_{\theta JL}$ 36°C/W.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:04Z
Check the source to verify that this is the current version before use.



NOTES:

L = 13T H22 on 1 inch (25.4 mm) diameter form (air core).
C ~ 1 to 10 μfd to give 20 μs pulse width.
V - Adjustable to 200 volts for power desired in DUT.
D1 - 3 kV; 600 Ma (1N3647 or equivalent).
D2, D3 - 600 V; 3A (1N5552 or equivalent).
* Values not stated are determined at the time of test.




FIGURE 4. Peak reverse power measurement circuit and waveform.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:04Z
Check the source to verify that this is the current version before use.

5. PACKAGING

5.1 Packaging. For acquisition purposes, the packaging requirements shall be as specified in the contract or order (see 6.2). When packaging of materiel is to be performed by DoD or in-house contractor personnel, these personnel need to contact the responsible packaging activity to ascertain packaging requirements. Packaging requirements are maintained by the Inventory Control Point's packaging activities within the Military Service or Defense Agency, or within the Military Service's system commands. Packaging data retrieval is available from the managing Military Department's or Defense Agency's automated packaging files, CD-ROM products, or by contacting the responsible packaging activity.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory. The notes specified in MIL-PRF-19500 are applicable to this specification.)

6.1 Intended use. Semiconductors conforming to this specification are intended for original equipment design applications and logistic support of existing equipment.

6.2 Acquisition requirements. Acquisition documents should specify the following:

a. Title, number, and date of this specification.

b. Packaging requirements (see 5.1).

c. Lead finish (see 3.5.1).

d. Product assurance level and type designator.

* 6.3 Qualification. With respect to products requiring qualification, awards will be made only for products which are, at the time of award of contract, qualified for inclusion in Qualified Manufacturers List (QML 19500) whether or not such products have actually been so listed by that date. The attention of the contractors is called to these requirements, and manufacturers are urged to arrange to have the products that they propose to offer to the Federal Government tested for qualification in order that they may be eligible to be awarded contracts or orders for the products covered by this specification. Information pertaining to qualification of products may be obtained from DLA Land and Maritime, ATTN: VQE, P.O. Box 3990, Columbus, OH 43218-3990 or e-mail vqe.chief@dla.mil. An online listing of products qualified to this specification may be found in the Qualified Products Database (QPD) at https://assist.daps.dla.mil .

6.4 Substitution information. Devices covered by this specification are substitutable for the manufacturer's and user's Part or Identifying Number (PIN). This information in no way implies that manufacturer's PINs are suitable as a substitute for the military PIN.

6.5 Suppliers of die (if applicable).

JANC ordering information	
	Manufacturer
PIN	14552
1N4245	JANHCA4245
1N4246	JANHCA4246
1N4247	JANHCA4247
1N4248	JANHCA4248
1N4249	JANHCA4249

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:04Z
Check the source to verify that this is the current version before use.

* 6.6 Changes from previous issue. The margins of this specification are marked with asterisks to indicate modifications generated by this amendment. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations.

Custodians:
Army - CR
Navy - EC
Air Force - 85
DLA - CC

Review activities:
Army - AR, MI
Navy - AS, MC
Air Force - 19, 99

Preparing activity:
DLA - CC

(Project 5961-2010-096)

* NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.daps.dla.mil .

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T14:04Z
Check the source to verify that this is the current version before use.