FF-S-200B
17 AUGUST 2004
SUPERSEDING
FF-S-200A
October 24, 1969

FEDERAL SPECIFICATION

SETSCREWS: HEXAGON SOCKET AND SPLINE SOCKET, HEADLESS

The General Services Administration has authorized the use of this federal specification by all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers hexagon socket and spline socket headless setscrews.

1.2 Classification.

1.2.1 Types. Setscrews shall be of the following types, as specified (see 6.2).

Type I - Hexagon socket, headless.

Type II - Spline socket, headless.

1.2.2 Styles. Setscrews shall be of the following styles, as specified (see 6.2).

Style 1 - Flat point.
Style 2 - Cone point.
Style 3 - Oval point.
Style 4 - Cup point.
Style 5 - Full-dog point.
Style 6 - Half-dog point.

1.2.3 Size. Setscrews shall be classified by size in accordance with the basic major diameter of the thread (see 6.2).

1.2.4 Length. Setscrews shall be of the length specified in 6.2.

Comments, suggestions, or questions on this document should be addressed to: Defense Supply Center Philadelphia, ATTN: DSCP-ITAA, 700 Robbins Avenue, Philadelphia, PA 19111-5096 or emailed to dscpg&ispeccomments@dla.mil. Since contact information can change, you may want to verify the currency of this address information using the ASSIST Online database at www.dodssp.daps.mil.

AMSC N/A FSC 5305

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:46Z
Check the source to verify that this is the current version before use.

2. APPLICABLE DOCUMENTS

2.1 Government Publications. The following documents, of the issues in effect on the date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

Military Specifications:

MIL-F-495 - Finish, Chemical, Black, for Copper Alloys.
MIL-DTL-l3924 - Coating, Oxide, Black, for Ferrous Metals.
MIL-DTL-18240 – Fastener Element, Self-Locking, Threaded Fastener 250ºF Maximum.

(Copies of Military Specifications and Standards required by contractors in connection with specification procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on the date of invitation for bids or request for proposals shall apply.

American Society of Mechanical Engineers (ASME)

ASME B1.1 - Unified Inch Screen Threads (UN and UNR Thread Form)
ASME B18.3 – Socket Cap, Shoulder, and Set Screws, Hex and Spline Key (Inch Series)

(Application for copies should be addressed to the American Society of Mechanical Engineers (ASME), Order Department: 22 Law Drive, P. O. Box 2900, Fairfield, NJ 07007-2900.)

American Society for Quality Control

ASQ Z1.4 – Sampling Procedures and Tables for Inspection by Attributes.

(Application for copies should be addressed to the American Society for Quality Control, 611 East Wisconsin Avenue, Milwaukee, WI 53202.)

American Society for Testing and Materials (ASTM)

ASTM A342 - Standard Test Methods for Permeability of Feebly Magnetic Materials
ASTM B36 - Standard Specification for Brass Plate, Sheet, Strip, and Rolled Bar
ASTM B134 - Standard Specification for Brass Wire
ASTM B633 - Standard Specification for Electrodeposited Coatings of Zinc on Iron and Steel
ASTM E18 - Standard Test Methods for Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials
ASTM E172 - Standard Practice for Describing and Specifying the Excitation Source in Emission Spectrochemical Analysis
ASTM E1282 - Standard Guide for Specifying the Chemical Compositions and Selecting Sampling Practices and Quantitative

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:46Z
Check the source to verify that this is the current version before use.

Analysis Methods for Metals, Ores and Related Materials

(Application for copies should be addressed to the American Society for Testing and Materials, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.)

Society of Automotive Engineer (SAE)

AMS-QQ-P-35	- Passivation Treatments for Corrosion-Resistant Steel
AMS-STD-66	- Steel: Chemical Composition and Hardenability
AMS-QQ-P-416	- Plating, Cadmium (Electrodeposited)
AMS-H-6875	- Heat Treatment of Steel Raw Materials

(Application for copies should be addressed to the SAE, International, 400 Commonwealth Drive, Warrendale, PA 15096-0001.)

2.3 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein, the text of this specification shall take precedence. Nothing in this specification, however, shall supersede applicable laws and regulations unless a specific exemption is obtained.

3. REQUIREMENTS

3.1 Material. Setscrews shall be made of one of the following material as specified (see 6.2).

3.1.1 Alloy Steel. Alloy steel shall be AISI 4032, 4037, 40L37, 4137, 4140, 41L40, 8630, 8740, in accordance with SAE-AMS-STD-66, which can be heat treated in accordance with SAE-AMS-H-6875 to meet the hardness requirement of 3.3.

3.l.2 Corrosion-resisting steel.

3.1.2.1 Austenitic. Austenitic corrosion-resisting steel shall be of the 300 Series in accordance with SAE-AMS-STD-66 or alloys 316/316L. For superior corrosion resistance in the marine environment, alloys 316/316L shall be specified (see 6.2).

3.1.2.1.1 Magnetic permeability. Austenitic corrosion-resisting steel setscrews shall have a magnetic permeability of 2.0 max (air = 1.0) for a field strength of H = 200 oersteds when using a permeability indicator in accordance with ASTM A342.

3.1.2.2 Martensitic. Martensitic corrosion-resisting steel shall be Steel Nos. 410 or 416 in accordance with SAE-AMS-STD-66 .

3.1.3 Brass. Brass shall be in accordance with alloy no. C26000 or C26800 of ASTM B36 or alloy no. C26000, C27000 or C27400 of ASTM B134.

3.2 Protective finish. Unless otherwise specified (see 6.2), setscrews shall be furnished uncoated. When specified (see 6.2), protective finishes shall be as follows.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:46Z
Check the source to verify that this is the current version before use.

3.2.1 Cadmium plating or zinc plating. Alloy steel socket setscrews shall be plated by specified (see 6.2) either cadmium plating or zinc plating. When cadmium plating is specified, it shall be in accordance with SAE-AMS-QQ-P-416, type II, class 3. When zinc plating is specified, it shall be in accordance with ASTM B633, type II, class FE/ZN 12. When cadmium plating or zinc plating is required for setscrews of 48 pitch or finer, the thickness may be reduced to .0001 inch minimum thickness. Hydrogen embrittlement relief treatment is mandatory for either plating (see 3.2.4).

3.2.2 Passivation. Corrosion-resisting steel setscrews shall be passivated in accordance with SAE-AMS-QQ-P-35.

3.2.3 B1ack oxide.

3.2.3.1 Brass. Brass setscrews shall be treated with a black chemical in accordance with MIL-F-495.

3.2.3.2 Corrosion-resisting steel. Corrosion-resisting steel setscrews shall be black oxide coated in accordance with MIL-DTL-13924, class 4.

3.2.4 Hydrogen embrittlement. Hydrogen embrittlement relief for zinc plated alloy steel setscrews shall be provided in accordance witih ASTM B633. Cadmium plated alloy steel setscrews shall be subjected to an embrittlement relief treatment in accordance with SAE-AMS-QQ-P-416 after plating to minimize the resulting embrittlement.

3.3 Hardness. Alloy steel setscrews shall be hardened by quenching. in oil from the hardening temperature and tampered to a hardness of Rockwell 45-53 HRC. Martensitic corrosion-resisting steel setscrews shall be hardened by heat treatment to Rockwell 35-45 HRC. Austenitic corrosion-resisting steel setscrews shall be hardened by heat treatment to Rockwell 96 HRB – 33 HRC and brass alloy setscrews shall be tempered to Rockwell 55 – 80 HRF.

3.3.1 Decarburization. The complete end partial decarburization of the threads of heat-treated setscrews shall not exceed the amounts shown in Figure 1 or the amount for such other class as may be specified in the contract or order. A carbon content throughout the threads equivalent to that of the core is desirable.

3.4 Design.

3.4.1 Dimensions. Dimensions and tolerances of setscrews shall be in accordance with ASME B18.3. For acceptable designs of cup points for military use, see applicable MS Standards.

3.4.2 Threads. Unless otherwise specified (see 6.2), the threads shall be class 3A in both UNC and UNF series in accordance with ASME B1.1.

3.4.3 Self-locking element. When specified (see 6.2) non-metallic, self-locking elements shall be in accordance with MIL-DTL-18240.

3.5 Workmanship. Setscrews shall be free from burrs, seams, laps, loose scale, irregular surfaces and any other defects which may affect serviceability. Unless otherwise specified (see 6.2), broach petal (chips) are acceptable provided they will not affect serviceability.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:46Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection. The contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may use his own or any other facilities suitable for the inspection requirements specified herein, unless disapproved by the Government. Inspection records of the examination and tests with itemized results shall be kept complete at the manufacturer's facility, available to the Government throughout the duration of the contract, or a minimum of two years, whichever is longer. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items shall meet all requirements of sections 3 and 5. The inspection set forth in this document shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in this document shall not relieve the contractor of the responsibility of ensuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling inspection, as part of manufacturing operations, is an acceptable practice to ascertain conformance to requirements, however, this does not authorize submission of known defective material either indicated or actual, nor does it commit the Government to accept defective material.

4.1.2 Component and material inspection. Components and materials shall be inspected in accordance with all the requirements specified herein and in application referenced documents.

4.1.3 Examination of preparation for delivery. An examination shall be made to determine that the packaging, packing and marking comply with the requirements in Section 5 of this specification.

4.2 Inspection provisions.

4.2.1 Lot. A Lot shall consist of all setscrews of the same type, style, material, protective finish, size and thread produced under essentially the same conditions and offered for acceptance at one time.

4.2.2 Sampling for examination. A random sample of setscrews shall be taken from each lot in accordance with QSC Z1.4, Inspection Level II. The Acceptable Quality Level (AQL) shall be as specified in Table I. Unless otherwise specified, the AQLs listed in this inspection shall be used to establish the sample size, however, the acceptance number shall be zero.

4.2.3 Sampling for hardness and decarburization tests. A random sample of setscrews shall be taken from each lot in accordance with QSC Z1.4, Inspection Level S-1, with an AQL of 1.0 percent defective for hardness test. Three (3) of these hardness test setscrews sample shall be subjected to decarburization test as specified in 4.4.2.

4.2.4 Sampling for protective finish tests. Sampling for tests of protective finishes shall be in accordance with the applicable specifications in 3.2.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:46Z
Check the source to verify that this is the current version before use.

4.2.5 Sampling for chemical analysis. When specified (see 6.2), a random sample of setscrews shall be taken from each lot in accordance with QSC Z1.4, Inspection Level S-1, with an AQL of 1.5 percent defective. Samples previously selected for examination or for the hardness and decarburization tests may be used.

4.3 Examination. Each setscrew taken as specified in 4.2.2 shall be examined to verify conformance with this specification. Examination shall be conducted in accordance with Table I. Any setscrew in the sample containing one or more defects shall be rejected and if the number of defective setscrews in any sample exceeds the acceptance number for that sample, the lot represented by the sample shall be rejected. Short setscrews, that pass through the no-go gage, shall not cause for rejection, providing the screws have less than six threads (including the start thread) and the major diameter shall not be undersize by more than .003 inch.

Table I. Classification Of Defects.

Categories	Defects	Inspection Method
Critical	None defined	
Major	AQL = 2.5	
101	Thread	SIE*
102	Socket dimensions	SIE
Minor	AQL = 4.0	
201	Magnetic permeability (3.1.2.1.1)	SIE
202	Applicable point dimensions	SIE
203	Setscrew length	SIE
204	Chamfer angle	SIE
205	Eccentricity	SIE
206	Workmanship (3.5)	Visual

*SIE = Standard Inspection Equipment

4.4 Tests.

4.4.1 Hardness. Each setscrew taken as specified in 4.2.3 shall be subjected to a hardness test conducted in accordance with ASTM E18.

a. Setscrews having a length of 2 diameters or longer shall be tested on a transverse section through the threads at a point one-quarter of the nominal diameter from the axis and one nominal diameter from the point.

b. Setscrews having a length less than 2 diameters shall be tested on a transverse section through the threads at a point one-quarter of the nominal diameter from the axis and located at the first full thread from the point.

c. Setscrews having nominal diameters of 1/4” and larger shall be tested using the Rockwell C Scale. For sizes smaller than 1/4” the Rockwell 30N Scale shall be used.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:46Z
Check the source to verify that this is the current version before use.

4.4.2 Decarburization. Each setscrew taken as specified in 4.2.3 shall be subjected to a decarburization test conducted as follows: The threaded part of the setscrew shall be sectioned longitudinally through the axis and polished so that rounding of the thread edges is held to a minimium. The section shall be etched with the usual metallographic etchants (such as nital) and examined with a metallurgical microscope. Measurements shall be made from the crest of the thread to the end of the decarburized zone. This distance shall not exceed that indicated in Figure 1. Measurements shall be made with a fixed-scale micrometer eyepiece. This test does not apply to austenitic corrosion-resisting steel and brass alloy.

4.4.3 Protective finish. Protective finish tests shall be conducted in accordance with the applicable specifications in 3.2.

4.4.4 Chemical analysis. Each setscrew selected as specified in 4.2.6 shall be subjected to a chemical analysis conducted in accordance with ASTM E172 or ASTM E1282, to verify conformance to the applicable material specification. A steel mill certification will be acceptable in lieu of this test.

4.4.5 Hydrogen embrittlement. The contractor shall furnish the Government certification that cadmium plated or zinc plated alloy steel setscrews have been subjected to the embrittlement relief treatment specified in 3.2.4.

5. PACKAGING

5.1 Packaging. For acquisition purposes, the packaging requirements shall be as specified in the contract or order (see 6.2). When packaging of materiel is to be performed by DoD or in-house contractor personnel, these personnel need to contact the responsible packaging activity to ascertain packaging requirements. Packaging requirements are maintained by the Inventory Control Point's packaging activities within the Military Service or Defense Agency, or within the military service's system commands. Packaging data retrieval is available from the managing Military Department's or Defense Agency's automated packaging files, CD-ROM products, or by contacting the responsible packaging activity.

6. NOTES

6.1. Intended use. Setscrews covered by this specification are intended to be used to locate machine parts in relation to each other, either permanently or temporarily. It is recommended that cup point setscrews, style *4,* be used wherever possible. For hardened shafts or when the cutting in of the cup point is objectionable, styles 1 or 6 should be used. It is recommended that styles 2, 3 or 5 be used only when it is impractical to use the other styles.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:46Z
Check the source to verify that this is the current version before use.

6.2 Order1ng data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents.

(a) Title, number and date of this specification.
(b) Type, style, size, length, thread series and class (1.2).
(c) Material (3.1).
(d Protective finish, if required (3.2).
(e) Self-locking feature, if required (3.4.3)
(f) Chemical analysis, when required (4.2.5)
(g) Broach petals removal, if required (3.5)
(h) Packaging requirements (5.1).

6.3 Military procurement. Items procured under this specification for military use are to be limited to the variety shown on the applicable Military Standards. Personnel of Military departments are requested to refer to these documents for guidance.

6.4 Supersession data. Cross reference between the types and styles of setscrews covered in part by this specification and FF-S-210, and the types and styles of the superseded FF-S-103, dated October 7, 1958, is as follows:

TABLE II. Cross reference data.

FF-S-lO3	FF-S-210	FF-S-200
Types	Types	Types
Type I- Square Head	Type I- Square Head	--- ---
Type II - Slotted Headless	Type II - Slotted Headless	
Type III - Hexagon Socket, Headless	---	Type I - Hexagon Socket, Headless
Type IV - Fluted Socket, Headless	---	Type II - Spline Socket, Headless
Styles	Styles	Styles
Style 1 - Flat point Style 2 - Cone point Style 3 - Oval point Style 4 - Cup point Style 5 - Full-dog point Style 6 - Half-dog point	Style 1 - Flat point Style 2 - Cone point Style 3 - Oval point Style 4 - Cup point Style 5 - Full-dog point Style 6 - Half-dog point	Style 1 - Flat point Style 2 - Cone point Style 3 - Oval point Style 4 - Cup point Style 5 - Full-dog point Style 6 - Half-dog point

6.5 Changes from previous issue. Asterisks (or vertical lines) are not used in this revisions to identify changes with respect to the previous issue due to the extensive changes.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:46Z
Check the source to verify that this is the current version before use.





Thds per inch	1/4 H
80	.002
72	.002
64	.003
56	.003
48	.003
44	.004
40	.004
36	.005
32	.005
28	.006
24	.007
20	.008
18	.009
16	.010
14	.012
13	.012
12	.014
11	.015
10	.016
9	.018
8	.020
7	.023
6	.027

1/4 H - l/4 BASIC THREAD DEPTH

Figure 1. – Decarburization limits.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:46Z
Check the source to verify that this is the current version before use.

Custodians:
Army – AR
Navy – SH
Air Force - 99

Preparing activity:
DLA - IS

(Project 5305-2556)

Review activities:
Army - AT, AV, CR4, EA, MI
Navy - AS,MC,OS,YD
Air Force - - 71

Civil agency coordinating activity:
GSA - FSS

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at www.dodssp.daps.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:46Z
Check the source to verify that this is the current version before use.