METRIC

DOD-E-18210B(SH)
AMENDMENT 1
14 August 1985

MILITARY SPECIFICATION

ENAMEL, INTERIOR, DECK, RED (FORMULA NO. 23) (METRIC)

This amendment forms a part of Military Specification DOD-E-18210B(SH), dated 9 January 1978, and is approved for use by the Naval Sea Systems Command, Department of the Navy, and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 1

Beneficial comments statement at bottom of page, line 3: Delete "Naval Ship Engineering Center, SEC 6124" and substitute "Naval Sea Systems Command, SEA 55Z3".

PAGE 2

2.2, under "AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)": Delete "D 600 - Liquid Paint Driers."

Table I: Delete and substitute:

"TABLE I. Formula No. 23.

Ingredients	Specification	Kg	(Pounds)1/
Indian red	TT-P-375, type I	59.091	(130)
Zinc oxide	MIL-Z-15486	45.455	(100)
Titanium dioxide2/		18.182	(40)
Yellow iron oxide	ASTM D 768	11.364	(25)
Silica3/		18.182	(40)
Magnesium silicate	MIL-P-15173, type A	27.273	(60)
Varnish solution	MIL-V-15218, type II	125.0	(275)
Alkyd resin solution4/		109.091	(240)
Paint thinner	TT-T-291, type II, grade A	75.0	(165)
Driers	(See 3.3.1)	---	---

See footnotes at top of next page.

FSC 8010

DISTRIBUTION STATEMENT A Approved for public release; distribution unlimited

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T11:07Z
Check the source to verify that this is the current version before use.

1/ The formula is given slightly in excess of 100 gallons to allow for normal manufacturing loss (see 6.7).

2/ The titanium dioxide pigment shall be an aluminum oxide, modified semi-chalking, rutile titanium dioxide containing no less than 86 percent titanium dioxide and between 0.5 and 2.5 percent aluminum oxide.

3/ The silica shall show no less than 98 percent of silica (SiO_2) and shall not lose more than 1-1/2 percent on ignition at 950 ± 50°C. Coarse particles shall not exceed 3 percent retained on a No. 325 sieve. Under 300-power magnification, the silica shall show crystals having sharp angles indicative of material made from crushed quartz of a variety of sizes of particles.

4/ The alkyd resin solution shall conform to type I, class A of TT-R-266. In addition, it shall conform to the solvent requirement of TT-R-266, applicable to alkyd resin solvents intended for use in coatings used in areas with regulations controlling the emission of solvents into the atmosphere (see 6.6).

Add as new paragraph, 3.3.1:

"3.3.1 Driers. Driers shall be of a quantity and type to promote through drying and surface drying to withstand requirements to 4.4.2. Driers containing heavy metals such as lead and mercury shall not be permitted."

PAGE 3

Table II., under "Requirements, maximum" column, opposite "Lead, percent by weight of total nonvolatile": Delete "0.5" and substitute "0.06".

LAST PAGE

DD Form 1426, STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL: Delete address and substitute:

"COMMANDER
NAVAL SEA SYSTEMS COMMAND (SEA 55Z3)
DEPARTMENT OF THE NAVY
WASHINGTON, DC 20362-5101"

Preparing activity:
Navy - SH
(Project 8010-N276)

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T11:07Z
Check the source to verify that this is the current version before use.