METRIC

DOD-E-19214B
15 February 1978
SUPERSEDING
MIL-E-18214A
27 September 1960
(See 6.7)

MILITARY SPECIFICATION

ENAMEL, INTERIOR, DECK, DARK GREEN (FORMULA NO. 19) (METRIC)

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers dark green interior deck enamel (Formula No. 19) for shipboard use. The materials covered by this specification may be used where air pollution regulations apply.

2. APPLICABLE DOCUMENTS

2.1 Issues of documents. The following documents, of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

SPECIFICATIONS

FEDERAL

TT-P-450 - Pigment, Ultramarine Blue: Dry.
TT-P-465 - Pigment, Zinc-Yellow (Zinc Chromate), Dry.
TT-R-266 - Resin, Alkyd; Solutions.
TT-T-291 - Thinner-Paint, Volatile Spirits, Petroleum Spirits.
PPP-P-1892 - Paint, Varnish, Lacquer, and Related Materials; Packaging, Packing, and Marking of.

MILITARY

MIL-P-15173 - Pigment, Magnesium Silicate; Dry (Paint Pigment).
MIL-V-15218 - Varnish, (Mixing, Phenolic).

STANDARDS

FEDERAL

FED-STD-141 - Paint, Varnish, Lacquer, and Related Materials; Methods of Inspection, Sampling, and Testing.
FED-STD-313 - Material Safety Data Sheets, Preparation and the Submission of.
FED-STD-595 - Colors.

(Copies of specifications, standards, drawings, and publications required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

D 34 - White Pigments, Chemical Analysis of.
D 93 - Flash Point by Pensky-Martens Closed Tester, Test for.
D 185 - Coarse Particles In Pigments, Pastes, and Paints, Tests for.
D 209 - Lampblack, Spec. for.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Commander, Naval Ship Engineering Center, SEC 6124, Department of the Navy, Washington, DC 20362 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

FSC 8010

Source: https://assist.dla.mil -- Downloaded: 202640-18T11:07Z
Check the source to verify that this is the current version before use.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM) (Continued)

D 476 - Titanium Dioxide Pigments, Spec. for.
D 562 - Consistency of Paints Using the Stormer Viscosimeter, Test for.
D 563 - Phthalic Anhydride Content of Alkyd Resins and Resin Solutions, Test for.
D 600 - Liquid Paint Driers, Spec. for.
D 765 - Raw and Burnt Sienna, Spec. for.
D 1210 - Fineness of Dispersion of Pigment-Vehicle Systems, Test for.
D 1296 - Odor of Volatile Solvents and Diluents, Test for.
D 1308 - Effect of Household Chemicals on Clear and Pigmented Organic Finishes, Test for.
D 1364 - Water in Volatile Solvents (Fischer Reagent Titration Method), Test for.
D 1475 - Density of Paint, Varnish, Lacquer, and Related Products, Test for.
D 1542 - Rosin in Varnishes, Qualitative Tests for.
D 1640 - Drying, Curing, or Film Formation of Organic Coatings at Room Temperature, Test for.
D 2088 - Low Concentrations of Lead in Paint, Determination of.
D 2244 - Color Differences of Opaque Material, Instrumental Evaluation of.
D 2369 - Volatile Content of Paints, Test for.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pennsylvania 19103.)

(Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

3. REQUIREMENTS

3.1 Toxicity. The material shall have no adverse effect on the health of personnel when used for its intended purpose (see 4.6). Questions pertinent to this effect shall be referred by the procuring activity to the appropriate service medical department which will act as advisor to the procuring activity.

3.2 Composition. The enamel shall be ready-mixed and prepared in accordance with table I. The enamel shall consist of ingredients conforming to the applicable specifications in the proportions shown in table I, except that the amount of tinting pigments may be varied as necessary to meet the color requirement. Additionally, to assist in meeting brushing, condit in container, and storage stability requirements, small amounts of antisettling, antisagging, and antiskinning agents may be added, provided that all the other requirements of the specifi cation are met and the exact formula used is furnished in the record required by method 1031 of FED-STD-141.

TABLE I. Formula No. 19.

| Ingredients | Specification | Kilograms | (Pounds) 1/ |
|---|---|---|---|
| Pigment, zinc-yellow | TT-P-465 | 77.273 | (170) |
| Titanium dioxide 2/ | ASTM D 476, type II | 20.455 | (45) |
| Pigment, ultramarine blue | TT-P-450 | 50.0 | (110) |
| Lampblack | ASTM D 209 | 3.182 | (7) |
| Pigment, raw sienna | ASTM D 765 | 7.273 | (16) |
| Magnesium silicate | MIL-P-15173, type A | 50.0 | (110) |
| Varnish, mixing | MIL-V-15218, type II | 54.545 | (120) |
| Resin, alkyd, solution 3/ | TT-R-266, type I, class A | 127.273 | (280) |
| Paint thinner | TT-T-291, type II, grade A | 90.909 | (200) |
| Lead naphthenate drier | ASTM D 600, class B | 4.545 | (10) |
| Cobalt naphthenate drier | ASTM D 600, class B | 0.773 | (1.7) |
| Manganese naphthenate drier | ASTM D 600, class B | 0.773 | (1.7) |

1/ The formula is given slightly in excess of 100 gallons to allow for normal manufacturing loss (see 6.6).

2/ The titanium dioxide shall be an aluminum oxide, modified semichalking, rutile titanium dioxide containing no less than 96 percent titanium dioxide and between 0.5 and 2.5 percent aluminum oxide.

3/ The alkyd resin solution shall conform to type I, class A of TT-R-266. In addition, it shall conform to the solvent requirement of TT-R-266, applicable to alkyd resin solutions intended for use in coatings used in areas with regulations controlling the emission of solvents into the atmosphere (see 6.4).



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T11:07Z
Check the source to verify that this is the current version before use.

3.3 Manufacture. The component raw materials shall be mixed and dispersed as required to yield a product which is uniform, entirely acceptable for the purpose intended, and in full conformity to the requirements of this specification.

3.4 Volatile portion. The volatile portion of the enamel shall conform to the following requirements by volume:

(a) A combination of hydrocarbons, alcohols, aldenydes, ethers, esters, or ketones having an olefinic or cycloolefinic type of unsaturation except perchloroethylene: 5 percent maximum.
(b) A combination of aromatic compounds with eight or more carbon atoms to the molecule except ethylbenzene, methyl benzoate, and phenyl acetate: 8 percent maximum.
(c) A combination of ethylbenzene, ketones having branched hydrocarbon structures, trichloroethylene, or toluene: 20 percent maximum.

3.5 Quantitative requirements. The enamel shall conform to the quantitative requirements in table II when tested in accordance with 4.4.

TABLE II. Quantitative requirements.

| Characteristic | Requirements | |
|---|---|---|
| | Minimum | Maximum |
| Pigment, percent by weight of enamel | 42.0 | 45.0 |
| Volatiles, percent by weight of enamel | 29.0 | 32.0 |
| Nonvolatile vehicle, percent by weight of enamel (calculated by difference) | 25.0 | 28.0 |
| Phthalic anhydride, percent by weight of nonvolatile vehicle | 16.0 | --- |
| Water, percent by weight of enamel | --- | 1.0 |
| Coarse particles and skins (as residue retained on No. 325 sieve), percent by weight of enamel | --- | 0.2 |
| Consistency, Krebs-Stormer shearing rate 200 RPM | | |
| grams | 130 | 180 |
| equivalent Krebs units | 68 | 78 |
| Weight per gallon, kg (pounds) | 4.773 (10.5) | 4.955 (10.9) |
| Drying time | | |
| set-to-touch, hours | --- | 2.0 |
| dry hard, hours | --- | 8.0 |
| Fineness of grind | 5 | --- |
| Flash point, °C | 38 | --- |
| Total zinc, expressed as ZnO, percent by weight of pigment | 12.0 | --- |
| Chromium trioxide ($CrO_3$), percent by weight of pigment | 14.0 | --- |
| Lead, percent by weight of total nonvolatile | --- | 0.5 |

3.6 Qualitative requirements.

3.6.1 Brushing properties. The enamel, when tested as specified (see 4.4.6), shall be capable of being brushed out and laid off without excess drag on the brush. When dry, the brushed surface shall be free from sags and runs and shall show a minimum of brush marks.

3.6.2 Spraying properties. The enamel, when tested as specified (see 4.4.7), shall spray satifactorily in all respects and shall show no running, sagging, or streaking. The film shall show no dusting, mottling, or color separation.

3.6.3 Flexibility. A film of enamel, prepared and tested as specified (see 4.4.8), shall withstand bending without cracking or flaking when observed at seven-diameter magnification.

3.6.4 Water resistance. A film of enamel, prepared and tested in accordance with 4.4.9, shall show no wrinkling or blistering immediately after removal of the panel from water. The enamel shall not be affected with regard to hardness and adhesion when observed 2 hours after removal from the water. After 24-hours air drying, the portion of the panel which was immersed shall be indistinguishable, with regard to hardness, adhesion, and general appearance, from the portion of the panel that was not immersed. Small changes in color and gloss on panels immersed in water shall be permitted.



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T11:07Z
Check the source to verify that this is the current version before use.

3.6.5 Color. The color shall acceptably match color No. 34092 of FED-STD-595 when tested as specified (see 4.4.10).

3.6.6 Condition in container. A freshly opened, full container of enamel, when tested as specified (see 4.4.11), shall be free from lumps, abnormal thickening, or livering and shall show no more pigment settling or caking than can be readily reincorporated to a smooth, uniform state.

3.6.7 Storage stability.

3.6.7.1 Partially full container. A three-quarter filled, closed 250-milliliter (mL) glass jar of enamel shall show no skinning at the end of 48 hours, when tested as specified (see 4.4.12.1). After aging as specified (see 4.4.12.1), the enamel shall show no livering, curdling, hard caking, or gummy sediment. It shall mix readily to a smooth, uniform state and skins formed shall be continuous and easily removed.

3.6.7.2 Full container. Enamel in original, unopened containers shall be usable for a period of 1 year of normal warehouse storage after date of manufacture. The enamel when tested as specified (see 4.4.12.2) shall be capable of being readily broken up with a paddle to a smooth, uniform consistency, shall be free from livering, curdling, gelling, or other objectional properties, shall not exceed 90 Krebs units in viscosity, shall not exceed 8-hours dry hard time, and shall match the standard color.

3.6.8 Dilution stability. When thinned as specified (see 4.4.13), the enamel shall remain stable and uniform, showing no precipitation, curdling, or separation. Slight pigment settling shall be permitted.

3.6.9 Rosin and rosin derivatives. The enamel shall give a negative test for the presence of rosin and rosin derivatives when tested as specified (see 4.4.14).

3.6.10 Phenolic resins. The enamel shall give a positive test for the presence of phenolic resins when tested as specified (see 4.4.15).

3.6.11 Odor. The odor shall be characteristic of the volatiles permitted in 3.4.

3.6.12 Surface appearance. A flow-out film on glass of the mixed enamel, after drying for 24 hours, shall exhibit a surface smooth in appearance and free of defects, such as pinholes, coarse particles, skins, or agglomerates of any kind (see 4.4.10).

3.6.13 Material safety data sheet. The procuring activity shall be provided a material safety data sheet (MSDS) at the time of contract award. The MSDS is DD Form 1813 found in and part of FED-STD-313. The MSDS shall be included with each shipment of the material covered by this specification.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.2 Quality conformance inspection. Quality conformance inspection shall be provided in accordance with method 1031 of FED-STD-141 as hereinafter supplemented. Submission of forms in accordance with the method 1031 shall cover complete tests other than the 1-year stability in full container test. The stability requirement (see 3.6.7.2) shall apply for 1 year after manufacture regardless of other testing or prior acceptance of material.

4.2.1 Manufacturing control. In addition to the other requirements of method 1031 of FED-STD-141, the contractor shall forward to the cognizant inspection office and testing laboratory a copy of the certification that each ingredient raw material conforms to the applicable specification.

4.2.2 Ingredient materials. When requested by the testing laboratory or other controlling authority, 1 pint of each ingredient in the formula specified (see table I) shall be supplied for test purposes.

4.3 Acceptance Acceptance of the enamel shall be based upon conformance of the enamel to the requirements of this specification. Failure to pass any test shall be cause for rejection of the lot.



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T11:07Z
Check the source to verify that this is the current version before use.

4.4 Test procedures. The enamel shall be tested in accordance with the applicable methods specified in table III and other test paragraphs listed in section 4.

TABLE III. Test procedures.

| Test | Applicable method in FED-STD-141 | Applicable ASTM test method | Section of this specification giving further reference | Section of this specification giving requirements |
|---|---|---|---|---|
| Pigment content | 4021 | --- | --- | Table II |
| Volatiles | --- | D 2369 | --- | Table II |
| Nonvolatile vehicle content | 4053 | --- | --- | Table II |
| Phthalic anhydride | --- | D 563 | 4.4.1 | Table II |
| Water | --- | D 1364 | --- | Table II |
| Coarse particles | --- | D 185 | --- | Table II |
| Consistency | --- | D 562 | --- | Table II |
| Weight per gallon | --- | D 1475 | --- | Table II |
| Drying time | --- | D 1640 | 4.4.2 | Table II |
| Fineness of grind | --- | D 1210 | --- | Table II |
| Flash point | --- | D 93 | --- | Table II |
| Zinc oxide | --- | D 34 | 4.4.3 | Table II |
| Chromium trioxide | 7331 | --- | 4.4.4 | Table II |
| Lead | --- | D 2088 | 4.4.5 | Table II |
| Brushing properties | 4321 | --- | 4.4.6 | 3.6.1 |
| Spraying properties | 2131, 4331 | --- | 4.4.7 | 3.6.2 |
| Flexibility | 6221 | --- | 4.4.8 | 3.6.3 |
| Water resistance | --- | D 1308, section 5 | 4.4.9 | 3.6.4 |
| Color | 4250 | --- | 4.4.10 | 3.6.5 |
| Condition in container | 3011 | --- | 4.4.11 | 3.6.6 |
| Stability in partially full container | 3021 | --- | 4.4.12.1 | 3.6.7.1 |
| Stability in full container | 3022 | --- | 4.4.12.2 | 3.6.7.2 |
| Dilution stability | 4203 | --- | 4.4.13 | 3.6.8 |
| Rosin | --- | D 1542 | 4.4.14 | 3.6.9 |
| Phenolic resin | 5141 | --- | 4.4.15 | 3.6.10 |
| Odor | --- | D 1296 | --- | 3.6.11 |
| Surface appearance | --- | --- | 4.4.16 | 3.6.12 |

4.4.1 Phthalic anhydride. Determine phthalic anhydride by ASTM D 563. A suitable portion of the vehicle, collected during the determination of pigment and evaporated on a steam bath until the volume has been reduced to approximately 10 mL, shall be used as the sample. The alcoholate precipitate obtained shall be corrected for carbonates by the use of the procedure in ASTM D 563.

4.4.2 Drying time. Determine drying time by ASTM D 1640, except that the specified conditions of temperature and humidity shall apply only for referee tests in case of dispute. All other tests shall be conducted under prevailing laboratory conditions.

4.4.3 Total zinc. Determine total zinc, expressed as ZnO, of the extracted pigment by ASTM D 34.

4.4.4 Chromium trioxide content. Determine total chromium, expressed as $CrO_3$, of the extracted pigment by method 7331 of FED-STD-141.

4.4.5 Lead content in nonvolatile. Determine lead content of total nonvolatile of enamel in accordance with ASTM D 2088.

4.4.6 Brushing properties. Apply the enamel, as packaged, in accordance with method 4321 of FED-STD-141 and observe for compliance with 3.6.1.

4.4.7 Spraying properties. Reduce eight parts by volume of enamel with one part by volume of thinner conforming to TT-T-291, type II, grade A. Spray on a steel panel to a dry film thickness of 0.00203 centimeter (cm) to 0.00279 cm and observe for spraying properties in accordance with method 4331 of FED-STD-141 and for compliance with 3.6.2. For referee test, use automatic application as specified in method 2131 of FED-STD-141.

4.4.8 Flexibility. Determine flexibility in accordance with method 6221 of FED-STD-141.



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T11:07Z
Check the source to verify that this is the current version before use.

4.4.8.1 Panel preparation. Prepare a flat tin plate panel in accordance with method 2012 of FED-STD-141, using the petroleum naptha ethylene glycol monoethyl ether mixture. Apply a 5.08-cm wide film of enamel on the tin plate with a film applicator that will give a dry film thickness of 0.00356 cm ± 0.00076 cm. Air dry the enamel in a horizontal position for 2 hours; then bake for 24 hours at 105°C ± 2°C. Condition the panel for at least 1/2 hour as specified in method 6221 of FED-STD-141.

4.4.8.2 Procedure. Bend 180 degrees over a 0.318-cm mandrel and examine the coating for cracks over the area of the bend in a strong light at a seven-diameter magnification and for compliance with 3.6.3.

4.4.9 Water resistance. Determine water resistance in accordance with section 5 of ASTM D 1308 as follows:

4.4.9.1 Panel preparation. Prepare a tin panel in accordance with method 2012 of FED-STD-141, using the petroleum naphtha ethylene glycol monethyl ether mixture. Draw a film of the enamel to obtain a dry film thickness of 0.00254 cm ± 0.00076 cm. Air dry the enamel for 48 hours.

4.4.9.2 Procedure. Immerse in distilled water at 23°C ± 1°C for 18 hours in accordance with section 5 of ASTM D 1308. Examine for compliance with 3.6.4 at 2 hours and at 24 hours after removal from the water.

4.4.10 Color. Prepare panel for test by applying a single drawdown coat of the enamel to a planar piece of opaque white glass using a doctor blade with a clearance of 0.0152 cm (designed to give a wet film thickness of approximately 0.0076 cm). After a 48-hour drying period, compare the panel with color No. 34092 of FED-STD-595 as specified in method 4250 of FED-STD-141. If doubt exists as to the acceptablility of the match, determine the color difference by instrument as specified in ASTM D 2244. An acceptable color match shall be within two units. Check for compliance with 3.6.5.

4.4.11 Condition in container. Determine package condition in accordance with method 3011 of FED-STD-141 and observe for compliance with 3.6.6.

4.4.12 Storage stability.

4.4.12.1 Partially full container. Determine skinning after 48 hours in accordance with method 3021 of FED-STD-141. Reseal and age for 7 days at 24°C and observe for complian with 3.6.7.1.

4.4.12.2 Full container. The Government, at its option and at any time not to exceed 1 year after manufacture, may test enamel stored in its original container for condition in container, viscosity, color, and dry-hard time for compliance with 3.6.7.2. Test in accordance with method 3022 of FED-STD-141.

4.4.13 Dilution stability. Reduce one part by volume of enamel as packaged with one part by volume of paint thinner conforming to type II, grade A of TT-T-291. Test according to method 4203 of FED-STD-141 for compliance with 3.6.8.

4.4.14 Rosin and rosin derivatives. Test for rosin and rosin derivatives in accordance with ASTM D 1542. Use a portion of the separated, nonvolatile vehicle for the test. Check for compliance with 3.6.9.

4.4.15 Phenolic resins. Test for phenolic resins in accordance with method 5141 of FED-STD-141. Use a portion of the separated, nonvolatile venicle for the test. Check for compliance with 3.6.10.

4.4.16 Surface appearance. Prepare a flow-out film of the enamel by pouring approximately 15 mL of the mixed enamel across a 15.24 cm x 30.48 cm glass panel near the upper edge, while the panel is lying flat. Then tilt the panel to allow the coating to spread over all but the upper edge. Next place the panel in an almost vertical position and allow to drain. After 24 hours, examine the film for compliance with 3.6.12. Coarse particles, skins, and agglomerates are characterized by being larger than the dispersed pigment in particle size and extending beyond the plane of the film.

4.5 Inspection of preparation for delivery. Sample packages and packs and the inspection of packaging, packing, and marking for shipment and storage shall be in accordance with the requirements of section 5 and the documents specified therein.



Source: https://assist.dla.mil -- Downloaded: 2026-10-18T11:07Z
Check the source to verify that this is the current version before use.

4.6 Toxicity. A manufacturer of material shall disclose the formulation of his product to the Navy Bureau of Medicine and Surgery, Navy Department, Washington, DC 20372. The disclosure of proprietary information, which shall be held in confidence by the Bureau of Medicine and Surgery, shall include : the name, formula, and approximate percentage by weight and volume of each ingredient in the product; the results of any toxicological testing of the product; identification of its pyrolysis products; and any such other information as may be needed to permit an accurate appraisal of any toxicity problem associated with the handling, storage, application, use, or disposal of the material.

5. PREPARATION FOR DELIVERY

(The preparation for delivery requirements specified herein apply only for direct Government procurements.)

5.1 Packaging, packing, and marking. The enamel shall be packaged, packed, and marked in accordance with PPP-P-1892. The level of packaging shall be level A, B, or C and the level of packing shall be level A, B, or C, as specified (see 6.2). The enamel shall be furnished in 1-gallon cans or 5-gallon pails as specified (see 6.2).

5.1.1 Special marking. In addition to other markings required on the containers, there shall be the following statement: "The volatile content of the material in this container is not photochemically reactive as defined by Rule 102 of the South Coast Air Quality Management District." (See 6.4.)

6. NOTES

6.1 Intended use. The enamel covered by this specification is intended for use as a finish coat on interior deck surfaces of ships.

6.2 Ordering data. Procurement documents should specify the following:

(a) Title, number, and date of this specification.
(b) Special samples if required (see 4.2.2.).
(c) Level of packaging and packing required (see 5.1).
(d) Size of container (see 5.1).
(e) Special marking required (see 5.1.1).

6.2.1 Level B packaging. Level B packaging is intended to provide economical but limited protection and should be specified only when it is determined that the enamel will be held in covered storage no more than 1 year from date of initial packaging.

6.3 Unit quantities. The enamel should be purchased by volume, the unit being 1 U.S. gallon at 15.6°C.

6.4 Volatile content. Although the container marking specifically refers to the South Coast Air Quality Management District, the enamel may be used anywhere else an enamel complying with 3.4 is allowed. This includes other air pollution control districts or similar areas controlling the emission of solvents into the atmosphere. Information regarding Los Angeles County Air Pollution Rules 102, 442, and 443 may be obtained from: South Coast Air Quality Management District, Management District, Metropolitan Zone, 434 South San Pedro Street, Los Angeles, California 90013.

6.5 If it is desired to use alkyd solution conforming the requirements for type I, class B of TT-R-266, intended for use in coatings used in areas with regulations controlling the emission of solvents into the atmosphere, the weight of alkyd resin solution, as specified herein, should be multiplied by 1.17 and the paint thinner reduced by 0.17 times the weight of alkyd resin solution.

6.6 Composition by volume. For information only and with the understanding that weight-volume relationships of ingredients may vary slightly, the following approximation of composition by volume is included.



Source: https://assist.dla.mil -- Downloaded: 202640-18T11:07Z
Check the source to verify that this is the current version before use.

TABLE IV. Composition by volume.

| Ingredients | Gallons |
|---|---|
| Zinc-yellow | 6.1 |
| Titanium dioxide | 1.3 |
| Ultramarine blue | 5.6 |
| Lampblack | 0.5 |
| Raw sienna | 0.6 |
| Magnesium silicate | 4.6 |
| Varnish solution | 15.8 (8.5) 1/ |
| Alkyd resin solution | 35.0 (22.3) 1/ |
| Paint thinner | 30.1 |
| Lead naphthenate drier | 1.0 |
| Cobalt naphthenate drier | 0.2 |
| Manganese naphthenate drier | 0.2 |
| Total volume | 101.0 |

1/ Figures in parentheses refer to volume of resin solids (nonvolatiles).

6.7 Changes from previous issue. The symbol "#" is not used in this revision to identify changes with respect to the previous issue, due to the extensiveness of the changes.

Custodians:
Army - ME
Navy - SH

User activities:
Navy - MC, CG

Preparing activity:
Navy - SH
(Project 8010-0775)



Source: https://assist.dla.mil -- Downloaded: 202610-18T11:07Z
Check the source to verify that this is the current version before use.

# STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers/ vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?

☐ YES ☐ NO *(If "Yes", in what way?)*

4. REMARKS

SUBMITTED BY *(Printed or typed name and address - Optional)*

TELEPHONE NO.

DATE

DD FORM 1 JAN 72 1426

REPLACES EDITION OF 1 JAN 66 WHICH MAY BE USED

S/N 0102-014-1802

Source: https://assist.dla.mil -- Downloaded: 202610-18T11:07Z
Check the source to verify that this is the current version before use.

FOLD

COMMANDER
NAVAL SHIP ENGINEERING CENTER (SEC 6124)
DEPARTMENT OF THE NAVY
WASHINGTON, D.C. 20362

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

POSTAGE AND FEES PAID

DEPARTMENT OF THE NAVY

DOD 316

U.S.MAIL

COMMANDER
NAVAL SHIP ENGINEERING CENTER (SEC 6124)
DEPARTMENT OF THE NAVY
WASHINGTON, D.C. 20362

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T11:07Z
Check the source to verify that this is the current version before use.