MIL-STD-1623A(SHIPS)
20 MAY 1974
SUPERSEDING
MIL-STD-1623(SHIPS)
10 SEPTEMBER 1973
(SEE 5.4)

MILITARY STANDARD

FIRE PERFORMANCE REQUIREMENTS AND APPROVED SPECIFICATIONS FOR INTERIOR FINISH MATERIALS AND FURNISHINGS

(NAVAL SHIPBOARD USE)

FSC MISC

Source: https://assist.dla.mil -- Downloaded: 2026-10-24T00:47Z
Check the source to verify that this is the current version before use.

DEPARTMENT OF THE NAVY

NAVAL SHIP SYSTEMS COMMAND

WASHINGTON, D.C. 20362

Fire Performance Requirements and Approved Specifications for
Interior Finish Materials and Furnishings (Naval Shipboard Use)
MIL-STD-1623A(SHIPS)

1. This Military Standard is approved for use by the Naval Ship Systems Command and is available for use by all Departments and Agencies of the Department of Defense.

2. Recommended corrections, additions, or deletions should be addressed to Commander, Naval Ship Engineering Center, Department of the Navy, Center Building, Prince George's Center, Hyattsville, Maryland 20782.

Source: https://assist.dla.mil -- Downloaded: 2026-10-24T00:47Z
Check the source to verify that this is the current version before use.

FOREWORD

The purpose of this standard is to establish fire performance criteria and provide a list of approved specifications for interior finish materials and furnishings to be used on new and existing Naval ships and submarines.

Although the development of limits for toxic products of combustion is of major concern, the information generally available is not refined to the degree to allow inclusion of finite limits in this standard at this time.

Where no fire test limits appear, technical data was not available as of the date of this standard.

Source: https://assist.dla.mil -- Downloaded: 2026-10-24T00:47Z
Check the source to verify that this is the current version before use.

CONTENTS

		Page
1.	SCOPE AND APPLICATION	1
1.1	Scope	1
1.2	Application	1
2.	REFERENCED DOCUMENTS	1
3.	REQUIREMENTS	1
3.1	Materials	2
4.	FIRE TEST PROVISIONS	2
4.1	Responsibility for testing	7
4.2	Methods of testing	7
4.2.1	Surface flammability	7
4.2.2	Vertical flame resistance	7
4.2.3	Smoke generation	7
4.2.4	Test for incombustibility	7
5.	NOTES	7 and 8

TABLE

I	Material requirements	3 through 7

Source: https://assist.dla.mil -- Downloaded: 2026-10-24T00:47Z
Check the source to verify that this is the current version before use.

1. SCOPE AND APPLICATION

1.1 Scope. This standard provides fire performance requirements and approved specifications for eight categories of interior finish materials and furnishings for use on new and existing surface ships and submarines.

1.2 Application. This standard applies to materials for bulkhead sheathing, overhead sheathing, furniture, draperies and curtains, adhesives, deck coverings, thermal insulation, and acoustic materials applications. The fire performance requirements of this standard supersede those contained in the applicable specifications.

2. REFERENCED DOCUMENTS

2.1 The issues of the following documents in effect on the date of invitation for bids form a part of this standard to the extent specified herein.

GOVERNMENTAL

SPECIFICATIONS

FEDERAL

L-F-450 - Flooring, Vinyl Plastic.
L-F-475 - Floor Covering Vinyl, Surface (Tile and Roll), With Racking.
HH-I-551 - Insulation Block, Pipe Covering and Boards, Thermal (Cellular Glass).
QQ-A-250/19 - Aluminum Alloy 5086, Plate and Sheet for Sea Water Application.
SS-C-160 - Cements, Insulation, Thermal.
SS-S-118 - Sound Controlling Blocks and Boards (Acoustical Tiles and Panels, Prefabricated).
SS-T-312 - Tile, Floor, Asphalt, Rubber, Vinyl, Vinyl-Asbestos.
ZZ-M-42 - Mats, Floor, Dental-Chair, Rubber.
CCC-A-680 - Artificial Leather (Cloth Coated), Vinyl Resin, Expanded Layer, (Upholstery).
CCC-C-436 - Cloth, Ticking Twill, Cotton.
CCC-C-700 - Cloth, Coated, Vinyl Coated (Artificial Leather).
CCC-C-1703 - Cloth, Drapery, Glass Fiber.
CCC-W-408 - Wall Covering, Vinyl-Coated.
LLL-F-1238 - Floor Covering, Linoleum.
MMM-A-130 - Adhesive, Contact.

MILITARY

MIL-I-742 - Insulation Board, Thermal, Fibrous Glass.
MIL-M-910 - Mats, Floor, Standing.
MIL-I-2781 - Insulation, Pipe, Thermal.
MIL-I-2818 - Insulation Blanket, Thermal, Fibrous Mineral.
MIL-I-2819 - Insulation Block, Thermal.
MIL-D-3134 - Deck Covering Materials.
MIL-D-3135 - Deck Covering Underlay Materials.
MIL-A-3316 - Adhesives, Fire-Resistant, Thermal Insulation.
MIL-P-15280 - Plastic Material, Unicellular (Sheets and Tubes).
MIL-I-15475 - Insulation Felt, Thermal, Fibrous Glass Semirigid.
MIL-M-15562 - Matting, Floor, Rubber.
MIL-I-16411 - Insulation Felt, Thermal, Glass Fiber.
MIL-D-16680 - Deck Covering Magnesia Aggregate Mixture.
MIL-T-17171 - Table Top, Plastic; Thermosetting Resin.
MIL-D-17951 - Deck Covering, Lightweight, Nonslip, Silicon Carbide Particle Coated Fabric and Sealing Compound.
MIL-T-18830 - Tile, Plastic, Fire Retardant.
MIL-M-19018 - Mats, Floor, Rubber or Plastic, Light Gray; for Shipboard Shower Stalls.
MIL-C-19565 - Coating Compounds, Thermal Insulation Pipe Covering -- Fire- and Water-Resistant, Vapor-Barrier and Weather-Resistant.
MIL-C-19993 - Coating Compound, Fibrous Glass Thermal Insulation Board, Water Vapor Barrier.
MIL-C-20079 - Cloth, Glass; Tape, Textile, Glass; and Thread, Glass.
MIL-R-20092 - Rubber Sheets and Molded Shapes, Cellular, Synthetic Open Cell (Foamed Latex).
MIL-A-21016 - Adhesive, Resilient Deck Covering.

Source: https://assist.dla.mil -- Downloaded: 2026-10-24T00:47Z
Check the source to verify that this is the current version before use.

MILITARY (Cont'd)

MIL-D-21631 - Deck Covering, Latex Concrete (For Ammunition Ships).
MIL-I-22023 - Insulation Felt, Thermal and Sound Absorbing Felt, Fibrous Glass, Flexible.
MIL-I-22344 - Insulation, Pipe, Thermal, Fibrous Glass.
MIL-C-22395 - Compound, End Sealing, Thermal Insulation Pipe Covering -- Fire-, Water-, and Weather-Resistant.
MIL-P-22581 - Plastic Sheet, Vibration Damping.
MIL-D-23003 - Deck Covering Compound, Nonslip, Lightweight.
MIL-A-23054 - Acoustical Absorptive Board, Fibrous Glass, Perforated Fibrous Glass Cloth Faced.
MIL-I-23128 - Insulation Blanket, Thermal, Refractory Fiber, Flexible.
MIL-P-23653 - Plastic Tiles, Vibration Damping.
MIL-P-24062 - Sprayable Vibration Damping Material for Light Steel Plate.
MIL-I-24172 - Insulation, Plastic, Cellular Polyurethane, Rigid, Preformed and Foam-in-Place.
MIL-A-24179 - Adhesive, Flexible Unicellular-Plastic Thermal Insulation.
MIL-P-24191 - Plastic Sheet, Cast, Acrylic, Shipboard Application (Illumination and Signal Lighting).
MIL-A-24456 - Adhesive for Plastic Vibration-Damping Tiles.
MIL-D-24483 - Deck Covering, Spray-On, Nonslip.
MIL-C-24500 - Cloth, Drapery, Bunk Curtain, Slipcovers, and Label, Polyaramid and Polyaramid/Novoloid Fiber Blends, Shipboard Use.

STANDARDS

FEDERAL

FED-STD-191 - Textile Test Methods.
FED-STD-501 - Floor Coverings, Resilient, Nontextile: Sampling and Testing.

PUBLICATION

UNITED STATES COAST GUARD

U.S.C.G. 164.009 - Test for Incombustibility.

(Application for copies should be addressed to the U.S. Coast Guard Headquarters, 400 Seventh Street, S.W., Washington, D.C. 20591.)

(Copies of specifications, standards, drawings, and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

NONGOVERNMENTAL

AMERICAN IRON AND STEEL INSTITUTE (AISI)

Steel Products Manual

(Application for copies should be addressed to the American Iron and Steel Institute, 150 East Forty Second Street, New York, New York 10017.)

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

E84-70 - Surface Burning Characteristics of Building Materials, Test for.
E162-67 - Surface Flammability of Materials Using a Radiant Heat Energy Source, Test for.
STP 422 - Special Technical Publication. Method for Measuring Smoke from Burning Materials.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pennsylvania 19103.)

(Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using federal agencies.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-24T00:47Z
Check the source to verify that this is the current version before use.

3. REQUIREMENTS

3.1 Materials. Interior finish materials and furnishings shall meet the requirements set forth in table I. Thicknesses for bulkhead sheathing, overhead sheathing, and furniture indicates maximum limits in both application and fire tests.

Table I - Material requirements.

Category	Material	Specification	Fire test	Maximum Test limits
Bulkhead sheathing 1/	High pressure laminate for vertical surfaces	MIL-T-17171, type IV	ASTM E84-70	Flame spread 25 Smoke developed 15 Thickness 0.045 inch
	Fabric-backed vinyl	CCC-W-408, type II	ASTM E84-70	Flame spread 25 Smoke developed 15 Thickness 0.025 inch
	Unsupported vinyl film-aluminum lamination	QQ-A-250/19, (for aluminum only)	ASTM E84-70	Flame spread 25 Smoke developed 15 Thickness film 0.010 inch Thickness aluminum 0.063 inch
	CRES panel	AISI type 304, finish 4	Not applicable	Not applicable
Overhead sheathing 2/	Fibrous glass opaque suspended ceiling panel	SS-S-118, type IX	ASTM E84-70	Flame spread 25 Smoke developed 35 Thickness 0.750 inch
	Ceramic opaque suspended ceiling panel	SS-S-118, type IX	ASTM E84-70	Flame spread 25 Smoke developed 25 Thickness 0.750 inch
	Acrylic light-diffusing panels/ windows (lighting fixture only)	MIL-P-24191,	ASTM E84-70	Flame spread 250 Smoke developed 450 Thickness 0.250 inch
	Vinyl clad perforated aluminum panel	QQ-A-250/19, (for aluminum only)	ASTM E84-70	Flame spread 25 Smoke developed 15 Thickness film 0.010 inch Thickness aluminum 0.063 inch
	CRES panel	AISI type 304, finish 4	Not applicable	Not applicable
	Steel or aluminum exposed grid suspension framework	Commercial	Not applicable	Not applicable
Furniture	Vinyl upholstery	CCC-A-680, class 2, treatment (a) 1	FED-STD-191, method 5903	Char length 3 inch After flame 2 sec
	Vinyl upholstery	CCC-C-700, class 4, treatment a (1)	FED-STD-191, method 5903	Char length 3 inch After flame 2 sec
	Aromatic polyamide upholstery	Commercial	FED-STD-191, method 5903	Char length 5 inch After flame 1 sec
	Treated cotton ticking	CCC-C-436, type II, class 2	FED-STD-191, method 5903	Char length 5 inch After flame 2 sec

See footnotes at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-24T00:47Z
Check the source to verify that this is the current version before use.

Table I - Material requirements (cont'd).

	Category	Material	Specification	Fire test	Maximum Test limits
#	Furniture (cont'd)	Neoprene cushioning and mattresses	MIL-R-20092, type II, class 4	ASTM E162-67	Flame spread index 10
#		High pressure laminate for table tops	MIL-T-17171, Type I	ASTM E84-70 (bonded)	Flame spread 75 Smoke developed 50 Thickness 0.062 inch
#	Draperies and curtains 3/	Fibrous glass	CCC-C-1703	FED-STD-191, method 5903 STP 422	Char length 1.5 inch After flame 1 sec After glow 2 sec DM corrected 20
#		Polyaramid	MIL-C-24500 Type I	FED-STD-191, method 5903 STP 422	Char length 5 inch After flame 1 sec After glow 5 sec DM corrected 20
#		~~Polyaramid~~/ Noroloid NOVOLOID YES	MIL-C-24500 Type II	FED-STD-191, method 5903 STP 422	Char length 5 inch After flame 1 sec After glow 5 sec DM corrected 20
	Adhesives 4/	Contact adhesive (sheathing on surface ships)	MMM-A-130		
		Contact adhesive (sheathing on on submarines)	MIL-A-24179, Type I		
#		Deck tile adhesive	MIL-A-21016		
		Carpet cement	Commercial		
		Bead sealer	MIL-D-17951		
		Thermal insulation	MIL-A-3316, class I		
		Thermal insulation cement	SS-C-160		
		Damping tile cement	MIL-A-24456		
#	Deck coverings	Vinyl asbestos tile	MIL-T-18830	FED-STD-501, method 6411	Char length 10 inch Combustion + ignition 4.0 min
		Vinyl tile	SS-T-312, type III	FED-STD-501, method 6411	Char length Combustion + ignition
		Vinyl sheet	L-F-450	FED-STD-501, method 6411	Char length Combustion + ignition
		Rubber roll	SS-T-312, type II	ASTM E162-67	Flame spread index 25

Typing error - Not picked up in proof reading YES 6/5/74

See footnotes at end of table

Source: https://assist.dla.mil -- Downloaded: 2026-10-24T00:47Z
Check the source to verify that this is the current version before use.

Table I - Material requirements (cont'd).

	Category	Material	Specification	Fire test	Maximum Test limits
#	Deck coverings (cont'd)	Vinyl tile or sheet with backing	L-F-475	FED-STD-501, method 6411	Char length Combustion + ignition
#		Conductive linoleum	LLL-F-1238, type II, grade H	FED-STD-501, method 6411	Char length Combustion + ignition
		Treads - non skid	MIL-D-17951	FED-STD-501, method 6411	Char length 8 inch Combustion + ignition 4.0 min
		Epoxy non-skid	MIL-D-23003	FED-STD-501, method 6411	Char length 6 inch Combustion + ignition 4.25 min
		Latex underlay	MIL-D-3135	FED-STD-501, method 6411	Char length 8 inch Combustion + ignition 4.5 min
#		Terrazzo	MIL-D-3134, type I, class 1 type I, class 2	FED-STD-501, method 6411	Char length 7 inch Combustion + ignition 4.0 min
		Latex mastic	MIL-D-3134, type II, class 1	FED-STD-501, method 6411	Char length 7 inch Combustion + ignition
		Latex concrete	MIL-D-21631	FED-STD-501, method 6411	Char length 3 inch Combustion + ignition 4.0 min
#		Magnesium aggregate	MIL-D-16680	FED-STD-501, method 6411	Char length 3 inch Combustion + ignition 4.0 min
#		Standing rubber mat	MIL-M-910	FED-STD-501, method 6411	Char length Combustion + ignition
#		Electrical grade rubber mat	MIL-M-15562	FED-STD-501 method 6411	Char length 10 inch Combustion + ignition
		Shower mat	MIL-M-19018	FED-STD-501, method 6411	Char length Combustion + ignition
		Beta fibrous glass carpet	Commercial	ASTM E162-67 without pad	Flame spread index 25
		Aromatic polyamide carpet	Commercial	ASTM E162-67 without pad	Flame spread index 25
#		Spray-on non skid	MIL-D-24483	FED-STD-501, method 6411	Char length 6 inch Combustion + ignition 4.25 min
		Barber shop mat	ZZ-M-42	FED-STD-501, method 6411	Char length Combustion + ignition

See footnotes at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-24T00:47Z
Check the source to verify that this is the current version before use.

Table I - Material requirements (cont'd).

	Category	Material	Specification	Fire test	Maximum Test limits
#	Thermal 5/ insulation	Insulating board	MIL-I-742	U.S.C.G. 164.009	Pass
#		Pipe insulation	MIL-I-2781	U.S.C.G. 164.009	Pass
#		Block insulation	MIL-I-2819	U.S.C.G. 164.009	Pass
#		Insulating blanket	MIL-I-23128	U.S.C.G. 164.009	Pass
#		Insulating felt	MIL-I-16411	U.S.C.G. 164.009	Pass
#		Insulating block	HH-I-551	U.S.C.G. 164.009	Pass
#		Insulating blanket	MIL-I-2818	U.S.C.G. 164.009	Pass
#		Insulating felt	MIL-I-15475	U.S.C.G. 164.009	Pass
		Coating compound	MIL-C-19565	ASTM E84-70 (bonded)	Flame spread 25 Smoke developed
		Coating compound	MIL-C-19993	ASTM E84-70 (bonded)	Flame spread 25 Smoke developed
		Glass cloth	MIL-C-20079	FED-STD-191, method 5903	Char length After flame After glow
		Pipe insulation	MIL-I-22344	ASTM E84-70 (bonded)	Flame spread 25 Smoke developed
		Urethane foam	MIL-I-24172	ASTM E84-70 (bonded)	Flame spread 25 Smoke developed
		End sealer	MIL-C-22395	ASTM E84-70 (bonded)	Flame spread 25 Smoke developed
		PVC - Nitrile	MIL-P-15280	ASTM E84-70 STP 422	Flame spread 25 Optical smoke density 250 Thickness 0.5 inch
#	Acoustic materials	Acoustic board	MIL-I-22023	ASTM E84-70 (bonded)	Flame spread Smoke developed
		Acoustic insulation	MIL-A-23054	U.S.C.G. 164.009	Pass
		PVC graphite	MIL-P-23653 class 1, 2	ASTM E162-67	Flame spread index
		Epoxy-sand (sheet)	MIL-P-22581	ASTM E162-67	Flame spread index

See footnotes at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-24T00:47Z
Check the source to verify that this is the current version before use.

Table I - Material requirements (cont'd).

Category	Material	Specification	Fire test	Maximum Test limits
Acoustic materials	Epoxy-sand (sprayable)	MIL-S-24062	ASTM E162-67	Flame spread index_____
	Felt-chromate	Commercial	ASTM E162-67	Flame spread index_____
	Vibration damping plastic tiles	MIL-P-23653, class 3	ASTM E162-67	Flame spread index_____

1/ Maximum test limits are based upon material bonded to a non-combustible substrate.

2/ Maximum test limits are based upon material attached to, or supported by, a non-combustible substrate.

3/ An 8-ounce weight shall be used for materials tested in accordance with FED-STD-191, method 5903.

4/ Fire test limits are not required.

5/ Materials tested in accordance with U.S.C.G. 164.009 shall pass all requirements for incombustibility.

4. FIRE TEST PROVISIONS

4.1 Responsibility for testing. Unless otherwise required in the applicable material specification, the manufacturer is responsible for conducting fire tests as specified herein. Except as otherwise specified, the manufacturer may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the tests set forth herein where such testing is deemed necessary to assure compliance to prescribed requirements.

4.2 Methods of testing. Fire tests shall be conducted on materials as specified in table I and the notes therein. All fire test procedures shall be in accordance with prescribed standards and test methods, and, unless otherwise specified herein, no less than three specimens shall be tested on material of the same lot with results averaged (arithmetic means). The following tests apply:

4.2.1 Surface flammability.

4.2.1.1 ASTM E84-70 (Tunnel test).

4.2.1.2 ASTM E162-67 (Radiant panel).

4.2.1.3 FED-STD-501, Method 6411.

4.2.2 Vertical flame resistance.

4.2.2.1 FED-STD-191, Method 5903 - A minimum of five specimens from each of the warp and filling directions on material of the same lot shall be tested and their results averaged (arithmetic means).

4.2.3 Smoke generation.

4.2.3.1 ASTM E84-70 (Tunnel test).

4.2.3.2 STP 422 (NBS Smoke Chamber).

4.2.4 Test for incombustibility.

4.2.4.1 U.S.C.G. 164.009 (Heated Tube Test).

5. NOTES

5.1 This standard will be updated periodically as additional data becomes available.

Source: https://assist.dla.mil -- Downloaded: 2026-10-24T00:47Z
Check the source to verify that this is the current version before use.

5.2 This standard will be implemented by the requirements of the applicable material specifications.

5.3 The materials specified in this standard reflect the present state-of-the-art.

5.4 THE MARGINS OF THIS STANDARD ARE MARKED "#" TO INDICATE WHERE CHANGES (ADDITIONS, MODIFICATIONS, CORRECTIONS, DELETIONS) FROM THE PREVIOUS ISSUE HAVE BEEN MADE. THIS WAS DONE AS A CONVENIENCE ONLY AND THE GOVERNMENT ASSUMES NO LIABILITY WHATSOEVER FOR ANY INACCURACIES IN THESE NOTATIONS. BIDDERS AND CONTRACTORS ARE CAUTIONED TO EVALUATE THE REQUIREMENTS OF THIS DOCUMENT BASED ON THE ENTIRE CONTENT IRRESPECTIVE OF THE MARGINAL NOTATIONS AND RELATIONSHIP TO THE LAST PREVIOUS ISSUE.

Preparing activity:
Navy - SH
(Project MISC-N960)

Source: https://assist.dla.mil -- Downloaded: 2026-10-24T00:47Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers/vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?
   A. GIVE PARAGRAPH NUMBER AND WORDING.

   B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?

   ☐ YES ☐ NO *(If "Yes", in what way?)*

4. REMARKS

SUBMITTED BY *(Printed or typed name and address - Optional)*

TELEPHONE NO.

DATE

DD FORM 1 JAN 72 1426 REPLACES EDITION OF 1 JAN 66 WHICH MAY BE USED

S/N 0102-014-1802

☆ U.S. GOVERNMENT PRINTING OFFICE: 1972—714-863/3404 2-1

Source: https://assist.dla.mil -- Downloaded: 2026-10-24T00:47Z
Check the source to verify that this is the current version before use.

FOLD

COMMANDER
NAVAL SHIP ENGINEERING CENTER
CENTER BUILDING - SEC 6124B
PRINCE GEORGE'S CENTER
HYATTSVILLE, MARYLAND 20782

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

POSTAGE AND FEES PAID
DEPARTMENT OF NAVY

DOD 316

U.S.MAIL

COMMANDER
NAVAL SHIP ENGINEERING CENTER
CENTER BUILDING - SEC 6124B
PRINCE GEORGE'S CENTER
HYATTSVILLE, MARYLAND 20782

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-24T00:47Z
Check the source to verify that this is the current version before use.