INCH-POUND

MIL-DTL-32154B
15 November 2024
SUPERSEDING
MIL-DTL-32154A(OS)
12 August 2011

DETAIL SPECIFICATION

CORD ASSEMBLY, DETONATING, SHIELDED MILD

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers the shielded mild detonating cord (SMDC) assembly (Drawing 841AS425).

2. APPLICABLE DOCUMENTS

2.1 General. The documents listed in this section are specified in sections 3 and 4 of this specification. This section does not include documents cited in other sections of this specification or recommended for additional information or as examples. While every effort has been made to ensure the completeness of this list, document users are cautioned that they must meet all specified requirements documents specified in sections 3 and 4 of this specification, whether or not they are listed.

2.2 Government documents.

2.2.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

DEPARTMENT OF DEFENSE SPECIFICATIONS

MIL-D-21625 - Design and Evaluation of Cartridges for Cartridge Actuated Devices

DEPARTMENT OF DEFENSE HANDBOOKS

MIL-HDBK-728/2 - Eddy Current Testing

(Copies of these documents are available online at https://quicksearch.dla.mil.)

2.2.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

NAVAL AIR SYSTEMS COMMAND (NAVAIR) DRAWINGS

841AS425 - Cord Assembly, Detonating, Shielded Mild

841AS450 - Test Tip, Shielded Mild Detonating Cord

841AS800 - Test Assembly, SMDC Configuration

Comments, suggestions, or questions on this document should be addressed to Commander, Naval Sea Systems Command, ATTN: SEA 05S, 1333 Isaac Hull Avenue, SE, Stop 5160, Washington Navy Yard, DC 20376-5160 or emailed to CommandStandards@navy.mil, with the subject line "Document Comment". Since contact information can change, you may want to verify the currency of this address information using the ASSIST Online database at https://assist.dla.mil.

AMSC N/A FSC 1377

Distribution Statement A. Approved for public release: distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T05:00Z
Check the source to verify that this is the current version before use.

841AS801 - Fitting Sensitivity Test

(Copies of these documents are available from Commander, Indian Head Division, Naval Surface Warfare Center, CAD/PAD Data Management Branch (Code E26), 4393 Benson Road, BLDG 1557, Indian Head, MD 20640-5092. Refer questions, inquires, or problems to nswc_iheodtd_dmo@navy.mil.)

2.3 Non-Government publications. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

AMERICAN NATIONAL STANDARDS INSTITUTE (ANSI)

ANSI/ASQ Z1.4 - Sampling Procedures and Tables for Inspection by Attributes

(Copies of this document are available online at https://webstore.ansi.org/.)

ASTM INTERNATIONAL

ASTM E748 - Standard Guide for Thermal Neutron Radiography of Materials

ASTM E1417/E1417M - Standard Practice for Liquid Penetrant Testing

ASTM E1444/E1444M - Standard Practice for Magnetic Particle Testing for Aerospace

ASTM E1742/E1742M - Standard Practice for Radiographic Examination

(Copies of these documents are available online at www.astm.org.)

BOEING COMPANY

76301-74B808225 - Cord, Mild Detonating, Shielded

(Copies of this drawing are available from The Boeing Company, 6200 James S McDonnel Blvd, St Louis, Missouri 63134.)

2.4 Order of precedence. Unless otherwise noted herein or in the contract, in the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 First article. When specified (see 6.2), a sample shall be subjected to first article inspection in accordance with 4.2.

3.2 Design and construction. SMDC shall be manufactured and tested in accordance with Drawing 841AS425 and this specification. The 3D coordinates of each SMDC shall be as specified in Boeing Company Drawing 76301-74B808225.

3.3 Materials. The SMDC design and construction, excluding bend configurations, shall conform to the standards established at technical release. Any divergence will require technical evaluation and potential design certification testing.

3.4 Interchangeability. All SMDC having the same part number shall be functionally, structurally, and dimensionally interchangeable with respect to installation and performance.

3.5 Electrostatic discharge (ESD). The cord, end fittings, and booster tip shall form a continuous metallic enclosure, i.e., faraday cage, around the explosive elements such that they are protected from the effects of Electrostatic Discharge (ESD).

3.6 Inspection requirements.

3.6.1 Metal parts. All metal parts shall be free of discontinuities when tested in accordance with 4.5.1.

3.6.2 SMDC tubing. The tubing required to confine the products of detonation shall be made of stainless steel and shall withstand a hydrostatic proof pressure test of 8000 psig. The tubing shall show no evidence of leakage, yielding, or permanent deformation when tested in accordance with 4.5.2.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T05:00Z
Check the source to verify that this is the current version before use.

3.6.3 Detonating cord. The detonating cord utilized in SMDC manufacture shall be silver sheathed Hexanitrostilbene (HNS), type II, grade A explosive in accordance with Drawing 841AS425. Silver sheathing shall be 99.9 percent silver. Only one lot of detonating cord shall be used in each SMDC production lot.

3.6.3.1 Moisture content. Maximum explosive lot moisture content at the time of cord manufacture shall not exceed 0.3 percent by weight when tested in accordance with 4.5.4.

3.6.3.2 Detonation velocity. The detonation velocity of the detonating cord shall be 21325.46±1640.42 feet per second (6500±500 meters per second) when tested at -65 °F and +350 °F in accordance with 4.5.3.1. The detonation wave shall propagate through the entire length of the test specimen.

3.6.3.3 Core load. The range of the explosive core loading in grains per foot divided by the nominal core load shall not exceed 24 percent when calculated from the detonating cord sample data obtained from 4.5.3.2.

3.6.4 Transition charge. The transition charge located between the end of the detonating cord and booster charge shall be Hexanitrostilbene (HNS), type I, grade A explosive in accordance with Drawing 841AS425. Only one lot of explosive shall be utilized in each SMDC production lot.

3.6.4.1 Moisture content. Maximum explosive lot moisture content at the time of SMDC manufacture shall not exceed 0.3 percent by weight when tested in accordance with 4.5.4.

3.6.5 Booster charge. The booster charge contained in the SMDC end cup shall be Hexanitrostilbene, type I, grade A explosive in accordance with Drawing 841AS425. The booster shall contain 1±1 grain of HNS pressed to 32,000±1,000 psi. Only one lot of explosive shall be utilized in each SMDC production lot.

3.6.5.1 Moisture content. Maximum explosive lot moisture content at the time of SMDC manufacture shall not exceed 0.3 percent by weight when tested in accordance with 4.5.4.

3.6.6 Booster tips. All booster tips shall meet the length and concentricity requirements of Drawing 841AS425 when tested in accordance with 4.5.5.

3.6.6.1 Torque. A sample of five ⅜ booster tips from each lot of outer ferrules and a sample of five 7/16 booster tips from each lot of outer ferrules shall be installed into a Navy-style port to a torque of 70 inch-pounds minimum, removed from the port and pass length and concentricity checks in accordance with 4.5.5.1.

3.6.7 Visual inspection requirement. SMDC shall be free of visual defects such as burrs, deep scratches, defective ferrules and fittings corrosion, chipped surfaces, or other defects which may prevent assembly or affect the environmental stability of the line.

3.6.8 Radiographic inspection requirement. Each SMDC shall be free of foreign material and shall have proper assembly, presence of parts, and correct use of epoxy when tested in accordance with 4.5.7. A maximum of two bright spots, indicating the presence of foreign particles, shall be allowed in each booster shell load. No particle shall exceed 0.005 inch in any dimension. No particles shall be allowed on explosive interfaces of pressed loads. No foreign material shall be allowed in the ferrule and cord explosive loads. Epoxy located on the shoulder of the booster cup and visible on the radiograph shall be considered acceptable, providing the epoxy can be verified by visual examination of the SMDC and does not mask the cord to ferrule interface. The amount of epoxy applied to the booster cup shall not be excessive enough to interfere with the interpretation of the radiograph. The gap between the inner ferrule charge and booster cup charge shall be no more than 0.005 inch over at least a continuous width of 0.100 inch as viewed on the N-ray. A change in N-ray film density at the ferrule/booster cup interface caused by the inner ferrule load not being exactly flat or a high inner ferrule load is permissible. No voids shall be permitted at any other location. Units containing one or more defects shall be rejected.

3.6.9 Leakage. The SMDC end fitting leakage rate shall not exceed 10^{-5} cc/sec of air when tested in accordance with 4.5.8.

3.6.10 End fitting strength. The end fitting joint between the outer ferrule and the stainless steel tubing shall be capable of withstanding a tensile load of 800 pounds minimum applied at a rate of 8±2 pounds per second with the 800-pound load being held for 3.5±0.5 minutes when tested in accordance with 4.5.9.

3.7 Environmental.

3.7.1 Temperature/humidity/altitude (THA) cycling. The SMDC shall not initiate or incur any degradation or damage when exposed to 28-day temperature, altitude, and cycling in accordance with MIL-D-21625 (see 4.6.1).

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T05:00Z
Check the source to verify that this is the current version before use.

3.7.2 Salt spray. The SMDC shall not initiate or incur any degradation or damage when exposed to salt spray in accordance with MIL-D-21625 (see 4.6.2).

3.7.3 Vibration. The SMDC shall not initiate or incur any degradation or damage when exposed to vibration environments in accordance with MIL-D-21625 (see 4.6.3).

3.7.4 Shock. The SMDC shall not initiate or incur any degradation or damage when exposed to shock environments in accordance with MIL-D-21625 (see 4.6.4).

3.8 Performance. The SMDC shall be initiated by the output from a SMDC test tip in accordance with Drawing 841AS450 over the temperature range of –65 to +350 °F and shall deliver sufficient energy to propagate a detonation wave in the next ordnance device or perform the necessary work function. SMDC shall be capable of transferring a detonation wave from one SMDC to another across the air gaps of the sensitivity fitting in accordance with Drawing 841AS801 and the fittings of applicable installation over the temperature range from -65 to +350 °F. The SMDC shall be constructed such that the portion of the assembly, external of the SMDC ports, remains intact when fired without rupturing, splitting cracking, emitting shrapnel, disengaging from end fittings, or shearing threads. The minimum depth of indentation produced in 6061 – T6 aluminum block shall be 0.040 inch when the SMDC is fired in accordance with 4.7.

3.9 Sets. Individual SMDC may be procured separately by applicable item dash numbers or sets may be procured by set numbers. Each set shall be composed of the SMDC dash numbers indicated on the applicable drawing.

3.10 Workmanship. Workmanship shall be in accordance with high-grade manufacturing practices to assure safety, proper operation, and service life. Assembled units shall be free of mechanical damage as specified (see 6.2).

4. VERIFICATION

4.1 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.2).

b. Production inspection (see 4.3).

c. Lot acceptance inspection (see 4.4).

4.2 First article inspection. When specified (see 6.2), a first article sample of 18 SMDC shall be subjected to first article testing. The environmental exposures shall be conducted sequentially as listed in table I. First article inspection shall be performed on sample units that have been produced with equipment and procedures normally used in production. A first article inspection shall be required if 2 or more years have passed since the item was manufactured, after major turnover in personnel, following major changes to the production facility, or following transfer of production to a new facility or site. Failure of any SMDC to meet the requirements of table I shall be cause for rejection of the first article represented. All 18 SMDC shall be expended in the tests listed in table I.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T05:00Z
Check the source to verify that this is the current version before use.

TABLE I. First article inspection.

Test	Requirement paragraph	Test paragraph	Quantity	
Visual inspection	3.6.7	4.5.6	9	9
Radiographic	3.6.8	4.5.7	9	9
Leakage	3.6.9	4.5.8	9	9
THA	3.7.1	4.6.1	9	9
Salt spray	3.7.2	4.6.2	9	9
Vibration	3.7.3	4.6.3	9	9
Shock	3.7.4	4.6.4	9	9
Visual inspection	3.6.7	4.5.6	9	9
Radiographic	3.6.8	4.5.7	9	9
Ballistic (-65 °F)	3.8	4.7	9	--
Ballistic (+350 °F)	3.8	4.7	--	9

4.3 Production inspection. All SMDC shall be inspected and screened to the examinations and tests listed in table II.

TABLE II. Production inspection.

Item	Test	Requirement paragraph	Test paragraph
Metal parts	Magnetic particle	3.6.1	4.5.1
SMDC tubing	Hydrostatic pressure	3.6.2	4.5.2
Detonating cord	Moisture content	3.6.3.1	4.5.4
Detonating cord	Detonation velocity	3.6.3.2	4.5.3.1
Detonating cord	Core load	3.6.3.3	4.5.3.2
Transition charge	Moisture content	3.6.4.1	4.5.4
Booster charge	Moisture content	3.6.5.1	4.5.4
Booster tip	Length and concentricity	3.6.6	4.5.5
Booster tip	Torque	3.6.6.1	4.5.5.1
End fitting	Leakage	3.6.9	4.5.8
SMDC	Visual	3.6.7	4.5.6
SMDC	Radiographic	3.6.8	4.5.7

4.4 Lot acceptance inspection. Lot acceptance shall consist of the examinations and tests specified in table III. Failure of any sample to comply with the requirements of table III shall be cause for rejection of the lot represented.

TABLE III. Lot acceptance inspection.

Test	Requirement paragraph	Test paragraph
Visual	3.6.7	4.5.6
Radiographic	3.6.8	4.5.7
End fitting tensile strength	3.6.10	4.5.9
Ballistic (-65 °F)	3.8	4.7
Ballistic (+350 °F)	3.8	4.7

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T05:00Z
Check the source to verify that this is the current version before use.

4.4.1 Sampling. Unless otherwise specified (see 6.2), the sampling plans and procedures used in the determination of the acceptability of lot samples shall be in accordance with ANSI/ASQ Z1.4, inspection level I, table II-A, normal inspection. All tests of table II shall have been passed successfully prior to the submittal of the lot sample. The sample shall be randomly selected from the SMDC lot prior to bending in a manner that will not produce a negative effect on planned deliverables. Any assembly or line not presented at lot acceptance test sample selection shall not be considered a part of the lot. Each SMDC selected shall then be bent in the standard SMDC lot acceptance test configuration in accordance with Drawing 841AS425. If a SMDC lot acceptance test sample is found to be unacceptable after lot acceptance test sample selection and prior to lot acceptance testing, another SMDC lot acceptance test sample shall be selected and does not need to be of the standard SMDC lot acceptance test configuration.

4.5 Tests and inspections.

4.5.1 Metal parts inspection. All high-stress steel parts capable of being magnetized shall be subjected to magnetic particle inspection in accordance with ASTM E1444/E1444M to verify conformance to the requirements of 3.6.1. Titanium, aluminum or non-magnetic steel high-stress parts shall be inspected in accordance with ASTM E1417/E1417M. Stainless steel tubing should be subjected to Eddy current testing in accordance with the principles and guidelines of MIL-HDBK-728/2. Discontinuities revealed by nondestructive testing may be removed by reworking. If it is established that such discontinuities cannot be removed by subsequent operations, the parts shall be rejected. All parts which have had discontinuities removed by machining shall be re-inspected to assure defect removal.

4.5.2 Tubing hydrostatic pressure test. All stainless steel tubing used in the SMDC shall be subjected to a hydrostatic proof pressure test of 8000 psig, minimum, prior to assembly to verify conformance to the requirements of 3.6.2.

4.5.3 Detonating cord tests. Prior to its use in SMDC manufacture, 21-inch long samples shall be selected from each tube in a lot of detonating cord in the following manner. Commencing with the initial 21 inches of detonating cord on the spool or coil, a 21-inch sample shall be taken at each 100-foot interval except for the final sample, which shall be the last 21 inches at the end of the cord on the spool or coil. Each sample shall be divided into three segments, two 9 inches long and the other 3 inches long, for the following tests. The failure of any sample to meet the requirements of 3.6.3 shall result in the rejection of the sampled tube.

4.5.3.1 Detonation velocity test. The 9-inch segments of the detonating cord sample shall be temperature conditioned for not less than 8 hours nor greater than 24 hours, one segment each, at -65±5 °F and +350±5 °F. Following temperature conditioning, each segment shall be fired by a commercial no. 6 electrical blasting cap and the detonation velocity measured to verify conformance to the requirements of 3.6.3.2.

4.5.3.2 Core load test. The amount of explosive contained in the 3-inch segment of the detonation cord samples shall be determined to verify conformance to the requirements of 3.6.3.3.

4.5.4 Explosive lot moisture content. Prior to the loading of explosives into components, the moisture content of the explosives shall be determined to verify conformance to the 0.3 percent maximum moisture content requirement specified in 3.6.3.1, 3.6.4.1, and 3.6.5.1.

4.5.5 Booster tip inspection. A 100 percent inspection of booster tip for length and concentricity shall be performed using gage set A51S62680-1 or an approved equivalent to verify conformance to the requirements of 3.6.6. Any booster tip that fails inspection shall be removed from the lot.

4.5.5.1 Torque test. The sample of booster tips shall be tested by installing into a Navy style port to a torque of 70 inch-pounds minimum. All torque test samples shall pass inspection for booster tip length and concentricity using gage set A51S62680-1 or an approved equivalent to verify conformance to the requirements of 3.6.6.1. Any defects found will be cause for rejection of the lot.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T05:00Z
Check the source to verify that this is the current version before use.

4.5.6 Visual inspection. Each SMDC produced shall be visually inspected. Units shall be rejected which have illegible, missing or inaccurate identification markings, missing o-rings, damaged or insufficient surface coatings, burrs, sharp edges, corrosion, dents, or other defects that might prevent proper installation or performance in accordance with 3.6.7. As an inspection aid, each SMDC should be visually compared with an inert master configuration SMDC to check the location of identification tags and to verify the proper bend configuration, assembly color, and size of fittings installed. The inert master configuration SMDC shall be verified by virtual analysis of vector data prior to manufacture of each SMDC line. Each line shape shall be approved as specified (see 6.2).

4.5.7 Radiographic inspection. All SMDC shall be verified by radiographic examination by X-ray and N-ray in accordance with ASTM E1742/E1742M and ASTM E748, respectively. SMDC shall conform to the requirements of 3.6.8 when subjected to the radiographic examinations of 4.5.7.1 and 4.5.7.2. SMDC shall be positioned on their sides for the most revealing exposure. All SMDC shall be identified with serial number prior to examination. The serial numbers shall be in consecutive numerical order, and each radiograph shall carry a permanent identification of the SMDC displayed thereon. Radiographic inspection plates shall be properly identified by the drawing number and item dash numbers, the lot number, and serial numbers of the SMDC displayed. Discontinuities in serial numbers shall be identified on the film. Defective SMDC shall be clearly identified on the film and those defective SMDC removed from the lot.

4.5.7.1 X-ray examination. Each assembled SMDC shall be X-rayed in accordance with ASTM E1742/E1742M after bending at each tip and the adjacent three inches of detonating cord along the longitudinal axis.

4.5.7.2 N-ray examination. Each assembled SMDC shall be N-rayed in accordance with ASTM E748 prior to bending along the full length of the longitudinal axis.

4.5.8 Leakage test. SMDC end fittings shall be leak tested in a dry gas leak tester to verify conformance to the requirements of 3.6.9. SMDC end fittings which exhibit a leak rate in excess of 10^{-5} cc/sec of air at a pressure differential of one atmosphere shall be considered defective and rejected.

4.5.9 End fitting tensile strength test. A tensile strength test sample shall be randomly selected from the SMDC lot prior to bending in accordance with the provisions for normal inspection at inspection level S-1, ANSI/ASQ Z1.4, and the following exception: rejected test specimens from other tests of the same SMDC lot may be utilized for the tensile strength test provided that the previous rejection was unrelated to the end fitting tensile strength. The sample thus selected shall be tested in a tensile strength testing machine to verify conformance to the requirements of 3.6.10. Failure of any test sample to meet the requirements of 3.6.10 shall be cause for rejection of the lot represented.

4.6 Environmental tests. The environmental exposures shall be conducted sequentially as listed in table I.

4.6.1 Temperature/humidity/altitude (THA) cycling test. The SMDC shall subjected to 28-day temperature/humidity/altitude cycling test in accordance with MIL-D-21625 to verify conformance to the requirements of 3.7.1.

4.6.2 Salt spray test. The SMDC shall be subjected to salt spray tests in accordance with MIL-D-21625 to verify conformance to the requirements of 3.7.2.

4.6.3 Vibration test. The SMDC shall be subjected to vibration environments in accordance with MIL-D-21625 to verify conformance to the requirements of 3.7.3.

4.6.4 Shock test. The SMDC shall be subjected to shock environments in accordance with MIL-D-21625 to verify conformance to the requirements of 3.7.4.

4.7 Functional testing. The sample selected from the production lot in accordance with 4.7.1 shall be divided, as nearly as possible, into two equal test groups for low- and high-temperature functional testing. If the sample is not equally divisible by two, the extra test specimen shall be placed in the low-temperature group. All test groups shall be temperature conditioned for a period of time not less than 4 hours nor greater than 24 hours. One group shall be temperature conditioned at -65 °F and the other at +350 °F. The SMDC shall be functionally fired within 5 minutes after removal of the condition chamber. The test specimen shall be fired in accordance with Drawing 841AS800. Failure of any SMDC to meet the requirements of 3.8 shall be cause for rejection of the first article or lot represented.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T05:00Z
Check the source to verify that this is the current version before use.

4.7.1 Retest. There shall be no retesting.

4.7.2 Test failure. If a test failure is attributable to an assignable cause, excluding the SMDC test specimen, at the option of the test activity, that portion of the test may be re-conducted.

5. PACKAGING

5.1 Packaging. For acquisition purposes, the packaging requirements shall be as specified in the contract or order (see 6.2). When packaging of materiel is to be performed by DoD or in-house contractor personnel, these personnel need to contact the responsible packaging activity to ascertain packaging requirements. Packaging requirements are maintained by the Inventory Control Point's packaging activities within the Military Service or Defense Agency, or within the military service's system commands. Packaging data retrieval is available from the managing Military Department's or Defense Agency's automated packaging files, CD-ROM products, or by contacting the responsible packaging activity.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. SMDC lines are intended as rapid energy transmission devices to provide an explosive release signal in aircraft emergency egress systems. The SMDC lines were developed for use in military aircraft and have no commercial application.

6.2 Acquisition requirements. Acquisition documents should specify the following:

a. Title, number, and date of this specification.

b. When first article inspection is required (see 3.1 and 4.2).

c. When assembled units are in accordance with high-grade manufacturing practices and free of mechanical damage to assure safety, proper operation, and service life (see 3.10).

d. When sampling plans and procedures used in the determination of the acceptability of lot samples are to be in accordance with ANSI/ASQ Z1.4, inspection level I, table II-A, normal inspection (see 4.4.1).

e. When each line shape is required to be approved in writing prior to manufacturer (see 4.5.6).

f. Packaging requirements (see 5.1).

g. Test activity.

h. Items of data required for each first article and production lot.

6.3 Explanation of terms. For the purpose of this specification, NAVSUPINST 4030.28, when applicable should be used to clarify terms.

6.4 Subject term (key word) listing.

Aircraft emergency egress systems
Hexanitrostilbene

6.5 Changes from previous issue. Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extent of the changes.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T05:00Z
Check the source to verify that this is the current version before use.

CONCLUDING MATERIAL

Custodians:
Army – MI
Navy – OS

Preparing activity:
Navy – OS
(Project 1377-2024-011)

Review activities:
Army – AV, TE
Navy – AS
Air Force – 11, 70, 84, 170

Civil agency:
GSA – FAS

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T05:00Z
Check the source to verify that this is the current version before use.