MILITARY SPECIFICATION

CLOTH, BROADCLOTH, POLYESTER/COTTON, POLYESTER FILAMENT, END TO END, (DURABLE PRESS)

This specification is approved for use by the Air Force Materials Laboratory, Department of the Air Force, and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers the requirements for polyester and cotton blended broadcloth, chemically treated with a durable press finish and cured.

2. APPLICABLE DOCUMENTS

2.1 Issues of documents. The following documents, of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

SPECIFICATIONS

FEDERAL

V-T-285	Thread, Polyester
PPP-P-1134	Packaging and Packing of Cotton and Cotton-Synthetic Fiber Blend Fabrics (Excluding Duck Fabrics)

STANDARDS

FEDERAL

FED-STD-4	Glossary of Fabric Imperfections
FED-STD-191	Textile Test Methods

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to the Aeronautical Systems Division, ENESS, WPAFB, Ohio 45433 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

FSC 8305

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:52Z
Check the source to verify that this is the current version before use.

MILITARY

MIL-STD-105 Sampling Procedures and Tables for Inspection by Attributes

(Copies of specifications, standards, drawings, and publications required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

Rules and Regulations Under the Textile Fiber Products Identification Act, effective 3 March 1960

(Application for copies should be addressed to the Federal Trade Commission, Washington, DC 20580.)

THE AMERICAN ASSOCIATION OF TEXTILE CHEMISTS AND COLORISTS

Technical Manual of the American Association of Textile Chemists and Colorists

(Application for copies should be addressed to the American Association of Textile Chemists and Colorists, Research Triangle Park, P.O. Box 886, Durham, NC 27709.)

3. REQUIREMENTS

3.1 Standard sample. The dyed, treated, and cured (finished) cloth shall match the standard sample for shade and shall be equal to or better than the standard sample with respect to all characteristics for which the standard sample is referenced (see 6.3).

3.2 Preproduction sample approval. When specified (see 6.2), before production is commenced, a 4-yard sample, full width, of the finished cloth shall be submitted or made ready for the contracting officer or his authorized representative for inspection as specified in 4.2. The approval of the first article authorizes the commencement of production, but does not relieve the contractor of responsibility for compliance with all applicable provisions of this specification. The first article sample shall be manufactured by the contractor in the same facilities to be used for manufacture of the production item.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:52Z
Check the source to verify that this is the current version before use.

3.3 Materials.

3.3.1 Fibers.

3.3.1.1 Polyester fiber. The fiber shall be polyethylene glycol teraphthalate (see 4.4.1).

3.3.1.2 Cotton. The cotton shall be carded and combed (see 4.4.1).

3.3.2 Yarns.

3.3.2.1 Warp. One warp yarn shall be 150 denier, 100 percent continuous filament polyester. One warp yarn shall be a blend of 65 percent polyester, 35 percent cotton ± 3 percent drawn and spun into single yarns.

3.3.2.2 Filling. The filling yarns shall be a blend of 65 percent ± 3 percent polyester, 32 percent cotton drawn and spun into single yarns.

3.4 Color. The color of the dyed treated, and cured (finished) cloth shall be Air Force Blue 1550 and shall match the standard sample (see 3.5.1). The cloth shall be cross (piece) dyed in such a manner that the 100 percent continuous filament polyester yarns are dyed solid blue and the blended polyester/cotton warp and filling yarns are white.

3.4.1 Matching. The treated and finished cloth shall match the standard sample under artificial daylight having a color temperature of 7500 Kelvin and shall be a good approximation to the standard sample under incandescent lamplight at 2800 Kelvin.

3.4.2 Colorfastness. The dyed, treated, and cured, (finished) cloth shall show fastness to combined laundering and bleaching, crocking, perspiration, and light equal to or better than the standard samples. When no standard sample has been established or designated as applicable to colorfastness, the dyed, treated, and cured (finished) cloth shall show good fastness to combined laundering and bleaching, perspiration and light, and shall show a Munsel value for crocking not lower than 8.5. Tests shall be made as specified in 4.5.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:52Z
Check the source to verify that this is the current version before use.

3.4.3 Sulfur content. The use of dyes and compounds containing elementary sulfur capable of oxidation to sulfuric acid is prohibited. The dyestuff shall be chosen and so applied that the dyed and finished cloth shall contain no more labile sulfur than shown by the standard sample when tested as specified in 4.5. When a standard sample is not available, the dyed and finished cloth shall show no more than a slight trace of labile sulfur as defined in the test method specified in 4.5.

3.5 Physical requirements. The treated and finished cloth shall conform to the requirements in table I, when tested as specified in 4.5.

Table I. Physical requirements.

oz/per/sq/yd		Yarns per Inch		Breaking Strength Pounds		Weave	Tearing Strength Pounds	
		Minimum		Minimum			Minimum	
Min	Max	Warp	Filling	Warp	Filling		Warp	Filling
3.7	4.2	85	54	100	80	Plain	5	5

3.5.1 Construction. The cloth shall be of an end and end construction with alternating warp ends of 100 percent continuous filament polyester yarn and 65 percent polyester, 35 percent cotton blend spun yarn. The finished cloth shall contain 75 ± 3 percent polyester fiber and not less than 22 percent cotton based on the dry weight of the desired specimen before treatment and finishing when tested as specified in 4.5.

3.5.2 Width. The width of the cloth shall be as specified (see 6.2) and shall be the minimum width inclusive of selvage.

3.6 Cloth preparation. The dyed and untreated cloth shall be scoured, singed, stabilized, and mercerized, when required, to result in a smooth and lustrous finish equal in character to that of the standard sample and to meet the requirements of this specification.

3.6.1 Nonfibrous material. The starch and protein content, including chloroform-soluble and water-soluble material, of the dyed and untreated cloth shall not exceed 1.5 percent when tested as specified in 4.5.

3.7 Shrinkage. The cloth shall be preshrunk and shall not shrink more than 2.0 percent in either direction of the warp or the filling when tested as specified in 4.5. The preshrinking process used shall not be identified by name or trademark either on the cloth, ticket, or package.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:52Z
Check the source to verify that this is the current version before use.

3.8 pH. The pH value of the water extract of the dyed, treated and cured (finished) cloth shall be no less than 5.0 nor more than 8.5 when tested as specified in 4.5.

3.9 Seam efficiency. The treated and finished cloth shall have a seam efficiency of not less than 85 percent when tested as specified in 4.5.

3.10 Treatment. The dyed cloth shall be given an approved (see 6.4) durable press treatment consisting of a suitable catalyzed resin or reactant system and hand modifiers. A wetting agent may be used to facilitate processing. Durable press resins other than those approved for use are prohibited. The cloth shall be so processed that the dyed, treated, and cured (finished) cloth shall meet the applicable requirements of this specification when tested as specified in 4.5.

3.10.1 Appearance. The cured cloth shall show ratings not less than the following when tested after 5 launderings as specified in 4.5.

	Minimum average rating per sample unit
Appearance rating	3.0

3.11 Length and put-up. Unless otherwise specified (see 6.2), the cloth shall be furnished in continuous lengths, each not less than 40 yards. Each length shall be put up on full width rolls as specified in PPP-P-1134.

3.12 Fiber identification. Each roll of cloth shall be labeled or ticketed for fiber content in accordance with the Rules and Regulations under the Textile Fiber Products Identification Act. The face side of the cloth shall be identified by applying a stamping on that side of the cloth with the word FACE at each end of the piece.

3.13 Workmanship. The cured and finished cloth shall conform to the quality established by this specification. The demerit points per 100 square yards when calculated as specified in section 4 shall not exceed the established maximum point value.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:52Z
Check the source to verify that this is the current version before use.

specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Certificate of compliance. Where certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3)
b. Quality conformance inspection (see 4.4).

4.3 First article sample inspection. When required, the first article sample of the treated and finished cloth, submitted in accordance with 3.2, shall be visually inspected for appearance, color, and finish. The sample shall be tested for physical and chemical characteristics in accordance with table II, FED-STD-191, and 4.5, as applicable.

Table II. Component test method.

Characteristic	Requirement Paragraph	Test Method	
Polyester identification	3.3.1.1	4.4.1	1/
Cotton identification	3.3.1.2	1200	1/
Cotton combed	3.3.1.2		1/

1/ Unless otherwise specified, a certificate of compliance shall be submitted and will be acceptable for the stated requirement.

4.4 Quality conformance inspection. Quality conformance inspection shall be in accordance with MIL-STD-105 except where otherwise indicated.

4.4.1 Component and material inspection. In accordance with 4.1, components and materials shall be tested in accordance with all the requirements of referenced specifications, drawings, and standards unless otherwise excluded, amended, modified, or qualified in this specification or applicable purchase documents.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:52Z
Check the source to verify that this is the current version before use.

4.4.2 Examination of the end item. Examination of the end item shall be in accordance with 4.3.4.1 through 4.4.2.4.

4.4.2.1 Yard-by-yard examination. Each roll in the sample shall be examined on the face side only. When the total yardage in the roll does not exceed 100 yards, the entire yardage of the roll shall be examined. When the total yardage in the roll exceeds 100 yards, only 100 yards shall be examined. All defects as defined in section I of FED-STD-4, which are clearly noticeable at normal inspection distance (3 feet), shall be scored and assigned demerit points as listed in 4.4.2.1.1, except that only those slubs and knots which exceed the limits shown on Sears Fabric Defect Scales, F for slubs and D for knots (see 6.5) shall be scored. No linear yard (increments of 1 yard on the measuring device of the inspection machine) from any one roll within the sample shall be penalized more than 4 points. The sample size shall be in accordance with the following:

Lot size (yards)	Sample size (rolls) 1/
3200 or less	8
3201 up to and including 10,000	13
10,001 and up	20

1/ No more than one roll shall be taken from any shipping container unless the number of shipping containers in the lot is less than the required number of rolls, in which case all shipping containers shall be present in the sample.

The lot shall be unacceptable if the points per 100 square yards of the total yardage examined exceeds 40 points. The lot shall be unacceptable if the points per 100 square yards of two or more individual rolls exceeds 55 points. If no individual roll exceeds the point level, the lot shall be acceptable with respect to this characteristic. If one roll exceeds the point level, a second sample equal in size to the first, shall be examined only for individual roll quality examination. The lot shall be unacceptable if one or more rolls in the second sample exceeds the point level. Point computation for lot quality and individual roll quality shall be as follows:

$$\frac{\text{Total points scored in sample} \times 3600}{\text{Contracted width of cloth (inches)} \times \text{total yards inspected}} = \text{Points per 100 sq yds}$$

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:52Z
Check the source to verify that this is the current version before use.

4.4.2.1.1 Demerit points. Demerit points shall be assigned as follows:

For defects 3 inches or less in any dimension	- one point
For defects exceeding 3 inches, but not exceeding 6 inches in any dimension	- two points
For defects exceeding 6 inches, but not exceeding 9 inches in any dimension	- three points
For defects exceeding 9 inches in any dimension	- four points

NOTE: The following defects, when present, shall be scored four points for each yard in which they occur:

Baggy, ridgy, or wavy cloth
Objectionable order
Width less than minimum specified
Poor dye penetration, mottled, streaky, or cloudy
Character of finish not equal to standard sample.

4.4.2.2 Examination for length.

4.4.2.2.1 Individual rolls. During the yard-by-yard examination, each roll in the sample shall be examined for length. Any length found to be less than the minimum specified or more than two yards less than the length marked on the ticket, shall be considered a defect with respect to length. The lot shall be unacceptable if two or more rolls in the sample are defective in respect to length.

4.4.2.2.2 Total yardage in sample. The lot shall be unacceptable if the total of the actual lengths of rolls in the sample is less than the total of the lengths marked on the roll tickets. The rolls examined shall be those selected for the examination of individual rolls.

4.4.2.3 Examination for shade. During the yard-by-yard examination, each roll in the sample shall be examined for shade. Any roll in the sample off shade, shaded side to side, side to center, or end to end shall be cause for rejection of the entire lot represented by the sample.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:52Z
Check the source to verify that this is the current version before use.

4.4.2.4 Examination for identification of preshrinkage process and noncompliance with Textile Fiber Products Identification Act and marking. During the yard-by-yard examination, each roll in the sample shall be examined for identification of preshrinkage process and noncompliance with the Textile Fiber Products Identification Act. The lot shall be unacceptable if two or more rolls in the sample contain identification of a preshrinkage process by name or trademark on the cloth or ticket, or are not labeled or ticketed in accordance with the Rules and Regulations under the Textile Products Identification Act or the FACE stamp missing from either or both ends, or the FACE stamp on the wrong side.

4.5 Tests. The methods of testing specified in FED-STD-191, wherever applicable, and as listed in tables III and IV shall be followed. The physical and chemical values specified in section 3 apply to the average result of the determinations made on a sample unit for test purposes as specified in the applicable test methods. The sample unit shall be 4 continuous yards full width of the finished cloth, and 1/2 yard full width of the dyed untreated cloth. The lot size shall be expressed in units of 1 yard each. The lot shall be unacceptable if one or more sample units fail to meet any test requirement specified. All test reports shall contain the individual value utilized in expressing the final results. The sample size shall be in accordance with the following:

Lot size (yards)	Sample size (units)
800 or less	2
801 up to and including 22,000	3
22,001 and over	5

Table III. Test methods (applicable to dyed untreated cloth).

Characteristic	Requirement Paragraph	Test Method
Fiber content		
Polyester (percent)	3.3.2	2100, 4.4.2
Cotton (percent)	3.3.2	2100, 4.4.2
Yarn (single)		
Warp	3.3.2	Visual 1/
Filling	3.3.2	Visual 1/
Weave	3.5	Visual 1/
Nonfibrous materials	3.6.1	2611
Mercerization	3.6	2/

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:52Z
Check the source to verify that this is the current version before use.

Table III (Footnotes).

1/ One determination per sample unit and the result reported as "pass" or "fail".

2/ Microscopic examination for swelling of the cloth fibers. One determination per sample unit and the result reported as "pass" or "fail".

Table IV. Test Methods (applicable to treated and finished cloth).

Characteristic	Requirement Paragraph	Test Method
Yarns per inch		
Warp	3.5	5050
Filling	3.5	5050
Breaking strength		
Warp	3.5	5100
Filling	3.5	5100
Tearing strength		
Warp	3.5	5132
Filling	3.5	5132
Sulfur content	3.4.3	2020
Colorfastness to:		
Combined laundering and bleaching	3.4.2	5605
Crocking	3.4.2	5651
Perspiration	3.4.2	5680
Light	3.4.2	5660 1/
Weight	3.5	5041
Appearance after 5 launderings	3.10.1	4.5.3
Shrinkage		
Warp	3.7	5552
Filling	3.7	5552
Seam efficiency	3.9	5110 2/
pH	3.8	2811

1/ Method 5660 shall be used except that exposure of the specimen and standard sample shall be for 20 standard fading hours. Any specimen showing discoloration less than or equal to that of the standard sample shall be rated "satisfactory". Any specimen showing discoloration greater than that of the standard sample shall be rated "unsatisfactory". One determination shall be made for each sample unit and the result reported as "pass" or "fail".

2/ The needle shall measure 0.036 ± 0.001 inch across the blade at the eye. The polyester thread shall be type I, class I of V-T-285. The

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:52Z
Check the source to verify that this is the current version before use.

needle thread shall be size AA and the looper thread shall be size A.

4.5.1 Fiber. The polyester filament shall be insoluble in each of the following solvents: Acetone (boiling); 70 percent sulfuric acid; 5.0 percent sodium hydroxide (boiling); and methylene chloride (boiling). The methylene chloride shall be prepared by mixing 9 parts methylene chloride with 1 part U.S.P. (95 percent) ethyl alcohol. The methylene chloride solution is extremely toxic and adequate ventilation or use of fume hood is recommended. Unless otherwise specified, the above solvents shall be used at room temperature, using 100 times as much solvent as fiber. The fiber shall remain in the solvent for 10 minutes with intermittent stirring. This is a visual qualitative test.

4.5.2 Test for polyester fiber and cotton content. The general procedures of method 2100, FED-STD-191 shall be followed and the fiber content percentage shall be calculated as follows:

$$\frac{\text{Weight of dry residual fiber X 100}}{\text{Weight of dry desized specimen}} = \text{percent cotton}$$

100 - percent polyester = percent cotton

4.5.2.1 Report. Two specimens shall be tested from each sample unit and the average percent polyester and the average percent cotton of the two specimens shall be reported to the nearest 1.0 percent.

4.5.3 Appearance of cloth. Apparatus and material shall be specified in AATCC 124-169.

4.5.3.1 Apparatus and material.

4.5.3.1.1 The following apparatus and materials are required for laundering:

a. Kenmore automatic washing machine, Model 600, or equivalent.

b. Kenmore automatic dryer, Model 600, or equivalent.

c. AATCC standard detergent, or equivalent.

d. Mineral, Nujol, Plough Incorporated, Memphis, Tennessee, or equivalent.

e. AATCC standard blotting paper, or equivalent.

f. Five-pound cylindrical weight, 2-1/2 inches diameter.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:52Z
Check the source to verify that this is the current version before use.

g. Dummy pieces for ballast - 36 by 36 inches hemmed of type 128 sheeting added to test specimens to make an approximate 4-pound load.

h. AATCC glassine paper, or equivalent.

4.5.3.2 Preparation of specimen for evaluating appearance. Three specimens 15 by 15 inches, measured parallel to the warp and filling shall be cut from a portion of the treated and finished cloth sample.

4.5.3.2.1 Laundering. Place the three 15 inch by 15 inch specimens in the washer. The washer load shall be approximately 4 pounds. A minimum of 10 dummy pieces shall be added to the machine along with the specimens to make up the 4-pound load. Fill to the full water level of the washer with water of a hardness not to exceed 50 parts per million, and at a temperature of 120° ± 5°F (48.9 ± 15.0°C). Add 140 grams of detergent. Set the washer to proceed automatically through the final spin cycle. Remove the specimens immediately at the completion of the final spin and separate from the dummy pieces and each other, if tangled. Place the completed washed load (4 pounds) in the dryer and dry at the permanent press cycle and setting which generates an exhaust temperature range of 140° to 160°F (60.0 to 71.1°C). Operate the dryer until the load is dry and continue tumbling 10 minute cool down cycle. Remove the load immediately after the machine stops. Repeat the wash and dry cycles for 4 additional cycles. When the fifth cycle is completed, the specimens shall be conditioned to equilibrium under standard conditions in accordance with FED-STD-191. During conditioning and during periods of interruption of the cycles, the samples shall be suspended from a line.

4.5.3.3 Evaluation. Three trained observers shall evaluate each sample unit for appearance characteristics. The observers shall make their observations independently. Each observer, while standing in front of the viewing board and 4 feet back from it, shall evaluate each specimen for appearance as it hangs on the viewing board.

4.5.3.3.1 Evaluation of the appearance of the cloth. The overhead lighting shall be used (see 4.5.3.1). Mount the specimen on the viewing board with the center of the specimen 5 feet from the floor. Place three dimensional plastic replicas on each side of the specimen with the centers 5 feet from the floor, to facilitate comparative rating. The specimen shall be rated according to the appearance on the plastic replica that most nearly matches the appearance of the cloth. The average of the rating values assigned for appearance of the cloth by the observers rounded off to the nearest 0.5 rating shall be the rating of the specimen. Each rating value given by the observers for appearance of the cloth shall also be reported.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:52Z
Check the source to verify that this is the current version before use.

4.6 Examination of preparation for delivery requirements. Examination shall be made in accordance with the provisions of PPP-P-1134 to determine that packaging, packing, and marking requirements of section 5 of this specification are complied with.

5. PACKAGING

5.1 Preservation-packaging. Preservation-packaging shall be level A or C as specified (see 6.2).

5.1.1 Levels A and C. The cloth, put up as specified shall be packaged in accordance with the applicable requirements of PPP-P-1134.

5.2 Packing. Packing shall be level A, B, or C as specified (see 6.2).

5.2.1 Levels A, B, and C. The cloth shall be packed in accordance with the applicable requirements of PPP-P-1134.

5.3 Marking. In addition to any special marking required by the contract, shipments shall be marked in accordance with the requirements of PPP-P-1134.

6. NOTES

6.1 Intended use. The cloth covered by this specification is intended for use in the manufacture of shirts worn by personnel of the Department of Defense.

6.2 Ordering data. Procurement documents should specify the following:

a. Title, number, and date of this specification.

b. When preproduction sample is required (see 3.2).

c. Width of cloth required (see 3.5.2).

d. Minimum length if other than specified (see 3.9).

e. Selection of applicable levels of packaging and packing (see 5.1 and 5.2).

6.3 Standard sample. For access to standard sample, address the procuring activity issuing the invitation for bids.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:52Z
Check the source to verify that this is the current version before use.

6.4 Approval of the durable press resins or reactants for utilization under this specification is the responsibility of the US Air Force. Only those treatments approved shall be considered acceptable.

6.5 Sears Fabric Defect Scales are available from Sears, Roebuck and Company, Department 769, Sears Replica Kit, Sears Tower, Chicago, IL 60684.

6.6 This specification supersedes Purchase Description ENEU 78-5.

Custodian:
Air Force - 11
Army - GL

Review activity:
DLA - DP, CT

Preparing activity:
Air Force - 11

(PROJECT NO. 8305-F736)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:52Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS This form is provided to solicit beneficial comments which may improve this document and enhance its use DoD contractors, government activities, manufacturers, vendors, or other prospective users of the document are invited to submit comments to the government Fold on lines on reverse side, staple in corner, and send to preparing activity. Attach any pertinent data which may be of use in improving this document If there are additional papers, attach to form and place both in an envelope addressed to preparing activity. A response will be provided to the submitter, when name and address is provided, within 30 days indicating that the 1426 was received and when any appropriate action on it will be completed.

NOTE This form shall not be used to submit requests for waivers, deviations or clarification of specification requirements on current contracts Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

DOCUMENT IDENTIFIER *(Number)* AND TITLE

MIL-C-87143

NAME OF ORGANIZATION AND ADDRESS OF SUBMITTER

☐ VENDOR ☐ USER ☐ MANUFACTURER

1 ☐ HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE? ☐ IS ANY PART OF IT TOO RIGID, RESTRICTIVE, LOOSE OR AMBIGUOUS? PLEASE EXPLAIN BELOW.

A GIVE PARAGRAPH NUMBER AND WORDING

B RECOMMENDED WORDING CHANGE

C REASON FOR RECOMMENDED CHANGE(S)

2 REMARKS

SUBMITTED BY *(Printed or typed name and address — Optional)*	TELEPHONE NO
	DATE

DD FORM 1426 PREVIOUS EDITION WILL BE USED.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:52Z
Check the source to verify that this is the current version before use.

FOLD

ASD/ENESS
Wright-Patterson AFB, O 45433

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

POSTAGE AND FEES PAID
DEPARTMENT OF AIR FORCE
DOD-316



ASD/ENESS
Wright-Patterson AFB, O 45433

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:52Z
Check the source to verify that this is the current version before use.