COMMERCIAL ITEM DESCRIPTION

CARVER, DENTAL, Interproximal

The General Services Administration has authorized the use of this Commercial Item Description.

This Commercial Item Description covers two types of interproximal dental carvers.

Salient characteristics:

General. The carvers shall be of the following types:

Type I Double-ended.
Type II Double-angled, double-ended

The carvers shall be double-ended, interproximal carvers suitable for use in carving proximal surfaces of amalgam restorations in the plastic state, following compacting in prepared cavities within the teeth.

Material. The operative ends shall be fabricated of martensitic corrosion resistant steel in accordance with ASTM F899. The handles shall be hollow, chrome plated brass or corrosion resistant steel.

Hardness. The Rockwell hardness of the operating ends of the carver shall be C52 to C56 after proper stress relieving in accordance with American Society for Testing and Materials (ASTM) Standards E18 or E92. Conversion of Vickers hardness values to Rockwell values shall be in accordance with ASTM E140.

AMSC N/A FSC 6520
DISTRIBUTION STATEMENT A. Approved for public release, distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:22Z
Check the source to verify that this is the current version before use.

Style, design and dimensions. The carvers shall be of thin-blade design having sufficient flexibility for interproximal carving. The blades shall be uniform in width, having a rounded free end. The carvers shall be of three piece construction, having a handle with an operative end at each end of the handle. The three piece design shall provide the capability of replacement (re-tipping) of the operative ends by the manufacturer. The operative ends of the Type I carver shall be contra-angled in opposite directions. The operative ends of the Type II carver shall be double-angled in opposite directions. The style, design, and dimensions of the carvers shall conform to DPSC drawing 24428 for the applicable type. The operative ends shall be securely attached to the handles. The interface of the shanks and handles shall be smoothly blended with no visible crevices. Handles shall have a serrated or knurled finger grip portion which shall provide suitable finger grip capability.

Finish. The blades shall have a mirror finish and shall be smoothly blended to form a sharp knife-like edge along the entire periphery of the blade. Finish on all edges and surfaces shall be uniform, free of burrs, crevices, grind marks, rough areas, cracks, and overlaps.

Passivation. The corrosion resistant steel components shall be properly passivated.

Corrosion resistance. The carvers shall meet the corrosion resistance requirements of ASTM F1089, when tested as specified therein; the copper sulfate test for the operative ends; and the boil test for the complete instrument.

Performance. The carver blades shall measure less than 2 degrees permanent set (deflection) when tested as specified in test section under angle deflection.

The carver blades shall measure less than 2 degrees set (deflection) when tested as specified in test section under force deflection.

The carver blades shall be capable of being bent 180 degrees (minimum) in one direction without any signs of fractures or breakage when tested as specified in test section under bend. The blades shall require a force of 22 $\pm$ 2 ounces to bend the blade 180 degrees.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:22Z
Check the source to verify that this is the current version before use.

Identification marking. Each carver shall be permanently and legibly marked on the smooth portion of the handle with the respective identification. IPC for Type I or IPC-B for Type II. Instruments made in U.S.A shall be marked with the name or registered trademark of the contractor and the word "stainless". Instruments of foreign (other than U.S.) manufacture shall be marked with the name of the country of origin, together with the name or registered trademark of the contractor.

Workmanship. Carvers shall be free from burrs, cracks, scale, pitting, corrosion or other defects which detract from their appearance or impairs their serviceability.

Product Quality Level.

Visual and dimensional examination. Shall be examined to verify that design, construction and workmanship are in accordance with applicable requirements.

Materials. The supplier shall be responsible for performing tests to assure that materials are in accordance with requirements specified.

Unit. Each (EA). One carver, as specified, constitutes one unit.

Quality Assurance Provisions.

Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of three years after delivery of the supplies to which such records relate.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:22Z
Check the source to verify that this is the current version before use.

Inspection. Inspection, as used herein, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

Sampling for examination. Sampling for examination shall be conducted in accordance with MIL-STD-105 and as specified herein. Unit of product for examination purpose shall be one carver. Sampling shall be level II and AQL of 1.0.

Examination. Examination shall be conducted to determine compliance with specification requirement. The carver shall be examined for defects including, but not limited to those listed below.

Defects

Instrument not free from cracks, pits, burrs, scale, rough area or corrosion.

Finish not as specified.

Type not as specified.

Identification markings not present, complete, correct, or legible.

Instruments not clean.

Sampling for tests. Sampling for tests shall be conducted in accordance with MIL-STD-105 and as specified herein. The unit of product for test purposes shall be one carver. Sampling shall be conducted at inspection level S-1. Acceptance for all sample sizes shall be zero.

Tests. Tests to include dimensions, shall be conducted to determine compliance with specification requirements. Where feasible, the same sample shall be used for the determination of two test characteristics.

Boil. The boil test shall be in accordance with ASTM F1089.

Copper Sulfate. The copper sulfate test shall be in accordance with ASTM F1089.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:22Z
Check the source to verify that this is the current version before use.

Angle deflection. The carver blades shall be deflected a minimum of 35 degrees, for a minimum of 5 times, in the same direction. The deflecting force shall be applied at 1.5 millimeter from the tip of the blade. The blades shall be allowed to return to their unstressed position after each deflection.

Force deflection. The carver blades shall be subjected to 10 ± 1 ounces applied perpendicular to the blade at 1.5 millimeters from the blade tip for a minimum of five times in the same direction. The blades shall be allowed to return to their unstressed position after each application of force.

Bend. The blades shall be bent 180 degrees (minimum) in one direction, over a 1 ± 0.2 millimeter diameter mandrel located at 5/32 ± 1/64 inch from the tip of the blade. A force of 22 ± 2 ounces shall be used to bend the blade 180 degrees.

Metric Products. Products manufactured to metric dimensions will be considered on an equal basis with those manufactured using inch-pound units, providing they fall within the tolerances specified using conversion tables contained in the latest revision of Federal Standard No. 376, and all other requirements of this document are met.

If a product is manufactured to metric dimensions and those dimensions exceed the tolerances specified in the inch-pound units, a request should be made to the contracting officer to determine if the product is acceptable.

The contracting officer has the option of accepting or rejecting the product.

Contractor certification. The contractor shall certify that the product offered meets the the salient characteristics of this description and conform to the producers' own drawings, specifications, standards, and quality assurance practices. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:22Z
Check the source to verify that this is the current version before use.

Regulatory requirements.

Federal Food, Drug and Cosmetic Act. If the product covered by this document has been determined by the U.S. Food and Drug Administration to be under its jurisdiction, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of the Federal Food, Drug and Cosmetic Act, as amended, and regulations promulgated thereunder. In addition, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of all other applicable Federal, State, and local statutes, ordinances, and regulations.

Recovered materials. The offeror/contractor is encouraged to use recovered material in accordance with Public Law 94-580, as amended, and as implemented for Federal Acquisition Regulation Subpart 23.4 to the maximum extent practical.

Preservation, packaging, packing, labeling, and marking. Unless otherwise specified, preservation, packaging and packing shall be to a degree of protection to preclude damage to containers and/or contents thereof under normal shipping conditions, handling, etc., involving shipment from the supply source to the receiving activity, plus reshipment from receiving activity, and shall conform to applicable carrier's rules and regulations. Intermediate and exterior package quantities and labeling and marking shall be as specified in the contract and/or order.

NOTE: The following National Stock Numbers are covered by this document:

Stock Number	Item Identification	TYPE
6520-01-053-5549	CARVER, DENTAL, Interproximal	I
6520-01-097-0693	CARVER, DENTAL, Double-Angled Interproximal	II

Ordering data. Intermediate/exterior package quantities, labeling, and marking must be as specified in the contract and/or order.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:22Z
Check the source to verify that this is the current version before use.

MILITARY INTERESTS:

Custodians:
Army - MD
Navy - MS
Air Force - 03

Preparing Activity:

DoD - MB

Agent:

DLA - DM

Civil Agency Coordinating Activities:

VA-OSS
PHS
FDA-MPQAS

Project No. 6520-2128

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:22Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
A-A-53643	CARVER, DENTAL, Interproximal

a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ USER
	☐ MANUFACTURER
	☐ OTHER *(Specify)*

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording

c. Reason/Rationale for Recommendation

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:22Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS. In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEFENSE LOGISTICS AGENCY

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATE

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO 4966 WASHINGTON D C

POSTAGE WILL BE PAID BY THE DEFENSE LOGISTICS AGENCY

Commander
Defense Personnel Support Center
ATTN: DPSC RSTE
2800 South 20th Street
Philadelphia, Pennsylvania 19101-8419

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:22Z
Check the source to verify that this is the current version before use.