A-A-53654
19 August 1988

COMMERCIAL ITEM DESCRIPTION

ABRASIVE, DENTAL
(Stick Form, Silicon Carbide)

The General Services Administration has authorized the use of this Commercial Item Description.

This Commercial Item Description covers a silicon carbide dental abrasive in stick form.

Salient characteristics:

General. The abrasive compound shall be suitable for polishing type III (hard) cast gold restorations in the dental prosthetic laboratory. The abrasive compound when used shall impart a smooth finish with a shine.

Materials. The abrasive compound shall consist of 30 ± 1 percent by weight of silicon carbide, 45 ± 1 percent by weight of 325 mesh silicon dioxide abrasive filler with remainder consisting of a binder containing stearic acid and glycerides. The compound shall contain no iron.

Physical properties. The particle size of silicon carbide shall be 180 mesh when tested in accordance with American National Standards Institute (ANSI) Standard B74.12-1976 (R1982). The net weight of the abrasive compound shall be a minimum of 130 grams. The flash point of the abrasive compound shall be a minimum of 400^0F when tested in accordance with American Society for Testing and Materials (ASTM) Standard D92. The melting point (temperature) of the binder shall be a minimum of 125^0F when tested in accordance with USP. The saponification number of the binder shall be a maximum of 180 when tested in accordance with ASTM D1962. The free fatty acid content of the binder expressed as percentage oleic acid, shall be 12 ± 1 percent when tested in accordance with ASTM D1980.

AMSC N/A FSC 6520
DISTRIBUTION STATEMENT A. Approved for public release, distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:22Z
Check the source to verify that this is the current version before use.

Design, construction and put-up. The compound shall be provided in the form of a smooth, one-piece, solid cylinder, contained in a dispenser consisting of a protective medium impact polystyrene case, with a replaceable medium impact polystyrene screw cap and a low density polyethylene push-type base used to extrude the compound stick from the case. The outside dimensions of the plastic dispenser shall be 1-5/8 ± 1/16 inches in diameter by 4-3/8 ± 1/8 inches long. The compound cylinder and the push-up base shall move freely within the case when pushed by finger pressure.

Performance. The abrasive compound shall polish type III (hard) cast gold restorations to a mirror polish finish.

Delivery schedule. No more than three months shall have elapsed from date of manufacture of the compound to date of delivery to the Government.

Manufacturer's instructions. Adequate and accurate instructions for using the abrasive compound shall appear on a label securely affixed to the dispenser, or shall be printed on the dispenser.

Workmanship. The abrasive compound shall be free from foreign matter, dirt, or other impurities. Dispenser shall be free from cracks or deformations. The product and its container shall be free from defects which detract from their appearance or impair their serviceability.

Unit. Each (EA). One abrasive dental stick, as specified, constitutes one unit.

Quality Assurance Provisions.

Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:22Z
Check the source to verify that this is the current version before use.

Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of three years after delivery of the supplies to which such records relate.

Inspection. Inspection, as used herein, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

Tests. Tests shall be conducted to determine compliance with specification requirements. Where feasible, the same sample shall be used for the determination of two or more test characteristics.

Sampling for inspection. Sampling for inspection shall be conducted in accordance with MIL-STD-105. Where feasible, the same sample shall be used for the determination of two or more examination characteristics. The unit of product for inspection purposes shall be one unit of issue as specified. Sampling for examination shall be conducted at inspection level II, AQL 1.0. The sample shall be examined for defects, including but not limited to the following.

Defects

Compound crumbled; not smooth, one-piece, solid cylinder.

Compound does not move freely in dispenser.

Push-type mechanism does not move freely in dispenser (by use of finger pressure).

Sampling for tests. The sampling for tests shall be conducted at inspection level S-1, AQL 1.0.

Contractor certification. The contractor shall certify that the product offered meets the the salient characteristics of this description and conform to the producers' own drawings, specifications, standards, and quality assurance practices. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:22Z
Check the source to verify that this is the current version before use.

Metric Products. Products manufactured to metric dimensions will be considered on an equal basis with those manufactured using inch-pound units, providing they fall within the tolerances specified using conversion tables contained in the latest revision of Federal Standard No. 376, and all other requirements of this document are met.

If a product is manufactured to metric dimensions and those dimensions exceed the tolerances specified in the inch/pound units, a request should be made to the contracting officer to determine if the product is acceptable.

The contracting officer has the option of accepting of rejecting the product.

Regulatory requirements.

Federal Food, Drug and Cosmetic Act. If the product covered by this document has been determined by the U.S. Food and Drug Administration to be under its jurisdiction, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of the Federal Food, Drug and Cosmetic Act, as amended, and regulations promulgated thereunder. In addition, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of all other applicable Federal, State, and local statutes, ordinances, and regulations.

Recovered materials. The offeror/contractor is encouraged to use recovered material in accordance with Public Law 94-580 to the maximum extent practical.

Preservation, packaging, packing, labeling, and marking. Unless otherwise specified, preservation, packaging and packing shall be to a degree of protection to preclude damage to containers and/or contents thereof under normal shipping conditions, handling, etc., involving shipment from the supply source to the receiving activity, plus reshipment from receiving activity, and shall conform to applicable carrier's rules and regulations. Intermediate and exterior package quantities and labeling and marking shall be as specified in the contract and/or order.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:22Z
Check the source to verify that this is the current version before use.

NOTE: The following National Stock Number is covered by this document:

Stock Number	Item Identification
6520-00-484-9496	ABRASIVE, DENTAL Stick Form, Silicon Carbide

Ordering data. Intermediate/exterior package quantities, labeling, and marking must be as specified in the contract and/or order.

MILITARY INTERESTS:

Custodians:
Army - MD
Navy - MS
Air Force - 03

Preparing Activity:

DoD - MB

Agent:

DLA - DM

Civil Agency Coordinating Activities:

VA-OSS
PHS
FDA-MPQAS

Project No. 6520-2105

☆U.S. GOVERNMENT PRINTING OFFICE: 1989 - 604-033/10119

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:22Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
A-A-53654	ABRASIVE, DENTAL (Stick Form, Silicon Carbide)

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ USER
	☐ MANUFACTURER
	☐ OTHER *(Specify)*:

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

(TO DETACH THIS FORM, CUT ALONG THIS LINE.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:22Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about *particular problem areas such as* wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEFENSE LOGISTICS AGENCY

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 4966 WASHINGTON D C

POSTAGE WILL BE PAID BY THE DEFENSE LOGISTICS AGENCY

Commander
Defense Personnel Support Center
ATTN: DPSC-RSTE
2800 South 20th Street
PHILADELPHIA, PENNSYLVANIA 19101-8419

Source: https://assist.dla.mil -- Downloaded: 202640-26T09:22Z
Check the source to verify that this is the current version before use.