July 20, 1962

SUPERSEDING
Feb. Spec. VV-K-211c
March 24, 1952

FEDERAL SPECIFICATION

KEROSENE

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE

1.1 This specification covers one type of kerosene for use in wick-fed lamps, stoves and heaters (NATO Symbol F-58).

2. APPLICABLE STANDARDS

2.1 The following standards, of the issues in effect on date of invitation for bids, form a part of this specification to the extent specified herein:

Federal Standards:

Fed. Test Method Std. No. 791 — Lubricants, Liquid Fuels, and Related Products; Methods of Testing.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications, Standards, and Handbooks and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington 25, D. C.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Washington, D. C., Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, and Auburn, Wash.)

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications, Standards, and Handbooks from established distribution points in their agencies.)

Military Standard:

MIL-STD-290 — Packaging, Packing, and Marking of Petroleum and Related Products.

(Copies of Military Specifications and standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

3. REQUIREMENTS

3.1 **Material.** Kerosene shall be a petroleum fraction without additives.

3.2 **Burning.** The kerosene shall conform to the following requirements when tested for burning quality as specified in 4.2.4:

(a) *Time of burning.* A minimum of 16 hours continuous burning after the first weighing will be required.

(b) *Rate of burning.* After the first weighing, the rate of burning shall be not greater than 29 milliliters per hour with the Institute of Petroleum (I.P.) burner or 45 milliliters per hour with the ASTM 27 burner.

(c) *Appearance of chimney at end of test.* The chimney shall show no more than a slight cloud.

(d) *Condition of wick at end of test.* The wick shall have no hard incrustation.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:22Z
Check the source to verify that this is the current version before use.

(e) *Flame characteristic at end of test.* The flame shall be undiminished and not smoky.

3.3 Physical and chemical requirements. The kerosene shall conform to the physical and chemical requirements shown in table I.

TABLE I. *Physical and chemical requirements*

Flash point, °F, minimum	115
End point, °F., maximum	572
Sulfur, percent maximum	0.13
Color, Saybolt Chromometer no darker than	+21
Color, Saybolt Chromometer no darker than (after heating 16 hours)	+16 (see 4.2.4.1)
Cloud point °F.	5

4. SAMPLING, INSPECTION, AND TEST PROCEDURES

4.1 The supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own or any other inspection facility and services acceptable to the Government. Inspection records of the examination and tests shall be kept complete and available to the Government as specified in the contract or order. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.2 **Inspection.** Unless otherwise specified herein, the inspection shall be made as specified in method 9601 of Fed. Test Method Std. No. 791.

4.2.1 *Lot.* For purposes of sampling, a lot shall consist of a manufacturer's batch. If the material cannot be identified by batch, a lot shall consist of not more than 5,000 gallons of oil.

4.2.2 *Sampling.* A composite sample of not less than 5 gallons of oil shall be taken from each lot in accordance with the applicable procedure of method 8001 of Fed. Test Method Std. No. 791, for the tests specified in 4.2.4.

4.2.3 *Examination of filled containers.* The product shall be examined for color, water, rust, and other contamination. The containers shall be examined for leaks and for compliance with proper marking requirements.

4.2.4 *Tests.* The following tests shall be conducted as specified in Fed. Test Method Std. No. 791:

Test	*Method No.*
Burning quality	2106
Flash point	1101
End point	1001
Sulfur	5201
Color	101
Color (after heating 16 hours)	See 4.2.4.1
Cloud point	201

4.2.4.1 *Color.*

4.2.4.1.1 The oil to be tested shall be filtered through qualitative filter paper to remove any moisture or foreign matter that may be present. About 100 milliliters of the filtered oil shall be placed in each of two chemically clean and dry 4-ounce bottles.

4.2.4.1.2 The bottles containing the filtered oil, loosely stoppered with clean new corks, shall be placed in the constant temperature bath maintained at 212°F. At the end of ½ hour, the cork stoppers shall be

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:22Z
Check the source to verify that this is the current version before use.