WW-P-377D
AMENDMENT 1
20 October 1976

FEDERAL SPECIFICATION

PIPE, COPPER, SEAMLESS, STANDARD SIZES

This amendment, which forms part of Federal Specification WW-P-377D, dated 5 November 1962, was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

PAGE 2

2.2: Add "American Society for Testing and Materials (ASTM) Standard

ASTM B 42-75 Seamless Copper Pipe, Standard Sizes

(Application for copies should be addressed to ASTM, 19 Race Street, Philadelphia PA 19103.)"

PAGE 4

Add: "4.4.1.2 Eddy-current test. In lieu of the hydrostatic pressure test specified in 4.4.1, or the air pressure test specified in 4.4.1.1, each pipe from 1/8 through 2-1/2 inch size may be eddy-current tested as specified in ASTM B42. For wall thicknesses greater than 0.120 inch, test frequencies of one (1) KHZ or less shall be used."

PAGE 9

Delete concluding material and substitute:

"Custodians:
Air Force - 99
Army - MR

"Review Activity:
DCSC - CS"

Preparing Activity:
Air Force - 99

Custodians:
Air Force - 99
Army - MR

Review Activity:
DCSC - CS

Preparing Activity:
Air Force - 99

Project No. 4710-0408

FSC 4710

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:22Z
Check the source to verify that this is the current version before use.