MIL-P-63073A (AR)
10 Jan 1980
SUPERSEDING
MIL-P-63073 (AR)
20 November 1976

MILITARY SPECIFICATION

PRIMER, ELECTRIC, M120
PARTS FOR

This specification is approved for use by US Army Armament Research and Development Command and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 This specification covers the parts for one type of electric primer designated as Primer, Electric, M120.

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

SPECIFICATIONS

MILITARY

MIL-P-116	- Preservation, Methods of
MIL-A-48078	- Ammunition, Standard Quality Assurance Provisions, General Specification for

STANDARDS

MILITARY

MIL-STD-105	- Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-1169	- Packaging, Packing and Marking for Shipment of Inert Ammunition Components

FSC: 1390

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Commander, US Army Armament Research and Development Command, Attn. DRDAR-QA, Dover, New Jersey 07801 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:09Z
Check the source to verify that this is the current version before use.

MIL-STD-1235 - Single and Multilevel Continuous Sampling Procedures and Tables for Inspection by Attributes.

DRAWINGS

ARMY

8831022	- Plug
9296616	- Body, Metal Parts Assembly
9312772	- Body, Metal Parts Assembly

(Copies of specification, standards, drawings and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer).

2.2 Other publication. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

AMERICAN SOCIETY FOR TESTING MATERIALS

ASTM-B-117-73 Salt Spray (FOG) Testing

(Copy may be purchased directly from the American Society for Testing Materials, 1916 Race Street, Philadelphia, PA. 19103)

3. REQUIREMENTS

3.1 Material. Materials shall be in accordance with applicable drawings and specifications.

3.2 Metal parts assembly and plug. The metal parts assemblies and plugs shall comply with all requirements specified on drawings (Dwgs.) 9296616 or 9312772 and 8831022 and with all requirements specified in applicable specifications.

3.3 Hydrostatic test. The primer body tubing shall withstand the application of a minimum (min.) hydrostatic pressure without rupture or indication of flaws, as evidenced by leaks, and without permanent deformation beyond drawing requirements, when tested as specified in 4.5.1 (see 6.3).

3.4 Pull test of brazed joint. The brazed joint securing the head to the primer body shall withstand a pull of 5500 pounds minimum without evidence of separation of the head from the primer body when tested as specified in 4.5.2.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:09Z
Check the source to verify that this is the current version before use.

3.5 Shelf life of sealant. The sealant used on the head to body threaded joint shall not be used beyond the manufacturer's expiration date.

3.6 Workmanship. All parts shall be fabricated and finished in a thorough, workmanlike manner. They shall be free of burrs, chips, sharp edges, cracks, unblended radii, surface defects, dirt, grease, rust, corrosion products and other foreign matter. The cleaning method shall not be injurious to any part nor shall the parts be contaminated by the cleaning agent. All required markings shall be neat and sharply defined.

3.7 First article inspection. This specification makes provisions for first article inspection. Requirements for submission of first article samples by the contractor shall be as specified in the contract.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection and standard quality assurance provisions. Unless otherwise specified herein or in the contract, the provisions of MIL-A-48078 shall apply and are hereby made a part of this detail specification.

4.2 Classification of inspection. The following types of inspection shall be conducted on this item.

a. First Article Inspection
b. Quality Conformance Inspection

4.3 First article inspection

4.3.1 Submission. The contractor shall submit a first article sample as designated by Contracting Officer for evaluation in accordance with provisions of 4.3.2. The first article sample shall consist of the following items in sample quantities as indicated:

Part Description	Drawings	Quantity
Head (as applicable)	8839501	25
Body (as applicable)	9296615	25
Body metal parts assembly (as applicable)	9296616	25
Head (as applicable)	9312770	25
Body (as applicable)	9312771	25
Body metal parts assembly (as applicable)	9312772	25
Plug	8831022	25
Body (as applicable)	9327418	25
Head (as applicable)	9327339	25

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:09Z
Check the source to verify that this is the current version before use.

TABLE I - FIRST ARTICLE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
	Metal Parts Components				See Below
					NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
	Head Primer (dwg. 9327339) (alternate) Examination for Defects	25		3.2	4.4.2.9
	Retainer (dwg. 8839509) (alternate) Examination for Defects	25		3.2	4.4.2.10
	Closing Plug (dwg. 9327342) (alternate) Examination for Defects	25		3.2	4.4.2.8
	Plug (dwg. 8831022) Examination for Defects	25		3.2	4.4.2.3
	Body (dwg. 9327418) Examination for Defects	25		3.2	4.4.2.11
	Head (dwg. 8839501) Examination for Defects	25		3.2	4.4.2.1
	Head (dwg. 9312770) Examination for Defects	25		3.2	4.4.2.5
	Body (dwg. 9312771) Examination for Defects	25		3.2	4.4.2.6

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:09Z
Check the source to verify that this is the current version before use.

4.3.2 Inspections to be performed. The first article parts submitted in accordance with paragraph 4.3.1 shall be subjected by the government to any or all requirements of the applicable drawings and to the inspection listed in this specification.

4.3.3 Rejection. See MIL-A-48078

4.4 Quality conformance inspection

4.4.1 Inspection lot formation. Inspection lots shall comply with the lot formation provisions of MIL-A-48078.

4.4.2 Examination. See MIL-A-48078

a. Sampling plans. Unless otherwise specified in the Classification of Defects and Test tables, sampling plans for major and minor defects shall be in accordance with MIL-STD-105 or MIL-STD-1235.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:09Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-P-63073A (AR)

PARAGRAPH	TITLE	SHEET 1 OF 1	DRAWING NUMBER
4.4.2.1	Head		8839501
			NEXT HIGHER ASSEMBLY
			9296616

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined				
Major	None defined				
Minor					
201	Depth of body counterbore		0.65%	3.2	Gage
202	Radii missing or inadequate		0.65%	3.2	Visual
203	Chamfer missing or inadequate		0.65%	3.2	Visual
204	Evidence of poor workmanship		0.65%	3.6	Visual

NOTES:

DRDAR-QA Form 160 Jul 77 Replaces SARPA-QA Form 2567 Feb 74 Which is Obsolete

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:09Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE	SHEET 1 OF 1	DRAWING NUMBER
4.4.2.2	Body		9296615
			NEXT HIGHER ASSEMBLY
			9296616

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical					
1	One or more flash holes missing		100%	3.2	Gage
2	Crack or split (Prior to plating)		100%	3.2	Visual
3	Hydrostatic Test		100%	3.3	4.4.3.1/4.5.1
Major					
101	Plug gage fails to pass through body		0.40%	3.2	Gage
102	Location of holes		0.40%	3.2	Gage
103	Wall thickness		0.40%	3.2	Gage
104	Diameter of holes		0.40%	3.2	Gage
105	Pitch diameter of thread, max.		0.40%	3.2	Gage
106	Minor diameter of thread, max.		0.40%	3.2	Gage
107	Outside diameter		0.40%	3.2	Gage
Minor					
201	Total length		0.65%	3.2	Gage
202	Length of thread		0.65%	3.2	Gage
203	Pitch diameter of thread, min.		0.65%	3.2	Gage
204	True position of holes with outside diameter		0.65%	3.2	Gage
205	True position of thread with outside diameter		0.65%	3.2	Gage
206	Surface finish		0.65%	3.2	Gage
207	Evidence of poor workmanship		0.65%	3.6	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:09Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-P-63073A (AR)

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER 8831022
4.4.2.3	Plug				NEXT HIGHER ASSEMBLY 9296616
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined				
Major					
101	Pitch diameter of thread, min.		0.40%	3.2	Gage
102	Major diameter of thread, min.		0.40%	3.2	Gage
103	Salt Spray	5/Lot		3.2	4.4.3.3/4.5.3
104	Protective coating missing or damaged		0.40%	3.2	Visual
Minor					
201	Pitch diameter of thread, max.		0.65%	3.2	Gage
202	Thickness		0.65%	3.2	Gage
203	Width of wrench slot		0.65%	3.2	Gage
204	Depth of wrench slot		0.65%	3.2	Gage
205	Chamfer(s) missing or inadequate		0.65%	3.2	Visual
206	Surface finish		0.65%	3.2	Visual
207	Evidence of poor workmanship		0.65%	3.6	Visual

NOTES:

DRDAR-QA Form 160 Jul 77 Replaces SARPA-QA Form 2567 Feb 74 Which is Obsolete

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:09Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-P-63073A (AR)

PARAGRAPH	TITLE	SHEET 1 OF 2	DRAWING NUMBER
4.4.2.4	Body Metal Parts Assembly		9296616
			NEXT HIGHER ASSEMBLY

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined				
Major					
101	Pull test of braze joint	150/or 50/lot		3.4	4.4.3.2/4.5.2
102	Salt spray	5/Lot		3.2	4.4.3.3/4.5.3
103	Pitch diameter of external thread, min.		0.40%	3.2	Gage
104	Major diameter of external thread, min.		0.40%	3.2	Gage
105	True position of internal thread for igniter with external thread		0.40%	3.2	Gage
106	Pitch diameter of internal thread for igniter, max.		0.40%	3.2	Gage
107	Minor diameter of internal thread for igniter, max.		0.40%	3.2	Gage
108	Depth of igniter counterbore		0.40%	3.2	Gage
109	Braze not full 360 degrees		0.40%	3.2	Visual
110	Protective coating missing or damaged		0.40%	3.2	Visual
Minor					
201	Length of external thread, including thread undercut		0.65%	3.2	Gage
202	Length of external thread undercut		0.65%	3.2	Gage
203	Length of internal thread for igniter		0.65%	3.2	Gage
204	Diameter of external thread undercut		0.65%	3.2	Gage
205	Diameter of igniter counterbore		0.65%	3.2	Gage

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:09Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE		SHEET 2 OF 2		DRAWING NUMBER
4.4.2.4	Body Metal Parts Assembly				9296616
					NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
206	Width of wrench slots (as applicable)		0.65%	3.2	Gage
207	Diameter of wrench holes (as applicable)		0.65%	3.2	Gage
208	Distance between wrench holes (as applicable)		0.65%	3.2	Gage
209	Depth of wrench holes (as applicable)		0.65%	3.2	Gage
210	Depth of wrench slots (as applicable)		0.65%	3.2	Gage
211	Inside diameter of head		0.65%	3.2	Gage
212	Outside diameter of head		0.65%	3.2	Gage
213	Thickness of flange		0.65%	3.2	Gage
214	Diameter of flange		0.65%	3.2	Gage
215	Pitch diameter of external thread, max.		0.65%	3.2	Gage
216	Total length of assembly		0.65%	3.2	Gage
217	True position of igniter counterbore with internal head thread		0.65%	3.2	Gage
218	True position of flange with external thread		0.65%	3.2	Gage
219	True position of head outside diameter with external thread		0.65%	3.2	Gage
220	Pitch diameter of internal thread for igniter, min.		0.65%	3.2	Gage
221	Total length of head		0.65%	3.2	Gage
222	Solder on interior surfaces		0.65%	3.2	Visual
223	Marking, missing, incorrect or unidentifiable		0.65%	3.2	Visual
224	Surface finish of head		0.65%	3.2	Visual
225	Evidence of poor workmanship		0.65%	3.6	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:09Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-P-63073A (AR)

PARAGRAPH	TITLE	SHEET 1 OF 3	DRAWING NUMBER
4.4.2.5	Head		9312770
			NEXT HIGHER ASSEMBLY
			9312772

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined				
Major					
101	Pitch diameter of external thread, min.		0.40%	3.2	Gage
102	Major diameter of external thread, min.		0.40%	3.2	Gage
103	Pitch diameter of internal thread for igniter, max.		0.40%	3.2	Gage
104	Minor diameter of internal thread for igniter, max.		0.40%	3.2	Gage
105	Depth of igniter counterbore		0.40%	3.2	Gage
106	Salt spray	5/Lot		3.2	4.4.3.3/4.5.3
107	True position of internal thread for igniter with external thread		0.40%	3.2	Gage
108	Pitch diameter of internal thread for body,max.		0.40%	3.2	Gage
109	Minor diameter of internal thread for body, max.		0.40%	3.2	Gage
110	True position of internal thread for body with external thread		0.40%	3.2	Gage
111	Protective coating missing or damaged		0.40%	3.2	Visual
Minor					
201	Total length		0.65%	3.2	Gage
202	Length of external thread, including thread undercut.		0.65%	3.2	Gage
203	Length of external thread undercut		0.65%	3.2	Gage
204	Length of internal thread for igniter		0.65%	3.2	Gage
205	Diameter of external thread undercut		0.65%	3.2	Gage

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:09Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE		SHEET 2 OF 3		DRAWING NUMBER
4.4.2.5	Head				9312770
					NEXT HIGHER ASSEMBLY
					9312772
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
206	Diameter of igniter counterbore		0.65%	3.2	Gage
207	Width of wrench slots (as applicable)		0.65%	3.2	Gage
208	Location of wrench slots from centerline (as applicable)		0.65%	3.2	Gage
209	Depth of wrench slots (as applicable)		0.65%	3.2	Gage
210	Inside diameter		0.65%	3.2	Gage
211	Outside diameter		0.65%	3.2	Gage
212	Thickness of flange		0.65%	3.2	Gage
213	Diameter of flange		0.65%	3.2	Gage
214	Pitch diameter of external thread, max.		0.65%	3.2	Gage
215	Pitch diameter of internal thread for igniter, min.		0.65%	3.2	Gage
216	Pitch diameter of internal thread for body, min.		0.65%	3.2	Gage
217	True position of internal thread counterbore with internal thread for igniter		0.65%	3.2	Gage
218	True position of flange with external thread		0.65%	3.2	Gage
219	True position of inside diameter with internal thread for igniter		0.65%	3.2	Gage
220	Diameter of wrench holes (as applicable)		0.65%	3.2	Gage
221	Depth of wrench holes (as applicable)		0.65%	3.2	Gage
222	Location of wrench holes from centerline (as applicable)		0.65%	3.2	Gage
223	Distance between wrench holes (as applicable)		0.65%	3.2	Gage
224	Minimum full internal thread for body		0.65%	3.2	Gage
225	Length of body thread		0.65%	3.2	Gage
226	Radii missing or inadequate		0.65%	3.2	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:09Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INCPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-P-63073A (AR)

PARAGRAPH	TITLE		SHEET 3 OF 3		DRAWING NUMBER
4.4.2.5	Head				9312770
					NEXT HIGHER ASSEMBLY
					9312772
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
227	Chamfer missing or inadequate		0.65%	3.2	Visual
228	Surface finish		0.65%	3.2	Visual
229	Evidence of poor workmanship		0.65%	3.6	Visual

NOTES:

DRDAR-QA Form 160 Jul 77 Replaces SARPA-QA Form 2567 Feb 74 Which is Obsolete

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:09Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-P-63073A (AR)

PARAGRAPH	TITLE	SHEET 1 OF 2	DRAWING NUMBER
4.4.2.6	Body		9312771
			NEXT HIGHER ASSEMBLY
			9312772

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical					
1	One or more flash holes missing		100%	3.2	Gage
2	Crack or split (Prior to plating)		100%	3.2	Visual
3	Hydrostatic Test		100%	3.3	4.4.3.1/4.5.1
Major					
101	Pitch diameter of external thread, min.		0.40%	3.2	Gage
102	Major diameter of external thread, min.		0.40%	3.2	Gage
103	Outside diameter		0.40%	3.2	Gage
104	Wall thickness		0.40%	3.2	Gage
105	Diameter of holes		0.40%	3.2	Gage
106	Location of holes		0.40%	3.2	Gage
107	Plug gage fails to pass through body		0.40%	3.2	Gage
108	Salt spray	5/Log		3.2	4.4.3.3/4.5.3
109	Pitch diameter of internal thread, max.		0.40%	3.2	Gage
110	Minor diameter of internal thread, max.		0.40%	3.2	Gage
111	Protective coating missing or damaged		0.40%	3.2	Visual
Minor					
201	Pitch diameter of external thread, max.		0.65%	3.2	Gage
202	Length of internal thread		0.65%	3.2	Gage
203	Total length		0.65%	3.2	Gage
204	Pitch diameter of internal thread, max.		0.65%	3.2	Gage
205	Minimum full external thread		0.65%	3.2	Gage
206	Diameter of external thread pilot		0.65%	3.2	Gage
207	Length of external thread pilot		0.65%	3.2	Gage

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:09Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-P-63073A (AR)

PARAGRAPH	TITLE		SHEET 2 OF 2		DRAWING NUMBER
4.4.2.6	Body				9312771
					NEXT HIGHER ASSEMBLY
					9312772
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
208	True position of holes with outside diameter		0.65%	3.2	Gage
209	True position of external thread with outside diameter		0.65%	3.2	Gage
210	True position of internal thread with outside diameter		0.65%	3.2	Gage
211	Evidence of poor workmanship		0.65%	3.6	Visual

NOTES:

DRDAR-QA Form 160 Jul 77 Replaces SARPA-QA Form 2567 Feb 74 Which is Obsolete

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:09Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-P-63073A (AR)

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.7	Metal parts assembly				9312772
					NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined				
Major					
101	Total length		0.40%	3.2	Gage
102	Disassembly torque		0.40%	3.2	Test
103	Shelf life of sealant exceeded		0.40%	3.5	4.4.3.4
104	Thread sealant missing or inadequate prior to assembly (must cover a minimum of one half the number of body threads for a full 360 degrees when assembled)		0.40%	3.2	Visual
Minor					
201	Marking missing, incorrect or unidentifiable		0.65%	3.2	Visual
202	Evidence of poor workmanship		0.65%	3.6	Visual

NOTES:

DRDAR-QA Form 160 Jul 77 Replaces SARPA-QA Form 2567 Feb 74 Which is Obsolete

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:09Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-P-63073A (AR)

PARAGRAPH	TITLE	SHEET 1 OF 1	DRAWING NUMBER
4.4.2.8	Plug, Closing (alternate)		9327399
			NEXT HIGHER ASSEMBLY

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined				
Major					
101	Pitch diameter, min.		0.40%	3.2	Gage
102	Hole missing or obstructed		0.40%	3.2	Gage
103	Major diameter, min.		0.40%	3.2	Gage
104	Thread length of engagement		0.40%	3.2	Gage
Minor					
201	Pitch diameter, max.		0.65%	3.2	Gage
202	Diameter of hole, min.		0.65%	3.2	Gage
203	Diameter of counterbore		0.65%	3.2	Gage
204	Total length, max.		0.65%	3.2	Gage
205	Length to shoulder, min.		0.65%	3.2	Gage
206	Length of thread relief		0.65%	3.2	Gage
207	Evidence of poor workmanship		0.65%	3.6	Visual

NOTES:

DRDAR-QA Form 160 Jul 77 Replaces SARPA-QA Form 2567 Feb 74 Which is Obsolete

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:09Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE		SHEET 1 OF 3		DRAWING NUMBER
4.4.2.9	Head Primer (alternate)				9327399
					NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined				
Major					
101	Pitch diameter of external threads, min.		0.40%	3.2	Gage
102	Major diameter of external threads, min.		0.40%	3.2	Gage
103	Pitch diameter of large internal threads, max.		0.40%	3.2	Gage
104	Minor diameter of large internal threads, max.		0.40%	3.2	Gage
105	True position of pitch diameter of large internal threads with pitch diameter of external threads		0.40%	3.2	Gage
106	Pitch diameter of small internal threads, max.		0.40%	3.2	Gage
107	Minor diameter of small internal threads, max.		0.40%	3.2	Gage
108	True position of pitch diameter of small internal threads with diameter of large unthreaded cavity		0.40%	3.2	Gage
109	Flange diameter		0.40%	3.2	Gage
110	True position of flange diameter with pitch diameter of external threads		0.40%	3.2	Gage
111	Flange thickness		0.40%	3.2	Gage
112	Diameter of large unthreaded cavity		0.40%	3.2	Gage
113	Diameter of small unthreaded cavity		0.40%	3.2	Gage
114	True position of diameter of small unthreaded cavity with diameter of large unthreaded cavity		0.40%	3.2	Gage
115	Protective coating missing		0.40%	3.2	Visual
116	Protective coating inadequate		See 4.5.8	3.2	4.5.2

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:09Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-P-63073A (AR)

PARAGRAPH	TITLE		SHEET 2 OF 3		DRAWING NUMBER
4.4.2.9	Head Primer (alternate)				9327339
					NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Minor					
201	Pitch diameter of external threads, max.		0.65%	3.2	Gage
202	Pitch diameter of large internal threads, min.		0.65%	3.2	Gage
203	Pitch diameter of small internal threads, min.		0.65%	3.2	Gage
204	Length, total		0.65%	3.2	Gage
205	Length from flange to beginning of external threads		0.65%	3.2	Gage
206	Length from flange to end of external threads		0165%	3.2	Gage
207	Depth of small unthreaded cavity		0.65%	3.2	Gage
208	Diameter, forward end, of large threaded cavity		0.65%	3.2	Gage
209	Outside diameter, forward		0.65%	3.2	Gage
210	Depth of large threaded cavity		0.65%	3.2	Gage
211	Minimum effective length of large internal Thread		0.65%	3.2	Gage
212	Depth from front face to rear of small threaded cavity		0.65%	3.2	Gage
213	Countersink angle at the rear of small threaded cavity		0.65%	3.2	Visual
214	Width of wrench slots (if applicable)		0.65%	3.2	Gage
215	Depth of wrench slots (if applicable)		0.65%	3.2	Gage
216	Distance between wrench slots (if applicable)		0.65%	3.2	Gage
217	Depth of wrench holes (if applicable)		0.65%	3.2	Gage
218	Diameter of wrench holes (if applicable)		0.65%	3.2	Gage
219	Distance between wrench holes (if applicable)		0.65%	3.2	Gage

NOTES:

DRDAR-QA Form 160 Jul 77 Replaces SARPA-QA Form 2567 Feb 74 Which is Obsolete

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:09Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE		SHEET 3 OF 3		DRAWING NUMBER
4.4.2.9	Head Primer (alternate)				9327339
					NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
220	Distance from center hole to wrench hole(s) (if applicable)		0.65%	3.2	Gage
221	Chamfers missing or incorrect		0.65%	3.2	Visual
222	Radii missing or incorrect		0.65%	3.2	Visual
223	Surface finish incorrect		0.65%	3.2	Visual
224	Evidence of poor workmanship		0.65%	3.6	Visual

NOTES:

DRDAR-QA Form 160 Jul 77 Replaces SARPA-QA Form 2567 Feb 74 Which is Obsolete

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:09Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.10	Retainer (alternate)	1 OF 1	8839509
			NEXT HIGHER ASSEMBLY

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined				
Major					
101	Pitch diameter, min.		0.40%	3.2	Gage
102	Major diameter, min.		0.40%	3.2	Gage
103	Diameter of hole, min.		0.40%	3.2	Gage
Minor					
201	Thickness, min.		0.65%	3.2	Gage
202	Slot missing		0.65%	3.2	Visual
203	Surface finish improper		0.65%	3.2	Visual
204	Pitch diameter, max.		0.65%	3.2	Gage
205	Evidence of poor workmanship		0.65%	3.6	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:09Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.11	Body (alternate)	1 OF 2	9327418
			NEXT HIGHER ASSEMBLY 9296617

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical					
1	One or more flash holes missing		100%	3.2	Gage
2	Crack or split (Prior to plating)		100%	3.3	Visual
3	Hydrostatic Test		100%	3.3	4.4.3.1/4.5.1
Major					
101	Pitch diameter of external thread, min.		0.40%	3.2	Gage
102	Major diameter of external thread, min.		0.40%	3.2	Gage
103	Outside diameter		0.40%	3.2	Gage
104	Wall thickness		0.40%	3.2	Gage
105	Diameter of holes		0.40%	3.2	Gage
106	Location of holes		0.40%	3.2	Gage
107	Plug gage fails to pass through body		0.40%	3.2	Gage
108	Salt spray	5/Lot		3.2	4.4.3.3/4.5.3
109	Pitch diameter of internal thread, max.		0.40%	3.2	Gage
110	Minor diameter of internal thread, max.		0.40%	3.2	Gage
111	Protective coating missing or damaged		0.40%	3.2	Visual
Minor					
201	Pitch diameter of external thread, max.		0.65%	3.2	Gage
202	Length of internal thread		0.65%	3.2	Gage
203	Total length		0.65%	3.2	Gage
204	Pitch diameter of internal thread, max.		0.65%	3.2	Gage
205	Minimum full external thread		0.65%	3.2	Gage
206	Diameter of external thread pilot		0.65%	3.2	Gage
207	Length of external thread pilot		0.65%	3.2	Gage

NOTES:

DRDAR-QA Form 160 Jul 77 Replaces SARPA-QA Form 2567 Feb 74 Which is Obsolete

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:09Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-P-63073 A (AR)

PARAGRAPH	TITLE		SHEET 2 OF 2		DRAWING NUMBER
4.4.2.11	Body (alternate)				9327418
					NEXT HIGHER ASSEMBLY 9296617
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
208	True position of holes with outside diameter		0.65%	3.2	Gage
209	True position of external thread with outside diameter		0.65%	3.2	Gage
210	True position of internal thread with outside diameter		0.65%	3.2	Gage
211	Evidence of poor workmanship		0.65%	3.6	Visual

NOTES:

DRDAR-QA Form 160 Jul 77 Replaces SARPA-QA Form 2567 Feb 74 Which is Obsolete

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:09Z
Check the source to verify that this is the current version before use.

4.4.3 Testing

4.4.3.1 Hydrostatic test. (see 3.3) This test shall be conducted 100 percent in accordance with the procedure specified in 4.5.1. If any primer body tubing fails to comply with the requirement specified, it shall be classed defective and no primer bodies shall be fabricated therefrom.

4.4.3.2 Pull test of brazed joint (see 3.4).

4.4.3.2.1 Beginning with the first lot produced and continuing until three consecutive lots have complied with the acceptance criteria specified, 150 body metal parts assemblies shall be randomly selected from each lot for this test. If any assembly fails to comply with the applicable requirement the lot shall be rejected. The test shall be as specified in 4.5.2 using equipment in accordance with 4.4.4. The sample assemblies subjected to this test shall not be returned to the lot.

4.4.3.2.2 After three consecutive lots have met the criteria specified in 4.4.3.2.1, 50 body metal parts assemblies shall be randomly selected from each lot. If any assembly fails to comply with the applicable requirement, the lot shall be rejected. the test shall be perfromed as specified in 4.5.2 using equipment in accordance with 4.4.4. The sample assemblies subjected to this test shall not be returned to the lot.

4.4.3.3 Salt spray (Fog) testing. A sample of five each body metal parts assembly, body, head, and plug, as applicable, from each lot shall be submitted to Salt Spray (Fog) Testing. The test shall be performed as specified in 4.5.3. Rejection criteria shall be as specified in the applicable finish specifications.

4.4.3.4 Shelf life of sealant. Prior to sealant use on the head to body threaded joint, compliance with the manufacturer's expiration date shall be validated. Sealant exceeding the manufacturer's expiration date shall bot be supplied or used when assembling the Body Metal Parts Assembly.

4.4.4 Inspection equipment. The inspection equipment required to perform the examinations and tests prescribed herein is described in the Paragraph Reference/Inspection Method Column in the tables starting with paragraph 4.4.2.1. The contractor shall submit for approval inspection equipment designs in accordance with the terms of the contract. See section 6 of MIL-A-48078.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:09Z
Check the source to verify that this is the current version before use.

4.5 Test methods and procedures

4.5.1 Hydrostatic test. Prior to machining, the primer body tubing shall be tested for not less than five seconds at the minimum hydrostatic pressure as calculated by the following formula:

$$P = \frac{1.8st}{D}$$

where:

P = test pressure in pounds per square inch (psi)
s = minimum specified yield strength, psi
t = specified minimum wall thickness in inches
D = specified maximum outside diameter in inches

4.5.2 Pull test of brazed joint. The body metal parts assembly shall be assembled to the applicable test fixture specified in 4.4.4. The specified load shall be applied in an axial direction. The rate of travel of the testing machine shall be 0.100 to 0.125 inch per minute. The sample assemblies subjected to this test shall not be returned to the lot.

4.5.3 Salt spray. The body metal parts assembly, body, head, and plug, as applicable, shall be tested in accordance with ASTM Standard Method of Salt Spray (Fog) Testing, ASTM Designation: B117-73. The primer parts so tested shall be scrapped.

4.5.4 Protective coatings. Procedures for testing, the cleaning of components and the application of protective coatings shall bne in accordance with the criteria for testing as specified on the applicable component drawings and in the specification referenced thereon.

5. PREPARATION FOR DELIVERY

5.1 Packaging, packing and marking. The parts shall be packaged, packed and marked in accordance with Standard MIL-STD-1169.

6. NOTES

6.1 Ordering data. See MIL-A-48078.

6.2 Submission of design for approval. See 6.2.3 of MIL-A-48078. Submit equipment designs, as required, to Commander, US Army Armament Research and Development Command, ATTN: DRDAR-QAT-I, Dover, New Jersey 07801

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:09Z
Check the source to verify that this is the current version before use.

6.3 Hydrostatic test. If the primer tubing procured for the bodies manufactured in accordance with this specification has been previously subjected to the hydrostatic test specified in the specification, a second hydrostatic test will not be required.

Custodian:
Army-AR

Preparing Activity:
Army-AR

Project Number: 1390-A246

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:09Z
Check the source to verify that this is the current version before use.