NOT MEASUREMENT SENSITIVE

MIL-PRF-87937E
27 September 2022

SUPERSEDING
MIL-PRF-87937D
24 September 2001

PERFORMANCE SPECIFICATION

CLEANING COMPOUND, AEROSPACE EQUIPMENT

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification establishes the requirements for biodegradable, water dilutable, environmentally safe cleaning compounds for use on aerospace equipment to include aircraft, aerospace ground equipment (AGE) and AGE engines.

1.2 Classification. The cleaning compounds covered by this specification will be of the following types.

Type I	-	Terpene Based, Solvent Emulsion, Water Dilutable Cleaning Compound
Type III	-	Gel-Type Cleaning Compound
Type IV	-	Heavy Duty, Water Dilutable Cleaning Compound

Comments, suggestions, or questions on this document should be addressed to AFPET/PTPS, 2430 C Street, Building 70, Area B, Wright-Patterson AFB, OH 45433 or e-mailed to AFPET.PTPS@us.af.mil. Since contact information can change, you may want to verify the currency of this address information using the ASSIST Online database at https://assist.dla.mil.

AMSC N/A FSC 6850

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T12:25Z
Check the source to verify that this is the current version before use.

2. APPLICABLE DOCUMENTS

2.1 General. The documents listed in this section are specified in sections 3 and 4 of this standard. This section does not include documents cited in other sections of this standard or recommended for additional information or as examples. While every effort has been made to ensure the completeness of this list, document users are cautioned that they must meet all specified requirements documents cited in sections 3 and 4 of this standard, whether or not they are listed.

2.2 Government documents.

2.2.1 Specifications, standards, and handbooks. The following specifications, standards and handbooks form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

FEDERAL SPECIFICATIONS

TT-I-735	-	Isopropyl Alcohol
TT-P-2760	-	Primer Coating, Polyurethane, Elastomeric, High-Solids
PPP-P-704	-	Pails, Metal: (Shipping, Steel, 1 through 12 gallons)

FEDERAL STANDARDS

FED-STD-141	-	Paint, Varnish, Lacquer and Related Materials: Methods of Inspection, Sampling and Testing
FED-STD-313	-	Material Safety Data Sheets, Preparation and the Submission of

COMMERCIAL ITEM DESCRIPTIONS

A-A-58054	-	Abrasive Mats, Non-Woven, Non-Metallic

DEPARTMENT OF DEFENSE SPECIFICATIONS

MIL-DTL-5541	-	Chemical Conversion Coatings on Aluminum and Aluminum Alloys
MIL-DTL-81381	-	Wire, Electric, Polyimide-Insulated, Copper or Copper Alloy
MIL-DTL-83488	-	Coating, Aluminum, High Purity
MIL-G-21164	-	Grease, Molybdenum Disulfide, For Low and High Temperatures, NATO Code Number G-353
MIL-PRF-2104	-	Lubricating Oil, Internal Combustion Engine, Combat/Tactical Service
MIL-PRF-5425	-	Plastic, Sheet, Acrylic, Heat Resistant
MIL-PRF-8625	-	Anodic Coatings, For Aluminum and Aluminum Alloys
MIL-PRF-22750	-	Coating, Epoxy, High-Solids

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T12:25Z
Check the source to verify that this is the current version before use.

MIL-PRF-23377	-	Primer Coatings: Epoxy, High-Solids
MIL-PRF-25690	-	Plastic, Sheets and Formed Parts, Modified Acrylic Base, Monolithic, Crack Propagation Resistant
MIL-PRF-81733	-	Sealing and Coating Compound, Corrosion Inhibitive
MIL-PRF-83282	-	Hydraulic Fluid, Fire Resistant, Synthetic Hydrocarbon Base, Metric, NATO Code Number H-537
MIL-PRF-85285	-	Coating: Polyurethane, Aircraft and Support Equipment
MIL-PRF-85582	-	Primer Coatings: Epoxy, Waterborne

(Copies of this documents are available online at https://quicksearch.dla.mil.)

2.2.2 Other Government documents, drawings, and publications. The following other Government documents form a part of this specification to the extent specified herein. Unless otherwise specified, the issue should be that in effect on the date of the solicitation.

CODE OF FEDERAL REGULATIONS

40 CFR	-	Protection of Environment
49 CFR	-	Transportation

(Copies of these documents are available online at https://gov.ecfr.io/cgi-bin/ECFR)

DEFENSE FORMS MANAGEMENT PROGRAM

DD Form 1718	-	Certification of Qualified Products

(Copies of this document are available online at https://www.esd.whs.mil/DD/.)

DEFENSE STANDARDIZATION PROGRAM OFFICE

SD-6	-	Provisions Governing Qualification

(Copies of this document are available online at https://quicksearch.dla.mil.)

ENVIRONMENTAL PROTECTION AGENCY

EPA/600/4-90/027	-	Methods for Measuring the Acute Toxicity of Effluents and Receiving Waters to Freshwater and Marine Organisms

(Copies of this document are available online at https://www.epa.gov.)

2.3 Non-Government publications. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T12:25Z
Check the source to verify that this is the current version before use.

ASTM INTERNATIONAL

ASTM A153/A153M	-	Standard Specification for Zinc Coating (Hot Dip) on Iron and Steel Hardware
ASTM D56	-	Standard Test Method for Flash Point by Tag Closed Cup Tester
ASTM D92	-	Standard Test Method for Flash and Fire Points by Cleveland Open Cup Tester
ASTM D93	-	Standard Test Methods for Flash Point by Pensky-Martens Closed Cup Tester
ASTM D1193	-	Standard Specification for Reagent Water
ASTM D2240	-	Standard Test Method for Rubber Property – Durometer Hardness
ASTM D4057	-	Standard Practice for Manual Sampling of Petroleum and Petroleum Products
ASTM D4177	-	Standard Practice for Automatic Sampling of Petroleum and Petroleum Products
ASTM E70	-	Standard Test Method for pH of Aqueous Solutions with the Glass Electrode
ASTM F483	-	Standard Practice for Total Immersion Corrosion Test for Aircraft Maintenance Chemicals
ASTM F484	-	Standard Test Method for Stress Crazing of Acrylic Plastics in Contact with Liquid or Semi-Liquid Compounds
ASTM F485	-	Standard Practice for Effects of Cleaners on Unpainted Aircraft Surfaces
ASTM F502	-	Standard Test Method for Effects of Cleaning and Chemical Maintenance Materials on Painted Aircraft Surfaces
ASTM F519	-	Standard Test Method for Mechanical Hydrogen Embrittlement Evaluation of Plating/Coating Processes and Service Environments
ASTM F1104	-	Standard Test Method for Preparing Aircraft Cleaning Compounds, Liquid Type, Water Base, for Storage Stability Testing

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T12:25Z
Check the source to verify that this is the current version before use.

ASTM F1110	-	Standard Test Method for Sandwich Corrosion Test
ASTM F1111	-	Standard Test Method for Corrosion of Low-Embrittling Cadmium Plate by Aircraft Maintenance Chemicals

(Copies of these documents are available from https://www.astm.org.)

SAE INTERNATIONAL

SAE AMS1640	-	Corrosion Removing Compound Aircraft Surfaces
SAE AMS2410	-	Plating, Silver, Nickel Strike, High Bake
SAE AMS3204	-	Rubber Synthetic Low-Temperature Resistant 25-35
SAE AMS3209	-	Chloroprene (CR) Rubber Weather Resistant 65-75
SAE AMS4377	-	Magnesium Alloy, Sheet and Plate 3.0Al – 1.0Zn – 0.20Mn (AZ31B-H24) Cold Rolled, Partially Annealed
SAE AMS5046	-	Carbon Steel, Sheet, Strip, and Plate (SAE 1020 and 1025)
SAE AMS-M-3171	-	Magnesium Alloy, Processes for Pretreatment and Prevention of Corrosion on
SAE AMS-P-83310	-	Plastic Sheet, Polycarbonate, Transparent
SAE AMS-QQ-A-250/4	-	Aluminum Alloy 2024, Plate and Sheet
SAE AMS-QQ-A-250/12	-	Aluminum Alloy 7075, Plate and Sheet
SAE AMS-S-8802	-	Sealing Compound, Fuel Resistant, Integral Fuel Tanks and Fuel Cell Cavities
SAE AMS-STD-595	-	Colors Used In Government Procurement

(Copies of these documents are available from https://www.sae.org/.)

AMERICAN IRON AND STEEL INSTITUTE AISI STANDARDS

AISI 4340	-	High Strength, Low Alloy Steel

(Copies of these documents are available from https://www.steel.org/.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T12:25Z
Check the source to verify that this is the current version before use.

2.4 Order of precedence. Unless otherwise noted herein or in the contract, in the event of a conflict between the text of this specification and a reference cited herein, the text of this specification takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 Qualification. The cleaning compounds furnished under this specification shall be a product which has been tested and has passed the qualification tests specified herein and has been listed or approved for listing on the applicable Qualified Products List (QPL) before contract award (see 4.2 and 6.3).

3.2 Materials. The composition and formulation of the cleaning compound shall be optional with the manufacturer within the restrictions specified herein.

3.2.1 Acceptable materials.

3.2.1.1 Type I. Type I compounds shall contain terpene hydrocarbons as specified in Table I. Certification from the manufacturer is required on the percentage of total terpenes contained in the cleaning compound. The terpene hydrocarbons used shall be of a high grade with no extraneous materials.

3.2.1.2 Type III and Type IV. Types III and IV compounds shall consist of one or more of the following: Surfactants, adjuvant solubilizers for organic soils such as greases and oils, alkaline builders, water conditioning agents and corrosion inhibitors.

TABLE I. Quantitative requirements.

Requirement	Type I	Type III	Type IV	Section
Insoluble Matter (wt%)	max 0.05	max 0.05	max 0.05	4.4.2
Flash Point (°F / °C)				4.4.7
10% solution	min 200 / 93	---	---	
Concentrated solution	min 120 / 49	None [1]	None [1]	
Emulsion Characteristics (mL in free water)				4.4.8
5 min	max 5.0	max 5.0	max 5.0	
8 hours	min 13.0	---	---	
24 hours	---	min 8.0	min 11.0	
Wet Adhesion Tape Test	---	---	pass	4.4.27
% Cleaning Efficiency	min 95	min 65	min 90	4.4.21
Terpene Hydrocarbons (% wt)	min 25 / max 40	None	None	4.4.23

NOTES

1. No flash point should be observed up to the boiling point of the compound.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T12:25Z
Check the source to verify that this is the current version before use.

3.2.2 Unacceptable materials. The cleaning compound shall not contain any hazardous compounds as defined in 40 CFR 261, toxic pollutants in 40 CFR 401, nor hazardous air pollutants in 40 CFR 63 (see 4.5). The cleaning compound shall not contain any chemical listed by the current report of known carcinogens of the National Toxicology Program (NTP). The cleaning compound shall not contain detectable amounts of any of the following: abrasives, chromates, cadmium, lead, mercury, phenols, cresols, ketones, chlorinated compounds or ozone depleting substances (ODS), except where specified within this specification. The following materials are unacceptable unless they are being used as an essential active ingredient in the cleaner: sodium chloride, urea, sodium sulfate, nitrites, nitrates, sucrose or any sugars. Types III and IV compounds shall contain no terpene hydrocarbons or other hydrocarbon solvents.

3.3 Toxicity. The cleaning compound shall have no adverse effect on the health of personnel or the environment when used for its intended purpose and with proper personal protective equipment (when required). The product shall be evaluated for aquatic toxicity with a 96-hour Fathead minnow (pimephales promelas) bioassay and a 48-hour Ceriodaphnia dubia bioassay in accordance with Methods for Measuring the Acute Toxicity of Effluents and Receiving Waters to Freshwater and Marine Organisms, EPA/600/4-90/027. The percent survival at 1, 10, 50, and 100 ppm shall be reported for both organisms.

3.4 Formulation. The manufacturer shall submit to the qualifying activity a certified statement that provides the identity and percentage by weight of each ingredient in the cleaning compound, including solvent, using a readily recognizable chemical name and CAS number. Trade names alone shall not be considered satisfactory. All proprietary information shall be protected as such.

3.4.1 Type I. The manufacturer shall submit to the qualifying activity the chemical name of each terpene used in the formulation including its CAS number and range of values in percent by weight of the formulation. The manufacturer shall also submit test procedures used to verity the terpene percentages within these ranges. All procedures shall be subject to approval by the qualifying activity.

3.4.2 Safety data sheet (SDS). The manufacturer shall submit to the qualifying activity a SDS for the finished product and for each component in the finished product. The SDS shall be prepared in accordance with the latest revision of FED-STD-313.

3.4.3 Toxicological data. The manufacturer shall submit to the qualifying activity a copy of pertinent toxicological data/information (see 4.5) for their product.

3.4.4 Biodegradability. The supplier of the cleaning compound shall furnish certification from the surfactant manufacturers that the surfactants are readily biodegradable in accordance with 40 CFR, Part 796, Subpart D. Biodegradability testing shall be accomplished as specified in paragraph 4.4.22 on the finished product by an independent laboratory approved by the qualifying activity. Biodegradability on the finished product shall be determined over 28 days by the Shake Flask Method monitored by analysis of Total Organic Carbon (TOC). The Type I compound shall meet the requirement of a minimum of 75% biodegradable and Types III and IV compounds shall meet the requirement of a minimum of 85% biodegradable at the end of the 28-day period.

3.5 Compositional assurance. The cleaning compound shall be tested for nonvolatile matter as specified in paragraph 4.4.1. The concentrated cleaning compound and a 10% solution

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T12:25Z
Check the source to verify that this is the current version before use.

of the cleaning compound in distilled water shall be tested for pH as specified in paragraph 4.4.3. Results of these tests as well as an infrared spectrogram of the nonvolatile matter (see 4.7.2) and a gas chromatogram (see 4.7.1 for Type I only) shall be recorded by the qualifying activity for use in conformance inspections (see 4.3). Conformance inspection results for nonvolatile matter shall not differ by more than 2 percent absolute from the recorded value. Conformance inspection results for pH shall not differ by more than 1 pH unit from the recorded value. Conformance inspection infrared spectrograms and gas chromatograms shall show no significant difference when compared to the original qualifying spectrogram.

3.6 Chemical properties.

3.6.1 Chemical requirements. The cleaning compound shall meet the requirements listed in Table I.

3.6.2 Residue rinsibility. When a freshly prepared solution of the cleaning compound is tested in accordance with 4.4.4, it shall not leave any residue or stains. A freshly prepared solution is defined as one being prepared no longer than 30 minutes prior to testing. The weight change shall be not greater than that obtained with standard hard water tested under the same conditions.

3.7 Physical properties (All types unless otherwise noted).

3.7.1 Heat stability. The concentrated cleaning compound, when tested in accordance with 4.4.5, shall show no marked color change or precipitation and shall not corrode or stain the AMS5046 (SAE 1020) steel strip (a slight darkening of the steel strip shall not be objectionable). Layering or separation shall constitute failure if it does not return to its original homogeneous state upon cooling.

3.7.2 Cold stability. The concentrated cleaning compound shall return to its original homogeneous condition when tested in accordance with 4.4.6.

3.7.3 Rheology (Type III only).

3.7.3.1 Consistency. When tested as specified in 4.4.24, the concentrated cleaning compound shall flow between 10 and 20 centimeters in 10 seconds. The product shall also exhibit rheology which enables it to meet the sprayability requirement.

3.7.3.2 Sprayability. The concentrated cleaning compound, when dispensed at 45 psig and tested in accordance with 4.4.25, shall give satisfactory spray characteristics and deposit a uniform layer on a vertical surface 3 feet away from the nozzle.

3.8 Effect on metals (All types unless otherwise noted).

3.8.1 Hydrogen embrittlement. When tested in accordance with 4.4.9, the concentrated cleaner (all types) and a 10% solution of the cleaner (Types I and IV only) in distilled water shall not cause hydrogen embrittlement of cadmium plated or IVD aluminum coated AISI 4340 steel.

3.8.2 Total immersion corrosion. When tested in accordance with 4.4.10 (ASTM F483), the concentrated cleaning compound (all types) and a 10% solution of the cleaning compound (Types I and IV only) in distilled water shall not show any indication of staining, etching, pitting, or localized attack on any of the panels, or cause a weight change of an average of three (3) test panels greater than that shown in Table II. A slight discoloration of the panels shall not be objectionable. The cleaning compound shall not layer or separate for the duration of the test.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T12:25Z
Check the source to verify that this is the current version before use.

TABLE II. Total immersion corrosion requirements.

Alloy	Average of 3 Panels Weight Loss, Max (mg/cm²/168 hrs)
Magnesium (AZ 31B-H24) AMS4377; surface treatment per SAE AMS-M-3171, Type III	0.50
Aluminum, SAE AMS-QQ-A-250/4, T3; surface treatment per MIL-A-8625, Type I, Class I	0.15
Aluminum, SAE AMS-QQ-A-250/4, Bare T3 Alloy	0.15
Aluminum, SAE AMS-QQ-A-250/12, Bare T6 Alloy	0.15
Titanium, SAE AMS-T-9046, 6AL-4V Class III, Composition C	0.10
Steel, AMS5046, SAE 1020	0.25
Steel, 410 SS, silver plated per SAE AMS2410	0.10

3.8.3 Low-embrittling cadmium plate corrosion. Steel panels coated with low-embrittling cadmium plate immersed in the concentrated cleaning compound (all types) and a 10% solution of the cleaning compound (Types I and IV only) in distilled water shall not show a weight change greater than 0.14 mg/cm^2 for 24 hours when tested in accordance with 4.4.11.

3.8.4 Effects on unpainted metal surfaces. The concentrated cleaning compound (Type III only) and a 10% solution (Types I and IV) of the cleaning compound in distilled water shall not cause streaking, stains or other deposits that cannot be easily removed with water when tested in accordance with 4.4.12.

3.8.5 Sandwich corrosion. When tested in accordance with 4.4.16, the concentrated cleaner (all types) and a 10% solution (Types I and IV only) shall show no corrosion in excess of that shown by control test coupons in ASTM D1193, Type IV reagent water.

3.8.6 Wet adhesion tape test (Type IV). A ten (10) percent solution of the cleaning compound, when used as directed, shall remove soil from a painted surface in preparation for repainting such that paint applied after cleaning with the compound shall adhere to the surface when tested in accordance with 4.4.27.

3.9 Effect on painted surfaces. The concentrated cleaning compound (Type III only) and a 25% solution (Types I and IV) of the cleaning compound in distilled water shall not cause streaking, blistering, discoloration or a permanent decrease in film hardness of more than one (1) pencil hardness level when tested in accordance with 4.4.13. The Type I material shall be tested using only the Polyurethane Paint Systems (panel set H).

3.10 Stress crazing of MIL-PRF-5425 (ASTM F484 Type A finish) and MIL-PRF-25690 (ASTM F484 Type C finish) acrylic plastics. The concentrated product (Type III only) and a 10% solution (Types I and IV) in distilled water shall not cause stress crazing or

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T12:25Z
Check the source to verify that this is the current version before use.

staining of acrylic plastics when tested in accordance with 4.4.14.

3.11 Stress crazing of polycarbonate plastic. The concentrated product (Type III only) and a 10% solution (Types I and IV) in distilled water shall not cause stress crazing or staining of polycarbonate plastic conforming to SAE AMS-P-83310 when tested in accordance with 4.4.15.

3.12 Long term storage stability. After being stored for a period of 12 months, in accordance with 4.4.17, the cleaning compound shall not layer, separate, precipitate or corrode the shipping container. Plastic containers shall not show leakage nor any cracking, crazing, or softening. All cleaning compounds shall meet the requirements of paragraphs 3.6.1, 3.8.1, 3.8.2, 3.16 and 3.17 of this specification.

3.13 Hot dip galvanizing corrosion. The concentrated product (Type III only) and a 10% solution of the cleaning compound (Types I and IV) in distilled water shall not show a weight change of an average of three (3) test panels greater than 0.14 mg/cm² when tested in accordance with 4.4.18.

3.14 Workmanship. The cleaning compound shall be a liquid having a uniform and homogenous appearance. The cleaning compound shall be manufactured from materials that shall produce a product harmless to metal surfaces and humans when used as directed.

3.15 Effect on polysulfide sealants. The concentrated cleaning compound (Type III only) and a 25% solution (Types I and IV) of the cleaning compound in distilled water shall not change the durometer hardness of the polysulfide sealant by more than 5 units when tested in accordance with 4.4.19.

3.16 Rubber compatibility. The concentrated cleaning compound (Type III only) and a 25% solution (Types I and IV) of the cleaning compound in distilled water shall not change the durometer hardness more than 5 units when tested in accordance with 4.4.20.

3.17 Effect on polyimide insulated wire. The cleaning compound, when tested according to 4.4.26, shall not cause dissolution, cracking, or dielectric breakdown (leakage) of the polyimide insulated wire in excess of that produced by distilled water.

4. VERIFICATION

4.1 Classification of tests. The inspection and testing of the cleaning compound shall be as follows.

a. Qualification inspection (4.2).

b. Conformance inspection (4.3).

4.2 Qualification inspection. Qualification inspection shall consist of all inspections and tests specified herein.

4.2.1 Qualification process. At the initiation of the qualification process, prospective suppliers will forward a written request for such action to the qualifying activity, Air Force Petroleum Office, AFPET/PTPS, 2430 C Street, Building 70, Area B, Wright-Patterson AFB, OH 45433. This request will contain general information on the proposed candidate material. The qualifying activity will reply in writing outlining the required information to be submitted, the governing regulations for qualified products, and the cost of testing. The information that will be submitted include:

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T12:25Z
Check the source to verify that this is the current version before use.

a. Letter stating the company will adhere to the appropriate provisions of the SD-6.

b. Complete formulation of the candidate product, including chemical composition in weight percent, the manufacturer and trade name, the purity, and use of each component.

c. Safety Data Sheet (SDS) for each component and final product. The SDS will not be older than 5 years.

d. Certified laboratory test data from the manufacturer, a commercial laboratory, or combination thereof showing quantitative results of all qualification tests required by this specification as identified in Table I.

e. Verification that the System for Award Management (SAM) (CAGE Codes for the corporate office and each plant) is current. This can be viewed at https://sam.gov/.

f. Identification of the manufacturing site of the specific batch of test sample to be submitted.

g. A completed DD Form 1718.

4.2.2 Qualification samples. The initial qualification samples shall consist of 12 liters (3 gallons) of the cleaning compound. The cleaning compound shall be furnished in containers of the type to be used in filling contract orders. Samples shall be identified as follows and forwarded to the laboratory responsible for testing, as designated in the letter of authorization ("Proceed Letter") from the qualifying activity (see 6.3).

4.2.3 Test reports. The contractor shall provide certified test reports showing that the material conforms to all the requirements of this specification. The initial report consisting of all specification requirements except the storage stability tests shall be provided upon completion of those tests. The final report shall be provided after the completion of the storage stability tests and shall consist of those test results. Certified test reports shall include the gas chromatogram (4.7.1) or the infrared spectrogram (4.7.2) as required.

4.2.4 Qualification (Initial). Prior to actual procurement, the cleaning compound shall pass the qualification inspections and requirements specified herein. If the product is later modified in any way, the modified form shall be subjected to and shall pass the same qualification inspections (see 3.1). Any changes or modifications from the formulation used at the initial qualification shall be approved by the qualifying activity and may require re-qualification (4.2.6). All initial qualifications shall be granted contingent upon compliance with the long term storage stability requirement specified in 3.12.

4.2.5 Retention of qualification. Re-qualification (4.2.6) is required every five (5) years. Verification by certification shall be at the 2½ year mark ("Recertification"). The manufacturer shall verify by certification via completed DD Form 1718 to the Qualifying Activity that the manufacturer's product complies with the requirements of this specification. The manufacturer shall also provide a recent Certificate of Analysis (COA) to include all conformance inspection requirements (see 4.3). The Government reserves the right to re-examine the qualified product whenever deemed necessary to determine if the product continues to meet any or all of the specification requirements.

4.2.6 Re-Qualification (Periodic). The cleaning compound furnished under this specification shall be re-qualified by the qualifying activity every five (5) years for the product to

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T12:25Z
Check the source to verify that this is the current version before use.

remain listed on the QPL. Re-qualification testing shall be accomplished on any qualified cleaning compound for which a using activity issues a valid deficiency report. The cleaning compound shall also be subject to re- qualification testing for any change in chemical formulation, material, process, or procedure in manufacturing the cleaning compound. A minor change in the product formulation might not need requalification testing, but only after notification to, and approval by the qualifying activity (see 6.3). Documentation required for requalification shall include product formulation, safety data sheet (SDS) not older than five (5) years for each component and the final product, and a COA showing compliance to all of the qualification requirements and a one (1) gallon requalification sample from a current or most recent production run. Upon periodic re-qualification, any cleaning compound which does not conform to all the qualification tests specified herein shall be removed from the QPL.

4.3 Conformance tests. Conformance tests (see 6.4) for acceptance of the cleaning compound shall consist of the following tests.

A. Workmanship

B. Cold Stability

C. Insoluble Matter

D. Consistency (Type III only)

E. Immersion Corrosion*

F. Emulsion Characteristics

G. Nonvolatile Matter

H. pH

I. Flash Point

J. Infrared Spectrogram (Types III and IV)

K. Gas Chromatogram (Type I only)

* Immersion Corrosion Conformance Test ran on Aluminum SAE AMS-QQ-A-250/4, Bare T3 alloy panel only.

If during conformance testing a lot fails any of the above acceptance tests, all tests required for qualification shall be repeated on a different lot. These tests shall be required until two successive lots meet all requirements of the specification, after which conformance testing shall again be authorized (see 4.3.2).

4.3.1 Sampling. Unless otherwise specified, not less than a 3.8-liter (1-gal) container of the cleaning compound shall be selected at random from each lot and subjected to the tests specified in 4.3. The contents of each selected container for sampling shall be thoroughly mixed by rolling and inverting immediately prior to sampling. Conformance tests (4.3) shall be made on the sample of product taken directly from the filled containers. Samples from a packaged lot (see 6.5.1) shall be taken for testing in accordance with ASTM D4057 or ASTM D4177, as appropriate. The contents of each container to be sampled shall be shaken, rolled, or stirred to mix the contents thoroughly.

4.3.2 Rejection and retest. When any sample of the product examined and tested in

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T12:25Z
Check the source to verify that this is the current version before use.

accordance with this specification fails to conform to the requirements specified herein, the entire lot represented by the sample shall be rejected. Rejected material shall not be resubmitted for acceptance without prior approval of the qualifying activity. The application for resubmission shall contain full particulars concerning previous rejections and all measures taken to correct those defects. Samples for retest shall be taken only from a sealed container.

4.4 Method of inspection. Tests shall be performed in accordance with the methods specified in 3.4 through 3.17, 4.4.1 through 4.7.2 and the contractual requirements (see 6.2). Physical and chemical values apply to the average of the determinations made on the samples.

4.4.1 Nonvolatile matter. Weigh 5.00 ± 0.01 g of the sample in a porcelain or glass dish about 6 to 8 cm in diameter and about 2 to 4 cm in depth. Dry to constant weight in an air oven at a temperature of 105 ± 2°C. Constant weight is attained when successive heating for 1-hour periods shows a loss (or gain) of not more than 0.1%. Nonvolatile matter determinations shall be made on a minimum of two samples and the average shall be reported. If the two weights differ by more than 0.5% (absolute) the procedure shall be repeated. The nonvolatile content of each sample shall be calculated as follows:

$$\%NVM = \left[\frac{A}{B}\right] \times 100$$

where:

A = weight of residue

B = weight of sample and

$\%\ NVM$ = Percent nonvolatile matter.

4.4.2 Insoluble matter. The concentrated cleaning compound shall be thoroughly agitated and a 200 mL test sample withdrawn. The insoluble matter shall be collected with the aid of a vacuum filtering apparatus, a 2,000 mL Erlenmeyer flask, a size 4 (126 mm ID) Buchner funnel and a piece of 126 mm diameter Whatman No 5 filter paper, or equivalent. The filter paper shall be dried at 60°C (140°F) for 30 minutes in a gravity convection oven, cooled for 3 minutes in a desiccator, and weighed to the nearest 0.1 mg. The filter paper shall be placed in the Buchner funnel so that its circumference coincides with the circumference of the funnel. The vacuum shall be started and the filter paper wetted with approximately 10 mL of distilled water in order to secure it properly in place. The test sample shall be filtered. The sides of the beaker which contained the test sample shall be rinsed with 25 mL of distilled water from a wash bottle and the rinse transferred to the funnel ensuring that any remaining insoluble matter is completely transferred with the rinse. When all the initial liquid and the rinse have been transferred through the filter, the sides of the funnel shall be washed with 25 mL of distilled water from a wash bottle and the rinse allowed to filter. The vacuum on the flask shall be relieved and the filter paper removed from the funnel. The filter paper shall be dried for 1 hour at 60°C (140°F) in a gravity convection oven, cooled for 3 minutes in a desiccator, and weighed to the nearest 0.1 mg. The percent insolubles shall be calculated as follows:

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T12:25Z
Check the source to verify that this is the current version before use.

$$I = \left[\frac{A-B}{W}\right] \times 100$$

where:

A = final weight of filter paper

B = initial weight of filter paper

W = weight of sample and

I = Percent nonvolatile matter.

Care should be exercised throughout the final drying and weighing cycle to maintain the flat surface of the filter paper in a horizontal position so that none of the insoluble matter will be lost. Insoluble matter determinations shall be made on a minimum of two samples and the average shall be reported. If the two results differ by more than 0.5% (absolute) the procedure shall be repeated.

4.4.3 pH value. The pH value of the concentrated cleaning compound and a 10 percent solution of the cleaning compound in freshly boiled distilled water shall be measured in accordance with ASTM E70.

4.4.4 Residue rinsibility. Six smooth aluminum dishes, containing no creases or crevices, shall be cleaned with Brite Boy, (from Carroll Company; www.carrollco.com), or equivalent), rinsed, and dried to constant weight. Ten mL of a 25% by volume solution of the cleaning compound in standard hard water (see 4.4.4.1) shall be placed in three of the pre-cleaned dishes and tested according to the procedure in 4.4.4.2.

4.4.4.1 Preparation of standard hard water. A 20-grain (as $CaCO_3$) hard-water stock solution shall be prepared by dissolving 0.40 ± 0.005 g of reagent grade Calcium Acetate, $Ca(C_2H_3O_2)_2 \cdot 2H_2O$ and 0.28 ± 0.005 g of reagent grade Magnesium Sulfate, $MgSO_4 \cdot 7H_2O$, in 1 liter of boiled distilled water.

4.4.4.2 Procedure. Dry three dishes each containing 10.0 mL of a 25% cleaning solution for 7 1/2 hours in a circulating oven at 68 ± 2 °C with full draft. Cool in desiccator overnight and weigh. Rinse with running distilled water for 1 minute. Brush with a sash-type brush containing long-fiber bristles (2.5 cm diameter by 3.8 cm to 6.4 cm long) for 1 minute using distilled water. Rinse for 30 seconds with running distilled water. Dry in oven as before, cool and reweigh. Standard hard water (4.4.4.1) shall be tested as control for weight change comparison in the remaining three pre-cleaned dishes, using the same procedure as above.

4.4.5 Heat stability. A 141.75 g sample of the well mixed concentrated cleaning compound shall be placed into each of two clean 355 mL (12 oz) clear glass bottles having approximate dimensions of 24 cm in height by 6.35 cm in diameter (9.5 in x 2.5 in). One bottle containing the concentrated cleaning compound shall be sealed with a screw type cap and stored in a dark place at standard conditions for 6 days (144 hrs) for reference purposes. Place into the second bottle of concentrated cleaning compound a strip of steel, 15.24 cm by 1.27 cm by 0.05 cm (6 in x 0.5 in x 0.02 in) conforming to AMS5046 (SAE 1020). Clean the steel strip by abrasively polishing to remove surface scale and corrosion followed by immersion for one minute in mineral spirits followed by immersion for 1 minute in isopropyl alcohol (TT-I-735,

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T12:25Z
Check the source to verify that this is the current version before use.

grade A or equivalent) at standard conditions. Wipe test panels with an alcohol wetted lint free cloth and dry with a clean, lint free cloth. Oven drying is optional. Seal the bottle containing the concentrated cleaning compound and the cleaned steel strip with a screw type cover and shake thoroughly for 1 minute. Place the bottle in a bath maintained at 46 ± 2 °C (115 ± 3 °F) for 5 hours, then remove and allow to cool to ambient conditions for 19 hours. This heating/cooling cycle shall be repeated 5 times. After completion of the test period, remove the test strip and inspect the portion of the strip which was immersed in the cleaning compound and the portion exposed to the vapor. Any corrosion, pitting or discoloration constitutes failure. The bottle is resealed and along with the control bottle that has been maintained in the dark is shaken thoroughly for 1 minute, then allowed to remain undisturbed for 1 hour at room temperature. The bottles are then examined. Any marked change in color, precipitation, layering or separation constitutes failure.

4.4.6 Cold stability. A 50 mL sample of the cleaning compound shall be poured into a test tube and cooled to 0°C. This temperature shall be maintained for 1 hour. The compound shall then be allowed to reach room temperature. After 5 (five) complete temperature inversion cycles of the test tube, the compound shall be examined for homogeneity. A slight turbidity shall not be objectionable provided no precipitation is present.

4.4.7 Flash point. The flash point of the concentrated cleaning compound (Type I, III, and IV) shall be determined in accordance with ASTM D56 (Tag Closed Cup) and for materials that have a tendency to form a surface film under the test conditions, use ASTM D93. The flash point of the 10% solution in distilled water (Type I only) shall be determined in accordance with ASTM D92.

4.4.8 Emulsion characteristics. 20 mL of a 25% by volume solution (Type I) of the cleaning compound (12.5% by volume solution for Types III and IV) shall be placed in a 50 mL glass stoppered graduated cylinder. 20 mL of lubricating oil conforming to MIL-PRF-2104, grade 10W, shall be added. An emulsion shall be formed by 10 inversions of the graduated cylinder followed by a vigorous 15-second shake. After the emulsion has stood for 5 minutes, the 15-second shake shall be repeated. At 5 minutes and 8 hours for Type I and at 5 minutes and 24 hours for Types III and IV cleaners, the amount of free water and cleaner which separates from the lubricating oil shall conform to the requirements of Table I.

4.4.9 Hydrogen embrittlement. The hydrogen embrittlement properties of the cleaning compound shall be determined as passive chemicals in a service environment according to ASTM F519 using two (2) sets of either Type 1a, 1c, or 2a AISI 4340 steel specimens. One set shall be plated per Table 2 Treatment B, ASTM F519. The second set shall be coated with Ion Vapor Deposited (IVD) Aluminum per MIL-DTL-83488, Class 2, Type I. Prior to coating, specimens for IVD Aluminum shall be prepared by grit blasting, including notched area, with size 180 virgin grain white aluminum oxide grit. The applied IVD coating shall not be peened or burnished in any manner. All specimens must be completely plated or coated except for the screw threads.

4.4.10 Total immersion corrosion. The total immersion corrosion effects of the cleaning compound on the new, unused metals and metal alloys listed in Table II shall be determined in accordance with ASTM F483. After immersion for 24 hours and after 168 hours, panels shall be evaluated for appearance. Conformance to the requirements in Table II shall be for weight loss after 168 hours. In order to obtain the best results on test panels in this very low weight

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T12:25Z
Check the source to verify that this is the current version before use.

category, the panels shall be handled with gloves, cleaned in a very careful manner and dried in an oven. They are cooled and dried in a desiccator both before and after each weighing.

4.4.11 Low-embrittling cadmium plate corrosion. The cleaning compound shall be evaluated for corrosion on low-embrittling cadmium plate in accordance with ASTM F1111.

4.4.12 Effects on unpainted metal surfaces. The cleaning compound shall be evaluated for effects on unpainted metal surfaces in accordance with ASTM F485.

4.4.13 Effect on painted surfaces. The concentrated cleaning compound (Type III only) and a 25% solution (Types I and IV) with distilled water shall be tested in accordance with ASTM F502 except that the panels used for testing shall be coated with the paint systems listed in Table III. For all paint systems tested, a separate panel shall be required for both 25% solution and concentrate. For Types III and IV compounds, conduct the test on all paint systems listed in Table III. For Type I compounds, conduct the test only on the polyurethane paint systems (panel set H).

TABLE III. Test panel finishes.

Primer Coatings				
Panel Set No.	Primer Material Specification	Dry Film Thickness Per Coat/mm (inches)	No. of Coats	Drying Time Before Topcoating
EH	MIL-PRF-23377, Type I, Class C High-Solids Epoxy Primer	0.0152-0.0229 (0.0006-0.0009)	1	2 - 8 hours

Top Coats, Color Number 17925 per SAE AMS-STD-595						
Panel Set	Topcoat Material	Dry Film Thickness Per Coat/ mm (inches)	No. of Coats	Drying Time Between Coats	Dry Film Thickness mm (inches)	Days to Dry Before Testing
E	MIL-PRF-22750 Coating, Epoxy Topcoat	0.0203 - 0.0305 (0.0008 - 0.0012)	2	1 hour	0.0406-0.0610 (0.0016 - 0.0024)	7
H	MIL-PRF-85285 Type I Coating: Polyurethane, High Solids	0.0203 - 0.0305 (0.0008 - 0.0012)	2	1 hour	0.0406-0.0610 (0.0016 - 0.0024)	7

4.4.14 Stress crazing of MIL-PRF-5425 and MIL-PRF-25690 acrylic plastics. The cleaning compound shall be evaluated for stress crazing of stretch acrylic plastics in accordance with ASTM F484 using Type A (MIL-PRF-5425) and Type C (MIL-PRF-25690) finishes.

4.4.15 Stress crazing of polycarbonate plastic. The cleaning compound shall be evaluated for stress crazing of polycarbonate plastics using the test procedure outlined in ASTM F484 with the exception that the acrylic plastics called for in the procedure be replaced with polycarbonate plastic conforming to SAE AMS-P-83310 of the same dimensions and the polycarbonate specimens shall be stressed for 30 ± 2 minutes to an outer fiber stress of 2000 psi.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T12:25Z
Check the source to verify that this is the current version before use.

4.4.16 Sandwich corrosion. The cleaning compound shall be tested in accordance with ASTM F1110 as specified in 3.8.5.

4.4.17 Long term storage stability. The cleaning compound shall be prepared and stored for long term storage stability in accordance with ASTM F1104 using one (1) 3.8-liter (one-gallon) can conforming to Federal Specification PPP-P-704 or DOT UN 1A1 steel container. Plastic containers shall conform to DOT UN 1H1 as required by 49 CFR 178. Manufacturers using both type materials in production packaging shall test each type container with their product.

4.4.18 Hot dip galvanizing corrosion. The total immersion corrosion effect of the cleaning compound shall be evaluated as specified in 3.13 after 24 hour immersion per ASTM F483. Test coupons shall be AMS5046 (SAE 1020) steel panels prepared by hot dip galvanizing per ASTM A153.

4.4.19 Effects on polysulfide sealant.

4.4.19.1 Preparation of test specimens. MIL-PRF-81733, Type I, and SAE AMS-S-8802 sealants shall be mixed as specified by their respective manufacturers and each pressed into a 1/8-inch thick sheet mold until cured (this shall be the sheet stock for each sealant). The sealants shall be cured for 7 days at 49°C. The specimens shall be cut from the sheet stock.

4.4.19.2 Test procedures. Immerse two specimens of each sealant in the concentrated product (Type III only) and a 25% solution of the cleaning compound (Types I and IV) at room temperature for 30 minutes. Remove from the solution, rinse with cool tap water, and test within 30 minutes for Shore A hardness in accordance with ASTM D2240.

4.4.20 Test on rubber compatibility. Tests shall be conducted on AMS3204 and AMS3209 rubbers for compatibility with the cleaning compounds.

4.4.20.1 Preparation of test specimens. Three (3) test specimens shall be used for each type rubber specified. Test specimens shall be cut from 1/8-inch sheet stock.

4.4.20.2 Test procedure. Test and record the Shore A hardness of each test specimen in accordance with ASTM D2240. Immerse each specimen in the concentrated product (Type III only) and a 25% solution of the cleaning compound (Types I and IV) at room temperature for 30 minutes. Remove from the solution, rinse with cool tap water, and test within 30 minutes for a Shore A hardness in accordance with ASTM D2240.

4.4.21 Cleaning efficiency (all types). The cleaning efficiency of the cleaning compound shall be reported as the average of three test results and shall conform to the requirements of Table I.

4.4.21.1 Preparation of control formula. The control formula shall be prepared by the testing laboratory in accordance with Table IV and subjected to the cleaning test (4.4.21.5) and evaluation (4.4.21.6). Valid control formula preparations shall produce denominator values greater than 0.95 during testing.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T12:25Z
Check the source to verify that this is the current version before use.

TABLE IV. Control formula for the cleaning efficiency test.

Component	Control Formula Composition (% by weight) [1]
d-limonene	30.0
diethanolamine	5.0
nonionic surfactant (Triton X-100)	5.0
distilled water (ASTM D 1193, Type IV)	60.0

NOTES

1. This formulation is corrosive and intended solely for use as the control for the cleaning efficiency test. It will not qualify to the requirements in this specification.

4.4.21.2 Panel preparation. Aluminum SAE AMS-QQ-A-250/4, bare T3 panels, 40.6 x 12.7 x 0.05 cm (16 x 5 x .02 in) shall be used.

4.4.21.3 Soil preparation. Molybdenum disulfide grease soil shall be prepared by blending 50 grams of carbon black and 500 grams MIL-G-21164 grease with a mechanical grease worker for 15 minutes.

4.4.21.4 Application of grease soil. Panels shall be wiped with clean lint free cloths soaked in reagent grade acetone then dried to a constant weight. Record the weight to the nearest 0.1 mg. Apply approximately 200 mg grease soil using a soft bristle brush over an area approximately 2" x 7" in the center of the panel. Remove excess grease soil by covering the test panel with a folded absorbent tissue and exerting pressure by rolling a five-pound rubber cylinder over the tissue. Repeat this blotting procedure twice. Each freshly soiled panel shall be baked at 105 ± 5 °C for 60 minutes then cooled to room temperature and weighed to the nearest 0.1 mg. Only use panels with more than 50 mg of grease soil. Panels shall be used within 4 hours.

4.4.21.5 Cleaning test. The test panels shall be cleaned using a Gardner heavy duty wear tester, or equivalent, fitted with a cellulose sponge. The sponge shall be cut such that the dimension parallel to the cleaning stroke is 9 cm (3.5 in) and the width is 7 cm (2.75 in). The cleaning head with the dry sponge attached shall be weighed to a mass of 495 to 505 grams. The cleaning stroke of the scrub tester shall be 12 inches. The cleaning compound (including Type III) and the control formula shall be diluted 1 part cleaner with 9 parts distilled water. After placing a soiled test panel in the template 100 mL of the cleaning solution shall be applied to the sponge then applied to the soiled test panel so that it is completely covered. After allowing a 30-second dwell time, the test panel shall be cleaned using 5 cycles of the wear tester. The panel shall then be rinsed with sufficient amounts of distilled water.

4.4.21.6 Evaluation. The rinsed panel shall be heated to 105°C ± 5°C for 10 minutes, cooled to room temperature, then weigh to the nearest 0.1 mg. Report the % Cleaning Efficiency as the average of three (3) tests using the following:

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T12:25Z
Check the source to verify that this is the current version before use.

$$\%\ Cleaning\ Efficiency = \frac{\left[\frac{A-B}{A-C}\right]}{\left[\frac{X-Y}{X-Z}\right]} * 100$$

where:

A = weight of the soiled panel before cleaning with product

B = weight of the soiled panel after cleaning with product

C = weight of the unsoiled panel used in the product cleaning test

X = weight of the soiled panel before cleaning with the control formula

Y = weight of the soiled panel after cleaning with the control formula and

Z = weight of the unsoiled panel used in the control formula cleaning test.

4.4.22 Biodegradability. Biodegradation shall be determined by the "Shake Flask Biodegradation Tests" for measuring ultimate or ready degradation potential, as found in EPA Chemical Fate Test Guidelines 40 CFR Method 796.3100 (Aerobic Aquatic Biodegradation Test). Biodegradability shall be shown as carbon transformation by both soluble organic carbon reduction and CO_2 evolution.

4.4.23 Terpene hydrocarbons (Type I only). An approved test procedure shall be used (see 3.3.1.1).

4.4.24 Consistency (Type III only). A consistometer (CSC Scientific Company, Inc., Fairfax, VA); or equivalent shall be used as follows: Shake the container of cleaning compound by hand for 10 seconds. Pour the material into the well of the consistometer completely filling it. Release the gate and determine the extent of flow in ten seconds.

4.4.25 Sprayability (Type III only). Fill the reservoir of the application test equipment with Type III compound, as supplied. Release the compound flow valve and gradually increase the nozzle tip pressure to not more than 8 psi pressure observing the discharge spray characteristics. Report the following:

a. The maximum pressure at which no bubbles are released into the surrounding air.

b. The distance the gel can be satisfactorily projected.

4.4.25.1 Technique. Under these optimized conditions apply with a sideways sweeping motion the compound to a vertical surface and examine the deposited film and record assessment. The product should display uniformity with absence of large and entrained air bubbles or a consistency which would not inhibit effective cleaning.

4.4.25.2 Application test equipment.

a. Reservoir: Hand pump pressure sprayer (modified), or pressure pot with air pressure applied from external compressor.

b. Nozzle: Fan jet with an equivalent orifice diameter 1.1 mm and spray angle 65°. (Spraying Systems Co., Wheaton Illinois, Item Number H-VV 6503)

4.4.26 Effect on polyimide insulated wire. Coil two segments of MIL-DTL-81381/11-20 wire approximately 61 cm (24 in) and place into separate 118 mL (4 oz)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T12:25Z
Check the source to verify that this is the current version before use.

wide mouth jars. To one jar add sufficient concentrate cleaning compound to completely cover the wire coil. To the other jar (control sample) add sufficient distilled water to cover the wire coil. Cap both jars and store at room temperature (20 - 25 °C) for 14 days. At the end of the storage period remove both coils, rinse thoroughly with distilled water and suspend to allow complete draining and drying. Uncoil the wires, examine each closely for dissolution, and report the results. The wire immersed in the cleaner shall perform as well as the wire immersed in distilled water. Both wires shall then be subjected to a double reverse wrap on a 0.3 cm (0.125 in) mandrel and examined for cracking. (Note: Failure of the control sample here voids the test and shall be repeated using new MIL-DTL-81381/11-20 material). Wire immersed in the cleaner shall then be examined for cracking. If cracking occurs, results shall be reported and the test ended. Passing wire shall then withstand a 1-minute dielectric test of 2,500 volts (rms), using a Hipot dielectric tester, or equivalent, and examined for breakdown or leakage. Wire immersed in the cleaner shall perform equally well as the control wire immersed in distilled water.

4.4.27 Wet adhesion tape test. This method tests the coating to metal and the intercoat adhesion of an organic coating system. This procedure is used to determine the cleanliness of the surface prior to coating.

4.4.27.1 Preparing test coupons. The test coupons shall consist of nine (9) 4 in x 6 in aluminum alloy coupons conforming to SAE AMS-QQ-A-250/12. The coupons shall be cleaned with reagent grade acetone, then cleaned with the diluted cleaning compound (10% solution) agitated for 20 seconds with a Scotch Bright pad (A-A-58054, Type I Class 1, Grade B, maroon color) and thoroughly rinsed with water and allowed to dry. Pretreat the coupons with AMS1640 and MIL-C-5541. The coupons shall be air dried and primed with MIL-PRF-23377, Type I Class C high solids epoxy primer. Topcoat the coupons according to Table V as follows:

Set 1: Six coupons (Code A plus D)

Primer: MIL-PRF-23377, Type I, Class C High-Solids Epoxy

Topcoat: MIL-PRF-85285, Type I High Solids Polyurethane Color # 34092

Set 2: Three coupons (Code A plus D)

Primer: MIL-PRF-23377, Type I, Class C High-Solids Epoxy

Topcoat: MIL-PRF-85285, Type I High Solids Polyurethane Color # 17925.

The coatings should be allowed to cure for a minimum of seven (7) days before being validated by performing the wet tape test.

4.4.27.2 Coupon validation procedure. The nine coupons (two sets in 4.4.27.1) shall be validated using the following wet tape test.

a. Immerse the test coupons in distilled water for 24 hours.

b. Remove the test coupons from the water and wipe dry with a clean lint free cloth.

c. Immediately apply a 25.4 mm wide strip of Masking Tape (3M Co., Code No. 250) with the adhesive side down. Do not apply the tape within ½ inch of any edge.

d. Press the tape against the surface of the coating by passing a 2.0 kg rubber covered roller, having a surface Durometer hardness value of 70 to 80, across the tape eight

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T12:25Z
Check the source to verify that this is the current version before use.

times.

e. Remove the tape with one quick motion and examine for damage to the intercoat or surface adhesion.

f. If there is no damage to the surface, note and proceed to 4.4.27.3. If three or more coupons fail the wet tape test or there is any unusual or non-typical condition, investigate to determine if use of cleaner contributed to failure or unusual condition. Report findings. Failed coupons or coupons with unusual surface conditions shall not be validated nor used in the repaint testing of 4.4.27.3.

TABLE V. Test panel finishes.

Primer Coatings				
Code	Primer Material Specification	Dry Film Thickness Per Coat mm (inches)	No. of Coats	Drying Time Before Topcoating
A	MIL-PRF-23377,Type I, Class C Primer Coatings; Epoxy, High-Solids	0.0152 - 0.0229 (0.0006 - 0.0009)	1	2 - 8 hours
B	MIL-PRF-85582, Type I, Class 1B Primer Coatings: Epoxy, Waterborne	0.0152 - 0.0229 (0.0006 - 0.0009)	1	2 - 8 hours
C	TT-P-2760, Type I, Class C Primer Coating: Polyurethane, Elastomeric, High-Solids	0.0380 - 0.0510 (0.0015 - 0.0020)	1	2 - 8 hours

Top Coats						
Code	Topcoat Material	Dry Film Thickness Per Coat/ mm (inches)	No. of Coats	Drying Time Between Coats	Dry Film Thickness mm (inches)	Time Before Testing (Days)
D	MIL-PRF-85285, Type I Coating: Polyurethane, High-Solids	0.0203 - 0.0305 (0.0008 - 0.0012)	2	1 hour	0.0406 - 0.0610 (0.0016 - 0.0024)	7

4.4.27.3 Test procedure. This test shall verify the cleaning compound's effectiveness to remove soil from a painted surface in preparation for repainting (touch up). Immerse the coupons validated in 4.4.27.2 in hydraulic fluid conforming to MIL-PRF-83282 for ten (10) minutes. Remove the panels from the fluid and blot excess fluid from the coupons with a paper napkin. Spray the diluted cleaning compound (10% solution) on the coupons, agitate for 20 seconds with a 3M Scotch Bright Pad (A-A-58054) and thoroughly rinse with clean water. After the coupons have air dried, recoat the panels from Table V as follows:

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T12:25Z
Check the source to verify that this is the current version before use.

Set 1: Three coupons (code B plus D)

Primer: MIL-PRF-85582, Type I, Class 1B Waterborne Epoxy

Topcoat: MIL-PRF-85285 Type I High Solids Polyurethane, Color #34092

Set 2: Three coupons (Code A plus D)

Primer: MIL-PRF-23377, Type I, Class C High Solids Epoxy

Topcoat: MIL-PRF-85285 Type I High Solids Polyurethane, Color # 34092

Set 3: Three coupons (Code C plus D)

Primer: TT-P-2760, Type I, Class C High Solids Elastomeric, Polyurethane

Topcoat: MIL-PRF-85285 Type I High Solids Polyurethane, Color # 34092

After the above coatings have air dried for seven (7) days, perform the Wet Tape Test in paragraph 4.4.27.2, steps (a) through (e). The coating system shall show no signs of damage.

4.5 Toxicity and waste disposal characteristics. The supplier shall provide the toxicological data and formulations required (see 3.3) to evaluate the safety of the material proposed for use. The manufacturer shall provide current procedures for disposal per federal EPA regulations.

4.6 Filler materials. The contractor shall furnish certification that the cleaning compound contains only the materials allowed and does not contain any filler materials disallowed per 3.2.

4.7 Qualitative identification of components (Types I, III, and IV).

4.7.1 Gas chromatogram (Type I only). A gas chromatogram of the Type I product shall be provided by a Government approved qualification laboratory (see 3.5). The chromatogram shall report all salient instrumental parameters (column type and dimensions, temperature(s), carrier gas and flow rate, detector type, sample dilution(s), etc. required to produce it.

4.7.2 Infrared spectrogram (Types III and IV). Infrared spectrograms of the nonvolatile matter shall be prepared by a Government approved qualification laboratory (see 3.5). The spectrogram, including method for sample preparation, shall be provided to the qualifying activity by the qualification laboratory.

5. PACKAGING

5.1 Packaging. For acquisition purposes, the packaging requirements shall be as specified in the contract or order (see 6.2). When packaging of material is to be performed by DoD or in-house contractor personnel, these personnel need to contact the responsible packaging activity to ascertain requisite packaging requirements. Packaging requirements are maintained by the Inventory Control Point's packaging activity within the Military Department or Defense Agency, or within the military service's system commands. Packaging data retrieval is available from the managing Military Department's or Defense Agency's automated packaging files, CD-ROM products, or by contacting the responsible packaging activity.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T12:25Z
Check the source to verify that this is the current version before use.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. The three types of cleaning compounds covered by this specification are intended to be used for cleaning Aerospace Equipment including aircraft, aerospace ground equipment (AGE) and AGE engines. These cleaners will be used in place of other cleaners when approved by the System Program Manager of the equipment being cleaned. Type I should be used only on polyurethane and enamel coatings as it may attack acrylic nitrocellulose lacquer coatings found in numerous aircraft. Types I and IV materials are intended for light to heavy duty removal of greases, oils, hydraulic fluid, and carbon. Type IV cleaning compounds is also intended for cleaning aircraft and aerospace ground equipment surfaces of contaminants prior to coating or recoating with primers, topcoats, sealants and adhesives. Types I and IV must be diluted with water before use. Type III is intended for light to heavy duty removal of greases, oils, hydraulic fluid, and carbon in wheel wells, wing butts and other areas where complete rinsing with water can be tolerated. After cleaning, rinse off with water. These cleaners are not intended to be used as canopy cleaners. These products have not been tested for use at elevated temperatures.

6.2 Acquisition requirements. Acquisition documents should specify the following:

a. Title, number and date of this specification.

b. Type I, Type III or Type IV.

c. Size containers required.

d. QPL reference or test number.

e. Level of packing required.

f. Palletization, when applicable.

6.3 Qualification. With respect to products requiring qualification, awards will be made only for products which are at the time set for opening of bids, qualified for inclusion in Qualified Products List QPL No. 87937 whether or not such products have actually been so listed by that date. The attention of the contractors is called to this requirement, and contractors are urged to arrange to have their products that they propose to offer to the Federal Government tested for qualification in order that they may be eligible to be awarded contracts or orders for the products covered by this specification. The activity responsible for specification qualification and the QPL is the Air Force Petroleum Office, AFPET/PTPS, 2430 C Street Building 70 Area B, Wright-Patterson AFB, OH 45433. An online listing of products qualified to this specification may be found in the Qualified Products Database (QPD) at https://assist.dla.mil.

6.3.1 Qualification information. It is understood that the material furnished under this specification subsequent to final approval will be of the same composition and will be equal to products on which approval was originally granted. In the event that fluid furnished under contract is found to deviate from the composition of the approval product, or that the product fails to perform satisfactorily, approval of such products may be subjected to immediate withdrawal from the QPL at the discretion of the approving activity.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T12:25Z
Check the source to verify that this is the current version before use.

6.3.2 Qualification authorization notification ("Proceed Letter"). Upon successful review of the submitted information, the Air Force Petroleum Office will issue authorization to ship the qualification sample(s) for testing.

6.3.3 Qualification samples. Upon receiving authorization from the Air Force Petroleum Office, qualification sample(s) may be shipped to the qualification activity, as detailed in the authorization letter ("Proceed Letter"). Sample(s) should be accompanied by an SDS and a copy of the authorization letter. Each sample should be plainly identified by securely attached durable tags or labels marked with the following information:

a. QUALIFICATION SAMPLE

b. Cleaning Compound, Aerospace Equipment

c. MIL-PRF-87937

d. Type identification (Type I, III, or IV)

e. Name and address of manufacturer and plant where product was manufactured (including CAGE codes)

f. Product code identification

g. Batch ID

h. Date of manufacture (DOM)

i. SDS of submitted sample of finished product

6.4 Conformance tests. Conformance inspection should consist of examinations and tests necessary to ensure that production items meet specification requirements. Conformance inspection should include a description of the inspection procedure, sequence of inspections, number of units to be inspected, and the criteria for determining conformance to the requirement specified. Conformance examinations and tests should not duplicate any long term or special tests that were used to justify inclusion of qualification in a specification.

6.5 Definitions.

6.5.1 Lot. A lot consists of one of the following:

The cleaning compound produced from a continuous process not to exceed 24 hours used to fill individual packaging containers or an intermediate holding tank directly from the process output is a lot or batch. A continuous process is the production of product by continuous input of raw materials and output of finished product by one manufacturer in one plant with no change in manufacturing conditions or materials.

a. Packaged lot. A packaged lot (batch) is an indefinite number of unit containers of identical size and type offered for acceptance and filled with a homogeneous material mixture from one isolated container or filled with a material mixture manufactured in a single plant run not exceeding 24 hours through the same processing equipment with no change in ingredient material.

b. Bulk lot. A bulk lot (batch) is an indefinite quantity of a homogenous material mixture offered for acceptance in a single isolated container or manufactured in a single plant run not exceeding 24 hours through the same processing equipment with no change in ingredient material and subsequently withdrawn to fill shipping

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T12:25Z
Check the source to verify that this is the current version before use.

containers.

6.5.2 Concentrated cleaner / compound. Concentrated cleaner or compound refers to that concentration of the cleaner/compound as received from the manufacturer. No further concentration is to be performed on the product.

6.6 Shelf-life. This specification covers items where the assignment of a Federal shelf-life code is a consideration. Specific shelf-life requirements should be specified in the contract or purchase order, and should include, as a minimum, shelf-life code, shelf-life package markings IAW MIL-STD-129 or FED-STD-123, preparation of a materiel quality storage standard for type II (extendible) shelf-life items, and a minimum of 85 percent shelf-life remaining at time of receipt by the Government. These and other requirements, if necessary, are in DoDM 4140.27, Volume 1, *Shelf-Life Management Program: Program Administration*; and Volume 2, *Shelf-Life Management Program: Materiel Quality Control Storage Standards*. The shelf-life codes are in the Federal Logistics Information System Total Item Record. Additive information for shelf-life management may be obtained from DoDM 4140.27 Volumes 1 and 2, or the designated shelf-life Points of Contact (POC). The POC should be contacted in the following order: (1) the Inventory Control Points that manage the item and (2) the DoD Service and Agency administrators for the DoD Shelf-Life Program. Appropriate POCs for the DoD Shelf-Life Program can be contacted through the DoD Shelf-Life Management website: https://www.shelflife.dla.mil/.

6.7 Key words.

AGE

Biodegradable Gel-type

QPL

Terpene

6.8 Changes from previous issue. Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extent of the changes.

a. Main changes in this revision:

i. Elimination of Type II (Water Dilutable Cleaning Compound). Type IV (Heavy Duty, Water Dilutable Cleaning Compound) is a concentrated form of Type II. The requirements for Types I, III, and IV remain unchanged.

ii. Relocation of the tables from Appendix A to more correct locations within MIL-PRF-87937.

i. Table III “Sampling for tests” in MIL-PRF-87937D has been eliminated in MIL-PRF-87937E and replaced by suitable language for sampling.

ii. Table IV “Test panel finishes”, Table V “Control formula for the Cleaning efficiency test”, and VI “Test panel finishes” in MIL-PRF-87937D have been renumbered as Table III, Table IV, and Table V, respectively, in MIL-PRF-87937E.

iii. Clarification of the qualification and requalification processes.

iv. Some of the military specifications and SAE standards referenced in MIL-PRF-87937D have been canceled since its publication in September 2001. These references have been corrected in this revision.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T12:25Z
Check the source to verify that this is the current version before use.

CONCLUDING MATERIAL:

Custodians:
Air Force - 68
Navy - AS

Preparing activity:
Air Force - 68
(Project 6850-2022-003)

Review activities:
Air Force - 20
DLA - GS

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information using the ASSIST Online database at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T12:25Z
Check the source to verify that this is the current version before use.