OO-I-520a
April 10, 1967

SUPERSEDING
Int. Fed. Spec. OO-I-00520(Army-GL)
July 29, 1965

FEDERAL SPECIFICATION

INKING PAD, LAUNDRY MARKING MACHINE

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers wool felt inking pads (see 6.1).

1.1.1 *Federal specification coverage.* Federal specifications do not include all varieties of the commodity as indicated by the title of the specification, or which are commercially available, but are intended to cover only those generally used by the Federal Government.

1.2 Classification.

1.2.1 *Types and classes.* The inking pad shall be of the following types and classes as specified (see 6.2):

Type I—Plain.
- Class 1—Length 1-3/16 inches.
- Class 2—Length 1-13/16 inches.
- Class 3—Length 3-1/8 inches.

Type II—Beveled edge.
- Class 1—Length 3-1/2 inches.

2. APPLICABLE DOCUMENTS

2.1 The following specifications and standards of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

Federal Specifications:

TT-I-542—Ink, Marking, Laundry, Black.
CCC-T-191—Textile Test Methods.
NNN-P-35—Paper, Blotting, (Laboratory).
PPP-B-566—Boxes, Folding, Paperboard.
PPP-B-636—Box, Fiberboard.
PPP-B-665—Boxes; Paperboard, Metal Stayed (Including Stay Material).
PPP-B-676—Boxes, Setup.
PPP-T-45—Tape, Gummed Paper, Reinforced and Plain, for Sealing and Securing.

Federal Standard:

Fed. Std. No. 123—Marking for Domestic Shipment (Civilian Agencies).

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, D.C. 20402.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Washington, D.C., Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, Los Angeles, and Seattle, Wash.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Specification:

MIL-B-43291—Boxes: Fiberboard; Corrugated, Double-Wall, Weather Resistant.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:59Z
Check the source to verify that this is the current version before use.

Military Standards:

MIL-STD-105—Sampling Procedures and Tables for Inspection by Attributes.

MIL-STD-129—Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

3. REQUIREMENTS

3.1 Material. The marking pad shall contain not less than 95 percent wool based on the oven dry weight of the specimen when tested as specified in 4.3.

3.2 Construction. The finished pad shall be double woven fulled felt and shall conform to the dimensional properties shown in table I when tested as specified in 4.3.

TABLE I. *Dimensional properties*

Type	Class	Length, inches ± 1/32	Width, inch ± 1/32	Thickness, inch ± 0.006
I	1	1-3/16	13/32	0.125
I	2	1-13/16	13/32	.125
I	3	3-1/8	13/32	.125
II	1	3-1/2	13/32	.125

3.3 Color. The color shall be gray (undyed) with colored stripes.

3.4 Shrinkage. The finished inking pad shall not shrink in length or width when tested as specified in 4.3.1.

3.5 Workmanship. The finished pad shall conform to the quality and grade of product established by this specification.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.2 Inspection. Inspection shall be in accordance with the provisions of MIL-STD-105, except when otherwise indicated.

4.2.1 *Component and material inspection.* In accordance with 4.1, components and materials shall be tested in accordance with all the requirements of referenced specifications, drawings, and standards unless otherwise excluded, amended, modified, or qualified in this specification or applicable purchase document.

4.3 Tests. The methods of testing specified in CCC-T-191, wherever applicable, and as listed in table II shall be followed. The pads shall be conditioned for testing under standard conditions for testing as defined in CCC-T-191. The sample unit for testing shall be 10 pads. The lot size shall be expressed in units of one pad. The lot shall be unacceptable if one or more sample units fail to meet any test requirements specified. All test reports shall contain the individual value utilized in expressing the final result. The sample size (number of sample units) shall be in accordance with the following:

Lot size (pads)	Sample size (multiples of sample units)
800 or less	2
801 up to and including 22,000	3
22,001 and over	5

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:59Z
Check the source to verify that this is the current version before use.

TABLE II. *Test methods*

Characteristic	Requirement paragraph	Number of individual pads tested. One determination per pad	Test method
Wool[1]	3.1	—	2101
Weave—double woven, fulled[1]	3.2	—	—
Length[2]	3.2	10	Graduated (1/32") scale
Width[2]	3.2	10	Graduated (1/32") scale
Thickness[3]	3.2	10	5030
Shrinkage:			
Length	3.4	3	4.3.1
Width	3.4	3	4.3.1

[1] The contractor shall submit a certificate of compliance to the contracting officer for these characteristics.

[2] Average of 10 dimensions reported to the nearest 1/32 inch.

[3] A 6-ounce total load shall be applied and the pressure foot diameter shall be 3/8 inch. The ten thickness determinations shall be averaged and reported to the nearest 0.001 inch.

4.3.1 *Shrinkage.* Three conditioned pads from each sample unit shall be measured initially for length and width and the pads marked to retain identity. The three pads shall then be saturated with ink conforming to TT-I-542. The excess ink shall be removed by placing the specimen between two sheets of blotting paper conforming to NNN-P-35 and rolling once over and back with a 1-kilogram nominal weight round steel bar 1.8125 ± 0.010 inch in diameter by 3.000 ± 0.010 inch long, or equivalent. After the excess ink has been removed, the pads shall be allowed to air dry at room temperature for 48 hours. After drying, the pads shall be allowed to reach equilibrium under standard conditions and remeasured. The dimensional measurements (length and width), after ink saturation, shall be compared with the original measurements and any evidence of shrinkage in one or more pads shall be cause for rejection of the unit. All measurements shall be recorded to the nearest 1/32 of an inch.

4.4 Examination of preparation for delivery. An examination shall be made to determine that packaging, packing, and marking requirements of section 5 are complied with. Defects shall be scored in accordance with table III. The sample unit shall be one shipping container fully prepared for delivery with the exception that it need not be sealed. Defects of closure listed in table III shall be examined on shipping containers fully prepared for delivery. The lot size shall be the number of shipping containers in the end item inspection lot. The inspection level shall be S-2 and the acceptable quality level (AQL) shall be 2.5 defects per hundred units.

TABLE III. *Classification of preparation for delivery defects*

Examine	Defects
Marking (exterior and interior)	Omitted, incorrect, illegible, of improper size, location, sequence, or method of application.
Materials	Any component missing. Any component damaged, affecting serviceability.
Workmanship	Inadequate application of components, such as incomplete closure of container flaps; improper taping; loose strapping, inadequate stapling. Bulging or distortion of containers. Improper closure of polyethylene bag or wrap.
Contents	Number per container is more or less than specified. Net weight exceeds requirements.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A or C, as specified (see 6.2).

5.1.1 *Level A.* One-hundred inking pads of one type and class shall be packaged in a snug-fitting folding paperboard box conforming to variety 1, style III, type B, class a of

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:59Z
Check the source to verify that this is the current version before use.

PPP-B-566; set-up paperboard box conforming to type I, variety 1, class A, style 4 of PPP-B-676; or metal-stayed paperboard box conforming to style A of PPP-B-665. Box closure shall be secured with 2-inch minimum width gummed paper tape conforming to PPP-T-45, type III, grade A.

5.1.2 *Level C.* Inking pads shall be packaged to afford adequate protection against damage during shipment from the supply source to the first receiving activity. The contractor may use his standard practice when it meets this requirement.

5.2 **Packing.** Packing shall be level A, B, or C, as specified (see 6.2).

5.2.1 *Level A.* A quantity as specified (see 6.2), of unit packages in accordance with 5.1.1 or 5.1.2, as applicable, of one type and class of inking pads shall be packed in a snug-fitting fiberboard shipping container conforming to grade, V3c or V3s of PPP-B-636. Alternatively, shipping containers shall conform to style RSC, V15c of MIL-B-43291. Each container shall be waterproofed in accordance with the appendix of PPP-B-636. Each shipping container shall be closed and reinforced with flat steel strapping or tape banding in accordance with the appendix of the applicable container specification.

5.2.2 *Level B.* A quantity, as specified (see 6.2), of unit packages in accordance with 5.1.1 or 5.1.2, as applicable, of one type and class of inking pads shall be packed in a snug-fitting fiberboard shipping container conforming to class domestic, grade 275 of PPP-B-636. Each shipping container shall be closed in accordance with method II in the appendix of the container specification.

5.2.2.1 *Alternate containers.* When specified (see 6.2), level B shipping containers shall be fabricated from grade V3c or V3s fiberboard of PPP-B-636.

5.2.3 *Level C.* Inking pads, packaged as specified in 5.1, shall be packed to insure carrier acceptance and safe delivery at destination at the lowest transportation rate for such supplies. Containers shall be in accordance with rules or regulations of carriers applicable to the mode of transportation.

5.3 **Marking.**

5.3.1 *Civil agencies.* In addition to any special marking required by the contract or order (see 6.2), interior packages and shipping containers shall be marked in accordance with Fed. Std. No. 123.

5.3.2 *Military requirements.* In addition to any special marking required by the contract or order (see 6.2), interior packages and shipping containers shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 **Intended use.** The inking pad covered by this specification is intended for use in laundry power-operated marking machines. The 1-3/16-inch pad is used in the 6-character machine; the 1-13/16-inch pad is used in the 8- or 10-character machine, and the 3-1/8 and 3-1/2-inch pad is used in the 8-through 16-character machine.

6.2 **Ordering data.** Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

(*a*) Title, number, and date of this specification.

(*b*) Type and class required (see 1.2).

(*c*) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).

(*d*) Quantity of unit packages required in shipping containers (see 5.2.1 and 5.2.2).

(*e*) When weather-resistant grade V3c or V3s of PPP-B-636 fiberboard shipping containers are required for level B shipments (see 5.2.2.1).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:59Z
Check the source to verify that this is the current version before use.

(*f*) Additional marking when required (see 5.3.1 and 5.3.2).

6.3 **Level B packaging.** When level B packaging requirements are specified for civil agency procurements, the requirements in 5.1.1 shall apply.

MILITARY INTEREST

Custodians:
Army—GL
Navy—YD
Air Force—67

Review activity:

Navy—YD

User activities:

Navy—SA, MC
Air Force—67

Preparing activity:

Army—GL

CIVIL AGENCY INTEREST

GSA—FSS

Review and user information is current as of the date of this document. For future coordination of changes to this document, draft circulation should be based on the information in the current DODISS.
OO-I-520a

☆ U.S. GOVERNMENT PRINTING OFFICE: 1967—253333/266

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents referenced herein. Price 5 cents.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:59Z
Check the source to verify that this is the current version before use.

"to detach this form, cut along this line"

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 119-R004

INSTRUCTIONS

This sheet is to be filled out by personnel either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity.

SPECIFICATION

Inking Pad, Laundry, Marking Machine — 00-I-520a

ORGANIZATION	CITY AND STATE

CONTRACT NO.	QUANTITY OF ITEMS PROCURED	DOLLAR AMOUNT
		$

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO IF "YES", IN WHAT WAY?

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity)*	DATE

DD FORM 1 OCT 64 1426

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:59Z
Check the source to verify that this is the current version before use.