MIL-C-47246(MI)
AMENDMENT 1
11 May 1977

MILITARY SPECIFICATION

COATING, ABLATIVE, APPLICATION OF

This Amendment forms a part of Military Specification MIL-C-47246(MI) dated 26 July 1974.

Page 4, paragraph 3.3.6, subparagraph b. Delete entire paragraph and substitute:

"The two-component coating material (see MIL-C-47244) shall be mixed in accordance with the manufacturer instructions."

"NOTE: The application life of the mixed coating is as specified by the manufacturer. If the temperature is lowered, the application will be lengthened."

Page 4, paragraph 3.3.6, subparagraph c. Delete entire paragraph and substitute:

"Apply the coating over the primed area, as specified on the applicable engineering drawing, by troweling. Work the coating into small areas, exercising care to prevent voids and air pockets and to maintain the coating thickness compatible with the depth control strips installed and the form templates used. Heat may be applied to the coating material or tooling (see 3.1.3) to facilitate material flow and improve finish smoothness but care shall be taken to avoid excessive reduction of material application life (see 6.3). Open any existing air pockets and fill voids with additional coating material."

Page 3

Paragraph 3.2.2.5, line 1, delete: "mode" and substitute: "mold".

CUSTODIAN:
ARMY-MI

PREPARING ACTIVITY
ARMY-MI
PROJECT NO. 8030-A087

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T08:04Z
Check the source to verify that this is the current version before use.