METRIC

MIL-P-52108B(AV)
21 September 1994
SUPERSEDING
MIL-P-52108A(MR)
12 October 1965

MILITARY SPECIFICATION

PAINT, WATER EMULSION TYPE

(FOR STENCILING AND OBLITERATING)

This specification is approved for use within the USA Belvoir Research, Development, and Engineering Center, Department of the Army, and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers one type of water emulsion paint for stenciling, for obliterating markings, and for service color markings on wood and fiberboard containers.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications and standards. The following specifications and standards form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DoDISS) and supplement thereto, cited in the solicitation (see 6.2).

SPECIFICATIONS

FEDERAL

MMM-A-179	-	Adhesive: Paper Label.
PPP-P-1892	-	Paint, Varnish, Lacquer and Related Materials; Packaging, Packing and Marking of.

STANDARDS

FEDERAL

FED-STD-141	-	Paint, Varnish, Lacquer and Related Materials; Methods of Inspection, Sampling and Testing.
FED-STD-313	-	Material Safety Data, Transportation Data and Disposal Data for Hazardous Materials Furnished to Government Activities.
FED-STD-595	-	Colors Used in Government Procurement.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: US ARMY AVIATION & TROOP CMD, ATTN AMSAT R EDS, ST LOUIS MO 63120-1798 by using the Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 8010

DISTRIBUTION STATEMENT A. Approved for public release, distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:07Z
Check the source to verify that this is the current version before use.

(Unless otherwise indicated, copies of federal and military specifications, standards, and handbooks are available from: STDZN DCMNT ORDER DESK, BLDG 4D, 700 ROBBINS AVE, PHILADELPHIA PA 19111-5094.)

2.2 Non-Government publications. The following document(s) form a part of this document to the extent specified herein. Unless otherwise specified, the issues of the documents which are DoD adopted are those listed in the issue of the DoDISS cited in the solicitation. Unless otherwise specified, the issues of documents not listed in the DoDISS are the issues of the documents cited in the solicitation (see 6.2).

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

D 93 - Flash Point by Pensky-Martens Closed Tester, Test Method for.
D 358 - Wood to Be Used as Panels in Weathering Tests of Coatings, Specification for.
D 562 - Consistency of Paints Using the Stormer Viscometer, Test Method for.
D 659 - Evaluating Degree of Chalking of Exterior Paint.
D 1005 - Measurement of Dry-Film Thickness of Organic Coatings Using Micrometers, Test Method for.
D 1200 - Viscosity of Paints, Varnishes, and Lacquers by Ford Viscosity Cup, Test Method for.
D 1729 - Visual Evaluation of Color Differences of Opaque Materials, Practice for.
D 1849 - Package Stability of Paint.
D 2369 - Volatile Content of Coatings, Test Method for.
D 2244 - Calculations of Color Differences from Instrumentally Measured Color Coordinates.
D 3335 - Low Concentrations of Lead, Cadmium, and Cobalt in Paint by Atomic Absorption Spectroscopy.
D 4214 - Evaluating Degree of Chalking of Exterior Paint Films, Method for.
D 4727 - Corrugated and Solid Fiberboard Sheet Stock (Container Grade) and Cut Shapes.
E 97 - 45-Deg. 0-Deg. Directional Reflectance Factor of Opaque Specimens by Broad-Band Filter Reflectometry, Test Method for.
G 23 - Operating Light- and Water-Exposure Apparatus (Carbon-Arc Type) for Exposure of Nonmetallic Materials, Practice for.
G 53 - Operating Light - and Water-Exposure Apparatus (Fluorescent UV - Condensation Type) for Exposure of Nonmetallic Materials.

(Application for copies should be addressed to: AMERCN SCTY FOR TEST & MTRLS, 1916 RACE STRET, PHILADELPHIA PA 19103.)

(Non-Government standards and other publications are normally available from the organizations that prepare or distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 First article. Unless otherwise specified (see 6.2), a sample shall be subjected to first article inspection (see 6.3) in accordance with 4.3.1.

3.2 Color. The paint shall be supplied in the following colors of FED-STD-595 as specified in the contract or purchase order (see 6.2).

Sand - No. 30277	Black - No. 37038
Yellow - No. 33538	White - No. 37875

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:07Z
Check the source to verify that this is the current version before use.

When tested as specified in 4.4.7, the color shall acceptably match the standard color chip in FED-STD-595.

3.3 Composition.

3.3.1 Pigment. The paint shall be formulated with select prime and extender pigments to attain the correct color, opacity, body, and adequate pigment volume concentration. The pigment shall not contain any lead, hexavalent chromium compounds, mercury, or arsenic.

3.3.2 Vehicle. The vehicle shall be any water emulsion polymer, which in combination with required additives and preservatives, will provide a stable and functional base for the paint. Coalescing and flow promoting agent(s) shall be such, as not to lower the flash point.

3.4 Quantitative requirements. The paint shall conform to the quantitative requirements of table I when tested as specified in 4.4.

TABLE I. Quantitative requirements.

Characteristics	Requirements	
	Minimum	Maximum
Total solids, percent by weight of paint	45	--
Pigment, percent by weight of paint	--	35
60° specular gloss	--	10
Viscosity (package), Krebs Stormer shearing rate 200 rpm	150	200
Grams Equivalent Kreb units (KU) Viscosity (reduced), No. 4 Ford cup, seconds	 72 15	 82 40
Drying time, air drying Dust free, minutes Dru through, minutes	 -- --	 15 60
Hiding power (contrast ratio) Sand - No. 30277; Black - No. 37875 Yellow - No. 30277; Black - No. 37038	 0.99 0.90	 -- --
Flash point, closed cup °C (°F)	82 (180)	--
Coarse particles and skins (retained on a 325 sieve) percent by weight of pigment	--	1.0
Directional reflectance, white only, percent	80	--
Lead content, percent	--	0.06
Hexavalent chromium	None detected	

3.5 Qualitative requirements.

3.5.1 Condition in container. When tested as specified in 4.4.8, the paint shall be free from grit, seediness, skins, or livering in a freshly opened container and shall show no more pigment settling or caking than can be easily and completely reincorporated to a smooth homogeneous state. In the freshly opened package, there shall be no rusting of the container, and no offensive, disagreeable or putrid odor.

3.5.2 Storage stability. When tested as specified in 4.4.9, the paint shall show no skinning, livering, curdling, tough gummy sediment, or hard

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:07Z
Check the source to verify that this is the current version before use.

3.5.2 Storage stability. When tested as specified in 4.4.9, the paint shall show no skinning, livering, curdling, tough gummy sediment, or hard caking, and shall remix readily to a smooth and uniform consistency. There shall be no rusting of the container, and no offensive, disagreeable, or putrid odor shall develop.

3.5.3 Brushing properties. When tested as specified in 4.4.10, the paint shall brush satisfactorily in all respects and shall dry to a smooth uniform film free from seeds, runs, sags or streaks.

3.5.4 Spraying properties. When tested as specified in 4.4.11, the paint shall spray satisfactorily in all respects and shall show no running, sagging, streaking or blushing. The dried film shall show no dusting, mottling, or color separation and shall present a smooth finish free from seediness.

3.5.5 Freeze-thaw stability. When tested as specified in 4.4.12, the paint shall show no coagulation, flocculation, discoloration and shall not increase or decrease by more than 10 KU from its original viscosity.

3.5.6 Skinning. When tested as specified in 4.4.13, there shall be no evidence of lumps or undispersed skin particles.

3.5.7 Compatibility with label adhesive. Panels prepared and tested as specified in 4.4.14 shall show no deterioration of the paint and no streaking of the paint over the label. The label shall adhere tightly after drying for one week.

3.5.8 Recoating. A film of paint, prepared and tested as specified in 4.4.15, shall not blister, wrinkle or show other evidence of lifting of the previous coat.

3.5.9 Accelerated weathering. When tested as specified in 4.4.16, the paint shall show no checking, peeling or flaking, and no more than slight chalking. Color after exposure shall not show a change of more than 3.0 CIELAB units.

3.5.10 Weather resistance. A film of paint, prepared and tested as specified in 4.4.17, shall exhibit no checking or flaking, and no more than a chalking. Color after exposure shall not show a change of more than 3.0 CIELAB units.

3.6 Hazardous material. The contractor shall comply with the hazardous material requirements of FED-STD-313 (see 6.4).

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements (examinations and tests) as specified herein. Except as otherwise specified in the contract or purchase order, and unless disapproved by the Government the contractor's own or any other facilities suitable for the performance of the inspection requirements specified herein, may be used. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to ensure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items shall meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of ensuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling inspection, as part of manufacturing operations, is an acceptable practice to ascertain conformance to requirements, however, this does not authorize submission of known

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:07Z
Check the source to verify that this is the current version before use.

defective material, either indicated or actual, nor does it commit the Government to acceptance of defective material.

4.1.2 Hazardous material. Failure to meet the hazardous material requirements of FED-STD-313 shall be cause for rejection (see 3.6).

4.2 Sampling, inspection and testing. Unless otherwise specified, sampling, inspection and testing shall be in accordance with FED-STD-141, methods 1011, 1022, and 1031.

4.3 Classification of tests. Testing under this specification shall be for the following:

a. First article (4.3.1).
b. Acceptance of individual lots (see 4.3.2).

4.3.1 First article testing. First article testing shall consist of testing for all requirements specified in section 3 (see 6.3).

4.3.2 Acceptance testing. Acceptance testing shall normally consist of the following tests: total solids, condition in container, viscosity, 60 degree specular gloss, drying time, fineness of grind, and spraying properties as specified in sections 3 and 4.

4.4 Test methods.

4.4.1 Test conditions. Except as otherwise specified herein, the routine and referee testing conditions shall be in accordance with FED-STD-141.

4.4.2 Tests. The following tests shall be conducted in accordance with FED-STD-141 and as specified herein (see table II).

TABLE II. Index.

Item	ASTM Method	FED-STD-141 Method	Test Paragraph	Requirement Paragraph
Vehicle	--	--	4.4.3.1	Table I
Total solids	D 2369	--	--	Table I
Pigment content	--	--	4.4.3.2	Table I
Specular gloss	--	6101	--	Table I
Viscosity Packaged Reduced	 D 562 D 1200	 -- --	 4.4.4.1 4.4.4.2	 Table I Table I
Drying time Dust free Dry through	 -- --	 4061 4061	 4.4.5 4.4.5	 Table I Table I
Hiding power	--	4121	4.4.6	Table I
Flash point	D 93	--	--	Table I
Coarse particles and skins	--	4092	--	Table I
Directional reflectance	E 97	--	--	Table I
Color	--	4250	4.4.7	3.2
Condition in container	--	3011	4.4.8	3.5.1

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:07Z
Check the source to verify that this is the current version before use.

TABLE II. Index. - (continued)

Item	ASTM Method	FED-STD-141 Method	Test Paragraph	Requirement Paragraph
Storage stability	D 1849	--	4.4.9	3.5.2
Brushing properties	D 358	4321	4.4.10	3.5.3
Spraying properties	--	4331	4.4.11	3.5.4
Freeze-thaw stability	--	--	4.4.12	3.5.5
Skinning	--	--	4.4.13	3.5.6
Compatibility with label adhesive	--	--	4.4.14	3.5.7
Recoating	--	--	4.4.15	3.5.8
Accelerated weathering	G 23, D 4214	6122	4.4.16	3.5.9
Weather resistance		--	4.4.17	3.5.10
Lead content	D 3335	--	4.4.18	Table I
Hexavalent chromium content	--	--	4.4.19	Table I

4.4.3 Composition.

4.4.3.1 Vehicle. Weigh approximately a 0.5 to 1.0 gram sample into a centrifuge tube. After centrifuging, pour off the supernatant liquid into an aluminum foil pan, being careful not to transfer any solid material to the pan. Heat in a forced air oven at 105 °C for one hour. Cool the sample and identify the type of resin from its infrared absorption spectrum. Identification is made by comparison to spectra obtained from known materials.

4.4.3.2 Pigment content. Weigh accurately, a 0.5 to 1.0 gram sample into an aluminum foil pan (60 mm diameter) and allow to dry in air, without heat for 24 hours. Strip the entire film from the pan and transfer quantitatively to a 125-mL glass-stopper Erlenmeyer flask. Add 25 mL toluene, attach an air condenser and reflux for one hour. Cool to room temperature, insert a magnetic stirring bar and stir vigorously for 15 minutes. Remove the stirring bar, washing with toluene and transfer the sample to a weighed 40 mL or 50 mL centrifuge tube, using toluene for a quantitative transfer. After centrifuging, pour off the supernatant liquid, and add ethyl acetate, stir, centrifuge and decant as before. Repeat a third time, using ethyl acetate as solvent. Finally, pour off all excess solvent and dry the tube in the oven at 105 °C, cool and weigh. Calculate the percent pigment.

4.4.4 Viscosity.

4.4.4.1 Package. Determine package viscosity in accordance with ASTM D 562, except hand stir the paint 300 stirs in 2 minutes with a square-ended spatula having a blade approximately 5 inches in length and 13/16 inches in width. Immediately after stirring, measure the viscosity and check for compliance with table I.

4.4.4.2 Reduced. Reduce eight parts by volume of packaged paint with a maximum of two parts by volume of water. Stir as specified in 4.4.4.1 and test in accordance with ASTM D 1200 for compliance with table I.

4.4.5 Drying time. Determine drying time in accordance with FED-STD-141, method 4061 under referee conditions.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:07Z
Check the source to verify that this is the current version before use.

4.4.6 Hiding power (contrast ratio). Determine the contrast ratio in accordance with FED-STD-141, method 4121, except measure the dry film thickness in accordance with ASTM D 1005, procedure A. Use a film applicator that will deposit a 3 inch wide film with a dry film thickness of 25 ±2 µm (0.001 ±0.0001 inch) and air dry for 48 hours. Determine the reflectance and verify the film thickness in the area in which the reflectance was measured. Calculate the contrast ratio and check for compliance with table I.

4.4.7 Color. The color at complete hide shall match the color specified when tested in accordance with ASTM D 1729.

4.4.8 Condition in container. Determine package condition for acceptance testing in accordance with FED-STD-141, method 3011. For first article testing, determine pigment settling or caking as follows: Proceed as specified in FED-STD-141, method 3011, but do not stir. Reseal and then agitate the can for 5 minutes on a paint shaker 1/. Let stand for 5 minutes and examine for gel structures, excessive air bubbles, and undispersed pigment particles. Check for compliance with 3.5.1.

4.4.9 Package stability. Expose the paint in accordance with ASTM D 1849. At the end of the 4th week exposure to 52 °C (125 °F) examine content for compliance with the requirements of 3.5.2.

4.4.10 Brushing properties. Using a 3.8 cm (1-1/2 inch) brush, apply the paint as received or reduced with not more than 5 percent by volume of water, on a 13 x 30.5 cm (5 by 12 inch) Western white pine panel selected in accordance with ASTM D 358 and observe for brushing properties in accordance with FED-STD-141, method 4321 for compliance with 3.5.3.

4.4.11 Spraying properties. The paint, thinned with not more than 20 percent by volume of water and sprayed on a 7 x 23 cm (2-3/4 by 9 inch) wood panel of the type specified in 4.4.10 to give a dry film thickness between 45-50 microns (0.0018 and 0.0020 inch), shall be observed for spraying properties in accordance with FED-STD-141, method 4331 and observed for compliance with 3.5.4. The distance between the gun and the panel shall be 20-25 cm (8-10 inches).

4.4.12 Freeze-thaw stability. Place 420 mL (14 fluid ounces) of the paint in a one pint multiple friction top can, determine its viscosity as specified in 4.4.4.1, seal and then subject the paint to the following cycle:

16 hours at - 40 °C (-40 °F)
8 hours at 60 °C (+140 °F)

This cycle shall be repeated four times. At the conclusion of the test allow the paint to return to room temperature and then examine for compliance with 3.5.5.

4.4.13 Skinning. Place 70 milliliters of paint in a 100 milliliter Griffin beaker with a diameter of approximately 5 cm (2 inches) and leave uncovered and undisturbed for a period of one hour under referee conditions. The beaker shall be placed in an area that is free from drafts or direct rays of the sun. At the end of the test period, stir the paint thoroughly and examine for compliance with 3.5.6.

4.4.14 Compatibility with label adhesive. Spray a film of the paint on a panel as specified in 4.4.11 and air dry one hour. Brush a thin continuous film of adhesive conforming to MMM-A-179 over the paint and place a paper label, 6.35 x 14.0 cm (2-1/2 x 5-1/2 inches) of approximately 180 N (40 pound

---

1/ An apparatus of this type powered by a 1/4 hp motor, operates at a rate of 1350 shakes per minute is manufactured by Red Devil Tools, Irvington, NJ or equal.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:07Z
Check the source to verify that this is the current version before use.

[17 x 22 - 1000]) bond immediately over the surface. Then brush a thin continuous film of the adhesive over the label and examine for compliance with 3.5.7. Air dry one week and observe for compliance with 3.5.7.

4.4.15 Recoating. Prepare a film of paint as specified in 4.4.10 and air dry for one hour. At the end of this period, apply another brush coat of the paint and examine for compliance with 3.5.8.

4.4.16 Accelerated weathering. Spray test specimens of the paint as specified in 4.4.11 on 7 x 23 cm (2-3/4 by 9 inch) panels of Western white pine and V3c fiberboard conforming to ASTM D 48727 and air dry 24 hours. Measure color in accordance with illuminant D_{65}. Weather the panel for 200 hours in accordance with ASTM G 53 using UV-A-351/302 lamps and a cycle of 8 hours UV exposure at 60 °C (140 °F) followed by 4 hours of condensation at 50°C (122°F). Examine the exposed panels for chalking in accordance with ASTM D 659 using a black velvet cloth. Measure color in accordance with ASTM D 2244 using illuminant D_{65} and calculate color difference. Check accelerated weathering test results for compliance with 3.5.9.

4.4.17 Weather resistance. Prepare test specimens of the paint on two 13 x 30.5 cm (5 by 12 inch) Western white pine panels as specified in 4.4.16 and place on outdoor exposure for 12 months at an angle of 45° south in a climate similar to that of Washington, DC. At the conclusion of the exposure period, inspect the panels for compliance with 3.5.10. Determine chalking as specified in 4.4.16 and examine for color change.

4.4.18 Lead content. Determine lead content in accordance with ASTM D 3335 or by the use of an X-ray fluorescence spectrometer capable of determining lead at a minimum range of 0.03 through 1.0 percent mass of nonvolatile with an accuracy within ±5.0 percent. The X-ray method shall be used in case of dispute.

4.4.19 Hexavalent chromium content. Add 5 mL of 25 percent aqueous potassium hydroxide to 1/2 gram extracted pigment in a centrifuge tube. Agitate by shaking and centrifuge. A yellow color in the supernatant liquid indicates the presence of hexavalent chromium.

4.5 Inspection of packaging. The sampling and inspection of the preservation, packing, and container marking shall be in accordance with the requirements of PPP-P-1892 and for compliance with section 5 herein.

5. PACKAGING

5.1 Packaging. The paint shall be delivered in 1 quart or 1 gallon multiple friction top containers, in 5 gallon lug covered steel pails or in 55 gallon steel drums as specified (see 6.2). The paint shall be packaged in level A or C; packed level A, B, or C as specified (see 6.2) in accordance with PPP-P-1892.

5.2 Marking. The containers shall be marked in accordance with PPP-P-1892.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. The paint covered by this specification is intended for markings and for obliterating markings on wood and fiberboard containers. The material is non-flammable and can be safely stored indoors. It may be used in lieu of TT-E-489 (yellow and white). The paint cannot be used in lieu of MIL-P-13983, Paint, Temporary Lustreless, Gasoline Removable except that the paint can be used to stencil over a painted metal surface.

6.2 Acquisition requirements. Acquisition documents should specify the following:

Source: https://assist.dla.mil -- Downloaded: 202610-22T21:07Z
Check the source to verify that this is the current version before use.

a. Title, number, and date of the specification.
b. Issue of DoDISS to be cited in the solicitation, and if required, the specific issue of individual documents referenced (see 2.1.1).
c. Color and color number (see 3.2).
d. Level of packaging and packing required (see 5.1).
e. Size of container required (see 5.1).
f. The paint covered by this specification should be purchased by volume, the unit being one US liquid gallon of 231 cubic inches at 60 °F (15.6 °C).

6.3 First article. When a first article inspection is required, the item(s) should be a first production lot. The first article should consist of two quarts. The contracting officer should include specific instructions in acquisition documents regarding arrangements for examinations, approval of the first article test results and disposition of the first article.

6.4 Material Safety Data Sheets. Contracting officers should identify those activities requiring copies of completed Material Safety Data Sheets prepared in accordance with FED-STD-313. The pertinent Government mailing addressed for submission of data are listed in appendix B of FED-STD-313.

6.5 Disposability. Residual quantities of paint and paint containers shall be disposed of in a manner consistent with applicable environmental statutes and ordinances.

6.6 Subject term (key word) listing.

Marking
Non-flammable

6.7 Changes from previous issue. Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extensiveness of the changes.

Custodian:
Army - AV

Preparing activity:
Army - AV

Agent - ME
Project 8010-A445

Review activities:
Army - EA, SM

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:07Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

RECOMMEND A CHANGE:	1. DOCUMENT NUMBER MIL-P-52108B(AV)	2. DOCUMENT DATE (YYMMDD) 940921

3. DOCUMENT TITLE
PAINT, WATER EMULSION TYPE (FOR STENCILING AND OBLITERATING)

4. NATURE OF CHANGE (Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle Initial)	b. ORGANIZATION	
c. ADDRESS (Include Zip Code)	d. TELEPHONE (Include Area Code) (1) Commercial (if applicable) (2) DSN	7. DATE SUBMITTED

8. PREPARING ACTIVITY

a. NAME	b. TELEPHONE (Include Area Code) (1) Commercial (2) DSN
c. ADDRESS (Include Zip Code) US ARMY AVIATION & TROOP CMD ATTN AMSAT-R-EDS 4300 GOODFELLOW BOULEVARD ST LOUIS MO 63120-1798	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT: DEFNS QLTY & STDZN OFC 5203 LEESBURG PIKE STE 1403 FLS CHURCH VA 22041-3466 Telephone (703) 756-2340 DSN 289-2340

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:07Z
Check the source to verify that this is the current version before use.

Flash point, °F 99 --- 100