INCH-POUND

MIL-DTL-32416
w/AMENDMENT 2
13 April 2018
SUPERSEDING
MIL-DTL-32416
W/AMENDMENT 1
10 May 2016

DETAIL SPECIFICATION

BANDOLEER: 5.56 MILLIMETER CARTRIDGES – M8A1

This specification is approved for use by all Departments and Agencies of the Department of Defense within the distribution limitations noted at the bottom of the page.

1. SCOPE

1.1 Scope. This specification covers one type of bandoleer, the M8A1 bandoleer, intended to hold 5.56mm ammunition for use in M16 rifle and M4 carbine.

2. APPLICABLE DOCUMENTS

2.1 General. The documents listed in this section are specified in sections 3 and 4 of this standard. This section does not include documents cited in other sections of this specification or recommended for additional information or as examples. While every effort has been made to ensure the completeness of this list, document users are cautioned that they must meet all specified requirements of documents cited in sections 3 and 4 of this specification, whether or not they are listed.

Comments, suggestions, or questions on this document should be addressed to: Commander, U.S. Army ARDEC, ATTN: RDAR-EIQ-SA, Picatinny Arsenal, New Jersey 07806-5000 or e-mailed to usarmy.pica.ardec.list.ardec-stdzn-branch@mail.mil. Since contact information can change, you may want to verify the currency of this information using ASSIST Online database at https://assist.dla.mil/.

AMSC N/A FSC 1305

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

2.2 Government documents.

2.2.1 Specifications, standards and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the solicitation or contract.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T06:18Z
Check the source to verify that this is the current version before use.

DEPARTMENT OF DEFENSE STANDARDS

MIL-STD-1916	-	DOD Preferred Methods for Acceptance of Product
MIL-W-63150	-	Weapons and Support Materiel Standard Quality Assurance Provisions for

(Copies of this document are available online at http://quicksearch.dla.mil/ or from the Standardization Document Order Desk, 700 Robbins Avenue, Building 4D, Philadelphia, PA 19111-5094.)

2.2.2 Other Government documents, drawings and publications. The following other Government documents, drawings and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

U.S. ARMY ARDEC DRAWINGS

13032627	-	Bandoleer, M8A1

(Copies of these drawings may be requested online at pica.drawing.request@conus.army.mil or from US Army ARDEC, ATTN: RDAR-AIS-T, Picatinny Arsenal, NJ 07806-5000)

2.3 Non-Government publications. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation.

AMERICAN SOCIETY FOR TESTING AND MATERIALS INTERNATIONAL (ASTM)

ASTM-D-1683	-	Failure in Sewn Seams of Woven Fabrics
ASTM-D-6193	-	Standard Practice for Stitches and Seams

(Copies of ASTM standards maybe ordered online at http://www.astm.org or from ASTM international, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959).

2.4 Order of precedence. Unless otherwise noted herein or in the contract, in the event of a conflict between the text of this document and references cited herein, the text takes precedence. Nothing in this document however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 General. The bandoleer shall comply with the requirements specified on Drawing 13032627 for which an examination or test is specified in 4.1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T06:18Z
Check the source to verify that this is the current version before use.

3.2 First article. When specified (see 6.2), a sample shall be subjected to first article inspection in accordance with 4.3.

3.3 Conformance inspection. Samples of the bandoleer shall be subjected to conformance inspection in accordance with 4.4.

3.4 Ultrasonic bag mid-seam weld.

3.4.1 Mid-seam finish. The finished seam shall offer a neat, even appearance, and with no holes evident when the seam is held up to a light source.

3.4.2 Mid-seam strength. The seam shall possess a minimum of 20 pounds bond strength (see 4.5.1.1).

3.5 Ultrasonic strap to bag (side) seam weld.

3.5.1 Side seam finish. The finished seam shall offer a neat, even appearance, and with no holes evident when the seam is held up to a light source.

3.5.2. Side seam strength. The strap to bag seam shall possess a minimum of 90 pounds bond strength (see 4.5.2.1).

3.6 Marking. Marking shall be clear and legible in accordance with drawing 13032627.

3.7 Workmanship. The bandoleer shall be free of rips, tears, irregular welds/sewn seams, and other defects.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T06:18Z
Check the source to verify that this is the current version before use.

4. VERIFICATION

TABLE I. Requirement/verification cross reference matrix.

Method of Verification	Classes of Verification
1 – Analysis 2 – Demonstration 3 – Examination 4 – Test	A – First article B – Conformance

Section 3 Requirement	Description	Verification Methods				Verification Class		Section 4 Verification Method
		1	2	3	4	A	B	
3.1	General			X	X	X	X	4.1
3.2	First article			X	X	X		4.3
3.3	Conformance inspection			X	X		X	4.4
3.4.1	Mid-seam finish (Ultrasonic bag)				X	X	X	TABLE IV
3.4.2	Mid-seam strength (Ultrasonic bag)				X	X	X	4.5.1
3.5.1	Side seam finish (Ultrasonic strap to bag)				X	X	X	TABLE IV
3.5.2	Side seam strength (Ultrasonic strap to bag)				X	X	X	4.5.2
3.6	Marking			X		X	X	TABLE IV
3.7	Workmanship			X		X	X	4.5.3

4.1 Classification of inspection. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3)
b. Conformance inspection (see 4.4)

4.2 Inspection condition. Unless otherwise specified, all inspections shall be performed in accordance with the test conditions specified in section 4.5.

4.3 First article. When specified, a sample shall be subjected to first article verification in accordance with TABLE II and III.

4.3.1 Initial production sample. At the beginning of regular production, a sample shall be submitted for testing in accordance with contract requirements. The sample shall be manufactured using the same material, equipment, processes and procedures as will be used for

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T06:18Z
Check the source to verify that this is the current version before use.

regular production. All parts and materials shall be the same as used for regular production and shall be obtained from the same sources of supply.

4.3.2 First article quantity. The first article sample shall consist of the following items in sample quantities as indicated in TABLE II.

TABLE II. First article quantity.

Part description	Drawing	Quantity
Bandoleer, M8A1	13032627	50

4.3.3 First article inspection/rejection. If any assembly, component or test specimen fails to comply with any of the first article requirements in TABLE II and TABLE III, the first article shall be rejected (see 6.5).

TABLE III. First article tests and inspection.

Examination or test	Requirement Paragraph	Quantity	Inspection Method/ Paragraph Reference
Examination for defects	3.1	50	TABLE IV
Ultrasonic bag mid-seam weld	3.4	50	4.5.1
Ultrasonic strap to bag (side) seam weld	3.5	50	4.5.2

4.4 Conformance inspection. Conformance inspection shall be conducted on a sample lot in accordance with TABLE IV.

4.4.1 Inspection lot formation. Lot formation shall be in accordance with paragraph 4.2.4 of MIL-STD-1916. Unless otherwise specified, component parts shall be homogenous.

4.4.2 Classification of characteristics. Definitions of Critical, Major and Minor shall be in accordance with MIL-STD-1916.

4.4.3 Conformance inspection quantity. The conformance inspection sample shall consist of the following items in sample quantities as indicated in TABLE IV.

4.4.4 Conformance rejection. If any assembly, component or test specimen fails to comply with any of the conformance inspection requirements in TABLE IV, the lot shall be rejected.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T06:18Z
Check the source to verify that this is the current version before use.

TABLE IV. Conformance tests and inspection.

Classification	Examination or Test	Conformance Criteria	Requirement Paragraph	Inspection Method Reference
Critical	None defined			
Major				
101	Improper stitch type	Level IV	3.1	Visual
102	Skipped, broken or omitted stitching greater than 1/4 inch in length	Level IV	3.1	Gage
103	Rips or tears	Level IV	3.7	Visual
104	Missing back tack (if Type 301 stitched)	Level IV	3.1	Visual
105	Width of pockets	Level III	3.1	Gage
106	Depth of pockets	Level III	3.1	Gage
107	Flap Length	Level III	3.1	Gage
108	Pocket overlap	Level III	3.1	Gage
109	Ultrasonic bonded seam: Individual bond point equal to 1/16 ± 1/32 Spacing equal to 1/4 ± 1/32	Level III	3.1	Gage
110	Ultrasonic strap seam is not double welded	Level III	3.1	Visual
111	Mid-seam holes	Level III	3.4.1	Visual
112	Mid-seam strength	3*	3.4.2	Gage
113	Side seam holes	Level III	3.5.1	Visual
114	Side seam strength	3*	3.5.2	Gage

* Sample size of 3 at the end of each production lot accept on 0 reject on 1

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T06:18Z
Check the source to verify that this is the current version before use.

TABLE IV. Conformance tests and inspection- Continued.

Classification	Examination or Test	Conformance Criteria	Requirement Paragraph	Inspection Method Reference
Minor				
201	Twisted strap	Level II	3.3	Visual
202	Missing back tack (if Type 301 stitched)	Level II	3.3	Visual
203	Insufficient or excessive stitching per inch	Level II	3.3	Gage
204	Missing identification	Level II	3.3	Visual
205	Stain or soil greater than 1/2 inch	Level II	3.3	Gage
206	Strap Intersection Location	Level II	3.3	Gage
207	Length of strap (as assembled)	Level II	3.3	Gage
208	Length of stitching runoff (tails)	Level II	3.3	Gage
209	Marking	Level II	3.3	Visual
210	Workmanship	Level II	3.3	4.5.3

4.5 Test Methods

4.5.1 Evaluation of ultrasonic bag mid-seam weld. The specimens shall be prepared in accordance with 4.5.1.1 and subjected to the seam strength test. The ultrasonic machine shall be properly set when the specimens with the same machine setting have minimum peak bag seam strength of 20 pounds. The test shall be run at the end of each production lot.

4.5.1.1 Bag Mid-Seam Strength test preparation. The 3 mid-seam specimens shall be prepared to appropriate machine settings in order to achieve maximum seam strength. Test as follows:

a. Use bandoleer bag assembly per Drawing 13032627.

b. Set the ultrasonic machine with proper weld time, pressure and frequency to longitudinally bond a prototype bag sample representative of initial and ongoing production.

c. Cut in between mid-point of each of 4 pockets with mid-seams in middle.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T06:18Z
Check the source to verify that this is the current version before use.

d. Place cut strip in horizontal position with seam between grips. In top grip take the top layer of fabric and insert into grip face and tighten. In bottom grip take the bottom layer of fabric and insert into grip and tighten. Test per ASTM –D-1683 and repeat procedure for remaining 2 seams. Total of 6 seams required to assure proper ultrasonic machine settings.

e. Each seam shall possess peak bond strength no less than 20 lbs. Note that both layers of material shall not be in grips since test is to determine bond strength between layers of material and not base material.

f. As an alternate test method, a calibrated spring scale with the capability to detect a minimum of 20 pounds may be used. The specimen shall be pulled down in a smooth, even manner as not to jerk the spring scale.

4.5.2 Preproduction evaluation of ultrasonic strap to bag (side) seam weld. The specimens shall be prepared in accordance with 4.5.2.1 and subjected to the strap to bag seam strength test. The ultrasonic machine shall be properly set when the specimens with the same machine setting have minimum peak strap to bag seam strength of 90 pounds. The test shall be run at the end of each production lot.

4.5.2.1 Strap to Bag (Side) Seam Strength test preparation. The 2 side-seam specimens shall be prepared to appropriate machine settings in order to achieve maximum seam strength. Test as follows:

a. Use bandoleer strap assembly per Drawing 13032627.

b. Set the ultrasonic machine with proper weld time, pressure and frequency to longitudinally bond a prototype bag sample representative of initial and ongoing production.

c. Cut in between mid-point of each side seam and first mid-point seam to extract the “strap to bag” test specimens.

d. Place cut strip side seam in horizontal position with seam between grips. Set strap into top grip face at appropriate degree angle between grips and tighten. Place double layer nonwoven body bag material into lower grip faces being careful not to include any webbing and tighten. Test per ASTM-D-1683 and repeat procedure to determine “strap to bag” strengths for total of 4, 60 degree and 90 degree angle settings within grips.

e. Secure strap webbing vertical to the grips, vary angle of grip on bag per below.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T06:18Z
Check the source to verify that this is the current version before use.

i. 90 lbs (min) tested IAW ASTM-D-1683, except use 2 inch wide grips on all jaw sets at 3 inches apart at speed of 12 in/ min.(pull direction 60° from seam, parallel to strap angle)
ii. 90 lbs (min) tested IAW ASTM-D-1683 (pull direction 90° from seam)

4.5.3 Workmanship. The attachments shall pass visual inspections. Workmanship shall be in accordance with the workmanship requirements paragraph 3.6.9 of MIL-W-63150.

5. PACKAGING

5.1 Packaging. For acquisition purposes, the packaging requirements shall be as specified in the contract or order (see 6.2). When packaging of materiel is to be performed by DOD or in-house contractor personnel, these personnel need to contact the responsible packaging activity to ascertain packaging requirements. Packaging requirements are maintained by the Inventory Control Point's packaging activity within the Military Service or Defense Agency, or within the military service's system commands. Packaging data retrieval is available from the managing Military Department's or Defense Agency's automated packaging files, CD-ROM products, or by contacting the responsible packaging activity.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory).

6.1 Intended use for Bandoleer, M8A1. The bandoleer M8A1 is intended to hold 5.56mm ammunition for use in M16 rifle and M4 carbine.

6.2 Acquisition requirements. Acquisition documents should specify the following:

a. Title, number, and date of this specification.
b. Requirements for submission of first article sample.
c. Type and level of packing for the item.
d. Provision for submission of Inspection Equipment Designs (See 6.3).
e. Provision for submission of detailed inspection plan for the Bandoleer (See 6.6).
f. Provisions for submission of acceptance inspection results for each lot of the Bandoleer M8A1, presented to the Government (See 6.5).

6.3 Submission of inspection equipment designs for approval. Submit equipment designs as required to Commander, ARDEC, ATTN: RDAR-QEM-D, Picatinny Arsenal, NJ 07806-5000. Request letter of submittal should state contractor, contract number, specification number, item nomenclature and classification of defects or tests. This address will be specified on the Contract Data Requirements List in the contract.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T06:18Z
Check the source to verify that this is the current version before use.

6.4 Submission of test data. In addition to the normal distribution of records, when the Bandoleer is procured, one (1) copy of test data for each lot should be forwarded to: Commander, ARDEC, ATTN: RDAR-QEM-D, Picatinny Arsenal, NJ 07806-5000.

6.5 Submissions of detailed inspection plan for review. The detailed inspection plan for the Bandoleer should be submitted to the responsible U.S. Government quality assurance element.

6.6 Submission of alternative quality conformance provisions. Unless otherwise specified in the contract, proposed alternative quality conformance provisions should be submitted by the contractor for evaluation by the technical activity responsible for the preparation of this specification.

6.7 Shipping. When Bandoleers from more than one lot are shipped at one time, each lot should be kept separate and the division between lots clearly indicated to prevent mixing of the lots in transit. Bandoleers should be shipped as specified in the contract or order. Marking for shipment should be in accordance with MIL-STD-129.

6.8 Subject term (key word) listing.

Ammunition
Rifle
Machine gun

6.9 Changes Incorporated. MIL-DTL-32416(2) incorporates Engineering Change Proposal R18K2003.

6.10 Amendment Notations. The margins of this specification are marked with vertical lines to indicate where modifications from this amendment were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T06:18Z
Check the source to verify that this is the current version before use.

CONCLUDING MATERIAL

Custodians:
Army – AR
Navy – OS

Preparing activity:
Army - AR
(Project 1305-2018-061)

Review Activities:
Army – MR
Navy – AS, MC, SH

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T06:18Z
Check the source to verify that this is the current version before use.