INCH-POUND

MIL-PRF-32433

11 December 2012

PERFORMANCE SPECIFICATION

BLANKET, WASHABLE, FLAME RESISTANT, SHIPBOARD

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers washable, flame resistant shipboard blankets for use aboard U.S. Navy vessels including surface ships and submarines.

1.2 Classification. The blankets covered by this specification are of the following types and classes as specified (see 6.2).

1.2.1 Types. The types of blanket construction are as follows:

Type I - Woven construction

Type II - Knit construction

Type III - Nonwoven construction

Type IV - Multi-component

1.2.2 Classes. The classes of blankets are as follows:

Class A - 100 percent wool

Class B - Wool/other fibers blend

Class C - Other fibers

Comments, suggestions, or questions on this document should be addressed to: Commander, Naval Sea Systems Command, ATTN: SEA 05S, 1333 Isaac Hull Avenue, SE, Stop 5160, Washington Navy Yard DC 20376-5160 or emailed to CommandStandards@navy.mil, with the subject line "Document Comment". Since contact information can change, you may want to verify the currency of this address information using the ASSIST Online database at https://assist.dla.mil.

AMSC N/A FSC 7210

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T06:20Z
Check the source to verify that this is the current version before use.

1.3 Part or identifying number (PIN). PINs to be used for blankets acquired to this specification are created as follows:

M	**32433**	**-**	**X**	**X**
Prefix for Military Specification	Specification Number		Type (see code below)	Class (see code below)

Type Code		Class Code	
Type	Code	Class	Code
I	A	A	1
II	B	B	2
III	C	C	3
IV	D		

Example: M32433 -A1
M32433 -D3

2. APPLICABLE DOCUMENTS

2.1 General. The documents listed in this section are specified in sections 3, 4, or 5 of this specification. This section does not include documents cited in other sections of this specification or recommended for additional information or as examples. While every effort has been made to ensure the completeness of this list, document users are cautioned that they must meet all specified requirements of documents cited in sections 3, 4, or 5 of this specification, whether or not they are listed.

2.2 Government documents.

2.2.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

DEPARTMENT OF DEFENSE SPECIFICATIONS

MIL-DTL-32075 - Label: For Clothing, Equipage, and Tentage, (General Use)

DEPARTMENT OF DEFENSE STANDARDS

MIL-STD-1623 - Fire Performance Requirements and Approved Specifications for Interior Finish Materials and Furnishings (Naval Shipboard Use)

(Copies of these documents are available online at https://assist.dla.mil/quicksearch/ or https://assist.dla.mil.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T06:20Z
Check the source to verify that this is the current version before use.

2.2.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

NAVAL SEA SYSTEMS COMMAND (NAVSEA) PUBLICATIONS

S9510-AB-ATM-010 - Nuclear Powered Submarine Atmosphere Control Manual

(Copies of the chapter titled "Material Control Program" are available from Commander, Naval Sea Systems Command, ATTN: SEA 05Z4, 1333 Isaac Hull Ave. SE Stop 5122, Washington Navy Yard, DC 20376-5122 or by email request to CommandStandards@navy.mil.)

U.S. DEPARTMENT OF AGRICULTURE

United States Standards for Grades of Wool

(Copies of this document are available from U.S. Department of Agriculture, Agricultural Marketing Service, 1400 Independence Avenue, S.W., Washington, DC 20250 or online at www.ams.usda.gov/AMSv1.0/.)

2.3 Non-Government publications. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

AMERICAN ASSOCIATION OF TEXTILE CHEMISTS AND COLORISTS (AATCC)

AATCC Evaluation Procedure 1	-	Gray Scale for Color Change
AATCC Evaluation Procedure 2	-	Gray Scale for Staining
AATCC Evaluation Procedure 8	-	AATCC 9-Step Chromatic Transference Scale
AATCC Test Method 8	-	Colorfastness to Crocking: AATCC Crockmeter Method
AATCC Evaluation Procedure 9	-	Visual Assessment of Color Difference of Textiles
AATCC Test Method 15	-	Colorfastness to Perspiration
AATCC Test Method 16	-	Colorfastness to Light
AATCC Test Method 20	-	Fiber Analysis: Qualitative
AATCC Test Method 20A		Fiber Analysis: Quantitative
AATCC Test Method 61	-	Colorfastness to Laundering: Accelerated
AATCC Test Method 81	-	pH of the Water-Extract from Wet Processed Textiles
AATCC Test Method 96	-	Dimensional Changes in Commercial Laundering of Fabric Except Wool

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T06:20Z
Check the source to verify that this is the current version before use.

AATCC Test Method 135	-	Dimensional Changes of Fabrics after Home Laundering

(Copies of these documents are available from AATCC, P.O. Box 12215, Research Triangle Park, NC 27709 or online at www.aatcc.org.)

ASTM INTERNATIONAL

ASTM C518	-	Standard Test Method for Steady-State Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus
ASTM D1424	-	Standard Test Method for Tearing Strength of Fabrics by Falling-Pendulum Type (Elmendorf) Apparatus
ASTM D3512/D3512M	-	Standard Test Method for Pilling Resistance and Other Related Surface Changes of Textile Fabrics: Random Tumble Pilling Tester
ASTM D3776/D3776M	-	Standard Test Methods for Mass Per Unit Area (Weight) of Fabric
ASTM D3787	-	Standard Test Method for Bursting Strength of Textiles-Constant-Rate-of-Traverse (CRT) Ball Burst Test
ASTM D5034	-	Standard Test Method for Breaking Strength and Elongation of Textile Fabrics (Grab Test)

(Copies of these documents are available from ASTM International, 100 Barr Harbor Dr., P.O. Box C700, West Conshohocken, PA 19428-2959 or online at www.astm.org.)

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION (ISO)

ISO/IEC 17025	-	General Requirements for the Competence of Testing and Calibration Laboratories

(Copies of this document are available from International Organization for Standardization (ISO), 1, ch. de la Voie-Creuse, Case postale 56 CH-1211 Geneva 20, Switzerland or online at www.iso.org.)

2.4 Order of precedence. Unless otherwise noted herein or in the contract, in the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 Qualification. Blankets furnished under this specification shall be products that are authorized by the qualifying activity for listing on the applicable qualified products list before contract award (see 4.2 and 6.3).

3.1.1 Identification characteristics. Identification characteristics shall be as specified in Table I to ensure that the proper type and class of blanket is identified prior to initiating qualification testing.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T06:20Z
Check the source to verify that this is the current version before use.

TABLE I. Identification characteristics.

Characteristic	Paragraph
Fabric properties: Chemical nature of each fabric treatment (e.g., fire retardant, shrinkage control, et al.)	3.2.1
Blanket type (Types I, II, and III)	3.2.2
Blanket class (Classes A, B, and C)	3.2.3
Fabric composition and content (fiber identification and for blends the percentage of each type fiber used)	3.3.4
Wool grade (Classes A and B only)	3.3.5
Fabric weight (oz/yd^2)	3.3.6

3.2 Materials.

3.2.1 Fabric properties. The fabric used for the construction of the blankets shall be capable of meeting all requirements specified herein. Where required, flame resistance and shrink resistance may be obtained by the use of durable treatments.

3.2.2 Blanket type. The base fabric used in the manufacture of blankets shall be woven, knitted, or otherwise constructed so as to meet the requirements of this specification. The front and back sides of the blanket shall have a raised, soft nap finish.

3.2.2.1 Type I. Type I blankets shall be constructed of woven (interlaced) fabric.

3.2.2.2 Type II. Type II blankets shall be constructed of knitted (interlooped) fabric.

3.2.2.3 Type III. Type III blankets shall be constructed of fabric that is neither woven (interlaced) nor knitted (interlooped).

3.2.2.4 Type IV. Type IV blankets are those consisting of multiple layers of different types of materials, which could include, but are not limited to, woven fabric, knit fabric, non-woven fibers (e.g., batting), foam, or other material forms.

3.2.3 Blanket class.

3.2.3.1 Class A. Class A blankets shall be composed of 100 percent wool.

3.2.3.2 Class B. Class B blankets shall be composed of a blend of wool combined with other fibers, either natural or synthetic.

3.2.3.3 Class C. Class C blankets shall be composed of 100 percent non-wool fibers, either natural or synthetic.

3.3 Performance requirements.

3.3.1 Construction.

3.3.1.1 Stitching. The blanket shall be finished on all four edges with either a lock stitch hem or an overedge stitch. The use of a chain stitch to hem the blanket shall be prohibited. When edges are finished with overedge stitching, a minimum ¼-inch bight shall be used with a minimum of 8 stitches per inch.

3.3.1.2 Finish. Both surfaces of the blanket shall have a raised, soft nap finish.

3.3.2 Dimensions. The finished dimensions of the blanket shall be 66 (+3, -1) inches wide by 84 (+3, -1) inches long. The dimensions shall be measured in accordance with 4.5.1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T06:20Z
Check the source to verify that this is the current version before use.

3.3.3 Color. The color of the finished blanket shall be Navy shade Gray 3119 or Olive Green 118 and shall match the standard sample (see 4.5.2, 6.2, and 6.5).

3.3.4 Fiber identification and content. Fiber identification and content shall be determined in accordance with 4.5.3. The fiber type shall be in accordance with the requirements of the applicable class. The percentages of the fabric content shall be as established in the identification characteristics as determined in accordance with 4.5.3.

3.3.5 Wool grade (classes A and B only). For blankets constructed of wool or a wool blend, the wool shall be of fleece or pulled sheep's wool or both, with an average grade of 64's with no more than 5 percent coarser than Grade 54's when measured in accordance with 4.5.4.

3.3.6 Fabric weight. Fabric weight shall be as required to meet the requirements of this specification and shall be determined in accordance with 4.5.5. Fabric weight for delivered blankets shall be within ±5 percent of the value determined during qualification. In no case shall fabric weight exceed 16 ounces per square yard (oz/yd^2).

3.3.7 pH. The pH shall be 4.0 to 10.0 when tested as specified in 4.5.6.

3.3.8 Dimensional stability. The maximum shrinkage or elongation in both the length and width directions shall be not greater than 10 percent when tested in accordance with 4.5.7.

3.3.9 Breaking strength (type I only). The breaking strength shall be 30 pounds minimum in both the warp and fill directions when tested in accordance with 4.5.8.

3.3.10 Tear strength (type I only). The tear strength shall be 8 pounds minimum in both the warp and fill directions when tested in accordance with 4.5.9.

3.3.11 Bursting strength (types II and III only). The bursting strength shall be not less than 50 pound force when tested in accordance with 4.5.10.

3.3.12 Pilling appearance. The pilling appearance shall be not less than Class 3.0 when rated in accordance with 4.5.11.

3.3.13 Colorfastness ratings.

3.3.13.1 Colorfastness resistance to light. The colorfastness rating for light (40 hours or 170 kilojoules) shall be equal to or better than Grade 4.0 when tested in accordance with 4.5.12.

3.3.13.2 Colorfastness resistance to laundering. The colorfastness rating for laundering (three laundering cycles) shall be equal to or better than Grade 4.0 when tested in accordance with 4.5.13.

3.3.13.3 Colorfastness resistance to perspiration. The colorfastness rating for perspiration shall be equal to or better than Grade 3.0 when tested in accordance with 4.5.14.

3.3.13.4 Colorfastness resistance to crocking. The colorfastness rating for crocking (wet and dry) shall be equal to or better than Grade 3.0 when tested in accordance with 4.5.15.

3.3.14 Fire performance. All blankets shall meet the fire performance requirements of MIL-STD-1623 when tested in accordance with 4.5.16 (see 6.2). To clarify the fire performance acceptance criteria as listed in MIL-STD-1623, note that any holing, flame penetration, or burnthrough in any of the plies shall specifically not be permitted. The thread shall not contribute to the flammability of the blanket.

3.3.15 Thermal insulation. The blanket shall yield a minimum Clo of 1.0 initially and after 10 laundering cycles when tested in accordance with 4.5.17.

3.3.16 Off-gassing. The finished blanket shall be tested for off-gassing in accordance with the requirements of 4.5.18. The Navy will review the results and assign a usage category. The required usage category is "Permitted" or "Limited" (see 4.5.18 and 6.6).

3.3.17 Toxicity. When evaluated in accordance with 4.5.19 (the HHA), the finished blanket shall have no adverse effect on the health of personnel when used for its intended purpose (see 4.5.19 and 6.7).

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T06:20Z
Check the source to verify that this is the current version before use.

3.4 Labels. Each blanket shall have a combination identification and care instruction label and bar code label. The identification and care labels may be combined into one label. The labels shall be in accordance with MIL-DTL-32075, Type V (see 3.5 and 4.5.20).

3.4.1 Identification and care label. The identification and care label shall be permanently attached to the blanket at one end. As a minimum, each blanket shall have a label showing the following information:

a. Manufacturer's identification (Example: M32433 -A1)

b. Contractor's name (Example: ABC Company)

c. Contract or order number (Example: SPM1C1-11-D-0000)

d. Date of manufacture (Example: 05-01-2011)

e. Item name and number (Example: Blanket, Shipboard, Type I, Class A, MIL-PRF-32433)

f. Fiber identification (Example: 100 percent wool)

g. Lot number (Example: Lot 10)

h. Care requirements (Example: Launder using Shipboard Formula III)

The lettering shall be permanent and legible and be a height that is easily readable. The instruction portion shall state the manufacturer's instructions for cleaning, which shall include the following information:

Launder using Shipboard Formula III.

The acquisition agency may have additional marking requirements (see 6.2).

3.4.2 Bar code label. Each blanket unit shall be individually labeled with a with a pressure sensitive bar-code label. The label shall have two individual bar codes; a 13-digit national stock number (NSN) and a 12-digit Universal Product Code (UPC). The UPC shall be that which has been assigned by the Government for the particular NSN, and the initials "UPC" shall appear beneath the code. The bar codes for NSN and UPC shall be a medium to high density, clearly legible and readable by scanner, and shall be located so that they are completely visible on the item when packaged as specified. Attachment of the label shall cause no damage to the blanket.

3.5 Workmanship. The finished blanket shall be clean and free from defects (cuts, holes, tears, stains, splicing, repairs, needle chews). The blanket shall not be composed of more than one piece (except for layers provided in 3.2.2.4). There shall be no run-off, raveled or incomplete overedge stitching, loose tension in stitching resulting in an insecure or unsightly edge, or edges not overedge or lock stitched. The blanket shall have the proper label and the text in the label shall not be smeared or otherwise illegible. No defects that affect appearance or serviceability shall be permitted (see 4.5.20).

4. VERIFICATION

4.1 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. Qualification inspection (see 4.2).

b. Conformance inspection (see 4.3).

4.1.1 Inspection conditions. Unless otherwise specified (see 6.2), all inspections shall be performed in accordance with the requirements of the tests specified in 4.2 through 4.4.

4.2 Qualification inspection. Qualification inspection shall consist of all the inspections and tests specified in Table II. Qualification tests shall be conducted at a laboratory acceptable to NAVSEA.

4.2.1 Retention of qualification. Periodic control inspection for the retention of qualification shall be made at 2-year intervals from the date of the originally approved qualification test for materials subjected to the fire performance test specified in 4.5.16.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T06:20Z
Check the source to verify that this is the current version before use.

TABLE II. Qualification inspection.

Characteristic	Requirement	Test
Construction	3.3.1	4.5.20
Dimensions	3.3.2	4.5.1
Color	3.3.3	4.5.2
Fiber identification and content	3.3.4	4.5.3
Wool grade (Classes A and B only)	3.3.5	4.5.4
Fabric weight	3.3.6	4.5.5
pH	3.3.7	4.5.6
Dimensional stability	3.3.8	4.5.7
Breaking strength	3.3.9	4.5.8
Tear strength	3.3.10	4.5.9
Bursting strength	3.3.11	4.5.10
Pilling appearance	3.3.12	4.5.11
Colorfastness resistance to light	3.3.13.1	4.5.12
Colorfastness resistance to laundering	3.3.13.2	4.5.13
Colorfastness resistance to perspiration	3.3.13.3	4.5.14
Colorfastness resistance to crocking	3.3.13.4	4.5.15
Fire performance	3.3.14	4.5.16
Thermal insulation	3.3.15	4.5.17
Off-gassing	3.3.16	4.5.18
Toxicity	3.3.17	4.5.19
Label and Workmanship	3.5	4.5.20

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T06:20Z
Check the source to verify that this is the current version before use.

4.3 Conformance inspection.

4.3.1 Inspection of end item. Inspections shall be in accordance with Table III.

TABLE III. Conformance inspection.

Characteristic	Requirement	Test
Construction	3.3.1	4.5.20
Dimensions	3.3.2	4.5.1
Color	3.3.3	4.5.2
Fiber identification and content	3.3.4	4.5.3
Wool grade (Classes A and B only)	3.3.5	4.5.4
Fabric weight	3.3.6	4.5.5
Breaking strength	3.3.9	4.5.8
Tear strength	3.3.10	4.5.9
Bursting strength	3.3.11	4.5.10
Workmanship	3.5	4.5.20

4.3.2 Lot. A lot shall consist of all units of the same type that are produced under similar conditions and are ready for inspection or shipment at one time. Unless otherwise specified (see 6.2), the lot size shall be expressed in the number of finished blankets.

4.3.3 Sampling for inspection of end item. Samples shall be randomly selected from each lot. At a minimum, the sampling rate shall be 3 percent on lots of 500 or less, and 1.5 percent on lots greater than 500. The inspections shall be as specified in 4.3.1.

4.4 Test sample preparation. Unless otherwise specified (see 6.2), samples for individual tests shall be prepared in accordance with the specified test protocol.

4.4.1 Laundering cycle. For tests incorporating measurements after laundering, the laundering shall be accomplished in accordance with AATCC Test Method 135 in accordance with the alternative washing and drying conditions for a normal wash cycle, a hot wash temperature (120±5 ºF), and a tumble dry cycle. The laundered samples shall be marked in accordance with AATCC Test Method 96, paragraph Test Specimens, subparagraph Size, Preparation and Marking.

4.5 Test procedures.

4.5.1 Dimensions. The length and width of the blanket shall be measured and the results recorded as pass or fail (see 3.3.2).

4.5.2 Visual examination for shade and finish. Each roll of material in the lot of material used to manufacture the blanket shall be examined visually against a standard sample (see 6.5) for finish as required in 3.3.1.2 and shade match as required in 3.3.3. A sample unit shall be drawn from each roll in the lot. The sample unit shall be a 4-inch by 20-inch swatch of material. The material shall be viewed using AATCC Evaluation Procedure 9, Option A, under filtered tungsten lamps which approximate artificial daylight D75 illuminant having a correlated color temperature of 7500 (±200) Kelvin, with illumination of 100 - 20 foot candles, and under incandescent lamplight at 2856 (±200) Kelvin to determine if it is a good match to the standard sample. A material shall be rejected if it fails to meet the requirements for shade match and finish. The results shall be recorded as pass or fail.

4.5.3 Fiber identification and content. The fiber identity shall be determined in accordance with AATCC Test Method 20 and content shall be determined in accordance with AATCC Test Method 20A.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T06:20Z
Check the source to verify that this is the current version before use.

4.5.4 Wool grade. The wool grade shall be measured and graded using the United States Standards for Grades of Wool, Official Standards of the United States for Grades of Wool Top.

4.5.5 Fabric weight. The fabric weight, in oz/yd^2, shall be determined in accordance with ASTM D3776/D3776M, Option C.

4.5.6 pH. The pH shall be determined in accordance with AATCC Test Method 81.

4.5.7 Dimensional stability. The shrinkage, measured as a percentage, shall be determined in accordance with AATCC Test Method 96 after 10 laundering cycles using a 40-minute, 160 ºF tumble dry cycle.

4.5.8 Breaking strength. The breaking strength, measured in pounds, shall be determined in accordance with ASTM D5034 and shall be measured in both the warp and fill directions.

4.5.9 Tear strength. The tear strength, measured in pounds, shall be determined in accordance with ASTM D1424 and shall be measured in both the warp and fill directions.

4.5.10 Bursting strength. The bursting strength, measured in pounds, shall be determined in accordance with ASTM D3787.

4.5.11 Pilling appearance. The pilling appearance shall be determined using ASTM D3512/D3512M-conformant replicas after the first and tenth laundering cycles.

4.5.12 Colorfastness resistance to light. The colorfastness rating for resistance to light shall be determined in accordance with AATCC Test Method 16, Option 1, Carbon-Arc (40 hours), or Option 3, Xenon-Arc (70 kilojoules), and rated using AATCC Evaluation Procedure 1.

4.5.13 Colorfastness resistance to laundering. The colorfastness rating for resistance to laundering shall be determined after three laundering cycles in accordance with AATCC Test Method 61, Test 3A, and rated using AATCC Evaluation Procedure 1.

4.5.14 Colorfastness resistance to perspiration. The colorfastness rating for resistance to perspiration shall be determined in accordance with AATCC Test Method 15 in both the acid and alkaline conditions, and rated using AATCC Evaluation Procedure 1 and AATCC Evaluation Procedure 2.

4.5.15 Colorfastness resistance to crocking. The colorfastness rating for crocking shall be determined in accordance with AATCC Test Procedure 8 for both the dry and wet conditions and rated using AATCC Evaluation Procedure 8.

4.5.16 Fire performance. The blanket shall be fire tested in accordance with the requirements as specified in MIL-STD-1623 for blankets (see 3.3.14). Fire performance value shall be measured on an initial sample and after 10 laundering cycles.

4.5.16.1 Fire testing provisions. All fire tests specified in this document shall be conducted by an independent testing laboratory that is accredited to ISO/IEC 17025. Accreditation shall be obtained from a recognized accreditation body such as American Association for Laboratory Accreditation (A2LA) or International Code Council's International Accreditation Services (IAS). The scope of accreditation shall include specific flammability and fire tests required for qualification. All other fire test provisions shall be as specified (see 6.2).

4.5.16.2 Testing of individual components (type IV only). Where the blanket is composed of individual components consisting of layers, each individual layer shall be tested in accordance with the requirements of MIL-STD-1623 for blankets.

4.5.17 Thermal insulation. The thermal insulation Clo value shall be determined in accordance with ASTM C518. The thermal insulation value shall be measured on an initial sample and after 10 laundering cycles.

4.5.18 Off-gassing. The blanket shall be tested for off-gassing at a Government approved testing facility in accordance with S9510-AB-ATM-010 chapter titled "Material Control Program" (see 3.3.16 and 6.6).

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T06:20Z
Check the source to verify that this is the current version before use.

4.5.19 Toxicity. A Health Hazard Assessment shall be conducted to ensure conformance to 3.3.17, as required by the qualifying activity. The Navy and Marine Corps Public Health Center (NMCPHC) will evaluate the blanket using the administrative Health Hazard Assessment (HHA) data provided by the manufacturer/distributor to the NMCPHC.

4.5.20 Workmanship. The blanket shall be examined for construction as identified in 3.3.1, the presence of the proper labeling as identified in 3.4, and for defects noted in 3.5. If any sample has a defect, it shall indicate a failure to meet this requirement.

5. PACKAGING

5.1 Packaging. For acquisition purposes, the packaging requirements shall be as specified in the contract or order (see 6.2). When packaging of materiel is to be performed by DoD or in-house contractor personnel, these personnel need to contact the responsible packaging activity to ascertain packaging requirements. Packaging requirements are maintained by the Inventory Control Point's packaging activities within the Military Service or Defense Agency, or within the military service's system commands. Packaging data retrieval is available from the managing Military Department's or Defense Agency's automated packaging files, CD-ROM products, or by contacting the responsible packaging activity.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. The blankets covered by this specification are intended for use aboard naval ships and vessels.

6.2 Acquisition requirements. Acquisition documents should specify the following:

a. Title, number, and date of this specification.
b. Type and class required (see 1.2).
c. The specific issue of individual documents referenced (see 2.2.1, 2.2.2, and 2.3).
d. Color (see 3.3.3).
e. Additional marking requirements (see 3.4.1).
f. Inspection conditions (see 4.1.1).
g. Lot size (see 4.3.2).
h. Test sample preparation (see 4.4).
i. Packaging requirements (see 5.1).
j. Additional fire testing provisions (see 6.8).

6.3 Qualification. With respect to products requiring qualification, awards will be made only for products which are, at the time of award of contract, qualified for inclusion in Qualified Products List QPL No. 32433 whether or not such products have actually been so listed by that date. The attention of the contractors is called to these requirements, and manufacturers are urged to arrange to have the products that they propose to offer to the Federal Government tested for qualification in order that they may be eligible to be awarded contracts or orders for the products covered by this specification. Information pertaining to qualification of products may be obtained from Commander, Naval Sea Systems Command, ATTN: SEA 05S, 1333 Isaac Hull Avenue, SE, Stop 5160, Washington Navy Yard DC 20376-5160 or emailed to CommandStandards@navy.mil. An online listing of products qualified to this specification may be found in the Qualified Products Database (QPD) at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T06:20Z
Check the source to verify that this is the current version before use.

6.4 Noncompliance. If a sample fails to pass its conformance inspections, the lot should be rejected and the manufacturer should notify the cognizant inspection activity of such failure and take corrective action on the materials or processes, or both, as warranted. Acceptance and shipment of the product should be discontinued until corrective action, suitable to the contracting activity, has been taken. After the corrective action has been taken, conformance inspections should be repeated on the lot. In the event of failure after re-inspection, information concerning the failure should be furnished to the contracting activity.

6.5 Information requests. For access to information such as purchase descriptions, patterns, drawings, and standard shade samples of cloth and Navy buttons, go to the Defense Logistics Agency Troop Support's website at www.troopsupport.dla.mil/Portal/sreqfrm.aspx for their Specification/Pattern/Drawing Request form. Complete and submit the request form. Requests to use equivalent materials and components or to make changes to the pattern should be sent to the contracting officer and NAVSEA for approval.

6.6 Material certification. Materials to be installed in submarines are to be controlled to prevent off-gassing, which contaminates the submarine's atmosphere and can result in health hazards to personnel or deleterious effects on machinery. These controls are administered through the Submarine Material Control Program, which is described in the Nuclear Powered Submarine Atmosphere Control Manual, S9510-AB-ATM-010 chapter titled "Material Control Program." Under the Submarine Material Control Program, all materials considered for use on submarines require certification and assignment of a usage category. Under the certification process, candidate materials are selected by Navy activities or contractors, and a request for certification is submitted to the Naval Sea Systems Command, SEA 05S, 1333 Isaac Hull Avenue, SE, Stop 5160, Washington Navy Yard, DC 20376-5160 or emailed to CommandStandards@navy.mil. The certification request is accompanied by detailed information, including descriptions of the material, method of application, usage, and storage. A chemical analysis is conducted, which is normally accomplished through off gas testing. The off gas test is required to be conducted in a Government approved laboratory designated by the preparing activity. Information pertaining to this test requirement may be obtained from the Naval Sea Systems Command, SEA 05S, 1333 Isaac Hull Avenue, SE, Stop 5160, Washington Navy Yard, DC 20376-5160 or emailed to CommandStandards@navy.mil. Based on the chemical analysis results, a usage category is assigned to the material defining whether, and to what extent, the material may be used on submarines.

6.7 Toxicity evaluation. The Navy and Marine Corps Public Health Center (NMCPHC) requires sufficient information to permit an HHA of the product. Upon completion of the HHA, a copy will be provided by the NMCPHC to the Government for evaluation.

6.8 Additional fire testing provisions. NAVSEA reserves the right to witness the tests, and/or perform any of the tests set forth herein where such testing is deemed necessary to assure compliance to prescribed requirements of the qualification tests.

6.9 Subject term (key word) listing.

Fiber

Knit

Synthetic

Wool

Woven

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T06:20Z
Check the source to verify that this is the current version before use.

Custodians:
Army – GL
Navy – SH
Air Force – 99

Review activities:
Navy – CG, NU
Air Force – 03, 11
DLA – CT

Civil agencies:
GSA – FAS

Preparing activity:
Navy – SH
(Project 7210-2011-001)

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T06:20Z
Check the source to verify that this is the current version before use.