MIL-T-10372A(MU)
13 DECEMBER 1965
SUPERSEDING
MIL-T-10372(CmIC)
27 JUNE 1950

MILITARY SPECIFICATION

TAPE, TEXTILE, 1-INCH

1. SCOPE

1.1 This specification covers one type of cotton tape for use in the manufacturing of dust respirators.

2. APPLICABLE DOCUMENTS

2.1 Government documents. The following documents of the issue in effect on date of invitation for bids or request for proposal form a part of this specification to the extent specified herein:

SPECIFICATIONS

FEDERAL

CCC-T-191 — Textile Test Methods.

STANDARDS

FEDERAL

FED-STD-4 — Glossary of Fabric Imperfections.

MILITARY

MIL-STD-105 — Sampling Procedures and Tables for Inspection by Attributes.

MIL-STD-129 — Marking for Shipment and Storage.

(Copies of specifications, standards, drawings, and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following document forms a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal, shall apply.

UNIFORM CLASSIFICATION COMMITTEE

Uniform Freight Classification Ratings, Rules and Regulations.

(Application for copies of these freight classification rules and regulations should be addressed to Uniform Classification Committee, 202 Union Station, Chicago, Illinois 60606.)

3. REQUIREMENTS

3.1 Material. The cotton used in the manufacture of the yarn shall be thoroughly cleaned and carded or combed, and evenly drawn, spun, and twisted into 2-ply yarn. The warp yarn shall be 26/2 count and the filling yarn shall be 30/2 count.

3.2 Color. The color shall be olive drab, shade No. 7 (see 6.3). The use of sulfur dye and dyes containing elementary sulfur or compounds capable of oxidation to sulfuric acid is prohibited.

3.3 Construction.

FSC 8315

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:58Z
Check the source to verify that this is the current version before use.

3.3.1 *Weave.* The weave shall be a four-harness herringbone twill, 2/2, with five divisions alternating to the right and to the left.

3.3.2 *Yarn count.* The fabric shall have a total warp of 114 and 46 picks per inch in the filling.

3.4 Width. The width shall be 1 ± 1/16-inch.

3.5 Length. The tape shall be put in continuous piece rolls of no less than 36 yards length.

3.6 Physical requirements.

3.6.1 *Weight.* The cotton tape shall weigh a minimum of 0.20 ounce per linear yard.

3.6.2 *Warp breaking strength.* The warp breaking strength, full width, shall be 140 pounds minimum.

3.6.3 *Mildew resistance.* The fabric shall be mildew resistant and shall show no evidence of growth when tested as specified in 4.6.1.

3.7 Toxicity. The cotton tape, when applied to the skin, shall produce no evidence of irritation or sensitivity to the wearer when tested as specified in 4.6.3.

3.8 Preproduction. When specified in the contract or order, a preproduction sample shall be produced for examination and test. The preproduction sample shall be manufactured using the same materials, methods, and equipment as will be used during regular production (see 6.2).

3.9 Workmanship. The tape shall be free from fabric and dyeing defects when examined as specified in 4.5.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection.

4.1.1 *Supplier's responsibility.* Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specifications where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.2 *Government's responsibility.* The Government will be responsible for the performance of the test in 4.6.3. Samples will be forwarded to the laboratory designated by the contracting officer (6.2).

4.2 Special provisions.

4.2.1 *Alternative inspection.* The supplier may utilize any alternative inspection procedure which will provide equal or better assurance of quality by submitting a written proposal with justification and obtaining written approval from the Government prior to instituting the procedure. In case of dispute, the procedure of this specification will govern.

4.2.2 *Objective evidence.* The supplier shall provide objective evidence acceptable to the contracting officer that the requirements of 3.1, 3.2, 3.3.1 and section 5 for which specific inspection has not been provided in this specification have been satisfied.

4.3 Lotting. A lot shall consist of the cotton tape produced by one manufacturer, at one plant, from the same materials and processes, under essentially the same manufacturing conditions.

4.4 Sampling.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:58Z
Check the source to verify that this is the current version before use.

4.4.1 *For examination.* Sampling shall be in accordance with MIL–STD–105 and table I.

4.4.2 *For test.* A sample of 2 continuous yards, full width of the finished tape, shall be taken from each sample roll selected in accordance with table I.

TABLE I. *Sample size (in rolls)*

Lot size (yards)	Sample size in rolls *
Up to 400	3
401 to 800	5
801 to 2000	7
2001 and up	10

* If a lot contains fewer than 3 rolls, each roll in the lot shall be examined.

4.5 Inspection provisions.

4.5.1 *Yard by yard examination.* The required yardage of each roll shall be examined on both sides and visual defects classified as listed in table II. All defects found shall be counted regardless of their proximity to each other, except where two or more defects represent a single local condition of the tape, in which case only the more serious defect shall be counted. A continuous defect shall be counted as one defect for each warpwise yard or fraction thereof in which it occurs. The unit of product for this examination shall be one linear yard. The Acceptable Quality Level (AQL) shall be 4.0 Major and 10.0 total defects per hundred units. The number of rolls from which the sample is to be selected shall be in accordance with table I. An approximate equal number of yards shall be examined in each roll of the sample.

TABLE II. *Yard by yard examination*

Glossary No. FED–STD–4; Section 1	Defects	Classification	
		Major	Minor
79	Abrasion mark-resulting in a weak place	X	
11, 33	Broken or missing ends or picks:		
	Two or more continguous	X	
	Single, ½-inch or more in length	.....	X
90, 91, 92	Cut, hole or tear - any	X	
48, 49, 54	Edges:		
	Cut, frayed or torn	X	
	Loopy or slack	X	
	Rolled or wavy which will not flatten under normal pressure.	.....	X
8, 9	Fine or light filling or picks, fine or light filling bar, or light places — clearly visible *	X	

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:58Z
Check the source to verify that this is the current version before use.

TABLE II. *Yard by yard examination (continued)*

Glossary No. FED–STD–4; Section 1	Defects	Classification	
		Major	Minor
13, 34	Filling float, skip or overshoot:		
	Multiple, more than ½-inch in combined warp and filling directions.	X	
	Multiple, ½-inch or less in combined warp and filling directions.	.....	X
	Single, ½-inch or more in length	.....	X
1, 2	Heavy filling bar or heavy place, coarse or heavy filling or picks-clearly visible *.	.....	X
3, 5, 5A, 27	Jerked-in filling, slub or slug, slough off, more than three times the thickness of the normal yarn.	.....	X
6, 28	Kink or loop on surface of tape	.....	X
7, 29	Knots-large, improperly pieced knots, clearly visible * protruding from surface or with tails extending from surface of tape.	.....	X
10	Mispicks-two or more within ½-inch	.....	X
14, 70	Shade bar or dye streak—clearly visible *	.....	X
78	Smash-any	X	
74, 75, 76	Spot, stain or streak—clearly visible *	.....	X
89	Weak or tender spot	X	
40	Wrong draw — 9-inches or more in length	.....	X

* Clearly visible at normal inspection distance (approximately 3 feet)

4.5.2 *Overall examination.* Each defect listed in table III shall be counted no more than once in each roll examined. The unit of product shall be one roll. The number of rolls to be examined (sample size) shall be in accordance with table I; the acceptance number shall be 0 for up to 7 rolls, 1 for all over 7 rolls.

TABLE III. *Overall examination*

Defects
Off shade, not within established tolerance
Cloudy, mottled, or streaky throughout
Overall uncleanness

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:58Z
Check the source to verify that this is the current version before use.

4.5.3 *For tests.* The sample tape shall be tested in accordance with 4.6. The lot shall be rejected if one or more samples fail to meet any of the specified tests.

4.6 Tests.

4.6.1 *Construction and physical properties.* Sample cotton tape shall be tested in accordance with the applicable test method of CCC–T–191 and table IV.

TABLE IV. *Construction and physical properties*

Characteristics	Requirement	Test method
Sulfur dye content	3.2	4.6.2
Yard count	3.3.2	5050.1
Width	3.4	5020
Length	3.5	5010
Weight	3.6.1	5040
Warp breaking strength	3.6.2	5102
Mildew resistance	3.6.3	5758 *
Toxicity	3.7	4.6.3

* Except test specimen shall be 1 inch by 2 inches.

4.6.2 *Detection of sulfur dyes.* Analytical reagent grade chemicals and distilled water shall be used throughout the test. A 1-inch square piece of cloth, taken from the unit of product shall be placed in a test tube and covered with a solution containing 1 gram of stannous chloride for every 2 milliliters of 6N hydrochloric acid. The mouth of the test tube shall be covered with a piece of filter paper which has been moistened with a few drops of a 0.5N solution of lead acetate. The solution in the test tube shall be heated over a low flame until the solution is boiling. The appearance of a black stain on the filter paper indicates the presence of sulfur dye.

4.6.3 *Toxicity.* All tests for evaluating the tape for toxicity shall be conducted by the Government. Such tests, including human skin tests, as are deemed necessary for properly evaluating the toxicity of the tape will be conducted in accordance with the directions of Surgeon General, Department of the Army (6.4).

5. PREPARATION FOR DELIVERY

5.1 Packaging, level C. The cotton tape shall be packaged to afford adequate protection from the supply source to the first receiving activity for immediate use.

5.2 Packing, level C. Cotton tape, packaged as specified in 5.1, shall be packed to insure carrier acceptance and safe delivery to the first domestic destination. Containers shall comply with Uniform Freight Classification rules or regulations of other carriers applicable to the mode of transportation.

5.3 Marking. In addition to any special marking required by the contract or order, unit packages and shipping containers shall be marked in accordance with MIL–STD–129.

6. NOTES

6.1 Intended use. This cotton tape is intended for use with the ABC–M4 dust respirator.

6.2 Ordering data. Procurement documents should specify the following:

(a) Title, number and date of this specification.

(b) Whether a preproduction sample is required.

(1) Quantity required.

(2) Time allowed for supplier submission of samples for Government test and evaluation after award of contract.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:58Z
Check the source to verify that this is the current version before use.

(3) Name and address of test facilities and shipping instructions when testing is performed by the Government.

(4) Time required for the Government to notify the supplier whether or not to proceed with production.

(c) Laboratory to which toxicity samples are to be sent.

6.3 **Color.** The color shall be in accordance with the US Army Standard Color Code issued by the Textile Color Card Association of the United States, Inc.

6.4 **Toxicity.** The technique of determining toxicity by means of patch tests is given in Schwartz, Tulipan, and Peck, "*Occupational Diseases of the Skin*," 2d Edition, page 54 to 66 and 302 to 308 (1947).

6.5 **International interest.** Certain provisions of this specification are the subject of international standardization agreement ABC. When amendment, revision, or cancellation of this specification is proposed, the departmental custodians will inform their respective Departmental Standardization Offices so that appropriate action may be taken respecting the international agreement concerned.

Custodian:

Army — MU

Review activity:

Army — GL

International interest (see section 6)

Preparing activity:

Army — MU(EA)

Project No. 8315–A049

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:58Z
Check the source to verify that this is the current version before use.