[METRIC]
A-A-96A
April 2, 1998
Superseding
A-A-96
October 8, 1979

COMMERCIAL ITEM DESCRIPTION

CLEANING COMPOUND, OVEN (AEROSOL)

The General Services Administration has authorized the use of this commercial item description, for all federal agencies.

1. Scope. This commercial item description covers an aerosol oven cleaner suitable for removing heavy, baked-on grease and carbonized soil deposit on grills, ovens, fryers, other kitchen equipment (including stainless steel), and vertical and horizontal surfaces where such deposits might occur.

2. Salient Characteristics:

2.1 pH. The oven cleaner (without the propellant as a component) shall have a pH, at 25^{0}C (77^{0}F), not less than 13.0 when tested in accordance with ASTM E 70.

2.2 Delivery rate. The aerosol oven cleaner shall have a delivery rate , at 21^{0}C (70^{0}F), of 1.0 to 3.5 grams per second when tested in accordance with ASTM D 3069.

2.3 Flammability. The oven cleaner nor the propellant shall be flammable.

2.4 Test soil composition. When tested in accordance with paragraph 2.6, the aerosol oven cleaner shall completely remove a soil of the following composition:

Soil composition	Wt., percent
Corn oil (Mazola)	84
Sugar (granulated)	8
Flour (Standard, bleached)	8

2. Preparation of soil. While stirring, heat corn oil to 65.5^{0}C to 93^{0}C (150^{0}F to 200^{0}F.) While continuing to stir, add sugar and flour and mix thoroughly. Allow mixture to cool to room temperature before use.

2.6.1 Equipment. Paint brush, two porcelain enamel test panels and two stainless steel Grade 430 test panels. The test panels shall be approximately 7.62 cm X 7.62 cm (3 inches X 3 inches.) The porcelain test panels may be obtained from the Ferro Corporation, 4150 E. 56th Street, Cleveland, OH. The stainless steel test panels may be obtained from various oven and range manufacturers.

Beneficial comments, recommendations, additions, deletions, clarification, etc., and any data which may improve this document, should be sent to: GSA, Paints and Chemicals Center, 400 15th Street, S.W., Auburn, WA 98001.

FSC 7930

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:04Z
Check the source to verify that this is the current version before use.

2.6 Cleaning Performance.

2.6.2 Test procedure. Soil mixture is stirred constantly during application to panels. Using a paint brush, apply soil to the test panels in a thin film. Bake panels in a horizontal position for 20 minutes at 218^{0}C - 232^{0}C (425^{0}F - 450^{0}F.) After panels have cooled to room temperature, place them in a horizontal position. Apply the aerosol oven cleaner to the soiled panels until the cleaner completely covers the surface of the panels. Allow panels to set for 30 minutes in a horizontal position at room temperature. Damp sponge lightly and flush with water to remove the soil. Dry panels and apply aerosol oven cleaner again and repeat the procedure. After damp sponging and flushing with water, the oven cleaner shall, by visual observation, completely remove all the soil on the panel and leave no visible film.

3. Product Conformance. The products provided shall meet the salient characteristics of this commercial item description, conform to the producer's own drawings, specifications, standards, and quality assurance practices and be the same product offered for sale in the commercial market. The Government reserves the right to require proof of such conformance.

ASTM standards are available from the American Society for Testing and Materials, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

NOTE: The contractor may use his normal quality assurance procedures for manufacture of this product; however, should a disagreement arise between the Government and its customer or between the Government and the manufacturer concerning compliance to the salient characteristics of this commercial item description, the test methods and tests stated in this commercial item description will be used to determine compliance of the product.

PREPARING ACTIVITY:
GSA - FSS

FSC 7930

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:04Z
Check the source to verify that this is the current version before use.