[METRIC]
A-A-3009
January 30, 1997

COMMERCIAL ITEM DESCRIPTION
TAPE, TELETYPEWRITER,PERFORATOR

The General Services Administration has authorized the use of this commercial item description as a replacement for UU-T-120 which is cancelled.

1. SCOPE: This description covers two types of unpunched teletypewriter perforator paper tape in roll form.

2. CLASSIFICATION: Teletypewriter perforator tape in accordance with this commercial item description shall be of the following two types.

Type I - Oiled taped.
Type II - Unoiled tape (for optical readers)

3. SALIENT CHARACTERISTICS:

3.1 Stock. The teletypewriter perforator paper tape shall be made from 100 percent bleached chemical wood pulp which shall contain recycled content as specified in the Ordering Data.

3.2 Impregnated Oil. The oil used for Type I tape shall be well refined, paraffin base, light grade lubricating oil. It shall be light in color, free from acids, and as free of odor as commercially possible. Type I tape shall be uniformly impregnated with oil and shall contain 8-16% oil, based on the weight of the deoiled paper when tested in accordance with paragraph 5.5.

3.3 Color. Type I tape shall be as specified in the Ordering Data. Type II tape shall be black. Both tapes shall be uniformly colored throughout the entire roll.

3.4 Roll assembly. Perforator teletypewriter tape shall be in rolls of one continuous length without splice. The tape at the inner end of the roll shall be fastened to the core so that it cannot be pulled loose without tearing. The outer end of the tape shall be fastened to the adjacent layer in such a way that it is retained in shipment and handling but can be pulled loose without cutting and without damaging more than two turns of the roll.

3.5 Roll diameter. The outside diameter of the roll shall be as specified in the Ordering Data with a +/-3.175 mm (+/-1/8 inch) tolerance.

3.6 Roll length. When the outside diameter of the roll is not specified, the roll shall not contain less than the minimum length specified in the Ordering Data.

Beneficial comments,recommendations,additions,deletions, clarifications etc. Any data which may improve this document should be sent to:	General Services Administration: Federal Supply Service, Engineering Branch (2FYEE) 26 Federal Plaza, New York,NY 10278

FSC 7530

Source: https://assist.dla.mil -- Downloaded: 202640-26T08:28Z
Check the source to verify that this is the current version before use.

3.7 Physical properties. The base paper and the end item shall conform to the requirements of Table I.

TABLE I
(Physical Properties for Types I and II)

Characteristics	Requirement	Test Method
Base paper:		
Basis Weight	81g/m^2(50 - 24x36-500) +/- 5% tolerance	T410
Tearing resistance, Machine direction	50-80 g	T414
Cross direction	55-90 g	T414
Opacity (Type II only)	35 % min	T425
Acidity	pH 4.5 min	T435
Ash	1.0 % max	T413
Grit content	0.10 % max	par.5.6
End Item Tape		
Avg. Thickness Tol. +/- 0.00762mm (+/-.0003")	0.1016 mm (0.0040")	T411
Tensile breaking strength (machine direction)	5.604KN/m (32lbs/inch) min	T404 or T494

3.8 Roll width. Rolls width shall be as specified in the Ordering Data with a +/- 0.0762 mm (+/-0.003 inch) tolerance.

3.9 Warning signal. Each roll of tape shall be marked with a contrasting color on at least one-half the width of the tape. This mark shall begin 6.096 to 9.144 m (20 to 30 ft.) from the core end of of the paper roll and shall extend to 1.5 to 3.0 m (5 to 10 ft.) from the inner end of the roll.

3.10 Roll core: Each roll of perforator teletypewriter tape shall be uniformly and tightly wound on a fiberboard core. The core shall have a wall thickness between 3.175 and 4.763 mm (1/8 and 3/16 inch). The length of the core shall be equal to the specified tape width with a tolerance +/-1.5875 mm (+/- 1/16 inch). Cores shall have an inside diameter as specified in the Ordering Data.

3.11 Workmanship: All types of paper in accordance with this specification shall be clean, free from dirt spots, oil spots, shives, foreign matter, and shall be uniform in color. The sheets shall be free from holes, tears, cuts, folds, scuff marks, lint, fuzz, or loose particles. There shall be no splices within a sheet and there shall be no partial sheets. There shall be no defects that may affect appearance or serviceability.

4. REGULATORY REQUIREMENT:

4.1 Certification: The contractor shall certify that the regulatory requirements shall be as specified in the Ordering Data. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

4.2 Labeling: The recycled content shall be marked on the product or unit pack.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:28Z
Check the source to verify that this is the current version before use.

5. QUALITY ASSURANCE PROVISIONS:

5.1 Product Conformance: The products provided shall meet the salient characteristics of this commercial item description,conform to the producer's own drawings, specification, standards and quality assurance practices and be the same product offered for sale in the commercial market. The government reserves the right to require proof of such conformance.

Suppliers are encouraged to use quality control (QC) techniques that exhibit control over their processes (e.g. (Statistical Process Control) SPC techniques) as defined in American National Standards Institute (ANSI) Z1.1, Z1.2 and Z1.3/ American Society for Quality Control (ASQC) B.1, B.2 and B.3 that systematically reduce excess variations. Objective evidence shall be available that demonstrates overall measurement adequacy techniques and controls. These techniques shall ensure quality levels equal to, or greater than, those cited in applicable technical document or, herein.

End item inspection/testing may be used by the offeror or the Government representative, as a means to determine the effectiveness of the in process quality controls. In process controls shall not be substituted for end item performance testing.

For those characteristics for which there are no such controls, or for end item performance test, lot by lot sampling for inspection/test shall be required. Sampling shall be in accordance with the American National Standards Institute (ANSI) / American Society for Quality Control (ASQC) Z1.4, Sampling procedures and Tables for inspection by Attributes.

5.2. Paper Component Testing. Testing and sampling for the base paper shall be in accordance with the referenced test methods in Table I . The inspection level shall be S-1. There shall be no failure to meet the requirements. The supplier must provide objective evidence (tests and inspection records) that the presented material meets the requirements of the sampling plan as indicated above.

5.3. End item testing: For visual, dimensional, and workmanship defects the inspection level shall be S-3 with an AQL of 2.5%.

The roll of teletypewriter perforator tape shall be tested for the end item characteristics in accordance with the referenced test methods in Table III. The lot size shall be expressed in rolls of tape of one type, size, and color. The test sample unit shall consist of one roll of tape, and no more than one sample unit shall be taken from any one shipping container. The inspection level shall be taken from any one shipping container. The inspection level shall be S-1. There shall be no failure to meet the requirements. The first three layers of tape shall be removed from then rolls before taking specimens for tests.

Source: https://assist.dla.mil -- Downloaded: 202610-26T08:28Z
Check the source to verify that this is the current version before use.

Table III

Characteristic	Test Method
Thickness	TAPPI 411
Tensile Breaking Strength	TAPPI 404 or 494
Oil Content, Type 1	par. 5.5
Width, roll	par. 5.7

For suppliers providing **pre-oiled perforator tape**, in lieu of testing for oil content in accordance with par. 5.5, a certification of conformance for par 3.2 shall be required.

5.5 Oil content. Perform two determinations on the sample unit. Cut the tape into 6 x 40 mm strips and allow to condition as specified in TAPPI T402. Weigh out 10 g +/- 0.01 g of the strips. Make small zigzag folds in the strips, then place them lengthwise into the siphon cup of a Soxhlet extractor. Do not pack the strips tightly into the siphon cup. Fill the siphon cup with carbon tetrachloride to cover the sample strips tightly into the siphon cup. Fill the siphon cup with carbon tetrachloride to cover the sample strips. Allow the liquid to stand for 5 minutes without draining . Then add 1.5 times the volume of carbon tetrachloride required to fill the siphon cup. Extract by heating until the siphon cup has been filled by condensation and emptied by siphon 30 times. Remove the sample strips as specified in TAPPI T402. Weigh the reconditioned sample strips to the nearest 0.01 g.

$$\% \text{ Oil content} = \frac{\text{Original sample weight - extracted sample weight}}{\text{Original sample weight}} \times 100$$

Report the percent oil content as the average of the two determinations to the nearest 0.1 % .

5.6 Grit content. Perform two determinations on the sample unit. Condition the sample as specified in TAPPI T402. Weigh out about 25 g of the conditioned tape to the nearest 0.01 g and place in an 800 ml Kjeldahl flask. Add 100 ml of fuming HNO_3 and warm until the paper becomes a thin paste. Then boil gently until a low viscosity solution remains. Evaporate the solution to volume of 30 to 40 ml, then cool to room temperature. Add 20 ml of concentrated H_2SO_4 and heat until white fumes of SO_3 are evolved. Clarify the solution by adding small volumes of fuming HNO_3 allowing the drops to run down the inside wall of the flask and reheat until SO_3 fumes are evolved.

Repeat this clearing operation as often as necessary to produce a clear light straw color solution which does not darken after further heating. When clear, give the solution a final fuming to remove the HNO_3. Cool the solution to room temperature and dilute to 400 ml with distilled water. Boil gently for 10 minutes. Filter through a previously fried and weighted medium fritted glass crucible. Rinse the flask three times with distilled water, and, after each rinse, pour the water through the fritted crucible. Dry the crucible with contents at 105^0 +/- 2^0 C, then cool to room temperature and weigh.

$$\% \text{ of Grit} = \frac{\text{Weight of solids after drying}}{\text{Original weight of sample}} \times 100$$

Report the percent of grit as the average of the two determinations to the nearest 0.001 %.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:28Z
Check the source to verify that this is the current version before use.

5.7 Width. Use a vernier micrometer clamped in such a manner so that the analyst does not have to hold the micrometer during the test. Condition the sample in accordance with TAPPI T402. The tape shall be doubled back on itself with the edges parallel and held between the fingers so as to form loop approximately 25.4mm (1 inch) in diameter. The loop should not be creased nor its edges handled. One edge of the loop shall be held against the fixed anvil of the micrometer and the loop slowly oscillated back and forth. The micrometer spindle shall be moved up slowly until the first definite increase in resistance is felt in moving the tape. Five determinations, spaced at least 152.401 mm (6 inches) apart, shall be made. Report the five separate readings and the average width of the roll inches to the nearest 0.0254mm (0.001 inch).

6. PRESERVATION, PACKAGING, PACKING, LABELING AND MARKING. Preservation, packaging, packing, labeling and marking shall be as specified in the contract or order.

7. NOTES

7.1 Referenced Documents: The issue of the referenced documents in effect on the date of the solicitation for offers or request for proposals shall be used to determine conformance with the requirements of this Commercial Item Description.

7.1.1 TAPPI test methods are available from: Technical Association of the Pulp and Paper Industry, Technology Park/Atlanta, P.O. Box 105113, Atlanta, GA 30348 (404) 446-1400

7.1.2 ANSI/ASQC is available from: American Society for Quality Control,P.O.BOX 3005,611 E. Wisconsin Avenue, Milwaukee,WI 53201-4606

7.2 Ordering Data. Purchasers should select the preferred options permitted herein, and include the following information in procurement documents:

1) Title, number, and date of this specification
2) Type and color required
3) Outside roll diameter
4) Inside core diameter
5) Minimum length, when required
6) Width required
7) Packaging, packing and marking

8. Lists Of NSN'S

7530-00-285-2377 7530-00-067-8532 7530-00-634-6

Preparing activity
GSA-FSS

Source: https://assist.dla.mil -- Downloaded: 202640-26T08:28Z
Check the source to verify that this is the currentversion before use.