KK-L-136b

AMENDMENT—2
April 28, 1949

SUPERSEDING
AMENDMENT—1
July 23, 1946

FEDERAL STANDARD STOCK CATALOG

Section IV

(Part 5)

FEDERAL SPECIFICATION

FOR

LEATHER; ARTIFICIAL (UPHOLSTERY)

This amendment was approved on the above date by the Director, Bureau of Federal Supply, for the use of all departments and establishments of the Government, and shall become effective not later than July 15, 1949, for use in procurement initiated on or after that date. It may be put into effect, however, at any earlier date after promulgation.

The following changes shall be made in Federal Specification KK–L–136b, dated October 8, 1945:

Page 1:

Paragraph B–1. Following type III, add type IV and classes D, E, and F as follows:

Type IV.—Synthetic resin coated (special).
Class D.—Thick coated for heavy duty.
Class E.—Medium coated for general use.
Class F.—Thin coated for light duty.

Page KK–L–136b—2:

Paragraph C–1a (3). Delete heading "*Type III*" and substitute "*Types III and IV*".

Paragraph D–5:

Line 2. Delete "20" and substitute "20½".

Paragraph D–9. Delete in its entirety.

Paragraph E–2c. Delete heading "*Type III*" and substitute "*Types III and IV*".

Page KK–L–136b—3:

Paragraph E–3. Delete in its entirety and substitute:

E–3. *Abrasion resistance, types II, III, and IV.*—The surface coating shall not be abraded down to the fabric backing when subjected to 300 double rubs for type II, 500 double rubs for type III, and 1,500 double rubs for type IV, when tested as described in paragraph F–2g.

Table I. End of the table, add the following requirements for type IV:

Source: https://assist.dla.mil -
Check the source to verify that t

Type	Class	Width	Weight	Weight of coating (minimum)	Breaking strength, grab method (minimum)	
					Warp	Filling
		Inches	*Oz./sq. yd.*	*Oz./sq. yd.*	*Pounds*	*Pounds*
IV	D	50 or 54	21	10	120	110
	E	50 or 54	19	9	140	120
	F	54	15	9	85	45

Paragraph **E–4a.** In the heading, delete "*Types II and III*" and substitute "*Types II, III, and IV*".

Paragraph **E–4b.** Delete in its entirety and substitute:

E–4b. *Heat test requirement, types III and IV.*—The breaking strength of the material after the heat test described in paragraph F–2i (3) shall be not less than 75 percent of that of the material as received.

Paragraph **E–5.** In the heading, delete "*Types I and III*" and substitute "*Types I, III, and IV*".

Paragraph **E–6:**

Line 3. Delete "F–2i" and substitute "F–2l".

Section **E.** Following paragraph E–6, insert paragraph E–6a as follows:

E–6a. *Type IV.*—When tested as described in paragraph F–2l, no specimen shall continue flaming for more than 2 seconds, or glowing for more than 15 seconds after the burner flame is withdrawn. The average length of char of the 10 specimens shall be not more than 2 inches, and the maximum length of char of any specimen tested shall not exceed 3 inches.

Paragraph **E–7.**

Line 1. Delete "The" and substitute "When mildew-resistant material is specified, the".

Section **E.** Following paragraph E–7, insert paragraphs E–7a and E–8 as follows:

E–7a. *Type IV.*—The finished material shall show no visible growth of mildew after being exposed to the mildew-infection test described in Federal Specification CCC–T–191, and the material shall retain a breaking strength of not less than 90 percent of that unexposed material.

E–8. *Resistance to cold.*—The coating shall not crack through to the fabric base when tested as described in paragraph F–2j, at the following temperatures for the respective types:

Type I_____ +32° F.
Types II and III__ 0° F. or lower, when specified.
Type IV_____ −65° F.

Page KK–L–136b—4:

Paragraph immediately following **F–2a (1).** Delete paragraph number and heading "F–2a (2). *Type II*" and substitute "F–2a (2). *Type II*".

Source: https://assist.dla.mil -- D
Check the source to verify that this

Paragraph **F–2a (3)** (line 18 of page). Delete heading "*Type III*" and substitute "*Types III and IV*".

Paragraph **F–2b (2)**. Delete heading "*Types II and III*" and substitute "*Types II, III, and IV*".

Page KK–L–136b—5:

Line 1 of page. Delete "type III" and substitute "types III and IV."

Paragraph **F–2c.**

Line 3. Delete "20" and substitute "20½".

Paragraph **F–2g.** Delete the table in its entirety and substitute:

	Types II, III, and IV
Pressure on specimen.....pounds..	2.
Tension on specimen.....do....	6.
Abrader.....	Silicon carbide cloth—Minnesota Mining Co., 240J.
Speed.....double rubs per hour..	5,000.
Temperature of room.....° F..	70 to 90.

Paragraph **F–2h.** In the heading, delete "*Types II and III*" and substitute "*Types II, III, and IV*".

Page KK–L–136b—6:

Paragraph **F–2j.** Delete in its entirety and substitute:

F–2j. *Resistance to cold.*—After exposure for not less than 2 hours for types I, II, and III, and 5 hours for type IV, at the temperature specified, the specimen, with the coated surface on the outside, shall be sharply folded flat upon itself. The coating shall then be visually examined for cracks.

Paragraph **F–2k.** In the heading, delete "*Types I and III*" and substitute "*Types I, III, and IV*".

Paragraph **F–2l.** In the heading delete "*Type III*" and substitute "*Types III and IV*".

Paragraph **F–2m.** In the heading, delete "*Type III*" and substitute "*Types III and IV.*"

Paragraphs **H–2** through **H–2b.** Delete in their entirety and substitute paragraphs **H–2** through **H–2d** as follows:

H–2. *Army.*—

H–2a. *Applicable specifications.*—

Joint Army-Navy Specifications:

JAN–P–105—Packaging and Packing for Overseas Shipment—Boxes, Wood, Cleated, Plywood.

JAN–P–106—Packaging and Packing for Overseas Shipment—Boxes; Wood, Nailed.

JAN–B–107—Boxes, Wood, Wirebound (Overseas Type).

JAN–P–125—Packaging and Packing for Overseas Shipment—Barrier-Materials, Waterproof, Flexible.

JAN–P–128—Packaging and Packing for Overseas Shipment—Tape; Water Resistant, Gummed.

JAN–P–140—Packaging and Packing for Overseas Shipment—Adhesives, Water Resistant, Case Liner.

Source: https://assist.dla.mil -- Check the source to verify that th

Army Specification:
100-2—Standard Specification for Marking Shipments by Contractors.

Copies of specifications required for Army purchases may be obtained upon application to the procuring agency. Both the title and identifying symbol or number should be stipulated when requesting copies.

H-2b. *Packaging.*—Unless otherwise specified, the artificial leather, in the widths and lengths of rolls specified in paragraphs D-3 and D-4, respectively, shall be wound on standard fiberboard cores and wrapped in not less than two thicknesses of waterproof material conforming to the requirements of Joint Army-Navy Specification JAN-P-125, type C-1. The ends of each roll shall be protected by headers of the same, or equal, material securely taped or glued to the body of the outer wrapping with water-resistant tape or water-resistant adhesive conforming to the requirements of Joint Army-Navy Specifications JAN-P-128 and JAN-P-140, respectively.

H-2c. *Packing.*—

H-2c (1). *For domestic shipment.*—Rolls, packaged as specified in paragraph H-2b, will not require overpacking.

H-2c (2). *For overseas shipment.*—Each individual roll, packaged as specified in paragraph H-2b, shall be overpacked in a snug-fitting box constructed in conformance with the requirements of one of the following Joint Army-Navy Specifications:

JAN-P-105	Style A or B, type 3 load.
JAN-P-106	Style 2, type 3 load.
JAN-B-107	Style 1 or 2, type 3 load.

The boxes shall be designed to fit the rolls in a compact manner and shall be strapped in conformance with the requirements of the appendix to the applicable box specification.

H-2d. *Marking.*—Each shipping container shall be marked in conformance with the requirements of U. S. Army Specification 100-2.

Page KK-L-136b—9:

Paragraph I-3.

Line 5. Delete "where fire resistance is or is not a factor,".

Section I. Following paragraph I-3, insert paragraph I-3a as follows:

I-3a. Type IV artificial leather is intended primarily for use by the Army Ordnance.

Paragraph I-4. Delete in its entirety and substitute:

I-4. *Ordering information.*—Purchasers should specify the type, class, color, and grain required (see pars. B-1 and D-1); if type III is specified, purchasers should also specify whether fire- and mildew-resistance is required (see pars. E-6 and E-7). If a temperature lower than 0° F. is required for resistance to cold for types II and III (see par. E-8), it should be so specified. Purchasers should exercise any desired options offered herein. (See pars. G-1, G-2, H-2b, H-3d, and H-3e.)

Source: https://assist.dla.mil -
Check the source to verify that