K-P-146c
AMENDMENT—2
February 21, 1967

SUPERSEDING
Int. Amendment—1 (Army-GL)
March 11, 1966

FEDERAL SPECIFICATION

PAULINS: COTTON DUCK; FIRE, WATER, WEATHER AND MILDEW-RESISTANT

This amendment, which forms a part of Federal Specification K-P-146c, dated May 6, 1963, was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

PAGE 1

Paragraph 1.2.1: Under "Class 2", delete "grey" and substitute "gray Navy Shade 3104." Under "Class 3", delete and substitute: "Class 3—Cloth, cotton duck, No. 10 or No. 11, hard texture, unbleached."

Paragraph 2: Delete the heading and substitute: "APPLICABLE DOCUMENTS".

Paragraph 2.1: Under *"Federal Specifications:"*, delete "T-R-00605" and substitute "T-R-605"; delete "T-R-00616—Rope; Mildew-Resistant" and substitute "T-T-616—Treatment: Mildew Resistant, for Rope and Cord."

PAGE 3

Paragraph 2.1: Under *"Federal Standards:"*, delete "Fed. Std. No. 102—Preservation, Packaging, and Packing Levels." Under *"Military Specifications:"*, add "MIL-T-40625—Tubing, Bias Sewn (Burlap or Osnaburg) Cloth."

Paragraph 2.2: Line eight, delete and substitute: "General Repair for Canvas and Webbing."

Paragraph 3.1: First sentence, delete "When" and substitute "Unless otherwise".

PAGE 4

Paragraph 3.2.1: Delete and substitute:

3.2.1 *Cloth, cotton duck.* The cloth for classes 1 and 2 paulins shall be No. 6, hard texture of CCC-C-419. The cloth for class 3 paulins shall be No. 10, hard texture, except the weight which shall be maximum; or No. 11, hard texture, except the weight which shall be minimum, of CCC-C-419. Air permeability requirements shall not be applicable to the class 3 cloth.

Paragraph 3.2.1.1: Delete and substitute:

3.2.1.1 *Color and treatment.* The finished cloth shall conform to type I, class 1 (for class 1 paulins), type II, class 1 (for class 2 paulins) of CCC-C-428. The finished cloth for class 3 paulins shall be unbleached, conforming to class 1 of CCC-C-428 except that the flexibility requirements shall not apply.

Paragraph 3.2.2: Lines four and five, delete "and class 3 paulins,". Line five, after "deck gray" insert "Navy Shade 3104".

Paragraph 3.2.3: Delete and substitute:

3.2.3 *Thread, polyester.* The thread shall conform to type I, class 1, subclass B of V-T-285. Sizes shall be as follows:

For all stitching except stitching indicated by "Z" on drawing	—Size FF
For stitching indicated by "Z" on drawing	—Size FF for needle and size F for looper.

Paragraph 3.2.3.1: First sentence, after "class 2" add "and class 3". Second sentence, delete "classes 1 and 3" and substitute "class 1."

Paragraph 3.2.7: Delete "T-R-00605" and

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:08
Check the source to verify that this is the current version before use.

substitute "T-R-605"; last line, delete "T-R-00616" and substitute "T-T-616":

Add the following new paragraph in proper sequence:

3.3.1.2 The addition of any lubricant to the polyester thread prior to or during the sewing operation is prohibited.

PAGE 5

Add the following new paragraph in proper sequence:

3.3.7 *Compliance with cup test.* There shall be no seepage of water through the panel lap seam stitching when the paulin is tested as specified in 4.4. The cup test is intended to insure that nonwicking thread has been utilized and that no lubrication has been added to the polyester thread during the sewing operation.

Section 4: Delete the heading and substitute "QUALITY ASSURANCE PROVISIONS".

Paragraph 4.3: Delete and substitute:

4.3 Sampling for inspection. Sampling for inspection shall be made in accordance with the provisions set forth in MIL-STD-105, except where otherwise indicated.

PAGE 7

Table I: In defect column, line fourteen, delete "repaired" and substitute "required".

PAGE 8

Paragraph 4.3.1.1.1: In table following paragraph, delete "L-6" and substitute "S-3".

Add the following new paragraph in proper sequence:

4.3.1.2 *Testing of the end product.* The paulin shall be tested as specified in 4.4 for compliance with 3.3.7. The sample unit shall be one completely fabricated paulin. The lot shall consist of all completely fabricated paulins of one size offered for inspection and the inspection level shall be S-3. Failure shall be cause for rejection of the lot.

Paragraph 4.3.2: Line fifteen, delete "L-4" and substitute "S-2"; delete "4.0" and substitute "2.5".

PAGE 9

Add the following new paragraphs in proper sequence:

4.4 Tests.

4.4.1 *Seam leakage test.* The paulin shall be tested in one area of a panel lap seam.

4.4.2 *Procedure.* Suspend the section of the paulin containing the test area by any convenient method so as to allow both sides of the seam to be viewed. The test area shall then be cupped into a hoop 6 to 7 inches in diameter, e.g., an embroidery hoop, with the seam running through the center of the cupped cloth. Pour approximately one pint of cold tapwater into the cupped area and allow to stand up to 5 minutes. At the end of the period, examine the test area for the seepage of water through the thread and along the entire portion of the stitching exposed to the cup test.

Section 5: Under "PREPARATION FOR DELIVERY" delete parenthetical paragraph.

Paragraph 5.1.2: Delete and substitute:

5.1.2 *Level C.* Paulins shall be packaged to afford adequate protection against deterioration and physical damage during shipment from the supply source to the first receiving activity. The supplier may use his standard practice when it meets these requirements.

Paragraph 5.2.1.1: First sentence, after "cloth conforming to" delete the balance of sentence and substitute "class 2 of CCC-C-429; or jute (or kenaf) cloth conforming to class 3 of CCC-C-467." Second sentence, delete "or type II"; delete "3 ply" and after the following "type I" insert "size number

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:08Z
Check the source to verify that this is the current version before use.

2". Last sentence, delete and substitute: "Alternatively, paulins shall be packed in bias-sewn tubing conforming to MIL-T-40625. The tubing shall have the open ends closed with the two double-looped wire ties. The wire ties shall be not less than 6 inches long, 0.072-inch thick galvanized soft iron or steel wire with a 1/2-inch diameter formed eye at each end. The first wire tie shall be applied as close to the bundle as possible. The second wire tie shall be applied at a distance approximately 1-inch from the first wire tie. The twisted ends of the wire shall alternate and face in opposite directions."

PAGE 10

Table III, third column under class 3: delete "10" and substitute "3"; delete "5" and substitute "3"; delete "3" and substitute "2".

Paragraph 6.3, subparagraph (*d*): between "is required" insert "not".

PAGE 11

Delete "Notice" paragraph.

CUSTODIANS:

Army—GL
Navy—SA
Air Force—82

Review activities:

Army—GL, MD
Navy—SA, YD, SH
Air Force—82, 85

User activities:

Army—CE, MI, ME
Navy—MC

Preparing activity:

Army—GL

CIVIL AGENCIES INTEREST:

GSA—FSS
COM—NBS
HEW
PO
VA—DMS
JUS—FPI

Review and user information is current as of the date of this document. For future coordination of changes to this document, draft circulation should be based on the information in the current Federal Supply Classification Listing of DOD Standardization Documents.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:08Z
Check the source to verify that this is the current version before use.