SS-C-621B
INT. AMENDMENT-2 (GSA-FSS)
June 18, 1970
SUPERSEDING
Int. Amendment-1 (GSA-FSS)
July 15, 1968

INTERIM AMENDMENT
TO
FEDERAL SPECIFICATION

CONCRETE MASONRY UNITS, HOLLOW
(AND SOLID, PREFACED AND UNGLAZED)

This Interim Federal Specification was developed by the General Services Administration, Federal Supply Service, Washington, D. C. 20406, based upon currently available technical information. It is recommended that Federal agencies use it in procurement and forward recommendations for changes to the preparing activity at the address shown above.

The General Services Administration has authorized Federal agencies to use this interim amendment as a valid exception to Federal Specification SS-C-621b, dated January 19, 1968.

PAGE 2

Paragraph 2.1. Under "American Society for Testing and Materials (ASTM) Publication," add the following document: "C 67- Sampling and Testing Brick."

PAGE 3

Paragraph 3.2.1, line 3. After "with" insert "a ceramic material."

Paragraph 3.2.3.2, line 2. Delete "1/8" and substitute "1/16".

Paragraph 3.2.4.2. Delete in its entirety and substitute the following:

3.2.4.2. Resistance to chemicals. The condition of the surface shall show no change after testing with each of the following chemicals for the duration in 4.4.2.2:

FSC 5620

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:13Z
Check the source to verify that this is the current version before use.

Acetic acid (5 Percent).
Hydrochloric acid (10 percent).
Potassium hydroxide (10 percent).
Trisodium phosphate (5 percent).
Hydrogen peroxide (3 percent).
Household detergent, Tide (10 percent).
Vegetable oil.
Blue-black ink (Waterman's).
Ethyl alcohol, industrial denatured (95 percent).

Paragraph 3.2.4.4. Delete in its entirety.

Paragraph 3.2.4.7, line 3. Delete in its entirety and substitute "texture and the color difference shall not exceed 5.0 units."

Paragraph 3.2.4.8, line 2. Insert a period after "4.4.2.8.1." Delete "and 4.4.2.8.2" and substitute "Spotting media shall be completely removed when tested in accordance with 4.4.2.8.2."

Paragraph 3.2.5. Add new paragraph as follows: "3.2.5. Efflorescence. The units shall show no efflorescence when tested in accordance with 4.4.2.9."

Paragraph 4.4.2.2. Delete in its entirety and substitute the following:

"4.4.2.2. Resistance to chemicals. Apply a convenient quantity of the following chemicals one at a time on the facing material and leave covered with a watch glass for the duration of the following test periods. For volatile chemicals place a saturated wad under the watch glass and keep saturated:

Chemical	Duration of test, hours
Acetic acid (5 percent)	24
Hydrochloric acid (10 percent)	3
Potassium hydroxide (10 percent)	3
Trisodium phosphate (5 percent)	24
Hydrogen peroxide (3 percent)	24
Household detergent, Tide (10 percent)	24
Vegetable oil	24
Blue-black ink (Waterman's).	1
Ethyl alcohol, industrial denatured (95 percent)	3

Upon completion of the test cycle wipe the test area clean with a clean cloth (see 3.2.4.2)."

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:13Z
Check the source to verify that this is the current version before use.

Paragraph 4.4.2.7. Delete in its entirety and substitute the following:

4.4.2.7 Color Change. Determine color difference in accordance with method 6123 of Fed. Test Method Std. No. 141. Measurements shall be taken before and after 500 hours of accelerated weathering using the single arc apparatus in accordance with method 6152 of Fed. Test Method Std. No. 141. Use test panels of not less than 3-inches wide by 6-inches long. Test panels need not be conditioned. Check results for compliance with 3.2.4.7.

PAGE 6

Paragraph 4.4.2.8.1, line 4. After "specimen" insert "for 80 cycles."

Paragraph 4.4.2.8.2. Delete the last two lines and substitute "clean the stained areas as specified in 4.4.2.8.1 except as follows: Use 100% isopropyl alcohol to clean spotting medium (b); clean spotting medium (a) for 10-cycles; clean spotting medium (b) for 150-cycles; clean spotting media (c) and (d) for 60-cycles."

Paragraph 4.4.2.9. Add new paragraph as follows:

4.4.2.9 Efflorescence. The units shall be tested for efflorescence in accordance with the procedure described in ASTM C67 with the following modifications:

(a) Specimens. Duplicate specimens, approximately 2 by 2 by 6 in., shall be tested in lieu of the ten specimens specified in the test procedure.

(b) Examination and Rating. After drying, examine the three unglazed faces of each specimen. The viewing shall be made from a distance of 10 ft. under an illumination of not less than 50 ft. candles by an observer with normal vision. If under these conditions efflorescence is observed on one or more of the unglazed faces, report the rating as "efflorescenced.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:13Z
Check the source to verify that this is the current version before use.