V-L-61H
AMENDMENT-2
June 27, 1985
SUPERSEDING
Int. Amendment-1
August 7, 1984

FEDERAL SPECIFICATION

LACES, NYLON

This amendment, which forms a part of Federal Specification V-L-61H, dated June 15, 1984, is approved by the Assistant Administrator, Office of Federal Supply and Services, General Services Administration, for the use of all Federal agencies.

PAGE 1

1.2.1, line 1: Delete "two types" and substitute "three types".

Add the following:

Type III - Multifilament nylon laces

Class 1 - 4/32 inch each side, square

PAGE 3

3.3.1: Add the following to end of paragraph

"The type III, class 1 laces shall be made from 210 denier by 5 by 3 cabled yarns manufactured from high tenacity, continuous multifilament nylon yarns. Each of the individual yarns used for type III, class 1 laces shall be twisted initially with not less than 7.0 nor more than 9.0 turns per inch (TPI) and

FSC 8335

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:21Z
Check the source to verify that this is the current version before use.

PAGE 3 (cont'd)

the final plied twist shall be in the opposite direction with not less than 5.0 nor more than 7.0 turns per inch."

PAGE 4

3.5: Delete and substitute:

"3.5 Braid. The braid for the laces shall be tubular braided without a core except for type II, class 3 which has a stuffer core. All laces shall use a two over and two under braiding except type II, class 2 which shall braid one pair over and one pair under and type III, class 1 which shall be square. The braid machine used for type III, class 1 shall be set such as to produce a resultant square braid exhibiting four separate sides with an equal number of picks per inch and an equal width per side of 4/32 ± 1/32 inch. The braid shall be pressed flat for type I, classes 1, 2, and 3, and for type II, class 2 laces in accordance with commercial practice. The braid for type II, classes 1, 3, and 4 laces shall be round and shall not be pressed. The braid for type III, class 1 laces shall be square and shall not be pressed. The braid for the laces shall conform to the physical requirements in table I when tested as specified in 4.4.4."

TABLE I: Add the following under the listed headings:

"Type	Class	Width Tol. ± 1/32 inch	Carriers minimum	Ends per carrier minimum	Warp ends minimum	Stuffer minimum	Picks per inch minimum	Breaking strength lbs. minimum
III	1	4/32 (each side)	8	1	-	-	14	250 "

3.6: Delete the second sentence and substitute

"Type III, class 1 laces shall be self tipped by an ultrasonic/heat molding process. This process may also be used as an alternate for all other types and classes of laces."

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:21Z
Check the source to verify that this is the current version before use.

PAGE 5

4.3, line 3: Delete "table III" and substitute "table II".

Page 7

Table II, opposite "Width or diameter" in "Results reported as" column: Delete "1/2" and substitute "1/32".

PAGE 8

4.4.5: Delete the third and fourth sentences and substitute "The sample unit shall be one shipping container fully packaged."

PAGE 14

5.3, after the first sentence: Add "Pallet type shall be type I (4-way entry), type IV or type V in accordance with MIL-STD-147."

MILITARY INTERESTS:

Custodians

Army - GL
Navy - NU

Review Activities

Army - MD
DLA - CT

User Activity

Navy - MC

CIVIL AGENCY COORDINATING ACTIVITY:

GSA - FSS

PREPARING ACTIVITY:

Army - GL

Project No. 8335-0156

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:21Z
Check the source to verify that this is the current version before use.