FEDERAL SPECIFICATION

GLASS, PLATE, SHEET, FIGURED (FLOAT, FLAT, FOR GLAZING, CORRUGATED, MIRRORS AND OTHER USES)

This interim amendment was developed by the General Services Administration, Federal Supply Service, Washington, DC 20406, based upon currently available technical information. It is recommended that Federal agencies use it in procurement and forward recommendations for changes to the preparing activity at the address shown above.

The General Services Administration has authorized the use of this interim amendment as a valid exception to Federal Specification DD-G-451C, dated January 15, 1968.

PAGE 5

Table II, column four. Opposite "gaseous inclusion", delete "1/64 inch" and substitute "1/16 inch". Opposite "Crush" in column four delete "Medium [c]" and substitute "Medium [e]".

PAGE 6

Table III. Delete "72" in the heading of column four and substitute "75".

PAGE 7

Table V. Opposite "wave, ream, strings, and lines" delete "45° [c]" and in its place substitute the following, and add the following for wave:

Defects

	q4 AA quality Central [d]	q4 AA quality Outer [d]	q5 A quality Central [d]	q5 A quality Outer [d]
Ream, strings, and lines.	Light [c]	Light [c]	Light [c]	Light [c]

PAGE 8

Table VI. Opposite "wave, ream, strings, and lines" delete "90°[c] and 45°[c]" and in its place substitute the following, and add the following for wave:

Defects

	q6 B quality Central [d]	q6 B quality Outer [d]	q7 A silvering quality Central [d]	q7 A silvering quality Outer [d]	q8 B silvering quality Centeral [d]	q8 B silvering quality Outer [d]
Ream strings and lines	Heavy [c]	Heavy [c]	Light [c]	Light [c]	Medium [c]	Medium [c]
Wave	Heavy [k]	Heavy [k]	Medium [k]	Medium [k]	Medium [k]	Medium [k]

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:43Z
Check the source to verify that this is the current version before use.

Under "Notes" delete "(A), (B), (C), (E), (G)" and in its place substitute "(a), (b), (e), and (g)". Add notes (C) and (K) as follows:

(c) Intensity - ream, strings and lines. When evaluated using the shadowgraph the intensities of these defects are defined as having shadowgraph readout at distances greater than or equal to the following (see 4.4.4):

Intensity	Minimum distance	
	Inches	Centimeters
Faint	6	15.2
Light	3	7.6
Medium	2	5.1
Heavy	1	2.5

(k) Intensity - wave. When evaluated using the shadowgraph the intensities of wave are defined as having shadowgraph readouts at distances greater than or equal to the following (see 4.4.4):

Intensity	Minimum distance	
	Inches	Centimeters
Faint	25	63.5
Light	15	38.1
Medium	10	25.4
Heavy	6 or 8	15.2, 20.3

PAGE 9

Table VIII. Delete "1/64" opposite 5/16 in the minus column under tolerance, thickness, and substitute "1/32".

PAGE 12

Table XI. Delete "Waveness, excessive".

Paragraph 4.3.2. Title, delete and in its place substitute" Ream, strings and distortion, type I." In the second line from the bottom delete "table II, III, V, and VI" and in its place substitute "tables II and III".

Paragraph 4.4.2. First sentence, delete "measure" between "transmittance" and "by illuminating".

PAGE 13

Add a new paragraph as follows:

4.4.4 Ream, strings, lines, and wave, type II, shadowgraph. Focus a light projector with a 500 watt lamp and an objective lens with an approximate 2 inch (5.1 cm.) aperture and an approximate 12 inch (30.5 cm.) focal length on a flat white projection screen positioned 25 feet (7.6 m) from the light source in a dark room. Place the glass in a vertical position parallel to the screen between the light and the screen. Move the glass slowly toward the screen with a vertical oscillating motion. The shadowgraph readout is the distance at which the distortion just blends with the general shadow of the glass on the screen (see tables V and VI).

Paragraph 5.2.1. Add the following: and each container shall be marked on both sides with the words GLASS - DO NOT DROP OR THROW; GLASS-HANDLE WITH CARE; or a similar precautionary marking with letters a minimum of 1-inch high.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:43Z
Check the source to verify that this is the current version before use.