METRIC

MIL-STD-1445A
21 September 1994
SUPERSEDING
DOD-STD-1445
21 October 1987

MILITARY STANDARD

METAL ORGANIC COMPOUNDS, TECHNICAL GRADE



AMSC N/A

FSC 6810

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

FOREWARD

Metal Organic Compounds, Technical Grade (Metric)

1. This Military Standard is approved for use by all Departments and Agencies of the Department of Defense.

2. Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Commander, U.S. Army Edgewood Research, Development and Engineering Center, Attn: SCBR-ENE (STD/SPECS/PKG), Aberdeen Proving Ground, MD 21010-5423, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

3. This standard is approved for use by all Departments and Agencies of the Department of Defense in the selection of items for application. It is intended to prevent the entry of unnecessary items (sizes, types, varieties) into the Department of Defense logistics system. This document is not intended to restrict any service in selecting new items resulting from state-of-the-art changes.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

CONTENTS

PARAGRAPH		PAGE
1.	SCOPE	1
1.1	Purpose	1
1.2	Application	1
2.	APPLICABLE DOCUMENTS	2
2.1	Government documents	2
2.1.1	Specifications, standards, and handbooks	2
2.1.2	Other Government documents, drawings, and publications	3
2.2	Other publications	4
2.3	Order of precedence	6
3.	DEFINITIONS	7
3.1	Definitions of technical terms	7
3.1.1	Flash point	7
3.1.2	Metal alkoxides	7
3.1.3	Metal carboxylates	7
3.1.4	Metal chelates	7
3.1.5	Organometallic compounds	7
3.1.6	Oxidizing agent	7
3.1.7	Reagent grade	7
3.1.8	Reducing agent	7
3.1.9	Technical grade	7
3.2	Abbreviations	8
4.	GENERAL REQUIREMENTS	9
4.1	Packaging data and labeling	9
4.2	Hazardous materials information	9
4.3	Safety	9
4.3.1	Personal protective measures	9
4.3.1.1	Respiratory protection	9
4.3.1.2	Skin protection	10
4.3.1.3	Face and eye protection	10
4.3.1.4	Training	10
4.3.1.5	Exercises	10
4.3.2	Storage conditions	10
4.3.2.1	Flammable, combustible, pyrophoric and ignitable materials	11
4.3.2.2	Water-sensitive fire and explosive hazardous materials	11

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

CONTENTS

PARAGRAPH		PAGE
4.3.2.3	Incompatible materials	12
4.3.3	Chemical hazardous exposure limits	11
4.3.4	Toxicity	12
4.3.4.1	EPA Toxicity (T)	12
4.3.4.2	EPA Acute Hazardous Toxicity (H)	12
4.3.4.3	EPA Toxicity Characteristic Leaching Procedure (TCLP)	12
4.3.4.3	Hazardous toxic constituents	12
4.4	Pollution and disposal	13
4.4.1	Pollution potential	13
4.4.2	Disposal of excess or unserviceable material	13
4.4.3	Disposal and storage of hazardous wastes	13
4.4.3.1	Cleanup of liquid spills	14
4.4.3.2	Ultimate disposal	14
4.4.4	Disclaimer	14
5.	DETAILED REQUIREMENTS	16
5.1	Metal Alkoxides	16
5.1.1	Aluminum Alkoxides	16
5.1.1.1	Aluminum n-Butoxide	16
5.1.1.2	Aluminum sec-Butoxide	17
5.1.1.3	Aluminum tert-Butoxide	17
5.1.1.4	Aluminum Ethoxide	17
5.1.1.5	Aluminum Isopropoxide	18
5.1.1.6	Use	18
5.1.1.7	Safety	18
5.1.1.8	Storage	18
5.1.1.9	Disposal	18
5.1.2	Antimony Alkoxides	18
5.1.2.1	Antimony n-Butoxide	19
5.1.2.2	Antimony Ethoxide	19
5.1.2.3	Antimony Methoxide	19
5.1.2.4	Use	20
5.1.2.5	Safety	20
5.1.2.6	Storage	20
5.1.2.7	Disposal	20
5.1.3	Boron Alkoxides	20
5.1.3.1	Boron n-Butoxide	20
5.1.3.2	Boron Ethoxide	21

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

CONTENTS

PARAGRAPH		PAGE
5.1.3.3	Boron Methoxide	21
5.1.3.4	Boron n-Octoxide	21
5.1.3.5	Boron n-Propoxide	22
5.1.3.6	Use	22
5.1.3.7	Safety	22
5.1.3.8	Storage	22
5.1.3.9	Disposal	22
5.1.4	Germanium Alkoxides	23
5.1.4.1	Germanium n-Butoxide	23
5.1.4.2	Germanium Ethoxide	23
5.1.4.3	Germanium Isopropoxide	23
5.1.4.4	Germanium Methoxide	24
5.1.4.5	Use	24
5.1.4.6	Safety	24
5.1.4.7	Storage	24
5.1.4.8	Disposal	24
5.1.5	Sodium Alkoxides	24
5.1.5.1	Sodium n-Butoxide	24
5.1.5.2	Sodium Ethoxide	25
5.1.5.3	Sodium Methoxide	26
5.1.5.4	Use	28
5.1.5.5	Safety	28
5.1.5.6	Storage	28
5.1.5.7	Disposal	28
5.1.6	Titanium Alkoxides	28
5.1.6.1	Titanium n-Butoxide	29
5.1.6.2	Titanium Ethoxide	29
5.1.6.3	Titanium 2-Ethylhexoxide	29
5.1.6.4	Titanium Isobutoxide	30
5.1.6.5	Titanium Isopropoxide	30
5.1.6.6	Titanium Methoxide	31
5.1.6.7	Use	31
5.1.6.8	Safety	31
5.1.6.9	Storage	31
5.1.6.10	Disposal	31
5.1.7	Zirconium Alkoxides	31
5.1.7.1	Zirconium n-Butoxide	31
5.1.7.2	Zirconium Ethoxide	32

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

CONTENTS

PARAGRAPH		PAGE
5.1.7.3	Zirconium Isopropoxide	32
5.1.7.4	Zirconium n-Propoxide	32
5.1.7.5	Use	33
5.1.7.6	Safety	33
5.1.7.7	Storage	33
5.1.7.8	Disposal	33
5.2	Metal Carboxylates	33
5.2.1	Aluminum Stearate	34
5.2.2	Barium Stearate	35
5.2.3	Calcium Resinate	35
5.2.4	Calcium Stearate	38
5.2.5	Chromium 2-Ethylhexanoate	40
5.2.6	Copper Naphthenate	41
5.2.7	Lead 2-Ethylhexanoate	42
5.2.8	Lead Salicylate	44
5.2.9	Lead Stearate	45
5.2.10	Lithium Stearate	47
5.2.11	Magnesium Stearate	49
5.2.12	Sodium Acetate, Anhydrous	50
5.2.13	Sodium Gluconate	51
5.2.14	Sodium Oxalate	52
5.2.15	Sodium Resinate	54
5.2.16	Zinc Stearate	55
5.3	Metal Chelates	56
5.3.1	Aluminum Acetylacetonate	58
5.3.2	Barium Oxalate	58
5.3.3	Calcium Oxalate	60
5.3.4	Chromic Acetylacetonate	61
5.3.5	Cobaltic Acetylacetonate	62
5.3.6	Cobaltous Acetylacetonate	63
5.3.7	Copper Acetylacetonate	64
5.3.8	Copper 8-Quinolinolate	65
5.3.9	Ferric Acetylacetonate	66
5.3.10	Magnesium Acetylacetonate	67
5.3.11	Manganic Acetylacetonate	67
5.3.12	Manganous Acetylacetonate	68
5.3.13	Nickel Acetylacetonate	69
5.3.14	Ruthenium Acetylacetonte	70

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

CONTENTS

PARAGRAPH		PAGE
5.3.15	Strontium Oxalate	71
5.3.16	Dibutyl Tin Acetylacetonate	72
5.3.17	Titanium Ammonium Dihydroxy Lactate	73
5.3.18	Titanium Diisopropoxide Acetylacetonate	74
5.3.19	Titanium Diisopropoxide Bis(triethanolamine)	75
5.3.20	Titanium Diisopropoxide Ethylacetoacetate	76
5.3.21	Titanium Potassium Oxalate, Dihydrate	77
5.3.22	Vanadyl Acetylacetonate	77
5.3.23	Zinc Acetylacetonate	78
5.3.24	Zinc 8-Quinolinolate	79
5.3.25	Zirconium Acetylacetonate	80
5.4	Organometallic Compounds	81
5.4.1	Aluminum Alkyls	81
5.4.1.1	Tri-n-Butylaluminum	81
5.4.1.2	Triethylaluminum	83
5.4.1.3	Triisobutylaluminum	84
5.4.1.4	Tri-n-Hexylaluminum	85
5.4.1.5	Trimethylaluminum	86
5.4.1.6	Tri-n-Propylaluminum	87
5.4.1.7	Safety	88
5.4.1.8	Storage	88
5.4.1.9	Disposal	88
5.4.2	Aluminum Alkyl Alkoxide	88
5.4.2.1	Diethylaluminum Ethoxide	89
5.4.3	Aluminum Alkyl Halides	90
5.4.3.1	Diethylaluminum Chloride	90
5.4.3.2	Diethylaluminum Iodide	92
5.4.3.3	Diisobutylaluminum Chloride	93
5.4.3.4	Dimethylaluminum Chloride	95
5.4.3.5	Ethylaluminum Dichloride	96
5.4.3.6	Ethylaluminum Sesquichloride	98
5.4.3.7	Isobutylaluminum Dichloride	100
5.4.3.8	Isobutylaluminum Sesquichloride	101
5.4.3.9	Methylaluminum Dichloride	103
5.4.3.10	Methylaluminum Sesquichloride	104
5.4.4	Aluminum Alkyl Hydrides	106
5.4.4.1	Diisobutylaluminum Hydride	106
5.4.4.2	Sodium Aluminum Diethyl Dihydride	108

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

CONTENTS

PARAGRAPH		PAGE
5.4.5	Magnesium Alkyl	109
5.4.5.1	Di-n-Hexylmagnesium	109
5.4.6	Metallocenes	110
5.4.6.1	2,2-Bis(Ethylferrocenyl) Propane	110
5.4.6.2	Ferrocene	111
5.4.6.3	Methylcyclopentadienylmanganese Tricarbonyl	112
5.4.7	Zinc alkyl	113
5.4.7.1	Diethylzinc	113
6.	NOTES	115
6.1	Subject term (key word) listing	115
6.2	Changes from previous issue	118

TABLES		PAGE
I.	Sodium n-Butoxide solution in butanol - physical properties	25
II.	Sodium n-Butoxide solution in butanol - typical chemical analysis	25
III.	Sodium Ethoxide, Anhydrous - requirements and properties	26
IV.	Sodium Ethoxide solution in ethanol - physical properties	26
V.	Sodium Ethoxide solution in ethanol - typical chemical analysis	26
VI.	Sodium Methoxide, anhydrous - chemical and physical requirements	27
VII.	Sodium Methoxide solution in methanol - physical properties	27
VIII.	Sodium Methoxide solution in methanol - requirements and typical chemical analysis	27
IX.	Sodium Methoxide solution in methanol - requirements	28
X.	Barium Stearate - chemical and physical requirements	36
XI.	Calcium Resinate - chemical and physical requirements	37
XII.	Calcium Stearate - chemical and physical requirements	39
XIII.	Chromium 2-Ethylhexoate - chemical and physical requirements	40

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

CONTENTS

TABLES		PAGE
XIV.	Lead 2-Ethylhexoate - chemical and physical requirements	43
XV.	Lead Salicylate - chemical and physical requirements (MIL-L-13788)	44
XVI.	Lead Salicylate - chemical and physical requirements (MIL-L-17700)	45
XVII.	Lead Stearate - chemical and physical requirements	46
XVIII.	Lithium Stearate - chemical and physical requirements	48
XIX.	Magnesium Stearate - chemical and physical requirements	49
XX.	Sodium Acetate, Anhydrous - specification requirements	51
XXI.	Sodium Gluconate - chemical and physical requirements	52
XXII.	Sodium Oxalate, technical - chemical requirements	53
XXIII.	Sodium Oxalate, technical - granulation requirements	53
XXIV.	Sodium Resinate - chemical and physical requirements	54
XXV.	Polydentate Chelate Ligands	57
XXVI.	Barium Oxalate - chemical and physical requirements	59
XXVII.	Calcium Oxalate - chemical and physical requirements	60
XXVIII.	Copper 8-Quinolinolate - commercial specification requirements	65
XXIX.	Strontium Oxalate - chemical and physical requirements	71
XXX.	Zinc 8-Quinolinolate - commercial chemical and physical requirements	80
XXXI.	Tri-n-Butylaluminum - commercial specification requirements	82
XXXII.	Tri-n-Butylaluminum - commercial specification requirements	82
XXXIII.	TEA - chemical requirements	83
XXXIV.	Triethylaluminum - commercial specification requirements	83
XXXV.	Triethylaluminum - commercial specification requirements	84
XXXVI.	Triisobutylaluminum - commercial specification requirements	85
XXXVII.	Triisobutylaluminum - commercial specification requirements	85
XXXVIII.	Tri-n-Hexylaluminum - commercial specification requirements	86

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

CONTENTS

TABLES		PAGE
XXXIX.	Trimethylaluminum - commercial specification requirements	86
XL.	Trimethylaluminum - commercial specification requirements	87
XLI.	Tri-n-Propylaluminum - commercial specification requirements	87
XLII.	Tri-n-Propylaluminum - commercial specification requirements	88
XLIII.	Diethylaluminum Ethoxide - commercial specification requirements	89
XLIV.	Diethylaluminum Ethoxide - commercial specification requirements	89
XLV.	Diethylaluminum Chloride - commercial specification requirements	91
XLVI.	Diethylaluminum Chloride - requirements and typical analysis	91
XLVII.	Diethylaluminum Iodide - requirements and typical analysis	92
XLVIII.	Diisobutylaluminum Chloride - requirements and typical analysis	94
XLIX.	Diisobutylaluminum Chloride - requirements and typical analysis	94
L.	Ethylaluminum Dichloride - commercial analysis range	97
LI.	Ethylaluminum Dichloride - requirements and typical analysis	97
LII.	Ethylaluminum Sesquichloride - commercial analysis range	98
LIII.	Ethylaluminum Sesquichloride - requirements and typical analysis	99
LIV.	Isobutylaluminum Dichloride - commercial analysis range	100
LV.	Isobutylaluminum Sesquichloride - requirements and typical analysis	102
LVI.	Methylaluminum Sesquichloride - commercial analysis range	104
LVII.	Methylaluminum Sesquichloride - requirements and typical analysis	105

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

CONTENTS

TABLES		PAGE
LVIII.	Diisobutylaluminum Hydride - commercial specification requirements	106
LIX.	Diisobutylaluminum Hydride - commercial specification requirements	107
LX.	Sodium Aluminum Diethyl Dihydride solution - typical analysis	108
LXI.	Di-n-Hexylmagnesium solution - typical analysis	109
LXII.	2,2-Bis (Ethylferrocenyl) Propane - chemical and physical requirements	111
LXIII.	Ferrocene (Dicyclopentadienyliron) - commercial requirements	112

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

1. SCOPE

1.1 Purpose. The purpose of this standard is to present the nomenclature, Chemical Abstracts Service Registry Numbers, formulas, physical and chemical properties, specification requirements, military and typical commercial uses, safety information, storage information and disposal information for metal organic compounds, technical grade. This standard does not necessarily include all of the items represented by the title or all those items which are commercially available. It does contain items preferred for use in the selection of metal organic compounds, for application by the Department of Defense. The metal organic compounds are classified and presented as four chemical types.

1. Metal alkoxides
2. Metal carboxylates
3. Metal chelates
4. Organometallic compounds

1.2 Application. Metal organic compounds, technical grade, are used in formulating munition fillings, in formulating lubricants, as chemical intermediates, as catalysts for polymerization reactions, and in the formulation of chemical products for a variety of applications.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation.

SPECIFICATIONS

FEDERAL

TT-P-595	Preservative Coating for Canvas
PPP-C-2020	Chemicals, Liquid, Dry and Paste, Packaging of

MILITARY

MIL-S-210	Sodium Oxalate, Technical (Metric)
JAN-C-263	Calcium Stearate
JAN-B-366	Barium Stearate
MIL-M-542	Magnesium Stearate (For Use in Ammunition)
JAN-C-628	Calcium Oxalate (For Use in Ammunition)
JAN-B-660	Barium Oxalate (For Use in Ammunition)
MIL-L-758	Lead Stearate (For Use in Ammunition)
MIL-S-12210	Strontium Oxalate
MIL-L-13788	Lead Salicylate
MIL-L-17699	Lead 2-Ethyl Hexoate
MIL-L-17700	Lead Salicylate
MIL-W-18142	Wood Preservative Solutions, Oil Soluble, Ship and Boat Use
MIL-C-20470	Calcium Resinate
MIL-F-46032	Fungus Resistant Treatment for Sandbags, Copper Processes
MIL-L-51131	Lithium Stearate
DOD-C-82660	Chromium 2-Ethyl Hexoate, Technical
MIL-C-85493	Catalyst, Burn-Rate 2,2-Bis (Ethylferrocenyl) Propane

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

STANDARDS

FEDERAL

FED-STD-313	Material Safety Data Sheets, Preparation and the Submission of

MILITARY

MIL-STD-12	Abbreviations for Use on Drawings and in Specifications, Standards and Technical Documents

Unless otherwise indicated, copies of Federal and military specifications, standards, and handbooks are available from: (Attn: DODSSP), Customer Service, Standardization Documents Order Desk, 700 Robbins Avenue, Bldg 4D, Philadelphia, PA 19111-5094.

2.1.2 Other Government documents, drawings and publications. The following other Government documents, drawings, and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues are those cited in the solicitation.

CODE OF FEDERAL REGULATIONS (CFR)

Title 29	Department of Labor, Occupational Safety and Health Agency (OSHA); General Industry Standards and Interpretations
Title 40	Environmental Protection Agency (EPA); Hazardous Waste and Consolidated Permit Regulations
Title 49	Department of Transportation (DOT); Hazardous Materials Regulations

DEPARTMENT OF DEFENSE (DOD) PUBLICATIONS

DOD 4145.19-R-1	Storage and Materials Handling
DOD 4160.21-M	Defense Utilization and Disposal Manual
DOD 6050.5-LR	DOD Hazardous Materials Information System, Hazardous Item Listing
TB MED 502 (DLAM 1000.2)	Occupational and Environmental Health Respiratory Protection Program
TB MED 506	Occupational and Environmental Health Occupational Vision

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

TM 38-250	Packaging, Materials Handling - Preparation of Hazardous Materials for Military Air Shipment
AR 11-34	The Army Respiratory Protection Program

DEPARTMENT OF HEALTH AND HUMAN SERVICES (DHHS)

U.S. Public Health Service National Toxicology Program, Fourth Annual Report on Carcinogens, Summary of 1985.

FEDERAL ACQUISITION REGULATION

Contractual acquisition of Material Safety Date Sheet Information (Paragraph 52.223-3).

NATIONAL INSTITUTE FOR OCCUPATIONAL SAFETY AND HEALTH (NIOSH)

Registry of Toxic Effects of Chemical Substances
Recommendation for Environmental Exposure Limits

RESOURCE CONSERVATION AND RECOVERY ACT (RCRA)

(Public Law 94-580 Management of Items Classified as Hazardous Waste.)

(Copies of specifications, standards, handbooks, drawings, and publications required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting officer.)

2.2 Non-Government publications. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted are those listed in the issue of the DODISS cited in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS are the issues of the documents cited in the solicitation.

AMERICAN CONFERENCE OF GOVERNMENTAL INDUSTRIAL HYGIENISTS (ACGIH)

Threshold Limit Values (TLVs) for Chemical Substances in the Work Environment Adopted by American Conference of Governmental Industrial Hygienists (ACGIH) with Intended Changes.

Volume 13: Transactions of ACGIH Activities 1985 Conference.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

(Application for copies should be addressed to American Conference of Governmental Industrial Hygienists, Kemper Woods Center, 1330 Kemper Meadow Drive, Cincinnati, Ohio 45240.)

AMERICAN NATIONAL STANDARDS INSTITUTE (ANSI)

ANSI Z358.1-1990 for Emergency Eyewash and Shower Equipment

(Application for copies should be addressed to American National Standards Institute, 11 West 42nd Street, New York, NY 10036.)

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

ASTM E 11 Standard Specification for Wire-Cloth Sieves for Testing Purposes
ASTM E 380 Standard for Metric Practice

(Application for copies should be addressed to American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

CHEMICAL ABSTRACTS SERVICE REGISTRY

The Chemical Abstracts Service (CAS) Registry Number provides a key to access the wealth of information available through CAS.

(For details on how to search for CAS files and database using the Registry Number, contact Chemical Abstracts Service, Customer Services, P.O. Box 3012, Columbus, Ohio 43210.)

INTERNATIONAL AGENCY FOR RESEARCH ON CANCER (IARC)

Monographs on the Evaluation of the Carcinogenic Risk of Chemicals to Man.

(Application for copies should be addressed to World Health Organization, International Agency for Research on Cancer, 49 Sheridan Street, Albany, New York 12210.)

INTERNATIONAL AIR TRANSPORT ASSOCIATION (IATA)

Dangerous Goods Regulations

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

(Applications for copies should be addressed to the Publications Assistant, International Air Transport Association, 2000 Peel Street, Montreal, Quebec, Canada H3A 2R4.)

INTERNATIONAL CIVIL AVIATION ORGANIZATION (ICAO)

Technical Instructions for the Safe Transport of Dangerous Goods by Air, DOC 9284-AN/905.

(Application for copies should be addressed to the Document Sales Unit, International Civil Aviation Organization, 1000 Sherbrooke Street West, Suite 400, Montreal, Quebec, Canada H3A, 2R4.)

INTERNATIONAL MARITIME ORGANIZATION (IMO)

International Maritime Dangerous Goods Code (IMDG), Publication 200 89.10.E, Vols. I-IV.

(Application for copies should be addressed to the International Maritime Organization, 4 Albert Embankment, London SEI 7SR.)

NATIONAL FIRE PROTECTION ASSOCIATION (NFPA)

National Fire Codes

(Application for copies should be addressed to National Fire Protection Association, Battery March Park, Quincy, MA 02269.)

THE UNITED STATES PHARMACOPEIA CONVENTION, INC. - NATIONAL FORMULARY (USP-NF)

The United States Pharmacopeia - National Formulary

(Application for copies should be addressed to The United States Pharmacopeia Convention, Inc. - National Formulary, Order Processing Dept., P.O. Box 2248, 12601 Twinbrook Parkway, Rockville, MD 20852.)

2.3 **Order of Precedence.** In the event of a conflict between the text of this document and the references cited herein, the text of this document shall take precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

3. DEFINITIONS

3.1 Definitions of Technical Terms.

3.1.1 Flash point. The lowest temperature at which a liquid or solid will give off a vapor sufficient to form an ignitable mixture in air.

3.1.2 Metal Alkoxides. Metal alkoxides are produced by the reaction of alcohols with active metals.

3.1.3 Metal Carboxylates. Metal carboxylates are the alkali, alkaline-earth, and heavy metal salts of the carboxylic acids.

3.1.4 Metal Chelates. The holding of a metal atom between two atoms of a simple molecule is called chelation.

3.1.5 Organometallic Compounds. An organometallic compound is one in which there is a bonding interaction (ionic or covalent, localized or delocalized) between one or more carbon atoms, of an organic group or molecule, and a main group, transition, lanthanide, or actinide metal atom or atoms.

3.1.6 Oxidizing agent. A substance that gains electrons as a result of an oxidation-reduction reaction. It causes an increase in the oxidation state of another substance.

3.1.7 Reagent grade. Denotes reagent grade chemicals which do not bear a label stating the percentages of the important impurities present. Reagent grade chemicals have limited use in analytical work because of the uncertainty as to the kind and amount of impurities present. These chemicals find extensive use in laboratory synthesis and in certain analytical procedures where the inherent impurities are not critical to the intended reaction.

3.1.8 Reducing agent. A substance that loses electrons during an oxidation-reduction reaction. It causes a decrease in the oxidation state of another substance.

3.1.9 Technical grade. Denotes a quality of chemicals which are generally used for industrial, solvent, and manufacturing applications. Generally, specific processes are not employed by the manufacturer to limit all the impurities, aside from the normal precautions which are taken in the manufacturing process. A technical chemical may be specially processed to reduce specific impurities so as to suit the chemical to a given industrial application. In such cases, the identification of the items must be further expanded to indicate the specific impurities limitation.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

3.2 **Abbreviations.** The use of abbreviations in this military standard is in accordance with MIL-STD-12 where applicable. Metric system abbreviations and symbols are in accordance with ASTM E 380. Other abbreviations are as follows:

ACGIH	American Conference of Governmental Industrial Hygienists
ANSI	American National Standards Institute
BM	Bureau of Mines
CAS	Chemical Abstracts Service
CFR	Code of Federal Regulations
CHEMTREC	Chemical Transportation Emergency Center
DOD	Department of Defense
DOT	Department of Transportation
DRMO	Defense Reutilization and Marketing Office
DRMS	Defense Reutilization and Marketing Service
EPA	Environmental Protection Agency
FW	Formula Weight
HMIS	Hazardous Materials Information System
IARC	International Agency for Research on Cancer
MSDS	Material Safety Data Sheet
MSHA	Mine Safety and Health Administration
NIOSH	National Institute for Occupational Safety and Health
OSHA	Occupational Safety and Health Administration
PEL	Permissable Exposure Limit
RCRA	Resource Conservation and Recovery Act
TCLP	Toxicity Characteristic Leaching Procedure

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

4. GENERAL REQUIREMENTS

4.1 Packaging data and labeling. All chemicals included in this standard shall be packaged in accordance with Federal Specification PPP-C-2020 and all applicable documents referenced therein. When the commodity is a hazardous material, the shipping containers for domestic shipments using commercial carriers shall be labeled in accordance with current Department of Transportation (DOT) Hazardous Materials Regulations applicable to each chemical. Likewise, shipping containers for international shipments using commercial carriers shall be labeled in accordance with the International Hazardous Materials Regulations appropriate for the mode of shipment used (see Para. 2.2 herein). When shipping hazardous material by military aircraft, the requirements of TM 38-250 shall apply. Additionally, each item shall be packaged and labeled as specified in the applicable contract or order. All labels shall comply with Hazard Communication Standard, 29 CFR 1910.1200 (f) and the appropriate domestic or International Hazardous Materials Regulations.

4.2 Hazardous materials information. DOD 6050.5, DOD Hazardous Materials Information System (HMIS) acquires, reviews, stores, and disseminates Material Safety Data Sheet (MSDS) information for all hazardous materials used by DOD. The contractual acquisition of a MSDS is accomplished through use of Federal Acquisition Regulation, paragraph 52.223-3, Hazardous Material Identification and Material Safety Data. The MSDS is prepared in accordance with the instructions in FED-STD-313 and shall comply with the requirements of Hazard Communication Standard, 29 CFR 1910.1200 (g).

4.3 Safety.

4.3.1 Personal protective measures. The necessary respiratory, eye and skin protection to be used when handling chemicals shall be prescribed by the responsible installation industrial hygiene, medical and safety authorities.

4.3.1.1 Respiratory protection. Respirators, approved by the National Institute for Occupational Safety and Health (NIOSH) or the Mine Safety and Health Administration (MSHA) or by particular respiratory schedules of the Bureau of Mines (BM) for the compounds being used, may be employed for intermittent, non-routine exposure (i.e., not exceeding 1 hour/day for 1 day/week), when the installation medical authority determines that there are no feasible engineering or work practice controls, during interim periods when engineering controls are being designed and/or installed, during emergencies, or for supplementing other control measures (refer to TB MED 502 or DLAM 1000.2). Ventilation containment, process controls, or other feasible engineering controls shall be adequate to remove hazardous concentrations. Employees assigned to use respiratory protective

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

equipment shall be included in a respiratory protection program that meets the minimal requirements as stipulated in AR 11-34, "The Army Respiratory Protection Program".

4.3.1.2 Skin protection. Personnel using these compounds shall be provided with and required to use impervious gloves, sleeves, aprons, and boots whenever indicated. Protective creams and ointments commonly known as "barrier creams" may be of value in certain cases. However, barrier creams shall not be used to replace protective clothing. During use, avoid contact with eyes, skin and clothing. Wash with soap and water after handling. When not in use, keep in a tightly closed container. In case of contact with the eyes, remove any contact lenses and irrigate with copious amounts of water for at least 20-30 minutes, and obtain medical attention. Eye lavages and emergency showers shall be located where there is a potential for direct contact with harmful chemicals. All emergency eyewashes and emergency showers shall be activated weekly to flush the line and to verify proper operation in accordance with ANSI standard Z-358-1-1990.

4.3.1.3 Face and eye protection. Personnel using these compounds shall be provided with and required to wear chemical splash-proof safety goggles. In addition, face shields shall be provided and worn over the goggles if splashing could occur. In case of contact with the eyes, immediately irrigate with copious amounts of water for at least 20-30 minutes, and obtain medical attention. (Refer to TB MED 506.)

4.3.1.4 Training. Employers shall provide employees with training and information, including MSDSs, on all chemical items in their work area, in accordance with 29 CFR 1910.1200 (h) and, 49 CFR 172 Subpart H, as may be applicable, to ensure that employees know potential hazards of the chemicals with which they come in contact and the symptoms of exposure, as well as how these chemicals that affect the body and bodily functions. Employees shall be adequately trained to render first aid. Additionally, any employee involved with the packaging, preparation, handling or causing a hazardous material to be shipped or transported, shall be provided with all of the training specified in 49 CFR 172 Subpart H.

4.3.1.5 Exercises. Participation in training exercises shall be stressed to demonstrate skills in the use of personal protective equipment and emergency response equipment.

4.3.2 Storage conditions. DOD 4145.19-R-1 describes general storage practices and requirements for hazardous materials in the DOD supply system. Specific requirements provided in the following paragraphs are supplementary in nature and shall be observed in consonance with the DOD storage regulations.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

4.3.2.1 Flammable, combustible, pyrophoric and ignitable materials. A flammable material is generally any solid, liquid, vapor or gas that ignites easily and burns rapidly. Combustible materials are generally those that are difficult to ignite and burn slowly. The DOT, in 49 CFR 173.115, defines a flammable liquid as one having a closed cup flash point below 37.8°C (100°F). In the DOT's Final Rule to Docket HM-181, the flash point for a flammable liquid was raised from below 37.8°C (100°F) to not more than 60.5°C (141°F). A combustible liquid is defined, by DOT in the above reference, as one having a closed cup flash point at or above 60.5°C (141°F) and below 93.3°C (200°F). A pyrophoric liquid is defined, by DOT in the above reference, as one that ignites spontaneously in dry or moist air at or below 54.5°C (130°F). Materials with flash points of 93.3°C (200°F) or higher are to be considered as burnable. The DOT has permitted, for domestic shipments only and except for shipments by air or water, that "...a flammable liquid with a flash point at or above 38°C (100°F)..." and which does not meet the definition of any other hazard class as defined in 49 CFR, may be re-classed as a combustible liquid. The Environmental Protection Agency (EPA), in 40 CFR 261.21, designates the criteria for flammable and combustible materials and oxidizers that exhibit the characteristic of ignitability (I).* Liquids with closed cup flash points of less than 60°C (140°F) are defined by EPA as ignitable. The autoignition point (temperature) of a substance is generally defined as the minimum temperature required to initiate or cause self-sustained combustion in the absence of a spark or flame. Materials that ignite easily under normal industrial conditions are considered to be dangerous fire hazards. Such materials shall be stored in a manner to prevent ignition and combustion. Easily ignitable substances, such as reducing agents, shall be kept away from strong oxidizing agents. All containers shall be tightly sealed. It is important to provide adequate ventilation in storage areas, and to locate the storage areas of these items away from fire hazards. Ample fire-control equipment shall be easily accessible. Storage buildings, rooms and cabinets shall comply with provisions of the National Fire Codes. The building shall be electrically grounded and signs posted to prevent the lighting of matches or smoking in the area. Flammable storage areas shall be equipped with smoke or fire detection equipment.

4.3.2.2 Water-sensitive fire and explosive hazardous materials. These materials include compounds that react violently or form explosive mixtures on contact with water or steam, or react with water to produce toxic gases. Such waste materials exhibit the characteristic of reactivity (R) as designated by the EPA in 40 CFR 261.23. These materials shall be stored in well-ventilated, cool, dry areas. All containers shall be tightly sealed. These materials are a fire hazard in contact with water or moisture; therefore, it is essential that no sprinkler be used. Otherwise, the building shall conform to that required for storage of flammable materials. The building shall be waterproof, located on high ground, separated from other storage areas and meet National Fire Codes.

*Refers to materials that have become hazardous waste.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

4.3.2.3 Incompatible materials. Materials that are chemically incompatible shall be segregated in the storage of both serviceable and unserviceable items. The degree of segregation will depend upon DOD 4145.19-R-1 and local supplementary requirements that insure safe storage conditions. Hazardous storage compatibility codes are provided in the HMIS referred to in 4.2. Hazardous material storage compatibility may also be determined through use of the EPA Hazardous Materials Compatibility Chart. This chart determines reactions of most binary combinations of hazardous wastes by assigning Reactivity Group Numbers (RGNs) based on chemical classes and general chemical reactivities.

4.3.3 Chemical hazardous exposure limits. Chemical hazardous exposure limits for airborne concentrations of substances are obtained from the current TLVs in Threshold Limit Values for Chemical Substances in the Work Environment adopted by the American Conference of Governmental Industrial Hygienists (ACGIH); current Occupational Safety and Health Administration (OSHA) Permissible Exposure Limits (PEL), 29 CFR 1910.1000; and NIOSH Recommendation for Environmental Exposure Limits. Such information is also shown in MSDSs and the HMIS referred to in 4.2.

Carcinogenic substances are listed by OSHA in Category I for confirmed carcinogens, and in Category II for suspected carcinogens. Category I substances have standard exposure limits set at the lowest possible levels. Category II substances have standard exposure limits set to prevent acute or chronic effects.

4.3.4 Toxicity. Toxicity information for chemical compounds is available from various publications and from MSDSs, which are collected in the DOD 6050.5-LR Hazardous Materials Information System.

4.3.4.1 EPA Toxic (T). Some waste chemical compounds have been designated by the EPA as toxic wastes (T) in accordance with the criteria shown in 40 CFR 261.11(a)(3).* Some commercial chemical wastes are listed as toxic wastes under 40 CFR 261.33 (f).

4.3.4.2 EPA Acute Hazardous Toxicity (H). Some waste chemical compounds have been designated by the EPA as acute hazardous wastes (H) based on toxicity in accordance with the criteria shown in 40 CFR 261.11(a)(2).* Some commercial chemical wastes are listed as acutely hazardous in toxicity under 40 CFR 261.33(e).

4.3.4.3 EPA Toxicity Characteristic Leaching Procedure (TCLP). This procedure is used to determine the properties of a waste that are directly related to the potential of the waste to pose a hazard to groundwater when disposed of in a landfill environment. It

*Refers to materials that have become hazardous waste.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

replaces the EPA EP toxicity test. The TCLP procedure is contained in EPA Method No. 1311, SW-846. Some 40 chemical contaminants have been designated by EPA as being a hazard to groundwater in a landfill environment. (See 40 CFR 261.24)*

4.4 Pollution and disposal.

4.4.1 Pollution potential. All items described in this standard shall be assumed to have a pollution potential. However, to minimize this potential, the proper use, storage and disposal methods shall be strictly followed.

4.4.2 Disposal of excess or unserviceable material. To minimize disposal problems, it is recommended that no more than a one year's supply of each item listed in this standard be stocked. When stocks have been declared excess or unserviceable, they will be disposed of in accordance with the Defense Utilization and Disposal Manual, DOD 4160.21-M, and applicable DOD Policy Memoranda. Guidance can be obtained from your servicing Defense Reutilization and Marketing Office (DRMO) on procedures required for proper reporting and turn-in.

4.4.3 Disposal and storage of hazardous wastes. Items are classified and managed as hazardous wastes as defined by the Resource Conservation and Recovery Act (RCRA) (Public Law 94-580). Items have been identified as meeting the characteristics of a hazardous waste (i.e., ignitable, corrosive, reactive or are subject to Toxicity Characteristic Leaching Procedure (TCLP); or they are listed (e.g., toxic or acute hazardous wastes) according to Identification and Listing of Hazardous Waste, 40 CFR Part 261, or have been determined to be hazardous wastes by declaration of the Defense Reutilization and Marketing Service (DRMS) in accordance with procedures set forth in DOD 4160.21-M. Disposal of such items shall be managed in accordance with the Installation Environmental Office, the DRMO, or the Safety and Health Office to insure proper reporting of disposal and treatment actions to the US EPA and State, and shall be managed in accordance with Federal, State and local laws. The three main disposal methods are turn-in to the DRMO, on-post disposal by installation personnel, or disposal by commercial contract. Hazardous wastes that cannot be used or disposed of as stated in 4.4.3.2 shall be stored under environmentally safe conditions until suitable methods of disposal are determined. Short-term storage (less than 90 days) requires proper containment (i.e., packaging and facilities) in accordance with 40 CFR 262.34 of the above reference. Long-term storage (greater than 90 days) requires permitting by the EPA or by the State under Public Law 94-580 (RCRA), in compliance with the requirements of 40 CFR, Parts 264 and 265. Physical custody will be accomplished by the activity with conforming storage or most nearly conforming storage. When physical custody is in question, the Post Commander will make the final decision. In all cases where the wastes are to be collected, stored, transported and disposed of at a State or local permitted disposal facility, the identity and description of the waste shall be maintained and recorded

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

in accordance with 40 CFR Part 262. Transportation of the waste must be in accordance with Part 263 of the above reference, Standards Applicable to Transporters of Hazardous Waste. State and/or local regulations may be more stringent than Federal requirements. It is essential that the Installation Environmental Office review all disposal actions for compliance with all applicable regulations.

4.4.3.1 Cleanup of liquid spills. To control the migration of spilled or leaking liquids, dike around the item with an inert, dry absorbent (e.g., clay sawdust or vermiculite) or follow installation spill plans (Spill Prevention Control and Countermeasure Plan and Installations Spill Contingency Plan). Control entry to the spill site and segregate salvageable materials away from the spill area. Initiate waste cleanup operations immediately in accordance with local procedures. The residue shall be safely handled and transported to an approved or permitted disposal or storage facility. Packaging, labeling, transportation and record-keeping requirements for this waste material are determined by the appropriate Federal and State agencies and local procedures. It is recommended that all activities involving disposal preparation and transportation to commercial facilities be properly coordinated with the appropriate Federal and State agencies responsible for health and environmental aspects of hazardous wastes. It is imperative that the proper description of the waste accompany the packaged item at all times. Final disposal of the waste item shall be accomplished by reutilization, transfer, donation or sales by DRMO in accordance with DOD 4160.21-M or by ultimate disposal as described in 4.4.3.2. Spill residue, including contaminants, to be turned into the DRMO shall first be properly identified, containerized, and labeled. For large scale spills that grossly contaminate the environment, the Chemical Transportation Emergency Center (CHEMTREC) can be called for assistance (1-800-424-9300). Applicable procedures of the local spill control plan shall be followed. Necessary respiratory, eye, and skin protection measures are to be used while performing cleanup operations.

4.4.3.2 Ultimate disposal. Ultimate disposal shall be accomplished at a permitted or approved hazardous waste treatment or disposal facility designated by the Installation Environmental Office, DRMO, or Safety and Health Offices.

4.4.4 DISCLAIMER. RECOMMENDED DISPOSAL INSTRUCTIONS ARE FORMULATED FOR USE BY ELEMENTS OF THE DEPARTMENT OF DEFENSE. THE UNITED STATES OF AMERICA IN NO MANNER WHATSOEVER, EITHER EXPLICITLY OR IMPLICITLY, WARRANTS, STATES, OR INTENDS SAID INSTRUCTION TO HAVE ANY APPLICATION, USE OR VIABILITY BY OR TO ANY PERSON OR PERSONS CONTRACTING OUTSIDE THE DEPARTMENT OF DEFENSE OR ANY PERSON OR PERSONS CONTRACTING WITH ANY INSTRUMENTALITY OF THE UNITED STATES OF AMERICA, AND DISCLAIMS ALL LIABILITY FOR SUCH USE. ANY PERSON USING THESE INSTRUCTIONS WHO IS NOT A MILITARY OR CIVILIAN EMPLOYEE OF THE UNITED STATES OF AMERICA SHOULD SEEK COMPETENT PROFESSIONAL ADVICE

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

TO VERIFY AND ASSUME RESPONSIBILITY FOR THE SUITABILITY OF THESE INSTRUCTIONS TO HIS PARTICULAR SITUATION, REGARDLESS OF SIMILARITY TO A CORRESPONDING DEPARTMENT OF DEFENSE OR OTHER GOVERNMENT SITUATION.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5. DETAILED REQUIREMENTS

5.1 Name. Metal Alkoxides.

Alcohols, as weak acids, can react with active metals, such as sodium, to form hydrogen gas and the metal alkoxides. Since alcohols are weaker acids than water, sodium alkoxides cannot be prepared by the reaction of the alcohol with sodium hydroxide. Aluminum, as an active metal, can also react with alcohols in the presence of mercuric chloride catalyst to form the metal alkoxides. Aluminum alkoxides can also be prepared by reacting aluminum chloride with sodium alkoxides.

Many metal chlorides undergo solvation and/or partial solvolysis with alcohols. In the presence of a base, such as ethoxide ion, ammonia, or pyridine, the replacement of chloride is complete and the metal alkoxide are formed. Titanium alkoxides and other transition metal alkoxides can be obtained by such reactions.

The metal alkoxides are polymeric, and the titanium alkoxides, $Ti(OC_2H_5)_4$, $Ti(OC_3H_7)_4$, and $Ti(OC_4H_9)_4$, are known to be trimeric. The metal alkoxides are also polymeric in solution in inert organic solvents. Monomeric species can exist in very dilute solutions.

The metal alkoxides are reactive with water. They are useful in organic synthesis.

Alcohols can react with a number of inorganic oxygen acids or very reactive inorganic halides to form esters. Some metal alkoxides, such as those of boron and titanium, are also considered to be inorganic esters, and can be named as trialkyl borates and tetraalkyl titanates.

5.1.1 Aluminum Alkoxides.

5.1.1.1 Name. Aluminum n-Butoxide $Al[O(CH_2)_3CH_3]_3$ FW 246.33
Aluminum butylate CAS 3085-30-1

5.1.1.1.1 Technical description. Aluminum n-butoxide (pure) is in the form of white crystals with a density of 1.025 g/cm^3. It has a melting point of 101.5°C and a boiling point of 290° to 310°C at 30 mm Hg. It is soluble in aliphatic, aromatic and chlorinated hydrocarbons.

5.1.1.1.2 Specification. Manufacturer's requirements. (No Government specification.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.1.1.1.2.1 Requirements. Commercially available aluminum n-butoxide has a purity of 90 to 95 percent.

5.1.1.2 Name. Aluminum sec-Butoxide $Al[OCH(CH_3)C_2H_5]_3$ FW 246.33
Aluminum sec-butylate CAS 2269-22-9

5.1.1.2.1 Technical description. Aluminum sec-butoxide is a liquid with a density of 0.967 g/cm^3, and a boiling point of 200° to 206°C at 30 mm Hg. The closed cup flash point is 27°C (82°F). The theoretical aluminum content is 10.97 percent.

5.1.1.2.2 Specification. Manufacturer's requirements. (No Government specification.)

5.1.1.2.2.1 Requirements. Commercially available aluminum sec-butoxide has an aluminum content of 10.7%, minimum, corresponding to a minimum assay of 97.7 percent.

5.1.1.3 Name. Aluminum tert-Butoxide $Al[OC(CH_3)_3]_3$ FW 246.33
Aluminum tert-butylate CAS 556-91-2

5.1.1.3.1 Technical description. Aluminum tert-butoxide (pure) is in the form of white crystals with a density of 1.0251 g/cm^3. It sublimes at 180°C, and has a melting point above 300°C in a sealed tube. It is very soluble in organic solvents.

5.1.1.3.2 Specification. Manufacturer's requirements. (No Government specification.)

5.1.1.3.2.1 Requirements. Commercially available aluminum tert-butoxide is supplied with an assay of 97 percent.

5.1.1.4 Name. Aluminum Ethoxide $Al(OC_2H_5)_3$ FW 162.17
Aluminum ethylate CAS 555-75-9
Triethoxyaluminum
Aluminum triethoxide

5.1.1.4.1 Technical description. Aluminum ethoxide (pure) is in the form of white crystals with a density of 1.142 g/cm^3. It has a melting point of 134°C, and a boiling point of 205°C at 14 mm Hg. It is very slightly soluble in alcohol and ether. It is decomposed by water.

5.1.1.4.2 Specification. Manufacturer's requirements. (No Government specification.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.1.1.4.2.1 Requirements. Commercially available aluminum ethoxide is supplied with an assay of 97 percent.

5.1.1.5 Name. Aluminum Isopropoxide $Al[OCH(CH_3)_2]_3$ FW 204.25
Aluminum isopropylate CAS 555-31-7

5.1.1.5.1 Technical description. Aluminum isopropoxide (pure) is in the form of white crystals with a density of 1.0346 g/cm^3. It has a melting point of 118.5°C, and a boiling point of 140.5°C at 8 mm Hg. It is soluble in alcohol, benzene and chloroform. The theoretical aluminum content is 13.2 percent.

5.1.1.5.2 Specification. Manufacturer's requirements. (No Government specification.)

5.1.1.5.2.1 Requirements. Commercially available aluminum isopropoxide has an aluminum content of 12.9%, minimum, corresponding to a minimum assay of 97.5 percent.

5.1.1.6 Use. Aluminum alkoxides provide a nonaqueous solvent soluble form of aluminum for use in the synthesis of organic compounds, as reducing agents and as transesterification catalysts. Other uses include the production of fabric water-proofing agents, printing ink modifiers, lubricants, and the curing of epoxy resins.

5.1.1.7 Safety. Aluminum alkoxides are flammable liquids or solids, and can emit irritating and toxic fumes if heated to decomposition. They are decomposed by water with the release of flammable alcohol vapors. There are no PELs or TLVs referenced for aluminum alkoxides. They are strong local irritants of eyes, skin and mucous membranes, so contact shall be avoided. (Refer to 4.3.1.)

5.1.1.8 Storage. Aluminum alkoxides shall be stored in tightly sealed corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

5.1.1.9 Disposal. In case of solid spills, recover in dry state and place in containers for disposal. In case of small liquid spills, absorb with non-reactive absorbent and place in containers for disposal. In case of large liquid spills, dike to prevent spreading. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

Aluminum alkoxides have EPA Hazardous Waste Classifications - Ignitable, Waste No. D001; and Reactive, Waste No. D003.

5.1.2 Antimony Alkoxides.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.1.2.1 Name. Antimony n-Butoxide $Sb[O(CH_2)_3CH_3]_3$ FW 341.10
Antimonous butoxide CAS 2155-74-0
Antimony (III) butoxide
Antimony butylate
Tributyl antimonite

5.1.2.1.1 Technical description. Antimony n-butoxide is a liquid with a boiling point of 133° to 135°C at 4 mm Hg. The theoretical antimony content is 35.7 percent.

5.1.2.1.2 Specification. Manufacturer's requirements. (No Government specification.)

5.1.2.1.2.1 Requirements. Commercially available antimony n-butoxide has an analysis for antimony content of 36.0 percent.

5.1.2.2 Name. Antimony Ethoxide $Sb(OC_2H_5)_3$ FW 256.93
Antimonous ethoxide CAS 10433-06-4
Antimony (III) ethoxide
Antimony ethylate
Triethyl antimonite

5.1.2.2.1 Technical description. Antimony ethoxide (pure) is a colorless liquid with a density of 1.524 g/cm^3, and a boiling point of 95°C at 11 mm Hg. It is soluble in organic solvents. The theoretical carbon content is 28.1%, and the hydrogen content is 5.88 percent.

5.1.2.2.2 Specification. Manufacturer's requirements. (No Government specification.)

5.1.2.2.2.1 Requirements. Commercially available antimony ethoxide has an analysis for carbon content of 27.9% and a hydrogen content of 5.87 percent.

5.1.2.3 Name. Antimony Methoxide $Sb(OCH_3)_3$ FW 214.88
Antimonous methoxide CAS 29671-18-9
Antimony (III) methoxide
Antimony methylate
Trimethyl antimonite

5.1.2.3.1 Technical description. Antimony methoxide is a crystalline solid. It is a water-sensitive compound.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.1.2.3.2 Specification. Manufacturer's requirements. (No Government specification.)

5.1.2.3.2.1 Requirements. Commercially available antimony methoxide with an assay of 95 percent.

5.1.2.4 Use. Antimony alkoxides provide a nonaqueous solvent soluble form of antimony for use in chemical synthesis.

5.1.2.5 Safety. Antimony alkoxides are flammable liquids, or flammable or burnable solids, and can emit irritating and toxic fumes if heated to decomposition. They are decomposed by water with the release of flammable alcohol vapors. The PEL and TLV for antimony compounds, as Sb, are 0.5 mg/m^3. Antimony alkoxides are strong irritants of the eyes, skin and mucous membranes, so contact shall be avoided. (Refer to 4.3.1.)

5.1.2.6 Storage. Antimony alkoxides shall be stored in tightly sealed corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

5.1.2.7 Disposal. In case of solid spills, recover in dry state and place in containers for disposal. In case of small liquid spills, absorb with non-reactive absorbent and place in containers for disposal. In case of large liquid spills, dike to prevent spreading. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

Antimony alkoxides have EPA Hazardous Waste Classifications - Ignitable, Waste No. D001; Reactive, Waste No. D003; and Toxic.

5.1.3 Boron Alkoxides.

5.1.3.1 Name. Boron n-Butoxide
Boron tributoxide
Tributoxyborane
Tributyl borate

$B[O(CH_2)_3CH_3]_3$

FW 230.16
CAS 688-74-4

5.1.3.1.1 Technical description. Boron n-butoxide is a colorless liquid with a boiling point of 103° to 106°C at 8 mm Hg. It is decomposed by water.

5.1.3.1.2 Specification. Manufacturer's requirements. (No Government specification.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.1.3.1.2.1 Requirements. Commercially available boron butoxide has a density of 0.853 g/cm^3, a refractive index of 1.4100, a melting point of -70°C, and a boiling point of 230° to 235°C. The closed cup flash point is 93.3°C (200°F).

5.1.3.2 Name. Boron Ethoxide — $B(OC_2H_5)_3$ — FW 146.00
Boron triethoxide — CAS 150-46-9
Triethoxyborine
Triethyl borate

5.1.3.2.1 Technical description. Boron ethoxide (pure) is a colorless liquid with a refractive index of 1.381, and a density of 0.864 g/cm^3, a melting point of -84.8°C, and a boiling point of 117.4°C. It is decomposed by water.

5.1.3.2.2 Specification. Manufacturer's requirements. (No Government specification.)

5.1.3.2.2.1 Requirements. Commercially available boron ethoxide has an assay of 97 percent. The closed cup flash point is 11°C (52°F).

5.1.3.3 Name. Boron Methoxide — $B(OCH_3)_3$ — FW 103.92
Boron trimethoxide — CAS 121-43-7
Trimethoxyborine
Trimethyl borate

5.1.3.3.1 Technical description. Boron methoxide (pure) is a colorless liquid with a refractive index of 1.3610 at 20°C, and a density of 0.915 g/cm^3, a melting point of -29° C, and a boiling point of 68.7°C. It is soluble in alcohol and ether, and is decomposed by water.

5.1.3.3.2 Specification. Manufacturer's requirements. (No Government specification.)

5.1.3.3.2.1 Requirements. Commercially available boron methoxide has a boiling range of 67° to 69°C. It has a closed cup flash point of -8°C (16°F).

5.1.3.4 Name. Boron n-Octoxide — $B[O(CH_2)_7CH_3]_3$ — FW 398.47
Boron trioctoxide — CAS 2467-12-1
Trioctoxyborine
Tri-n-octyl borate

5.1.3.4.1 Technical description. Boron n-octoxide is a colorless liquid with a refractive index of 1.4350 at 25°C, and a density of 0.846 g/cm^3 at 23°C, a boiling point

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

of 192° to 194°C at 2 mm Hg, and 378° to 379°C at 760 mm Hg. It is soluble in hydrocarbon fluids and carbon tetrachloride. It is decomposed by water or moisture by hydrolysis. The theoretical boron content is 2.72 percent.

5.1.3.4.2 Specification. Manufacturer's requirements. (No Government specification.)

5.1.3.4.2.1 Requirements. Commercially available boron octoxide has a boron content of 2.74 percent. It has an open cup flash point of 188°C (370°F).

5.1.3.5 Name. Boron n-Propoxide $B(OCH_2CH_2CH_3)_3$ FW 188.08
Boron tripropoxide CAS 688-71-1
Tripropoxyborine
Tripropoxyboron
Tripropyl borate

5.1.3.5.1 Technical description. Boron n-propoxide (pure) is a liquid with a density of 0.867 g/cm^3, a refractive index of 1.3948 at 20°C, and a boiling point of 175°C.

5.1.3.5.2 Specification. Manufacturer's requirements. (No Government specification.)

5.1.3.5.2.1 Requirements. Commercially available boron n-propoxide has a boiling point of 175° to 177°C. The closed cup flash point is 32°C (90°F).

5.1.3.6 Use. Boron alkoxides provide a nonaqueous solvent soluble form of boron for use in chemical synthesis. Other applications include uses as solvents, as dehydrating agents, in flame retardants for textiles, in brazing and welding fluxes, and in neutron scintillation counters.

5.1.3.7 Safety. Boron alkoxides are flammable, combustible or burnable liquids, and can emit irritating and toxic fumes if heated to decomposition. They are decomposed by water with the release of flammable alcohol vapors. There are no PELs or TLVs referenced for boron alkoxides. They are local irritants of eyes, skin and mucous membranes, so contact shall be avoided. (Refer to 4.3.1.)

5.1.3.8 Storage. Boron alkoxides shall be stored in tightly sealed corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

5.1.3.9 Disposal. In case of small liquid spills, absorb with nonreactive absorbents and place in containers for disposal. In case of large liquid spills, dike to prevent

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

spreading. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

Boron alkoxides have EPA Hazardous Waste Classifications - Ignitable, Waste No. D001 (depending on the flash point); and Reactive, Waste No. D003.

5.1.4 Germanium Alkoxides.

5.1.4.1 Name. Germanium n-Butoxide $Ge[O(CH_2)_3CH_3]_4$ FW 365.05
Germanium (IV) butoxide CAS 25063-27-8
Tetrabutoxygermanium
Tetrabutyl germanate

5.1.4.1.1 Technical description. Germanium n-butoxide is a liquid with a refractive index of 1.4255, a density of 1.0173 g/cm^3 at 20°C, and a boiling point of 143°C.

5.1.4.1.2 Specification. None.

5.1.4.2 Name. Germanium Ethoxide $Ge(OC_2H_5)_4$ FW 252.84
Germanium (IV) ethoxide CAS 14165-55-0
Tetraethoxygermanium
Tetraethyl germanate

5.1.4.2.1 Technical description. Germanium (IV) ethoxide is a liquid with a melting point of -81°C and a boiling point of 185.5°C.

5.1.4.2.2 Specification. None.

5.1.4.3 Name. Germanium Isopropoxide $Ge[OCH(CH_3)_2]_4$ FW 308.94
Germanium (IV) isopropoxide CAS 21154-48-3
Tetraisopropoxygermanium
Tetraisopropyl germanate

5.1.4.3.1 Technical description. Germanium isopropoxide is a liquid with a refractive index of 1.4141 at 20°C, a density of 1.0245 g/cm^3 at 20°C, and a boiling point of 108° C.

5.1.4.3.2 Specification. None.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.1.4.4 Name. Germanium Methoxide — $Ge(OCH_3)_4$ — FW 196.73
Germanium (IV) methoxide — CAS 992-91-6
Tetramethoxygermanium
Tetramethyl germanate

5.1.4.4.1 Technical description. Germanium methoxide is a liquid with a refractive index of 1.4015 and a density of 1.3254 g/cm^3 at 20°C, a melting point of -18°C, and a boiling point of 145°C.

5.1.4.4.2 Specification. None.

5.1.4.5 Use. Germanium alkoxides provide a nonaqueous soluble form of germanium for use in the synthesis of organic compounds.

5.1.4.6 Safety. Germanium alkoxides are flammable or combustible liquids, and can emit irritating and toxic fumes if heated to decomposition. They are decomposed by water with the release of flammable alcohol vapors. There are no PELs or TLVs referenced for germanium alkoxides, but they are strong local irritants of eyes, skin and mucous membranes, and contact shall be avoided. (Refer to 4.3.1.)

5.1.4.7 Storage. Germanium alkoxides shall be stored in tightly sealed corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

5.1.4.8 Disposal. In case of small liquid spills, absorb with nonreactive absorbents and place in containers for disposal. In case of large liquid spills, dike to prevent spreading. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

Germanium alkoxides have EPA Hazardous Waste Classifications - Ignitable, Waste No. D001; and Reactive, Waste No. D003.

5.1.5 Sodium Alkoxides.

5.1.5.1 Name. Sodium n-Butoxide — $Na[O(CH_2)_3CH_3]$ — FW 96.11
Sodium n-butylate — CAS 865-48-5

5.1.5.1.1 Technical description. Sodium n-butoxide is in the form of a solid that is soluble in n-butanol. It is decomposed by water.

5.1.5.1.2 Specification. Manufacturer's requirements. (No Government specification.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.1.5.1.2.1 Requirements. Commercially available sodium n-butoxide is in the form of a solution (19%) in n-butanol with the physical properties shown in Table I, and the typical chemical analysis shown in Table II.

TABLE I. Sodium n-butoxide solution in butanol - physical properties.

Color and appearance	Light yellow, slightly turbid
Specific gravity (20°C)	0.861
Freezing point	-21°C
Initial boiling point	115°C
Flash point (closed cup)	42.9°C (109°F)

TABLE II. Sodium n-butoxide solution in butanol - typical chemical analysis.

$NaOC_4H_9$	19.6%
Na_2CO_3	0.04%
NaOH	0.14%
C_4H_9OH	80.5%

5.1.5.2 Name. Sodium Ethoxide $NaOC_2H_5$ FW 68.05
Sodium ethylate CAS 141-52-6

5.1.5.2.1 Technical description. Sodium ethoxide, anhydrous, is in the form of a white powder with a melting point above 300°C. It's adduct with ethanol, $NaOC_2H_5 \cdot 2C_2H_5OH$, is also a white powder or needles which decomposes on heating with loss of C_2H_5OH. It is soluble in ethanol, and is decomposed by water.

5.1.5.2.2 Specification. Manufacturer's requirements. (No Government specification.)

5.1.5.2.2.1 Requirements. Commercially available sodium ethoxide is an anhydrous free-flowing powder with requirements and properties shown in Table III.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

TABLE III. Sodium ethoxide, anhydrous - requirements and properties.

Appearance	Powder, white-yellowish
$NaOC_2H_5$ content	94% min, 94-97% average
Total alkalinity (estimated as NaOR)	98-100%
NaOH + Na_2CO_3 (estimated as NaOH)	2-3% average
Particle size, mm	0.01-0.3
Properties	Hygroscopic, Caustic

Commercially available sodium ethoxide solution (21%) in ethanol, with the physical properties shown in Table IV, has a typical chemical analysis shown in Table V.

TABLE IV. Sodium ethoxide solution in ethanol - physical properties.

Color and appearance	Yellow, turbid
Specific gravity (20°C)	0.879
Freezing point	-12°C
Initial boiling point	77°C
Flash point (closed cup)	23.9°C (75°F)

TABLE V. Sodium ethoxide solution in ethanol - typical chemical analysis.

$NaOC_2H_5$	21.2%
Na_2CO_3	0.04%
NaOH	0.02%
C_2H_5OH	78.5%

5.1.5.3 Name. Sodium Methoxide $NaOCH_3$ FW 54.02
Sodium methylate CAS 124-41-4

5.1.5.3.1 Technical description. Sodium methoxide, anhydrous, is in the form of a white powder with a melting point above 300°C. It's adduct with methanol, $NaOCH_3 \cdot 2CH_3OH$, is also a white powder which decomposes on heating with loss of CH_3OH. It is soluble in methanol, and is decomposed by water.

5.1.5.3.2 Specification. Manufacturer's requirements. (No Government specification.)

5.1.5.3.2.1 Requirements. Commercially available sodium methoxide is an anhydrous powder with the chemical and physical requirements shown in Table VI.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

TABLE VI. Sodium methoxide, anhydrous - chemical and physical requirements.

	Specification	Typical Average
$NaOCH_3$ NaOH Na_2CO_3	97% min 1.1% max 0.4% max	98.7% 0.5% 0.3%
† Sieve size, US Standard Retained on No. 10 Pass through No. 150	Sieve: (2.00 millimeter) (104 micrometer)	 1% max 75% min

†NOTE: Standard sieve designation in accordance with ASTM E 11.

A sodium methoxide solution (25%) in methanol, is available with the physical properties shown in Table VII, and with the requirements and typical chemical analysis shown in Table VIII.

TABLE VII. Sodium methoxide solution in methanol - physical properties.

Color and appearance	Clear
Specific gravity (25°C)	0.945
Crystallization temperature after equilibrium	-1.1°C (30°F)
Initial boiling point (for 25% concentration)	86.7°C (188°F)
Flash point (open cup)	29°C (84°F)

TABLE VIII. Sodium methoxide solution in methanol - requirements and typical chemical analysis.

	Specification	Typical Average
$NaOCH_3$	25.0% min	25.3%
NaOH	0.35% max	0.12%
Na_2CO_3	0.10% max	0.05%
CH_3OH	——	74.5%

Sodium methoxide solution (25%) in methanol is available from a second manufacturer with the requirements as shown in Table IX.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

TABLE IX. Sodium methoxide solution in methanol - requirements.

$NaOCH_3$ content	24.0 - 25.5%
Total alkalinity	24.5 - 26.0%
NaOH + Na_2CO_3 (calculated as NaOH)	0.2 - 0.6%
Mercury content	Less than 2 ppm
Density (as 25°C)	0.94 kg/L
Flash point (closed cup)	12.2°C (54°F)
Crystallization	From approximately 2°C
Properties	Highly sensitive to water and air. Caustic.
Solubility	Miscible with methanol, ethanol, isopropanol. Insoluble in hydrocarbons. Reactive with esters, ketones, cyclic ethers, and halogenated organic compounds.

5.1.5.4 Use. Sodium alkoxides are intended for use in the synthesis of organic compounds by esterification and transerterification reactions, and condensation and polycondensation reactions. They are used for the preparation of other metal alkoxides, and in the preparation of ethers.

5.1.5.5 Safety. Sodium alkoxides are flammable solids or solutions, and can emit irritating and toxic fumes if heated to decomposition. They are decomposed by water with the release of flammable alcohol vapors. There are no PELs or TLVs referenced for sodium alkoxides, but they are strong local irritants of eyes, skin and mucous membranes. They can cause caustic burns, so contact shall be avoided. (Refer to 4.3.1.)

5.1.5.6 Storage. Sodium alkoxides shall be stored in tightly sealed corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

5.1.5.7 Disposal. In case of solid spills, recover in dry state and place in containers for disposal. In case of small liquid spills, absorb with nonreactive absorbents and place in containers for disposal. In case of large liquid spills, dike to prevent spreading. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

Sodium alkoxides have EPA Hazardous Waste Classifications - Ignitable, Waste No. D001; and Reactive, Waste No. D003.

5.1.6 Titanium Alkoxides.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.1.6.1 Name. Titanium n-Butoxide $Ti[O(CH_2)_3CH_3]_4$ FW 340.36
Tetrabutoxytitanium CAS 5593-70-4
Tetrabutyl titanate

5.1.6.1.1 Technical description. Titanium n-butoxide is in the form of a colorless liquid with a boiling point of about 312°C. It is soluble in n-butanol and n-heptane. It is hydrolyzed by water. The theoretical Ti content is 13.95 percent.

5.1.6.1.2 Specification. Manufacturer's requirements. (No Government specification.)

5.1.6.1.2.1 Requirements. Titanium n-butoxide is available as a pale yellow liquid with a specific gravity of 0.99 (25°/25°C), a viscosity of 65 cP(mPa•s) at 25°C, a thickening point below -40°C, and a closed cup flash point of 47°C (116°F). The Ti content of the product is 14.1 percent.

5.1.6.2 Name. Titanium Ethoxide $Ti(OC_2H_5)_4$ FW 228.15
Tetraethoxytitanium CAS 3087-36-3
Tetraethyl titanate

5.1.6.2.1 Technical description. Titanium ethoxide (pure) is a colorless oily liquid with a refractive index of 1.5082 at 25°C, a density of 1.1066 g/cm^3 at 25°C, and a boiling point of 133° to 135°C at 5 mm Hg. It is soluble in ethanol. It is hydrolyzed by water. The theoretical Ti content is 21 percent.

5.1.6.2.2 Specification. Manufacturer's requirements. (No Government specification.)

5.1.6.2.2.1 Requirements. Titanium ethoxide, technical grade, is available with a refractive index of 1.5043 at 20°C, a density of 1.088 g/cm^3 at 20°C, a boiling point of 150° to 152°C at 10 mm Hg, and a closed cup flash point of 28°C (84°F). The product has a Ti content of 20%, and is stabilized with excess ethanol.

5.1.6.3 Name. Titanium 2-Ethylhexoxide $Ti[OCH_2CH(C_2H_5)C_4H_9]_4$ FW 564.79
Tetrakis (2-ethylhexoxy) titanium CAS 1070-10-6
Tetrakis (2-ethylhexyl) titanate

5.1.6.3.1 Technical description. Titanium 2-ethylhexoxide is a liquid with a density of 0.926 g/cm^3 at 25°C, and a boiling point of 194°C at 0.25 mm Hg. It is soluble in isopropanol and n-heptane. It is hydrolyzed by water. The theoretical Ti content is 8.5 percent.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.1.6.3.2 Specification. Manufacturer's requirements. (No Government specification.)

5.1.6.3.2.1 Requirements. Titanium 2-ethylhexoxide is available as a pale yellow liquid with a specific gravity of 0.91 (25°/25°C), a viscosity of 140 cP(mPa•s) at 25°C, a thickening point below -25°C, and a closed cup flash point of 60°C (140°F). The Ti content of the product is 8.6 percent.

5.1.6.4 Name. Titanium Isobutoxide $Ti[OCH_2CH(CH_3)_2]_4$ FW 340.36
Tetraisobutoxytitanium CAS 681-98-1
Tetraisobutyl titanate

5.1.6.4.1 Technical description. Titanium isobutoxide (pure) is a crystalline solid with a melting point of 30°C. The liquid has a density of 0.960 g/cm^3, a refractive index of 1.475, and a boiling point of 269°C at 760 mm Hg. It is soluble in isobutyl alcohol and n-heptane. It is hydrolyzed by water.

5.1.6.4.2 Specification. Manufacturer's requirements. (No Government specification.)

5.1.6.4.2.1 Requirements. Titanium isobutoxide is available as a liquid with a boiling point of 141°C at 1 mm Hg.

5.1.6.5 Name. Titanium Isopropoxide $Ti[OCH(CH_3)_2]_4$ FW 284.25
Tetraisopropoxytitanium CAS 546-68-9
Tetraisopropyl titanate

5.1.6.5.1 Technical description. Titanium isopropoxide (pure) is a liquid with a density of 0.9550 g/cm^3 at 25°C, a melting point of 20°C and a boiling point of 58°C at 1 mm Hg. It is soluble in isopropanol and n-heptane. It is hydrolyzed by water. The theoretical Ti content is 16.85 percent.

5.1.6.5.2 Specification. Manufacturer's requirements. (No Government specification.)

5.1.6.5.2.1 Requirements. Titanium isopropoxide is available as a pale yellow liquid with a specific gravity of 0.95 (25°/25°C), a freezing point of 18°C, a viscosity of 3 cP (mPa•s), and a closed cup flash point of 21°C (70°F). The Ti content of the product is 16.7 percent.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.1.6.6 Name. Titanium Methoxide $Ti(OCH_3)_4$ FW 172.04
Tetramethoxytitanium CAS 992-92-7
Tetramethyl titanate

5.1.6.6.1 Technical description. Titanium methoxide (pure) is in the form of a solid with a melting point of 210°C and a boiling point of 243°C at 52 mm Hg. It is hydrolyzed by water.

5.1.6.6.2 Specification. None.

5.1.6.7 Use. Titanium alkoxides provide a nonaqueous soluble form of titanium for use in the synthesis of organic compounds, as esterification and transesterification catalysts, as polymerization catalysts, and as crosslinking agents for polymers.

5.1.6.8 Safety. Titanium alkoxides are flammable solids, or flammable or combustible liquids, and can emit irritating and toxic fumes if heated to decomposition. They are decomposed by water with the release of flammable alcohol vapors. There are no PELs or TLVs referenced for titanium alkoxides, but they are strong local irritants of the eyes, skin and mucous membranes. (Refer to 4.3.1.)

5.1.6.9 Storage. Titanium alkoxides shall be stored in tightly sealed corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

5.1.6.10 Disposal. In case of solid spills, gather up and place in containers for disposal. In case of small liquid spills, absorb with nonreactive absorbent, and place in containers for disposal. In case of large liquid spills, dike to prevent spreading. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

Titanium alkoxides have EPA Hazardous Waste Classifications - Ignitable, Waste No. D001; and Reactive, Waste No. D003.

5.1.7 Zirconium Alkoxides.

5.1.7.1 Name. Zirconium n-Butoxide $Zr[O(CH_2)_3CH_3]_4$ FW 383.69
$Zr[O(CH_3)_3CH_3]_4 \cdot C_4H_9OH$ FW 457.81
Tetrabutoxyzirconium CAS 1071-76-7
Tetrabutyl zirconate

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.1.7.1.1 Technical description. Zirconium n-butoxide is a white solid. It forms an adduct with n-butanol, $(C_4H_9O)_4Zr \cdot C_4H_9OH$, that is a liquid with a density of 1.05 to 1.08 g/cm^3, and a melting point below -70°C. The theoretical ZrO_2 content of the adduct is 27 percent.

5.1.7.1.2 Specification. Manufacturer's requirements. (No Government specification.)

5.1.7.1.2.1 Requirements. Zirconium n-butoxide is available as the adduct with butanol, with an analysis of 28% ZrO_2.

5.1.7.2 Name. Zirconium Ethoxide $Zr(OC_2H_5)_4$ FW 271.47
Tetraethoxyzirconium CAS 18267-08-8
Tetraethyl zirconate

5.1.7.2.1 Technical description. Zirconium ethoxide is a crystalline solid with a melting point of 171° to 173°C.

5.1.7.2.2 Specification. None.

5.1.7.3 Name. Zirconium Isopropoxide $Zr[OCH(CH_3)_2]_4$ FW 327.56
$Zr[OCH(CH_3)_2]_4 \cdot C_3H_7OH$ FW 387.67
Tetraisopropoxyzirconium CAS 2171-98-4
Tetraisopropyl zirconate

5.1.7.3.1 Technical description. Zirconium isopropoxide is a white solid that decomposes on heating before melting. It forms an adduct with isopropanol, $(C_3H_7O)_4Zr \cdot C_3H_7OH$, that is a crystalline solid. The theoretical carbon content is 46.5% and the theoretical hydrogen content is 9.1 percent.

5.1.7.3.2 Specification. Manufacturer's requirements. (No Government specification.)

5.1.7.3.2.1 Requirements. Zirconium isopropoxide is available as the adduct with isopropanol, with an analysis of 43.8% carbon and 8.8% hydrogen.

5.1.7.4 Name. Zirconium n-Propoxide $Zr[O(CH_2)_2CH_3]_4$ FW 327.56
Tetrapropoxyzirconium CAS 23519-77-9
Tetrapropyl zirconate

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.1.7.4.1 Technical description. Zirconium n-propoxide is a liquid with a density of 1.058 g/cm^3 and a refractive index of 1.454 at 20°C. The theoretical Zr content is 27.8 percent.

5.1.7.4.2 Specification. Manufacturer's requirements. (No Government specification.)

5.1.7.4.2.1 Requirements. Zirconium n-propoxide is available as a liquid with a density of 1.05 g/cm^3 and a refractive index of 1.457 at 20°C. The product has a Zr content of 21.6 percent.

5.1.7.5 Use. Zirconium alkoxides provide a nonaqueous soluble form of zirconium for use in organic synthesis as a condensation catalyst and cross-linking agent.

5.1.7.6 Safety. Zirconium alkoxides are flammable solids, or flammable or combustible liquids, and can emit irritating and toxic fumes if heated to decomposition. They are decomposed by water with the release of flammable alcohol vapors. The PEL and TLV for zirconium compounds, as Zr, are 5 mg/m^3. They are strong local irritants of the eyes, skin and mucous membranes. (Refer to 4.3.1.)

5.1.7.7 Storage. Zirconium alkoxides shall be stored in tightly sealed corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

5.1.7.8 Disposal. In case of dry spills, gather up and place in containers for disposal. In case of small liquid spills, absorb with nonreactive absorbent, and place in containers for disposal. In case of large liquid spills, dike to prevent spreading. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

Zirconium alkoxides have EPA Hazardous Waste Classifications - Ignitable, Waste No.D001; and Reactive, Waste No. D003.

5.2 Metal Carboxylates

Metal carboxylates are the alkali, alkaline-earth, and heavy metal salts of the carboxylic acids. The salts of the carboxylic acids are nonvolatile solids. In general, the alkali metal salts, with the exception of lithium, are soluble in water but insoluble in non-polar solvents. The salts of the alkaline-earth and heavy metals are insoluble in water, but show solubility or solvation in non-polar solvents. The alkaline-earth and heavy metal salts of the monocarboxylic acids are called metallic soaps, although salts of the acids of less than seven carbon atoms in the aliphatic series are not classed as such.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

Carboxylic acids are converted to alkali metal salts by reaction with aqueous alkali hydroxides. Metallic soaps may be prepared by either a fusion or a precipitation process. In the fusion process a metal oxide, hydroxide, or salt of the weak acid such as an acetate or carbonate, are reacted with a selected fatty acid at an elevated temperature in the absence of added water. Under these conditions, a neutralization reaction takes place, and as the water is driven off a metallic soap is formed as a molten mass which after solidification is crushed and pulverized to desired particle size ranges. In the precipitation process, a solution of sodium soap is first prepared by reaction of a selected fatty acid with caustic soda solution. When a separately prepared solution of the appropriated metal salt is added to the sodium salt solution a metathetic reaction occurs and the desired metallic soap precipitates, while an inorganic sodium salt remains in solution.

5.2.1 Name. Aluminum Stearate $Al(OOCH_{35}C_{17})_2COOH$ FW 895.44
$Al(OOCH_{35}C_{17})_2OH$ FW 611.0
Aluminum octadecanoate CAS 637-12-7

5.2.1.1 Technical description. Aluminum tristearate, $Al(OOCH_{35}C_{17}$, is nonexistent. This psuedo triacid aluminum stearate is actually composed of one mole of free fatty acid for each mole of aluminum distearate. The aluminum distearate is a polymeric compound where the aluminum has a coordination number of six. Aluminum stearate is a white powder with a slight fatty acid odor. The "tristearate" has a specific gravity of 1.010 and a melting point of 103°C. It is insoluble in water, alcohol and ether. It dissolves in hydrocarbon liquids at elevated temperatures, and on cooling forms viscoelastic solutions or "gels." It is decomposed by strong agueous acid and alkali solutions. The theoretical aluminum content of aluminum distearate is 4.4 percent. The theoretical aluminum content of the "triacid" aluminum stearate is 3.0%, and the theoretical free fatty acid content is 32 percent. Aluminum stearate with aluminum contents above 4.4% are mixtures of aluminum distearate and aluminum hydroxide.

5.2.1.2 Specifications. Manufacturer's requirements. (No Government specification.)

5.2.1.3 Requirements. Commercial grades of aluminum stearate are white powders with aluminum oxide contents ranging from 6.0 to 17.0% which corresponds to aluminum contents of 3.7 to 7.9%, and with free fatty acid contents ranging from 28.4 to 32 percent. The moisture contents range from 0.5 to 0.7 percent.

NOTE: Stearic acid is available in varying states of purity depending on the refining process. Commercial grades of stearic acid can contain, in addition to octadecanoic acid, up to 50% palmitic

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

acid (hexadecanoic acid), and also some oleic acid (cis-9-octadecanoic acid) and palmitoleic and (cis-9-hexadecanoic acid).

5.2.1.4 Use. Aluminum stearate is intended for military use as an ingredient in nonaqueous paints and related products such as varnishes and lacquers. Commercial applications include the above, and also uses as a thickening agent for lubricating oils to form greases, and as a waterproofing agent for masonry surfaces, leather, paper, and wood.

5.2.1.5 Safety. Aluminum stearate powder is burnable, and can form explosive dust mixtures in air. It can emit irritating and toxic fumes if heated to decomposition. The aluminum ion is nontoxic, but aluminum stearate can be irritating to the eyes, skin and mucous membranes. The TLV for aluminum stearate, as a nuisance particulate, is 10 mg/m^3 of total dust, so inhalation of dust shall be avoided. (Refer to 4.3.1.)

5.2.1.6 Storage. Aluminum stearate shall be stored in corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

5.2.1.7 Disposal. In case of dry spills, gather up and place in containers for disposal. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

An EPA Hazardous Waste Classification is not listed in 40 CFR.

5.2.2 Name. Barium Stearate $Ba(OOCH_{35}C_{17})_2$ FW 704.13
Barium octadecanoate CAS 6865-35-6

5.2.2.1 Technical description. Barium stearate is a white powder with a specific gravity of 1.145 and a melting point of 160°C. Its solubitity in water is 0.004 g/100 mL at 15°C and 0.006 g/100 mL at 50°C. Its solubility in alcohol is 0.005 g/100 mL at 16.5°C and 0.008 g/100 mL at 25°C. Its solubility in ether is 0.001 g/100 mL at 25°C. It solvates in hydrocarbon liquids. It is decomposed by strong aqueous acid solutions. The theoretical barium content of barium stearate is 19.5 percent.

5.2.2.2 Specification. Military, JAN-B-366, Barium Stearate.

5.2.2.2.1 Requirements. This specification covers one grade of barium stearate with the chemical and physical properties conforming to the requirements shown in Table X.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

TABLE X. Barium stearate - chemical and physical requirements.

Melting point, °C, min	240
Barium content, %	20.0 ± 0.5
Moisture, %, max	0.2
Water-soluble salts, %, max	0.5
Acidity or alkalinity, %, max	0.01
Grit	None
† Granulation, US Standard Sieves	
Through No. 100	
(150 micrometer), %, min	95.5
Through No. 200	
(75 micrometer), %, min	95

† Standard sieve designation in accordance with ASTM E 11.

5.2.2.3 Use. Barium stearate is intended for military use as a binder and lubricant in the pelleting of explosives. Commercial applications include use as a lubricant in metal working and wire-drawing, and as an ingredient in wax polishing compounds.

5.2.2.4 Safety. Barium stearate powder is burnable, and can form explosive dust mixtures in air. It can emit irritating and toxic fumes if heated to decomposition. The barium ion is toxic when the compound is soluble, and its compounds can be irritating to the eyes, skin and mucous membranes. The PEL and TLV for soluble barium compounds, as Ba, are 0.5 mg/m^3, so breathing of dust shall be avoided. (Refer to 4.3.1.)

5.2.2.5 Storage. Barium stearate shall be stored in corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

5.2.2.6 Disposal. In case of dry spills, gather up and place in containers for disposal. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer 4.4.)

Barium stearate has an EPA Hazardous Waste Classification - Toxicity Characteristic; Waste No. D005.

5.2.3 Name. Calcium Resinate $Ca(OOCH_{29}C_{19})_2$ FW 643.00
Calcium abietate CAS 9007-13-0

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.2.3.1 Technical description. Calcium resinate is either a yellowish-white amorphous powder or yellow to brown lumps depending on the method of preparation. It is insoluble in water. It is soluble in ether, amyl alcohol, and esters such as butyl acetate and amyl acetate. It is decomposed by strong aqueous acid solutions. The above formula and formula weight are for calcium abietate, since abietic acid is the predominant acid in rosin.

5.2.3.2 Specification. Military, MIL-C-20470A, Calcium Resinate.

5.2.3.2.1 Requirements. This specification covers two types of calcium resinate:

Type I - Fused
Type II - Precipitated

Type I fused calcium resinate shall be yellow or brown in color. Type II shall be a yellowish-white amorphous powder, free from lumps, cakes and agglomerations. The chemical and physical properties shall conform to the requirements shown in Table XI.

TABLE XI. Calcium resinate - chemical and physical requirements.

	Type I	Type II
Calcium resinate content, %, min	56.0	77.0
Acid number, max	64	33
Chloroform insoluble matter, %, max	2.0	3.0
Water content, %, max	2.0	5.0
†Granulation, US Standard Sieves:		
Through No. 60 (250 micrometer), %, min	None	75
Through No. 4 (4.75 millimeter), %, min	90	----
Flame test	Yellow-red	Yellow-red

† Standard sieve designation in accordance with ASTM E 11.

5.2.3.3 Use. Calcium resinate is intended for military use in pyrotechnic compositions. Commercial applications include use in varnishes to cause thickening and to increase the hardness of the dried film.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.2.3.4 Safety. Calcium resinate is a flammable solid, and the powder can form explosive dust mixtures in air. It can emit irritating and toxic fumes if heated to decomposition. The calcium ion is nontoxic, but its compounds can be irritating to the eyes, skin and mucous membranes. There is no PEL or TLV referenced for calcium resinate, but breathing of dust shall be avoided. (Refer to 4.3.1.)

5.2.3.5 Storage. Calcium resinate shall be stored in corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

5.2.3.6 Disposal. In case of dry spills, gather up and place in containers for disposal. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

An EPA Hazardous Waste Classification is not listed in 40 CFR.

5.2.4 Name. Calcium Stearate $Ca(OOCH_{35}C_{17})_2$ FW 607.04
Calcium octadecanoate CAS 1592-23-0

5.2.4.1 Technical description. Calcium stearate is a white granular powder with a melting point of 179° to 180°C. Its solubility in water is 0.004 g/100 mL at 15°C. It is insoluble in alcohol and ether. It solvates in hydrocarbon liquids. It is decomposed by strong aqueous acid solutions. The theoretical calcium content of calcium distearate is 6.6 percent.

5.2.4.2 Specification. Military, JAN-C-263, Calcium Stearate.

5.2.4.2.1 Requirements. This specification covers one grade of calcium stearate with the chemical and physical properties conforming to the requirements shown in Table XII.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

TABLE XII. Calcium stearate - chemical and physical requirements.

Calcium, as CaO, %	9.2 ± 0.2
Acidity or alkalinity, %, max	0.01
Moisture, %, max	3.0
Water-soluble salts, %, max	0.25
Grit	None
Melting point, °C, min	150
†Granulation, US Standard Sieves	
Through No. 100 (150 micrometer), %, min	98
Through No. 200 (75 micrometer), %, min	95

†Standard sieve designations in accordance with ASTM E 11.

NOTE: The CaO content of 9.0 to 9.4% is equivalent to a Ca content of 6.4 to 6.7 percent.

5.2.4.3 Use. Calcium stearate is intended for military use as a binder and lubricant in the pelleting of explosives. Commercial applications include use as a thickener for lubricating oils to form greases; as a waterproofing agent for concrete, paper, rope, fabric and wood; as a mold lubricant and internal lubricant for plastics; and as an ingredient in nonaqueous protective coatings.

5.2.4.4 Safety. Calcium stearate powder is burnable, and can form explosive dust mixtures in air. It can emit irritating and toxic fumes if heated to decomposition. The calcium ion is nontoxic, but its compounds can be irritating to the eyes, skin and mucous membranes. The TLV for calcium stearate, as a nuisance particulate, is 10 mg/m^3 as total dust, so inhalation of dust shall be avoided. (Refer to 4.3.1.)

5.2.4.5 Storage. Calcium stearate shall be stored in corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

5.2.4.6 Disposal. In case of dry spills, gather up and place in containers for disposal. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

An EPA Hazardous Waste Classification is not listed in 40 CFR.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.2.5 Name. Chromium (III) 2-Ethylhexanoate
$Cr[OOCCH(C_2H_5)C_4H_9]_3$ FW 481.62
Chromium (III) 2-ethylhexoate CAS 3444-17-5
Chromium (III) octoate

5.2.5.1 Technical description. Chromium (III) has a coordination number of six, and the composition of chromium soaps is complex. The properties of specific compounds are not available. The theoretical chromium content of chromium (III) 2-ethylhexanoate is 10.8 percent.

5.2.5.2 Specification. Military, DOD-C-82660, Chromium 2-Ethyl Hexoate.

5.2.5.2.1 Requirements. This specification covers one type of chromium 2-ethylhexoate. The material shall be a dark green liquid that is essentially pure chromium 2-ethylhexoate diluted with 2-ethylhexanoic acid. The chemical and physical properties of the solution shall conform to the requirements shown in Table XIII.

TABLE XIII. Chromium 2-ethylhexoate - chemical and physical requirements.

	Minimum	Maximum
Chromium content, wt %	5.3	5.7
Specific gravity, (25°/25°C)	0.97	1.03

5.2.5.3 Use. Chromium 2-ethylhexoate solution in 2-ethylhexanoic acid is intended for military use as an ingredient in solid propellants for cartridge devices.

5.2.5.4 Safety. The flash point (closed cup) of 2-ethylhexanoic acid is 124°C (256°F), and a solution of chromium 2-ethylhexoate in this solvent is burnable. The solution can emit irritating and toxic fumes if heated to decomposition. The chromium (III) ion is toxic and is a potential carcinogen. The PEL and TLV for chromium (III) compounds, as Cr, are 0.5 mg/m^3, and breathing of mists and fumes shall be avoided. The Cr (III) compound solution can be irritating to the eyes, skin, and mucous membranes. Burning of Cr (III) can form some Cr (VI). Chromium (VI) is considered a confirmed carcinogen by the International Agency for Research on Cancer (IARC) and Transactions of ACGIH. The TLV for chromium (VI) is 0.05 mg/m^3. Breathing of mists or fumes of chromium (VI) shall be avoided. (Refer to 4.3.1.)

5.2.5.5 Storage. Chromium 2-ethylhexoate solution shall be stored in corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.2.5.6 Disposal. In case of small solution spills, absorb with nonreactive absorbent and place in containers for disposal. In case of large solution spills, dike to prevent spreading. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

Chromium (III) 2-ethylhexoate has an EPA Hazardous Waste Classification - Toxicity Characteristic; Waste No. D007.

5.2.6 Name. Copper Naphthenate $Cu(OOCH_{11}C_6)_2$ FW 317.87
Copper cyclohexanecarboxylate CAS 1338-02-9
Copper hexahydrobenzoate

5.2.6.1 Technical description. Copper naphthenate is a green-blue or dark-green solid. It is soluble in hydrocarbon liquids. The formula and formula weight and synonyms are for copper naphthenate derived from cyclohexanecarboxylic acid, which is one of the components of naphthenic acids. The component acids of the naphthenic acid mixture also include alkylated cyclopentanecarboxylic acids of the general formula $C_nH_{2n-2}O_2$ containing 8 to 12 carbons, and other alkylated cyclic carboxylic acids of the general formula $C_nH_{2n-4}O_2$ containing 12 to 23 carbons. The properties of specific copper naphthenate compounds are not available.

5.2.6.2 Specifications.

5.2.6.2.1 Federal, TT-P-595A, Preservative Coating, Canvas.

5.2.6.2.1.1 Requirements. This specification covers two types of preservative coatings. Type I(b) shall be copper naphthenate combined with copper-8-quinolinolate. The properties of the copper naphthenate are not specified.

5.2.6.2.2 Military, MIL-W-18142B, Wood Preservative Solutions, Oil-Soluble, Ship and Boat Use.

5.2.6.2.2.1 Requirements. This specification covers two types of oil-borne wood preservatives. Type A shall be copper naphthenate in mineral spirits solution at a minimum concentration of 68 g/gal. The properties of the copper naphthenate are not specified.

5.2.6.2.3 Military, MIL-F-46032A, Fungus-Resistant Treatment for Sandbags, Copper Processes.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.2.6.2.3.1 Requirements. This specification covers three types of processes. Type I shall be a copper naphthenate treatment. The copper naphthenate used shall consist of a clear, green-colored solution containing no sediment; and manufactured from naphthenic acid, with an acid number of not less than 180, containing not more than 25% unsaponifiable matter. The metal content of this copper naphthenate solution is not specified.

5.2.6.3 Use. Copper naphthenate is intended for military use in preservative coatings for canvas tentage and tarpaulins, in oil-soluble preservative solutions for treatment of ship and boat lumber and plywood, and in solutions for treatment of sandbags against fungus attack. Commercial applications include the above, and also use in antifouling paints for ocean-going ships to prevent attachment and growth of marine plants and animals to ship hulls.

5.2.6.4 Safety. Copper naphthenate in solid form is burnable. It can emit irritating and toxic fumes if heated to decomposition. Copper naphthenate solutions can be flammable, combustible or burnable depending on the flash points of the hydrocarbon solvents. The PEL for copper fumes is 0.1 mg/m^3, and the TLV is 0.2 mg/m^3. The PEL and TLV for copper dusts and mists are 1 mg/m^3. The copper ion can cause irritation of the eyes, skin and mucous membranes. (Refer to 4.3.1.)

5.2.6.5 Storage. Copper naphthenate and its solutions shall be stored in corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

5.2.6.6 Disposal. In case of dry spills, gather up and place in containers for disposal. In case of small liquid spills absorb with nonreactive absorbent and place in containers for disposal. In case of large liquid spills, dike to prevent spreading. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

Copper naphthenate solutions have an EPA Hazardous Waste Classification - Ignitable; Waste No. D001 when flash point is less than 60°C (140°F).

5.2.7 Name. Lead 2-Ethylhexanoate $Pb[OOCCH(C_2H_5)C_4H_9]_2$ FW 493.60
Lead bis(2-ethylhexanoate) CAS 16996-40-0
Lead 2-ethylhexoate
Lead octoate (commercial use)

5.2.7.1 Technical description. The properties of the lead 2-ethylhexanoate compound are not available. Lead 2-ethylhexanoate is a white solid that is soluble in

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

hydrocarbon liquids and dialkylphthalate esters. It is decomposed by strong aqueous acid solutions. The theoretical lead content of lead bis(2-ethylhexanoate) is 41.8 percent. It solvates in hydrocarbon fluids. It is decomposed by mineral acids.

5.2.7.2 Specification. Military, MIL-L-17699, Lead 2-Ethyl Hexoate.

5.2.7.2.1 Requirements. This specification covers one grade of lead 2-ethylhexoate with the chemical and physical properties conforming to the requirements shown in Table XIV.

TABLE XIV. Lead 2-ethylhexoate - chemical and physical requirements.

Lead content, total, %, min	40.5
%, max	42.5
Moisture and volatiles, %, max	2.0
Acidity to phenolphthalein, as 2-ethylhexanoic acid, %, max	1.2
Alkalinity	None
Diethylphthalate insoluble material, %, max	1.0
Viscosity, (Gardner-Holdt), min	2 - 8
Color, (Gardner Standard), not darker than	7

5.2.7.3 Use. Lead 2-ethylhexoate is intended for use in various military applications. Commercial applications include use as an ingredient in nonaqueous paints, and as a curing agent for silicone paints and insulating varnishes.

5.2.7.4 Safety. Lead 2-ethylhexoate is burnable, and can form explosive dust mixtures in air. It can emit irritating and toxic fumes if heated to decomposition. The lead ion is toxic and considered to be a potential carcinogen by the National Toxicology Program (NTP). The PEL for organic lead soaps, as Pb, is 50 $\mu g/m^3$, so breathing of dust and fumes shall be avoided. (Refer to 4.3.1.)

5.2.7.5 Storage. Lead 2-ethylhexoate shall be stored in corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

5.2.7.6 Disposal. In case of dry spills, gather up and place in containers for disposal. In case of small liquid spills absorb with nonreactive absorbent and place in containers for disposal. In case of large liquid spills, dike to prevent spreading. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

Lead 2-ethylhexoate has an EPA Hazardous Waste Classification - Toxicity Characteristic; Waste No. D008.

5.2.8 Name. Lead Salicylate $Pb(OOCC_6H_4OH)_2$ FW 481.43
$Pb(OOCC_6H_4OH)_2 \cdot H_2O$ FW 499.45
Lead 2-hydroxybenzoate CAS 15748-73-9

5.2.8.1 Technical description. The properties of the anhydrous lead salicylate compound are not available. Lead salicylates are in the form of white crystals. The monohydrate has a specific gravity of 2.3 and a refractive index of 1.78. Lead salicylate is soluble in hot water and alcohol. It is decomposed by strong aqueous acid solutions. The theoretical lead content of the anydrous form is 43.04%, and the lead content of the monohydrate is 41.49 percent. The salicylate content of the anhydrous form is 56.96%, and the salicylate content of the monohydrate is 54.91 percent.

5.2.8.2 Specifications.

5.2.8.2.1 Military MIL-L-13788, Lead Salicylate.

5.2.8.2.1.1 Requirements. This specification covers one grade of lead salicylate with the chemical and physical properties conforming to the requirements shown in Table XV.

TABLE XV. Lead salicylate - chemical and physical requirements (MIL-L-13788).

Lead content, %, min	43.0
Salicylate content, %, min	55.4
Volatile matter, %, max	0.25
Form	Soft Crystals
Color	White
†Granulation, US Standard Sieve Retained on No. 325 (45 micrometer), %, max	0.1

†Standard sieve designation in accordance with ASTM E 11.

5.2.8.2.2 Military MIL-L-17700, Lead Salicylate.

5.2.8.2.2.1 Requirements. This specification covers one grade of lead salicylate with the chemical and physical properties conforming to the requirements shown in Table XVI.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

TABLE XVI. Lead salicylate - chemical and physical requirements (MIL-L-17700).

Lead content, %, max	43.7
%, min	42.2
Salicylate content, total %, max	59.0
%, min	55.0
Free salicylic acid content, %, max	1.0
Moisture and volatiles, %, max	1.0
Diethylene glycol insoluble material, %, max	2.5
Color	Cream-white to pure white
†Granulation, US Standard Sieve Retained on No. 325 (45 micrometer), %, max	0.5

† Standard sieve designation in accordance with ASTM E 11.

5.2.8.3 Use. Lead salicylate is intended for military use in ammunition and various military applications. Commercial applications include use as a stablizer or costabilizer for polyvinyl resin compounds requiring good light stability.

5.2.8.4 Safety. Lead salicylate is burnable, and can form explosive dust mixtures in air. It can emit irritating and toxic fumes if heated to decomposition. The lead ion is toxic and considered to be a potential carcinogen by the National Toxicology Program (NTP). The PEL for organic lead soaps, as Pb, is 50 $\mu g/m^3$, so breathing of dust and fumes shall be avoided. (Refer to 4.3.1.)

5.3.8.5 Storage. Lead salicylate shall be stored in corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

5.3.8.6 Disposal. In case of dry spills, gather up and place in containers for disposal. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

Lead Salicylate has an EPA Hazardous Waste Classification - Toxicity Characteristic; Waste No. D008.

5.2.9 Name. Lead Stearate $Pb(OOCH_{35}C_{17})_2$ FW 774.15
Lead octadecanoate CAS 1072-35-1

5.2.9.1 Technical description. Lead stearate is in the form of a white powder with a melting point of 115.7°C. Its solubility in water is 0.05 g/100 mL at 25°C and 0.06 g/100

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

mL at 50°C. It solvates in hot aromatic hydrocarbon liquids, and can be dispersed in hot paraffin oil. It is decomposed by strong aqueous acid solutions. The theoretical lead content of lead stearate is 26.77%, and the theoretical stearate content as stearic acid is 73.44 percent.

5.2.9.2 Specification. Military, MIL-L-758A, Lead Stearate (For Use in Ammunition).

5.2.9.2.1 Requirements. This specification covers one grade of lead stearate with the chemical and physical properties conforming to the requirements shown in Table XVII.

TABLE XVII. Lead stearate - chemical and physical requirements.

Purity	
Lead content, as Pb, %	26.8 to 29.5
Stearate, as stearic acid, %	70.8 to 73.5
Moisture, %, max	1.0
Water soluble material, %, max	0.5
Acidity and alkalinity	
Alkalinity	None
Acidity, as acetic acid,	
To phenolphthalein, %, max	0.05
To methyl orange	None
Melting point of lead stearate, °C, min	104
Melting point of fatty acid, °C, min	55
Iodine number of fatty acid, max	5.0
†Granulation, US Standard Sieves	
Retained on No. 100 (150 micrometer), %, max	5.0
Through No. 100 (150 micrometer) and retained on No. 200 (75 micrometer), %, max	13.0
Through No. 200 (75 micrometer) and retained on No. 325 (45 micrometer), %, max	15.0

† Standard sieve designation in accordance with ASTM E 11.

5.2.9.3 Use. Lead stearate is intended for military use and in propellant powder. Commercial applications include use in extreme pressure lubricants, as an ingredient in nonaqueous paints and varnishes, and in the manufacture of polyvinyl chloride plastics.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.2.9.4 Safety. Lead stearate powder is burnable, and can form explosive dust mixtures in air. It can emit irritating and toxic fumes if heated to decomposition. The lead ion is toxic and considered to be a potential carcinogen by the National Toxicology Program (NTP). The PEL for organic lead soaps, as Pb, is 50 $\mu g/m^3$, so breathing of dust and fumes shall be avoided. (Refer to 4.3.1.)

5.2.9.5 Storage. Lead stearate shall be stored in corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

5.2.9.6 Disposal. In case of dry spills, gather up and place in containers for disposal. For appropriate procedures, contact the installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

Lead stearate has an EPA Hazardous Waste Classification - Toxicity Characteristic; Waste No. D008.

5.2.10 Name. Lithium Stearate $LiOOCH_{35}C_{17}$ FW 290.41
Lithium octadecanoate CAS 4485-12-5

5.2.10.1 Technical description. Lithium stearate is in the form of white crystals with a melting point of 220.5 to 221.5°C. Its solubility in water is 0.010 g/100 mL at 18°C. Its solubility in alcohol is 0.010 g/100 mL at 25°C; 0.040 g/100 mL in ether at 18°C; and 0.457 g/100 mL in acetone at 15°C. It solvates in hydrocarbon liquids. It is decomposed by strong aqueous acid solutions. The theoretical lithium content is 2.4%, and the theoretical stearate content is 97.6 percent.

5.2.10.2 Specification. Military, MIL-L-51131A, Lithium Stearate.

5.2.10.2.1 Requirements. This specification covers two types of lithium stearate.

Type I - Maximum moisture content of 0.1%
Type II - Maximum moisture content of 0.2%

The chemical and physical properties shall conform to the requirements shown in Table XVIII.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

TABLE XVIII. Lithium stearate - chemical and physical requirements.

	Type I	Type II
Lithium content, %	2.2 to 2.8	2.2 to 2.8
Stearate content, %	94.6 to 97.8	94.6 to 97.8
Moisture, %, max	0.1	0.2
Free acid, calculated as stearic acid, %, max	——	0.5
Free aklaki, calculated as $LiOH \cdot H_2O$, %, max	——	None
Chloride, %, max	——	0.01
Water soluble material, %, max	1.5	0.5
pH value	8 to 10	8 to 10
Melting point, °C min	200	200
Melting point of fatty acid, °C, min	55	55
Iodine number of fatty acid, max	5.0	5.0
†Granulation, US Standard Sieve Through No. 100 (150 micrometer), %, min	99	99

† Standard sieve designation in accordance with ASTM E 11.

5.2.10.3 Use. Lithium stearate is intended for military use as a lubricant in ammunition. Commercial applications include the thickening of lubricating oils for the manufacture of multipurpose greases, and use as a lubricant in powder metallurgy.

5.2.10.4 Safety. Lithium stearate is burnable, and can form explosive dust mixtures in air. It can emit irritating and toxic fumes if heated to decomposition. The lithium ion is toxic to the central nervous system, and its compounds can be irritating to the eyes, skin and mucous membranes. The TLV for lithium stearate, as a nuisance particulate is 10 mg/m^3 of total dust, so inhalation of dust and fumes shall be avoided. (Refer to 4.3.1.)

5.2.10.5 Storage. Lithium stearate shall be stored in corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

5.2.10.6 Disposal. In case of dry spills, gather up and place in containers for disposal. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

An EPA Hazardous Waste Classification is not listed in 40 CFR.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.2.11 Name. Magnesium Stearate $Mg(OOCH_{35}C_{17})_2$ FW 591.27
Magnesium octadecanoate CAS 557-04-0

5.2.11.1 Technical description. Magnesium stearate is in the form of white powder or lumps with a melting point of 186° to 188°C. Its solubility in water is 0.003 g/100 mL at 15°C and 0.008 g/100 mL at 50°C. Its solubitility in alcohol is 0.020 g/100 mL at 25°C; and 0.003 g/100 mL in ether at 25°C. It solvates in hydrocarbon liquids. It is decomposed by strong aqueous acid solutions. The theoretical magnesium content of magnesium distearate is 4.1%, and the theoretical stearate content as stearic acid is 96 percent.

5.2.11.2 Specification. Military, MIL-M-542A, Magnesium Stearate.

5.2.11.2.1 Requirements. This specification covers one grade of magnesium stearate with the chemical and physical properties conforming to the requirements shown in Table XIX.

TABLE XIX. Magnesium stearate - chemical and physical requirements.

Magnesium content, %		4.3 ± 0.2
Stearate content as stearic acid, total,	%, max	97
	%, min	92
Moisture, %, max		6.5
Water-soluble salts, %, max		0.6
Alkalinity, %, max		0.03
Mineral acidity		None
Melting point, °C, min		130
Iodine number of fatty acid, max		5.0
Melting point of fatty acid, °C, min		55
Grit		None
† Granulation, US Standard Sieve		
Passing through No. 100 (150 micrometer), %, min		100
Passing through No. 200 (75 micrometer), %, min		95

† Standard sieve designation in accordance with ASTM E 11.

5.2.11.3 Use. Magnesium stearate is intended for military use as an ingredient in rocket propellants. Commercial applications include the thickening of drying oils, and as an ingredient in varnishes, printing inks, and plastics.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.2.11.4 Safety. Magnesium stearate is burnable, and can form explosive dust mixtures in air. It can emit irritating and toxic fumes if heated to decomposition. The magnesium ion is nontoxic, but its compounds can be irritating to the eyes, skin and mucous membranes. The TLV for magnesium stearate, as a nuisance particulate, is 10 mg/m^3 of total dust, so inhahalation of dust and fumes shall be avoided. (Refer to 4.3.1.)

5.2.11.5 Storage. Magnesium stearate shall be stored in corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

5.2.11.6 Disposal. In case of dry spills, gather up and place in containers for disposal. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

An EPA Hazardous Waste Classification is not listed in 40 CFR.

5.2.12 Name. Sodium Acetate, Anhydrous $NaOOCCH_3$ FW 82.04
Sodium ethanoate CAS 127-09-03

5.2.12.1 Technical description. Anhydrous sodium acetate is a white granular powder in the form of monoclinic crystals with a specific gravity of 1.528. It has a melting point of 324°C, and decomposes above its melting point. Its solubility in water is 119 g/100 mL at 0°C, and 170 g/100 mL at 100°C. Its solubility in methanol is 26 wt % at 25°C, and is 3.2 wt % in ethanol at 25°C. It is decomposed by strong aqueous acid solutions.

5.2.12.2 Specification. Manufacturer's requirements. (No Government specification.)

5.2.12.2.1 Requirements. Sodium acetate, anhydrous, technical, is available from a chemical producer with the chemical properties that conform to the requirements shown in Table XX.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

TABLE XX. Sodium acetate, anhydrous - specification requirements.

Purity, as $NaOOCCH_3$, dry basis, wt %	99.0 to 100
Acetic acid, wt %, max	1.0
Halides, as NaCl, wt %, max	0.3
Iron, as Fe, ppm, max	50
pH of 10% aqueous solution, at 25°C	6.5 to 9.5
Alkalinity, as NaOH, %, max	0.3
Carbonates, as Na_2CO_3, %, max	1.0
Loss on drying, wt %, max	2.0

5.2.12.3 Use. Sodium acetate, anhydrous, is intended for military use in the manufacture of chemical items. Commercial applications include use as an intermediate in the production of dyes and colors.

5.2.12.4 Safety. Sodium acetate can emit irritating and toxic fumes if heated to decomposition. The compound is nontoxic, but can be irritating to the eyes, skin and mucous membranes. There is no PEL or TLV referenced for sodium acetate, but inhalation of dust shall be avoided. (Refer to 4.3.1.)

5.2.12.5 Storage. Sodium acetate, anhydrous, shall be stored in corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

5.2.12.6 Disposal. In case of dry spills, gather up and place in containers for disposal. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

An EPA Hazardous Waste Classification is not listed in 40 CFR.

5.2.13 Name. Sodium Gluconate $NaOOC(CHOH)_4CH_2OH$ FW 218.13
Sodium dextronate CAS 527-07-1

5.2.13.1 Technical description. Sodium gluconate is a white crystalline powder. Its solubility in water is 59 g/100 mL at 25°C. It is sparingly soluble in alcohol, and insoluble in ether. It is decomposed by strong aqueous acid solutions. It forms water soluble complexes with calcium in alkaline solutions, and with iron in near neutral solutions.

5.2.13.2 Specification. Manufacturer's requirements. (No Government specification.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.2.13.2.1 Requirements. Sodium gluconate is available from a chemical producer with the chemical and physical properties conforming to the requirements shown in Table XXI.

TABLE XXI. Sodium gluconate - chemical and physical requirements.

Assay, %, min	99.0
Loss on drying, %, max	1.0
Reducing sugars, %, max	0.5
pH in solution, approximately	7
Specific rotation, °, approximately	+12
Coloration in solution at 40%, Gardner, max	5

5.2.13.3 Use. Sodium gluconate is intended for military use as a sequestering agent in the formulation of cleaning compounds, in metal plating solutions, and as an aluminum deoxidizer. Commercial applications are the same as above.

5.2.13.4 Safety. Sodium gluconate can emit irritating and toxic fumes if heated to decomposition. The compound is nontoxic, but can be irritating to the eyes, skin and mucous membranes. There is no PEL or TLV referenced for sodium gluconate, but inhalation of dust shall be avoided. (Refer to 4.3.1.)

5.2.13.5 Storage. Sodium gluconate shall be stored in corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

5.2.13.6 Disposal. In case of dry spills, gather up and place in containers for disposal. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

An EPA Hazardous Waste Classification is not listed in 40 CFR.

5.2.14 Name. Sodium Oxalate $Na_2(OOC - COO)$ FW 134.00
Sodium ethanedioate CAS 62-76-0

5.2.14.1 Technical description. Sodium oxalate is in the form of colorless crystals or white powder. It has a specific gravity of 2.34. It decomposes at 250° to 270°C on heating. Its solubility in water is 3.7 g/100 mL at 20°C and 6.33 g/100 mL at 100°C. It is insoluble in alcohol and ether. It is decomposed by strong aqueous acid solutions.

5.2.14.2 Specification. Military, MIL-S-210, Sodium Oxalate, Technical (Metric).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.2.14.2.1 Requirements. This specification covers one grade of sodium oxalate in three granulation classes. The chemical properties shall conform to the requirements shown in Table XXII.

The granulation requirements for the three classes are shown in Table XXIII.

TABLE XXII. Sodium oxalate, technical - chemical requirements.

Purity, as oxalate, %, min	99.0
Sodium acid oxalate, %, max	1.00
Moisture, %, max	0.50
Insoluble matter, %, max	0.50

TABLE XXIII. Sodium oxalate, technical - granulation requirements.

	Class A	Class B	Class C
†US Standard Sieves			
Passing through No. 40, (425 micrometer), %, min	99	——	——
Passing through No. 60, (250 micrometer), %, min	——	99.9	——
Passing through No. 100, (150 micrometer), %, min	90	——	99.9

† Standard sieve designation in accordance with ASTM E 11.

5.2.14.3 Use. Sodium oxalate is intended for military use as an ingredient in pyrotechnic compositions. Commercial applications include use as an ingredient in metal cleaning compounds, and also use in textile and leather finishing.

5.2.14.4 Safety. Sodium oxalate can emit irritating and toxic fumes if heated to decomposition. Oxalate salts are irritants of the eyes, skin and mucous membranes. There is no PEL or TLV referenced for sodium oxalate, but inhalation of dust shall be avoided. (Refer to 4.3.1.)

5.2.14.5 Storage. Sodium oxalate shall be stored in corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.2.14.6 Disposal. In case of dry spills, gather up and place in containers for disposal. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

An EPA Hazardous Waste Classification is not listed in 40 CFR.

5.2.15 Name. Sodium Resinate $NaOOOCH_{29}C_{19}$ FW 324.45
CAS 61790-51-0

Sodium abietate $NaOOCH_{30}C_{19}$ CAS 14351-66-7

5.2.15.1 Technical description. Sodium resinate is in the form of white or yellowish-white powder. The formula and formula weight are for sodium abietate; since abietic acid is the predominant acid. Sodium resinate is soluble in water and ethyl alcohol. It is decomposed by strong aqueous acid solutions.

5.2.15.2 Specification. Manufacturer's requirements. (No Government specification.)

5.2.15.2.1 Requirements. Sodium resinate (rosin soap) is available from a chemical producer with the chemical and physical properties conforming to the requirements shown in Table XXIV.

TABLE XXIV. Sodium resinate - chemical and physical requirements.

Sodium resinate, % by wt., min	90.0
Free acid, as abietic acid, % by wt., max	2.0
Free alkali, as NaOH, % by wt., max	0.10
Moisture and volatile matter, % by wt., max	5.0
Matter insoluble in water, % by wt., max	0.10
Matter insoluble in alcohol, % by wt., max	1.0

5.2.15.3 Use. Sodium resinate is intended for military use as an ingredient of cleaning and degreasing compounds for cleaning metal parts. Commercial applications include use as an ingredient in soaps and detergents.

5.2.15.4 Safety. Sodium resinate is burnable, and the powder can form explosive dust mixtures in air. It can emit irritating and toxic fumes if heated to decomposition. It can be irritating to the eyes, skin and mucous membranes. There is no PEL or TLV referenced for sodium resinate, but inhalation of dust shall be avoided. (Refer to 4.3.1.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.2.15.5 Storage. Sodium resinate shall be stored in corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

5.2.15.6 Disposal. In case of dry spills, gather up and place in containers for disposal. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

An EPA Hazardous Waste Classification is not listed in 40 CFR.

5.2.16 Name. Zinc Stearate $Zn(OOCH_{35}C_{17})_2$ FW 632.33
Zinc octadecanoate CAS 557-05-1

5.2.16.1 Technical description. Zinc stearate is a white powder with a melting point of 130°C. It is soluble in water, alcohol and ether. It dissolves in hot hydrocarbon liquids and oils. It is decomposed by strong aqueous acid and alkali solutions. Zinc stearate, as the diacid metal soap, has a theoretical zinc content of 10.3 percent.

5.2.16.2 Specification. Manufacturer's requirements. (No Government specification.)

5.2.16.2.1 Requirements. Zinc stearate is available from a chemical producer with total ash contents ranging from 13.0 to 14.5%, corresponding to zinc contents of 10.4 to 12.7 percent. The free fatty acid contents range from 0.5 to 1.0%, and the moisture contents range from 0.2 to 0.5 percent.

5.2.16.3 Use. Zinc stearate is intended for military use as an ingredient in nonaqueous paints, varnishes and lacquers; and rubber and plastics. Commercial applications include use as a lubricant in powder metallurgy.

5.2.16.4 Safety. Zinc stearate is burnable, and the powder can form explosive dust mixtures in air. It can emit irritating and toxic fumes if heated to decomposition. The zinc ion is nontoxic, but the compound can be irritating to the eyes, skin and mucous membranes. The TLV for zinc stearate, as a nuisance particulate is 10 mg/m^3 total dust, so breathing of dust shall be avoided. (Refer to 4.3.1.)

5.2.16.5 Storage. Zinc stearate shall be stored in corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

5.2.16.6 Disposal. In case of dry spills, gather up and place in containers for disposal. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

An EPA Hazardous Waste Classification is not listed in 40 CFR.

5.3 Metal Chelates

Complex coordination compounds or ions are those in which negative groups or neutral polar molecules are attached to metal ions or atoms. Formulation of a complex compound or ion requires the combination of an ion or molecule which has at least one pair of electrons available for bonding with a metal ion or atom, which has a sufficient attraction for electrons, to form a coordinate covalent bond with the attaching group. The coordination number is the number of electron pairs which an acceptor metal ion attracts in forming a complex ion. The groups attached to the central metal ion are referred to as coordinating groups or ligands. Ligands which have more than one electron pair available for coordination with metal ions are said to be bi-, tri-, or polydentate. Polydentate ligands whose structures permit the attachment of two or more electron donor sites to the same metal ion simultaneously, thus closing one or more rings, are called chelate ligands. Chelation refers to the coordination of a metal ion with a polydentate ligand. The metal chelate so formed may be an insoluble compound that precipitates or a water-soluble compound. Ligands that form stable, water-soluble metal chelates are said to be sequestering agents. Metal chelate stability decreases with increasing ring size and no compounds are known with a ring size greater than seven. Examples of polydentate chelate ligands are shown in Table XXV.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

TABLE XXV. Polydentate chelate ligands.

A. Bidentate Ligands Acetylacetonato ion ($AcAc^-$) Dimethylglyoxime anion 2,2'-Dipyridyl (dipy) Ethyl acetoacetate Ethylenediamine Lactic acid anion Oxalate ion 1,10-Phenanthroline (o-phen) 8-Quinolinolate anion Salicylaldehyde anion
B. Tridentate Ligands o-Azophenoxide ion Citrate anion Diethylenetriamine Iminodiacetic acid anion Triethanolamine
C. Tetradentate Ligands Bisacetylacetoneethylenediamine Nitriloacetic acid anion 2,2',2",-Triaminotriethylamine Triethylene tetramine
D. Pentadentate Ligand Ethylenediaminetriacetic acid
E. Hexadentate Ligand Ethylenediaminetetraacetic acid anion (EDTA)

Source: https://assist.dla.mil -- Downloaded: 202610-26T07:47Z
Check the source to verify that this is the current version before use.

5.3.1 Name. Aluminum Acetylacetonate $Al(C_5H_7O_2)_3$ FW 324.31
$Al[-O-C(CH_3)-CH-C(CH_3)=O]_3$
Aluminum(III) 2,4-pentanedionate CAS 13963-57-0

5.3.1.1 Technical description. Aluminum acetylacetonate is in the form of colorless monoclinic crystals with a specific gravity of 1.27, a melting point of 193°C, and a boiling point of 314°C. It is insoluble in water, very soluble in ethyl alcohol, and soluble in ether and benzene. The theoretical composition is 8.3% aluminum, 55.5% carbon, 6.5% hydrogen, and 29.6% oxygen.

5.3.1.2 Specification. Manufacturer's requirements. (No Government specification.)

5.3.1.2.1 Requirements. Commercially available aluminum acetylacetonate is a white crystalline powder with a melting point of 193°C, a sublimation point of 315°C, and a specific gravity (20°/4°C) of 1.213. The typical analysis is 8.3% aluminum, 55.4% carbon, and 6.5% hydrogen. The solubility of the compound at 25°C is 27.4 g/100 mL in benzene, 9.8 g/100 mL in methyl alcohol, <3.3 g/100 mL in water and <0.01 g/100 mL in cyclohexane.

5.3.1.3 Use. Aluminum acetylacetonate is intended for use as an olefinic polymerization catalyst, and as a crosslinking agent for epoxy resins.

5.3.1.4 Safety. Aluminum acetylacetonate is burnable, and can form explosive dust mixtures in air. It can emit irritating and toxic fumes if heated to decomposition. The aluminum ion is nontoxic, but aluminum acetylacetonate can be irritating to the eyes, skin and mucous membranes. There is no PEL or TLV referenced for aluminum acetylacetonate, but inhalation of dust shall be avoided. (Refer to 4.3.1.)

5.3.1.5 Storage. Aluminum acetylacetonate shall be stored in corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

5.3.1.6 Disposal. In case of dry spills, gather up and place in containers for disposal. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

An EPA Hazardous Waste Classification is not listed in 40 CFR.

5.3.2 Name. Barium Oxalate Ba(OOCCOO) FW 225.36
Barium ethanedioate CAS 516-02-9

Source: https://assist.dla.mil -- Downloaded: 202610-26T07:47Z
Check the source to verify that this is the current version before use.

5.3.2.1 Technical description. Barium oxalate is crystalline with a specific gravity of 2.658. It decomposes at 400°C. Its solubility in water is 0.0093 g/100 mL at 18°C, and 0.0228 g/100 mL at 100°C. It is insoluble in alcohol. It is decomposed by strong aqueous acid solutions.

5.3.2.2 Specification. Military, JAN-B-660, Barium Oxalate (For Use in Ammunition).

5.3.2.2.1 Requirements. This specification covers one grade of barium oxalate, manufactured by a precipitation process, with the chemical and physical properties conforming to the requirements in Table XXVI.

TABLE XXVI. Barium oxalate - chemical and physical requirements.

Barium oxalate, %, min	92
Moisture, %, max	0.3
Material insoluble in dilute acid, %, max	0.5
Material insoluble in water, %, max	0.3
Water-soluble alkalinity, %, max	0.1
Water-soluble acidity	Water extract not acid to methyl orange.
Calcium salts, %, max	0.5
Grit	None
Color	White
†Granulation, US Standard Sieve	
Through No. 100 (150 micrometer), %, min	90
Apparent density, g/mL max	0.50

† US Standard Sieve designation in accordance with ASTM E 11.

5.3.2.3 Use. Barium oxalate is intended for military use in the manufacture of pyrotechnic compositions. The compound does not have commercial uses.

5.3.2.4 Safety. Barium oxalate can emit irritating and toxic fumes if heated to decomposition. The barium ion is toxic when the compound is soluble. Oxalate salts are toxic, and are irritants of the eyes, skin and mucous membranes. The PEL and TLV for soluble barium compounds, as Ba, are 0.5 mg/m^3, so breathing of dust shall be avoided. (Refer to 4.3.1.)

5.3.2.5 Storage. Barium oxalate shall be stored in corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.3.2.6 Disposal. In case of dry spills, gather up and place in containers for disposal. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

Barium oxalate has an EPA Hazardous Waste Classification - Toxicity Characteristic; Waste No. D005.

5.3.3 Name. Calcium Oxalate $Ca(OOCCOO)$ FW 128.10
Calcium ethanedioate $Ca(OOCCOO)\cdot H_2O$ FW 146.12
CAS 5794-28-5

5.3.3.1 Technical description. Anhydrous calcium oxalate is in the form of colorless cubic crystals with a specific gravity of 2.2. The monohydrate is colorless and loses water on heating to 200°C. The anhydrous form decomposes on heating. Its solubility in water is 0.00067 g/100 mL at 13°C and 0.0014 g/100 mL at 95°C. The monohydrate is also insoluble in water. It is insoluble in acetic acid, and is decomposed by strong aqueous mineral acid solutions. The theoretical calcium content of the monohydrate is 27.5%, and the theoretical oxalate content is 60.4 percent.

5.3.3.2 Specification. Military, JAN-C-628, Calcium Oxalate (For Use in Ammunition).

5.3.3.2.1 Requirements. This specification covers one grade of calcium oxalate, consisting essentially of the monohydrate, with the chemical and physical properties conforming to the requirements in Table XXVII.

TABLE XXVII. Calcium oxalate - chemical and physical requirements.

Calcium, %, min	26.6
Oxalate, %, min	58.4
Ba salts, %, max	0.5
Moisture, %, max	0.5
Grit	None
Material soluble in water, %, max	0.4
Material, soluble in dilute acid (10% HCl), %, max	0.5
Apparent density, g/mL, max	0.60
† Granulation, US Standard Sieve	
Through No. 100 (150 μm), %, min	99

† US Standard Sieve designation in accordance with ASTM E 11.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.3.3.3 Use. Calcium oxalate is intended for military use in the manufacturer of pyrotechnic compositions. Commercial applications include the use in the manufacture of oxalic acid and organic oxalates.

5.3.3.4 Safety. Calcium oxalate can emit irritating and toxic fumes if heated to decomposition. The calcium ion is not toxic, but oxalate salts are toxic and are irritants of the eyes, skin and mucous membranes. There is no PEL or TLV referenced for calcium oxalate, but breathing of dust shall be avoided. (Refer to 4.3.1.)

5.3.3.5 Storage. Calcium oxalate shall be stored in corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

5.3.3.6 Disposal. In case of dry spills, gather up and place in containers for disposal. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

An EPA Hazardous Waste Classification is not listed in 40 CFR.

5.3.4 Name. Chromium Acetylacetonate $Cr(C_5H_7O_2)_3$ FW 349.33
Chromic acetylacetonate $Cr[-O-C(CH_3)=CH-C(CH_3)=O]_3$
Chromium(III) 2,4-pentanedionate CAS 21679-31-2

5.3.4.1 Technical description. Chromium acetylacetonate has a melting point of 216°C and a boiling point of 340°C. It is insoluble in water and soluble in organic solvents. The theoretical composition is 14.9% chromium, 51.5% carbon, 6.0% hydrogen, and 27.6% oxygen.

5.3.4.2 Specification. Manufacturer's requirements. (No Government specification.)

5.3.4.2.1 Requirements. Commercially available chromium acetylacetonate is a voilet monoclinic crystalline powder with a melting point of 217°to 220°C, a boiling point of 340°C, and a specific gravity of 1.35. It has an apparent bulk density of 0.47 g/cm^3. The typical analysis is 14.9% chromium. The total solids are 100%, and the methylene chloride insoluble is 0.5% maximum. The solubility of the product is 0.15 g/100 g in water at 30°C, 4.7 g/100 g in methanol at 25°C, 34 g/100 g in benzene at 30°C, 5.03 g/100 g in xylene at 30°C, and 13.6 g/100 g in toluene at 30°C.

5.3.4.3 Use. Chromic acetylacetonate is intended for use as a catalyst for organic synthesis, as a stabilizer for nitroparaffins, and also for tinting glass.

Source: https://assist.dla.mil -- Downloaded: 202610-26T07:47Z
Check the source to verify that this is the current version before use.

5.3.4.4 Safety. Chromic acetylacetonate is burnable, and can form explosive dust mixtures in air. It can emit irritating and toxic fumes if heated to decomposition. The chromium(III) ion is toxic and is a potential carcinogen. The PEL and TLV for chromium(III) compounds, as Cr, is 0.5 mg/m^3, so breathing of mists and fumes shall be avoided. Burning of Cr(III) can form some Cr(VI). Chromium(VI) is considered a confirmed carcinogen by the International Agency for Research on Cancer (IARC) and Transactions of ACGIH. The TLV for chromium(VI) is 0.05 mg/m^3. Breathing of mists or fumes of chromium(VI) shall be avoided. The Cr(III) compound solution can be irritating to the eyes, skin, and mucous membranes. (Refer to 4.3.1.)

5.3.4.5 Storage. Chromic acetylacetonate shall be stored in corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

5.3.4.6 Disposal. In case of dry spills, gather up and place in containers for disposal. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

Chromic acetylacetonate has an EPA Hazardous Waste Classification - Toxicity Characteristic; Waste No. D007.

5.3.5 Name. Cobaltic Acetylacetonate $Co(C_5H_7O_2)_3$ FW 356.30
Cobalt tris(acetylacetonate) $Co[-O-C(CH_3)=CH-C(CH_3)=O]_3$
Cobalt(III) 2,4-pentanedionate CAS 21679-46-9

5.3.5.1 Technical description. Cobaltic acetylacetonate is in the form of dark green or black crystals with a specific gravity of 1.43. The theoretical composition is 16.5% cobalt, 50.6% carbon, 5.9% hydrogen, and 27.0% oxygen.

5.3.5.2 Specification. Manufacturer's requirement. (No Government specification.)

5.3.5.2.1 Requirements. Commercially available cobaltic acetylacetonate is a dark green crystalline powder with a specific gravity of 1.43, and a melting point of 214° to 215°C. It has an apparent bulk density of 0.63 g/cm^3. The typical analysis is 16.6% cobalt(III), and 0.22% cobalt(II). The total solids are 99.96%, and the methylene chloride insolubles are 0.5% maximum. The solubility of the product, at 30°C, is 0.3 g/100 g in water, 16.3 g/100 g in benzene, 1.9 g/100 g in xylene, and 0.031 g/100 g in heptane. It is soluble in hot methanol, hot acetone, and hot ethylene glycol monoethyl ether.

5.3.5.3 Use. Cobaltic acetylacetonate is intended for use as a catalyst for organic synthesis, polymerization and vulcanization reactions, combustion of solid propellants, and as coloring for synthetic resins and glass tinting. It is also used for the vapor deposition of cobalt metal and oxide.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.3.5.4 Safety. Cobaltic acetylacetonate is burnable, and can form explosive dust mixtures in air. It can emit irritating and toxic fumes if heated to decomposition. The PEL and TLV for cobalt fumes is 0.1 mg/m^3, so breathing of fumes shall be avoided. Cobalt(III) compounds can be irritating to eyes, skin and mucous membranes. (Refer to 4.3.1.)

5.3.5.5 Storage. Cobaltic acetylacetonate shall be stored in corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

5.3.5.6 Disposal. In case of dry spills, gather up and place in containers for disposal. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

An EPA Hazardous Waste Classification is not listed in 40 CFR.

5.3.6 Name. Cobaltous Acetylacetonate $Co(C_5H_7O_2)_2$ FW 257.15
Cobalt bis(acetylacetonate) $Co[-O-C(CH_3)=CH-C(CH_3)=O]_2$
Cobalt(II) 2,4-pentanedionate CAS 14024-48-7

5.3.6.1 Technical description. Cobaltous acetylacetonate is crystalline and moisture-sensitive. It has a melting point of 172°C. The theoretical composition is 22.9% cobalt, 46.7% carbon, 5.4% hydrogen, and 24.9% oxygen.

5.3.6.2 Specification. Manufacturer's requirements. (No Government specification.)

5.3.6.2.1 Requirements. Commercially available cobaltous acetylacetonate is a purple powder that sublimes without melting. The typical analysis is 24.0% cobalt, 43.6% carbon, and 5.6% hydrogen. It is soluble in water. The solubility of the product at 25°C is 2.4 g/100 mL in methanol, and 8.1 g/100 mL in benzene.

5.3.6.3 Use. Cobaltous acetylacetonate is intended for use as a catalyst for the hydrogenation of diolefins and fatty acids; and for polymerization of olefins.

5.3.6.4 Safety. Cobaltous acetylacetonate is burnable and can form explosive dust mixtures in air. It can emit irritating and toxic fumes if heated to decomposition. The PEL and TLV for cobalt fumes are 0.1 mg/m^3, so breathing of fumes shall be avoided. Cobalt(II) compounds can be irritating to eyes, skin and mucous membranes. (Refer to 4.3.1.)

5.3.6.5 Storage. Cobaltous acetylacetonate shall be stored in corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.3.6.6 Disposal. In case of dry spills, gather up and place in containers for disposal. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

An EPA Hazardous Waste Classification is not listed in 40 CFR.

5.3.7 Name. Copper Acetylacetonate $Cu(C_5H_7O_2)_2$ FW 261.76
Copper(II) 2,4-pentanedionate $Cu[-O-C(CH_3)=CH-C(CH_3)=O]_2$
Cupric acetylacetonate CAS 13395-16-9

5.3.7.1 Technical description. Copper acetylacetonate is in the form of blue crystals with a melting point of >230°C and sublimation. It is insoluble in water and slightly soluble in alcohol. The theoretical composition is 42.3% copper, 45.8% carbon, 5.4% hydrogen, and 24.5% oxygen.

5.3.7.2 Specification. Manufacturer's requirements. (No Government specification.)

5.3.7.2.1 Requirements. Commercially available copper acetylacetonate is a light blue crystalline powder with a melting point of 240°C. The typical analysis of 24.2% copper, 45.8% carbon, and 5.5% hydrogen. The solubility of the product at 25°C is 0.2 g/100 mL in benzene and 0.3 g/100 mL in methanol.

5.3.7.3 Use. Copper acetylacetonate is intended for use as a catalyst for urethanes, diazo compounds, and dimerization reactions.

5.3.7.4 Safety. Copper acetylacetonate is burnable, and can emit irritating and toxic fumes if heated to decomposition. The PEL for copper fumes is 0.1 mg/m^3, and the TLV is 0.2 mg/m^3, so breathing of fumes shall be avoided. Copper(II) compounds can be irritating to the eyes, skin and mucous membranes. (Refer to 4.3.1.)

5.3.7.5 Storage. Copper acetylacetonate shall be stored in a cool, dry place. (Refer to 4.3.2.)

5.3.7.6 Disposal. In case of dry spills, gather up and place in containers for disposal. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

Source: https://assist.dla.mil -- Downloaded: 202610-26T07:47Z
Check the source to verify that this is the current version before use.

An EPA Hazardous Waste Classification is not listed in 40 CFR.

5.3.8 Name. Copper 8-Quinolinolate $Cu(C_9H_6NO)_2$ FW 351.83
Copper bis(8-oxyquinoline) CAS 10380-28-6

5.3.8.1 Technical description. Copper 8-quinolinolate is a nonhygroscopic odorless powder. It is insoluble in water and most organic solvents. It is somewhat soluble in pyridine and quinoline. It is decomposed by strong acids.

5.3.8.2 Specification. Manufacturer's requirements. (No Government specification.)

5.3.8.2.1 Requirements. Commercially available copper 8-quinolinolate is a yellow-green to olive-green powder with the specification requirements shown in Table XXVIII.

TABLE XXVIII. Copper 8-quinolinolate - commercial specification requirements.

Assay, %, min	90.0
Loss on drying, %, max	1.0
† Sieve size, US Standard Sieve	
Through No. 10 (2.00 mm), %, min	90

† US Standard Sieve designation in accordance with ASTM E 11.

5.3.8.3 Use. Copper 8-quinolinolate is intended for military use as a mildew inhibitor in preservative coatings for canvas and in formulations for the treatment of sandbags for fungus resistance, as described in federal specification TT-P-595 and military specification MIL-F-46032. Commercial applications include the fungus-proofing of cloth, paper, wood and other cellulose materials; treatment of vinyl resins to prevent fungus deterioration; and the control of fungus diseases in agriculture.

5.3.8.4 Safety. Copper 8-quinolinolate is burnable, and can form explosive dust mixtures in air. It can emit irritating and toxic fumes if heated to decomposition. The PEL for copper fumes is 0.1 mg/m^3 and the TLV is 0.2 mg/m^3, so breathing of fumes shall be avoided. 8-Quinolinol has moderate toxicity and is a suspected carcinogen. Copper(II) compounds can be irritating to the eyes, skin and mucous membranes. (Refer to 4.3.1.)

5.3.8.5 Storage. Copper 8-quinolinolate shall be stored in corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.3.8.6 Disposal. In case of dry spills, gather up and place in containers for disposal. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

An EPA Hazardous Waste Classification is not listed in 40 CFR.

5.3.9 Name. Ferric Acetylacetonate $Fe(C_5H_7O_2)_3$ FW 353.18
Iron(III) 2,4-pentanedionate $Fe[-O-C(CH_3)=CH-C(CH_3)=O]_3$
CAS 14024-18-1

5.3.9.1 Technical description. Ferric acetylacetonate is in the form of ruby red rhombic crystals with a specific gravity of 1.33 and a melting point of 184°C. It is slightly soluble in water, and soluble in alcohol, acetone, and benzene. The theoretical composition is 15.8% iron, 51.0% carbon, 6.0% hydrogen, and 27.1% oxygen.

5.3.9.2 Specification. Manufacturer's requirements. (No Government specification.)

5.3.9.2.1 Requirements. Commercially available ferric acetylacetonate is a bright orange-red rhombic crystalline powder with a specific gravity of 1.36 and a melting point of 181°C. The typical analysis is 16.14% iron, 0.25% sulfate, and 99.56% total solids. The methylene chloride insoluble is 0.5% maximum. The solubility of the product is <3.5% in water, and 22.3 g/100 g in benzene.

5.3.9.3 Use. Ferric acetylacetonate is intended for use as a catalyst for polymerization, cumbustion of solid propellants, and as coloring for synthetic resins and glass tinting.

5.3.9.4 Safety. Ferric acetylacetonate is burnable and can form explosive dust mixtures in air. It can emit irritating and toxic fumes if heated to decomposition. The PEL for iron oxide fumes is 10 mg/m^3 and the TLV for iron oxide fumes, as Fe, is 5 mg/m^3, so breathing of fumes shall be avoided. The iron(III) compounds can be irritating to the eyes, skin and mucous membranes. (Refer to 4.3.1.)

5.3.9.5 Storage. Ferric acetylacetonate shall be stored in corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

5.3.9.6 Disposal. In case of dry spills, gather up and place in containers for disposal. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

An EPA Hazardous Waste Classification is not listed in 40 CFR.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.3.10 Name. Magnesium Acetylacetonate $Mg(C_5H_7O_2)_2$ FW 222.53
Magnesium 2,4-pentanedionate $Mg[-O-C(CH_3)=CH-C(CH_3)=O]_2$
CAS 14024-58-9

5.3.10.1 Technical description. Magnesium acetylacetonate is in the form of a white powder. The theoretical composition is 10.9% magnesium, 53.9% carbon, 6.3% hydrogen and 28.4% oxygen.

5.3.10.2 Specification. Manufacturer's requirements. (No Government specification.)

5.3.10.2.1 Requirements. Commercially available magnesium acetylacetonate is available from a chemical manufacturer as a white powder with a specific gravity of 1.162 and a melting point of 262° to 263°C. The typical analysis is 11.1% magnesium. The solubility of the product at 25°C is 0.7 g/100 mL in benzene, and 2.9 g/100 mL in methanol.

5.3.10.3 Use. Magnesium acetylacetonate is intended for use as a curing agent and curing accelerator for epoxy resins.

5.3.10.4 Safety. Magnesium acetylacetonate is burnable, and can form explosive dust mixtures in air. It can emit irritating and toxic fumes if heated to decomposition. The PEL for magnesium oxide fumes is 15 mg/m^3, and the TLV is 10 mg/m^3, so breathing of fumes shall be avoided. The magnesium ion is nontoxic but its compounds can be irritating to the eyes, skin and mucous membranes. (Refer to 4.3.1.)

5.3.10.5 Storage. Magnesium acetylacetonate shall be stored in corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

5.3.10.6 Disposal. In case of dry spills, gather up and place in containers for disposal. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

An EPA Hazardous Waste Classification is not listed in 40 CFR.

5.3.11 Name. Manganic Acetylacetonate $Mn(C_5H_7O_2)_3$ FW 352.27
Manganese tris(acetylacetonate) $Mn[-O-C(CH_3)=CH(CH_3)=O]_3$
Manganese(III) 2,4-pentanedionate CAS 14284-89-0

Source: https://assist.dla.mil -- Downloaded: 202610-26T07:47Z
Check the source to verify that this is the current version before use.

5.3.11.1 Technical description. Manganic acetylacetonate is in the form of a black or brown crystalline powder. The theoretical composition is 15.6% manganese, 51.1% carbon, 6.0% hydrogen, and 27.3% oxygen. It is very slightly soluble in water, and soluble in acetone.

5.3.11.2 Specification. Manufacturer's requirements. (No Government specification.)

5.3.11.2.1 Requirements. Commercially available manganic acetylacetonate is a black powder with a melting point of 171°C. The typical analysis is 15.7% manganese, 50.9% carbon, and 5.9% hydrogen. The solubility of the product in benzene is 13.6 g/100 mL at 25°C, and in methanol, it is 34.8 g/100 mL at 30°C.

5.3.11.3 Use. Manganic acetylacetonate is intended for use as a catalyst for the polymerization of vinyl polymers, and as a curing agent for isocyanate resins.

5.3.11.4 Safety. Manganic acetylacetonate is burnable, and can form explosive dust mixtures in air. It can emit irritating and toxic fumes if heated to decomposition. The PEL and TLV for manganese compounds, as Mn, are 5 mg/m^3 as a ceiling limit. The TLV for manganese fumes is 1 mg/m^3, so breathing of fumes shall be avoided. The manganic ion is toxic, and its compounds can be irritating to the eyes, skin and mucous membranes. (Refer to 4.3.1.)

5.3.11.5 Storage. Manganic acetylacetonate shall be stored in corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

5.3.11.6 Disposal. In case of dry spills, gather up and place in containers for disposal. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

An EPA Hazardous Waste Classification is not listed in 40 CFR.

5.3.12 Name. Manganous Acetylacetonate $Mn(C_5H_7O_2)_2$ FW 253.14
Manganese bis(acetylacetonate) $Mn[-O-C(CH_3)=CH-C(CH_3)=O]_2 2$
Manganese(II) 2,4-pentanedionate CAS 14024-58-9

5.3.12.1 Technical description. Manganous acetylacetonate is in the form of light tan crystals. The theoretical composition is 21.7% manganese, 47.3% carbon, 5.6% hydrogen, and 25.4% oxygen.

5.3.12.2 Specification. Manufacturer's requirements. (No Government specification.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.3.12.2.1 Requirements. Commercially available manganous acetylacetonate is a light tan crystalline powder with a melting point of 180°C. The typical analysis is 21.5% manganese. The solubility of the product at 25°C is 4.4 g/100 mL in benzene, and 7.0 g/100 mL in methanol.

5.3.12.3 Use. Manganous acetylacetonate is intended for use as a catalyst for hydrogenation of olefins, polymerization of urethanes, and oxidation synthesis reactions.

5.3.12.4 Safety. Manganous acetylacetonate is burnable, and can form explosive dust mixtures in air. It can emit irritating and toxic fumes if heated to decomposition. The PEL for manganese is 5 mg/m^3 as a ceiling limit. The TLV for manganese compounds, as Mn, is 5 mg/m^3 as a ceiling limit. The TLV for manganese fumes is 1 mg/m^3, so breathing of fumes shall be avoided. The manganous ion is toxic, and its compounds can be irritating to the eyes, skin and mucous membranes. (Refer to 4.3.1.)

5.3.12.5 Storage. Manganous acetylacetonate shall be stored in corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

5.3.12.6 Disposal. In case of dry spills, gather up and place in containers for disposal. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

An EPA Hazardous Waste Classification is not listed in 40 CFR.

5.3.13 Name. Nickel Acetylacetonate, Hydrate $Ni(C_5H_7O_2)_2 \cdot H_2O$
$Ni[-O-C(CH_3)=CH-C(CH_3)=O]_2 \cdot H_2O$ FW 256.91
Nickel(II) 2,4-pentanedionate, hydrate CAS 120156-44-7

5.3.13.1 Technical description. Nickel acetylacetonate is in the form of green crystals. The theoretical composition is 21.4% nickel, 43.7% carbon, 5.8% hydrogen, and 29.1% oxygen.

5.3.13.2 Specification. Manufacturer's requirements. (No Government specification.)

5.3.13.2.1 Requirements. Commercially available nickel acetylacetonate is a bright green crystalline material with a melting point of 228°C, and a sublimation point of 220°C at 11 mm Hg. The typical analysis is 21.5% nickel, 42.5% carbon, and 5.9% hydrogen. The solubility of the product at 25°C is 1.5 g/100 mL in benzene, 2.2 g/100 mL in methanol, and 10.6 g/100 mL in ethyl alcohol. It is also soluble in chloroform.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.3.13.3 Use. Nickel acetylacetonate is intended for use as a catalyst for hydrogenation reactions.

5.3.13.4 Safety. Nickel acetylacetonate is burnable, and can form explosive dust mixtures in air. It can emit irritating and toxic fumes if heated to decomposition. The PEL for soluble nickel compounds is 1 mg/m^3 and the TLV is 0.1 mg/m^3, as Ni, so breathing of fumes shall be avoided. Nickel compounds are toxic and are confirmed carcinogens. They can be irritating to the eyes, skin and mucous membranes. (Refer to 4.3.1.)

5.3.13.5 Storage. Nickel acetylacetonate shall be stored in corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

5.3.13.6 Disposal. In case of dry spills, gather up and place in containers for disposal. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

Nickel acetylacetonate has an EPA Hazardous Waste Classification - Toxic.

5.3.14 Name. Ruthenium Acetylacetonate $Ru(C_5H_7O_2)_3$ FW 398.40
$Ru[-O-C(CH_3)=CH-C(CH_3)=O]_3$
Ruthenium(III) 2,4-pentanedionate CAS 14284-93-6

5.3.14.1 Technical description. Ruthenium acetylacetonate is in the form of red crystals. The theoretical composition is 25.5% ruthenium, 45.2% carbon, 5.3% hydrogen, and 24.0% oxygen.

5.3.14.2 Specification. Manufacturer's requirements. (No Government specification.)

5.3.14.2.1 Requirements. Commercially available ruthenium acetylacetonate is a red crystalline material with a melting point of 235° to 237°C. The typical analysis is 26.0% ruthenium. It is soluble in acetone, chloroform, ethanol, and toluene.

5.3.14.3 Use. Ruthenium acetylacetonate is intended for use as a catalyst.

5.3.14.4 Safety. Ruthenium acetylacetonate is burnable, and can form explosive dust mixtures in air. It can emit irritating and toxic fumes if heated to decomposition. There is no PEL or TLV referenced for ruthenium compounds, but breathing of fumes shall be avoided. Ruthenium compounds can be irritating to the eyes, skin and mucous membranes. (Refer to 4.3.1.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.3.14.5 Storage. Ruthenium acetylacetonate shall be stored in corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

5.3.14.6 Disposal. In case of dry spills, gather up and place in containers for disposal. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

An EPA Hazardous Waste Classification is not listed in 40 CFR.

5.3.15 Name. Strontium Oxalate — $Sr(OOCCOO)$ FW 175.62; $Sr(OOCCOO)\cdot H^2O$ FW 193.64

Strontium Ethanedioate — CAS 814-95-9

5.3.15.1 Technical description. Hydrated strontium oxalate is in the form of colorless crystals. It loses water on heating to 150°C. The anhydrous form decomposes on heating. The solubility in water of the hydrated form is 0.0051 g/100 mL at 15°C and 5 g/100 mL at 100°C. It is decomposed by strong aqueous mineral acids.

5.3.15.2 Specification. Military, MIL-S-12210, Strontium Oxalate.

5.3.15.2.1 Requirements. This specification covers two grades of strontium oxalate. Grade A shall be the anhydrous form and Grade B, the hydrated form. The chemical and physical properties shall conform to the requirements shown in Table XXIX.

TABLE XXIX. Strontium oxalate - chemical and physical requirements.

	Grade A	Grade B
Strontium oxalate, %, min	94.0	84.0
Moisture, %, max	0.25	10.0
Iron, %, max	0.01	----
Impurities by flame test		
Barium compounds	None	None
Calcium compounds, amount max	Slight	Slight
†Granulation, US Standard Sieves		
Through No. 60 (250 µm), %, min	----	99.0
Through No. 140 (100 µm), %, min	99.0	----
Color	White	White

† US Standard Sieve designation in accordance with ASTM E 11.

Source: https://assist.dla.mil -- Downloaded: 202610-26T07:47Z
Check the source to verify that this is the current version before use.

5.3.15.3 Use. Strontium oxalate is intended for military use in the manufacture of pyrotechnic compositions. Commercial applications include use in catalyst manufacture.

5.3.15.4 Safety. Strontium oxalate can emit irritating and toxic fumes if heated to decomposition. The strontium ion is low in toxicity, but oxalate salts are toxic and corrosive, and are strong irritants of the eyes, skin and mucous membranes. There is no PEL or TLV referenced for strontium compounds, but breathing of fumes shall be avoided. (Refer to 4.3.1.)

5.3.15.5 Storage. Strontium oxalate shall be stored in corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

5.3.15.6 Disposal. In case of dry spills, gather up and place in containers for disposal. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

An EPA Hazardous Waste Classification is not listed in 40 CFR.

5.3.16 Name. Dibutyl Tin Acetylacetonate $(C_4H_9)_2Sn(C_5H_7O_2)_2$ FW 431.14
$(C_4H_9)_2Sn[-O-C(CH_3)=CH-C(CH_3)=O]_2$
Dibutyl tin(IV) 2,4-pentanedionate CAS 22673-19-4

5.3.16.1 Technical description. Dibutyl tin acetylacetonate is in the form of a liquid above 21°C. The theoretical composition is 27.6% tin, 50.1% carbon, 7.5% hydrogen, and 14.9% oxygen. It is insoluble in water, but hydrolyzes on explosure to water.

5.3.16.2 Specification. Manufacturer's requirements. (No Government specification.)

5.3.16.2.1 Requirements. Commercially available dibutyl tin acetylacetonate is an amber liquid with a specific gravity (25°C) of 1.20, a melting point of 21°C, a Gardner viscosity of A-3, and a flash point (closed cup) of 91.1°C (195°F). The typical analysis is 27.3% tin.

5.3.16.3 Use. Dibutyl tin acetylacetonate is intended for use as a catalyst for polymerization of olefins and unsaturated polyesters.

5.3.16.4 Safety. Dibutyl tin acetylacetonate is a combustible liquid or a burnable solid depending on the temperature. It can emit irritating and toxic fumes if heated to decomposition. The PEL, as an organic tin compound, is 0.1 mg/m^3, and the TLV is 0.1 mg/m^3 (including skin), as Sn. The breathing of fumes shall be avoided. The compound is toxic and can be absorbed through the skin. It can be irritating to the eyes, skin and

Source: https://assist.dla.mil -- Downloaded: 202640-26T07:47Z
Check the source to verify that this is the current version before use.

mucous membranes, and may cause burns and tissue damage. In case of contact with the skin, flush with water, then wash with soap and water. In case of contact with the eyes, flush with water for at least 20 minutes, and obtain medical attention. (Refer to 4.3.1.)

5.3.16.5 Storage. Dibutyl tin acetylacetonate shall be stored in corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

5.3.16.6 Disposal. In case of dry spills of solid (below 21°C), recover in dry state and place in containers for disposal. In case of small liquid spills (above 21°C), absorb with nonreactive absorbent, and place in containers for disposal. In case of large liquid spills, dike to prevent spreading. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

An EPA Hazardous Waste Classification is not listed in 40 CFR.

5.3.17 Name. Titanium Ammonium Dihydroxy Lactate FW 294.12
$Ti(OH)_2[OCH(CH_3)COONH_4]_2$ CAS 65104-06-5
Ammonium dihydroxy bis(lactato)titanate
Ammonium dihydroxy bis(2-hydroxypropanato-O, O')titanate

5.3.17.1 Technical description. Titanium ammonium dihydroxy lactate is in the form of a solid. It is soluble in water, and hydrolyzes very slowly. The theoretical Ti content is 16.3 percent.

5.3.17.2 Specification. Manufacturer's requirements. (No Government specification.)

5.3.17.2.1 Requirements. Commercially available titanium ammonium dihydroxy lactate is a 50% solution in water with a Ti content of 8.2 percent. The solution is light amber in color with a specific gravity (25°/25°C) of 1.05, an approximate thickening point of -10°C, and an approximate viscosity (25°C) of 8 cP(mPa•s).

5.3.17.3 Use. Titanium ammonium dihydroxy lactate is intended for use as a crosslinking agent for resins and polymers in aqueous systems.

5.3.17.4 Safety. Titanium ammonium dihydroxy lactate solution is not burnable. It can emit irritating and toxic fumes if heated to decomposition. The PEL is 15 mg/m^3 and the TLV is 10 mg/m^3 for the resulting titanium dioxide as total dust as a nuisance particulate. The PEL for the resulting ammonia fumes is 35 mg/m^3 and the TLV is 18 mg/m^3. The compound solution is not toxic, but can be irritating to the eyes, skin and mucous membranes. (Refer to 4.3.1.)

Source: https://assist.dla.mil -- Downloaded: 202610-26T07:47Z
Check the source to verify that this is the current version before use.

5.3.17.5 Storage. Titanium ammonium dihydroxy lactate solution shall be stored in corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

5.3.17.6 Disposal. In case of small liquid spills, absorb with nonreactive absorbent and place in containers for disposal. In case of large liquid spills, dike to prevent spreading. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

An EPA Hazardous Waste Classification is not listed in 40 CFR.

5.3.18 Name. Titanium Diisopropoxide Acetylacetonate

$Ti[OCH(CH_3)_2]_2(C_5H_7O_2)_2$ FW 364.30

Titanium diisopropoxide bis(2,4-pentanedionate) CAS 17927-72-9

Bis(2,4-pentanedionate-0, 0')bis(2-propanolato)titanium

5.3.18.1 Technical description. Titanium diisopropoxide acetylacetonate is in the form of a solid. It is soluble in isopropanol. It is insoluble in water, but hydrolyzes slowly.

5.3.18.2 Specification. Manufacturer's requirements. (No Government specification.)

5.3.18.2.1 Requirements. Commercially available titanium diisopropoxide acetylacetonate is a 75% solution in isopropanol, with a Ti content of 9.9 percent. The solution is red in color with a specific gravity (25°/25°C) of 0.99, and approximate thickening point of -46°C, an approximate viscosity (25°C) of 15 cP(mPa•s), and a flash point (closed cup) of 12°C (54°F). The solution is soluble in ethyl acetate, isopropyl acetate, and methyl ethyl ketone. It is immiscible with water.

5.3.18.3 Use. Titanium diisopropoxide acetylacetonate is intended for use as a crosslinking agent for resins, polymers and heat-set printing inks; and for surface modification of plastic, metal, textile or paper for deposition by hydrolysis of an amorphous polar film of titanium dioxide.

5.3.18.4 Safety. Titanium diisopropoxide acetylacetonate solution in isopropanol is flammable. It can emit irritating and toxic fumes if heated to decomposition. The PEL is 15 mg/m^3 and the TLV is 10 mg/m^3 for the resulting titanium dioxide as total dust as a nuisance particulate. The compound solution is not toxic, but can cause eye burns and be irritating to the skin and mucous membranes. (Refer to 4.3.1.)

5.3.18.5 Storage. Titanium diisopropoxide acetylacetonate solution shall be stored in corrosion-resistant containers in a cool, dry place; away from heat, sparks and open flame. (Refer to 4.3.2.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.3.18.6 Disposal. In case of small liquid spills, absorb with nonreactive absorbent and place in containers for disposal. In case of large liquid spills, dike to prevent spreading. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

An EPA Hazardous Waste Classification is not listed in 40 CFR.

5.3.19 Name. Titanium Diisopropoxide Bis(triethanolamine) FW 462.44
$Ti[OCH(CH_3)_2]_2[OCH_2CH_2N(CH_2CH_2OH)_2]_2$ CAS 36673-16-2
Bis(2,2',2"-nitrilotrisethanol)bis(2-propanolato)titanium (4^+)
Bis(triethanolamine)titanium diisopropoxide
Titanium diisopropoxide bis(2,2',2"-nitrilotriethanol)

5.3.19.1 Technical description. Titanium diisopropoxide bis(triethanolamine) is in the form of a solid. It is soluble in water and hydrolyzes very slowly. It is also soluble in isopropanol.

5.3.19.2 Specification. Manufacturer's requirements. (No Government specification.)

5.3.19.2.1 Requirements. Commercially available titanium diisopropoxide bis(triethanolamine) is actually a mixture of chelates corresponding to the average formula above. The product is an 80% solution in isopropanol, with a Ti content of 8.3 percent. The solution is pale yellow in color with a specific gravity (25°/25°C) of 1.06, an approximate thickening point of -35°C, an approximate viscosity (25°C) of 90 cP(mPa•s), a flash point (closed cup) of 16°C (60°F). The solution is miscible with water.

5.3.19.3 Use. Titanium diisopropoxide bis(triethanolamine) is intended for use as a crosslinking agent for resins, polymers and heat-set printing inks; and for surface modification of pigments.

5.3.19.4 Safety. Titanium diisopropoxide bis(triethanolamine) solution in isopropanol is flammable. It can emit irritating and toxic fumes if heated to decomposition. The PEL is 15 mg/m^3 and the TLV is 10 mg/m^3 for the resulting titanium dioxide as total dust as a nuisance particulate. The compound solution is not toxic, but can be irritating to the eyes, skin, and mucous membranes. (Refer to 4.3.1.)

5.3.19.5 Storage. Titanium diisopropoxide bis(triethanolamine) solution shall be stored in corrosion-resistant containers in a cool, dry place away from heat, sparks and open flame. (Refer to 4.3.2.)

Source: https://assist.dla.mil -- Downloaded: 202610-26T07:47Z
Check the source to verify that this is the currentversion before use.

5.3.19.6 Disposal. In case of small liquid spills, absorb with nonreactive absorbent and place in containers for disposal. In case of large liquid spills, dike to prevent spreading. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

An EPA Hazardous Waste Classification is not listed in 40 CFR.

5.3.20 Name. Titanium Diisopropoxide Ethylacetoacetate
$[(CH_3)_2CHO]_2Ti[-O-C(CH_3)=CHCO(OC_2H_5)]_2$ FW 424.34
Bis(ethyl-3-oxobutanolato-O,O')bis(2-propanolato)titanium
Titanium diisopropoxide ethyl-3-oxobutanoate CAS 27858-32-8

5.3.20.1 Technical description. Titanium diisopropoxide ethylacetoacetate is in the form of a liquid. It is soluble in acetone, ethanol, and isopropanol. It hydrolyzes very slowly in water.

5.3.20.2 Specification. Manufacturer's requirements. (No Government specification.)

5.3.20.2.1 Requirements. Commercially available titanium diisopropoxide ethylacetoacetate is a yellow to amber colored liquid with a Ti content of 11.1 percent. The product is 100% of the compound with a specific gravity (25°/25°C) of 1.05, an approximate thickening point of 20°C, an approximate viscosity (25°C) of 50 cP(mPa•s), and a flash point (closed cup) of 27°C (81°F).

5.3.20.3 Use. Titanium diisopropoxide ethylacetoacetate is intended for use as a crosslinking agent for resins and polymers.

5.3.20.4 Safety. Titanium diisopropoxide ethylacetoacetate is a flammable liquid. It can release irritating and toxic fumes if heated to decomposition. The PEL is 15 mg/m^3 and the TLV is 10 mg/m^3 for the resulting titanium dioxide as total dust as a nuisance particulate. The compound is not toxic, but can be irritating to the eyes, skin and mucous membranes. (Refer to 4.3.1.)

5.3.20.5 Storage. Titanium diisopropoxide ethylacetoacetate shall be stored in corrosion-resistant containers in a cool, dry place away from heat, sparks and open flame. (Refer to 4.3.2.)

5.3.20.6 Disposal. In case of small liquid spills, absorb with nonreactive absorbent and place in containers for disposal. In case of large liquid spills, dike to prevent spreading. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

Source: https://assist.dla.mil -- Downloaded: 202610-26T07:47Z
Check the source to verify that this is the current version before use.

An EPA Hazardous Waste Classification is not listed in 40 CFR.

5.3.21 Name. Titanium Potassium Oxalate, Dihydrate
$K_2[TiO_3C_2O_4)_2 \cdot 2H_2O$ FW 354.17
Potassium bis(oxalato)oxotitanate, dihydrate CAS 14402-67-6
Potassium titanium oxalate, dihydrate
Titanyl potassium oxalate, dihydrate

5.3.21.1 Technical description. Titanium potassium oxalate, dihydrate, is in the form of a white crystalline powder that is very soluble in water.

5.3.21.2 Specification. Manufacturer's requirements. (No Government specification.)

5.3.21.2.1 Requirements. None available.

5.3.21.3 Use. Titanium potassium oxalate, dihydrate, is intended for use as a mordant in dyeing cotton and leather, and for the sensitization of aluminum for photography.

5.3.21.4 Safety. Titanium potassium oxalate, dihydrate, is not burnable. It can emit irritating and toxic fumes if heated to decomposition. The PEL is 15 mg/m^3 and the TLV is 10 mg/m^3 for the resulting titanium dioxide as total dust as a nuisance particulate. The compound, as an oxalate, is toxic and corrosive; and can be very irritating to the eyes, skin and mucous membranes. (Refer to 4.3.1.)

5.3.21.5 Storage. Titanium potassium oxalate shall be stored in corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

5.3.21.6 Disposal. In case of dry spills, gather up and place in containers for disposal. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

An EPA Hazardous Waste Classification is not listed in 40 CFR.

5.3.22 Name. Vanadyl Acetylacetonate $VO(C_5H_7O_2)_2$ FW 265.16
$O=V[-O-C(CH_3)=CH-C(CH_3)=O]_2$
Vanadium(IV) oxide bis(2,4-pentanedionate) CAS 3153-26-2
Vanadyl 2,4-pentanedionate

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.3.22.1 Technical description. Vanadyl acetylacetonate is in the form of blue-green crystals. The theoretical composition is 19.3% vanadium, 45.3% carbon, 5.28% hydrogen, and 30.12% oxygen. It is moderately soluble in acetone, chloroform, and ether.

5.3.22.2 Specification. Manufacturer's requirements. (No Government specification.)

5.3.22.2.1 Requirements. Commercially available vanadyl acetylacetonate is a blue-green crystalline product with a melting point of of 250°C. Its solubility at 25°C is 0.9 g/100 mL in benzene and 6.4 g/100 mL in methanol.

5.3.22.3 Use. Vanadyl acetylacetonate is intended for use as a catalyst for polymerization of olefins and the hydro-refining of heavy oils.

5.3.22.4 Safety. Vanadyl acetylacetonate is bumable, and can form explosive dust mixtures in air. It can emit irritating and toxic fumes if heated to decompositioin. The resulting vanadium oxide has a PEL (ceiling values) of 0.5 mg/m^3 as dust and 0.1 mg/m^3 as fumes. The TLV for vanadium compounds, as V_2O_5 respirable dust and fumes, is 0.05 mg/m^3, so breathing of dust and fumes shall be avoided. Vanadium compounds can be irritating to the eyes, skin and mucous membranes. (Refer to 4.3.1.)

5.3.22.5 Storage. Vandadyl acetylacetonate shall be stored in corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

5.3.22.6 Disposal. In case of dry spills, gather up and place in containers for disposal. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

An EPA Hazardous Waste Classification is not listed in 40 CFR.

5.3.23 Name. Zinc Acetylacetonate $Zn(C_5H_7O_2)_2$ FW 263.59
Zinc 2,4-pentanedionate $Zn[-O-C(CH_3)=CH-C(CH_3)=O]_2$
CAS 108503-47-5

5.3.23.1 Technical description. Zinc acetylacetonate is in the form of white needle crystals with a melting point of 138°C. The theoretical composition is 24.8% zinc, 45.5% carbon, 5.3% hydrogen, and 24.4% oxygen. It is soluble in water with decomposition. It is soluble in acetone and acetylacetone. It is insoluble in ethanol.

5.3.23.2 Specification. Manufacturer's requirements. (No Government specification.)

Source: https://assist.dla.mil -- Downloaded: 202610-26T07:47Z
Check the source to verify that this is the currentversion before use.

5.3.23.2.1 Requirements. Commercially available zinc acetylacetonate is a white crystalline product with a melting point of 138°C. The typical analysis is 24.8% zinc. Its solubility at 25°C is 1.3 g/100 mL in benzene and 5.4 g/100 mL in methanol.

5.3.23.3 Use. Zinc acetylacetonate is intended for use as a catalyst for polyesters and polyethers, and for alkylene oxides. It is also used as a rapid hardening agent for epoxy resins.

5.3.23.4 Safety. Zinc acetylacetonate is burnable and can form explosive dust mixtures in air. It can emit irritating and toxic fumes if heated to decomposition. The PEL and TLV is 5 mg/m^3 for the resulting zinc oxide fumes, so inhalation of fumes shall be avoided. The zinc ion is not toxic, but its compounds can be irritating to the eyes and mucous membranes. (Refer to 4.3.1.)

5.3.23.5 Storage. Zinc acetylacetonate shall be stored in corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

5.3.23.6 Disposal. In case of dry spills, gather up and place in containers for disposal. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

An EPA Hazardous Waste Classification is not listed in 40 CFR.

5.3.24 Name. Zinc 8-Quinolinolate $Zn(C_9H_6NO)_2$ FW 353.65
Zinc bis(8-oxyquinoline) CAS 13978-85-3

5.3.24.1 Technical description. Zinc 8-quinolinolate is in the form of a yellow solid. It is insoluble in water. It is decomposed by strong aqueous acid solutions.

5.3.24.2 Specification. Manufacturer's requirements. (No Government specification.)

5.3.24.2.1 Requirements. Commercially available zinc 8-quinolinolate is a yellow powder that conforms to the chemical and physical requirements shown in Table XXX.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

TABLE XXX. Zinc 8-quinolinolate - commercial chemical and physical requirements.

Assay,%, min	98.0
Water, %, max	0.5
Chlorides, %, max	0.1
Sulfates, %, max	0.1
Water-soluble zinc, %, max	0.1
† Sieve size, US Standard Sieves	
Through No. 10 (2.00 mm), %, min	90

† US Standard Sieve designation in accordance with ASTM E 11.

5.3.24.3 Use. Zinc 8-quinolinolate is intended for use as a mildew inhibitor and for fungus-proofing of cloth, wood and other cellulose materials, where the discoloration due to copper compounds shall be avoided.

5.3.24.4 Safety. Zinc 8-quinolinolate is burnable, and can form explosive dust mixtures in air. It can emit irritating and toxic fumes if heated to decomposition, including nitrogen oxides. The PEL and TLV are 5 mg/m^3 for the resulting zinc oxide fumes. The PEL for nitric oxide is 30 mg/m^3 and the TLV is 6 mg/m^3 for nitrogen dioxide, so breathing of fumes shall be avoided. The zinc ion is not toxic, but 8-quinolinol is a suspected carcinogen. The compound can be irritating to the eyes, skin and mucous membranes. (Refer to 4.3.1.)

5.3.24.5 Storage. Zinc 8-quinolinolate shall be stored in corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

5.3.24.6 Disposal. In case of dry spills, gather up and place in containers for disposal. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

An EPA Hazardous Waste Classification is not listed in 40 CFR.

5.2.25 Name. Zirconium Acetylacetonate $Zr(C_5H_7O_2)_4$ FW 487.66
Zirconium tetraacetylacetonate $Zr[-O-C(CH_3)=CH-C(CH_3)=O]_4$
Zirconium(IV) 2,4-pentanedionate CAS 17501-44-9

5.3.25.1 Technical description. Zirconium acetylacetonate is in the form of a colorless white crystalline solid with a specific gravity of 1.415, and a melting point of 194° to 195°C. Decomposition begins at 125°C. The theoretical zirconium content is 18.7 percent. It is soluble in acetone and benzene. It is slightly soluble in water.

Source: https://assist.dla.mil -- Downloaded: 202640-26T07:47Z
Check the source to verify that this is the current version before use.

5.3.25.2 Specification. Manufacturer's requirements. (No Government specification.)

5.3.25.2.1 Requirements. Commercially available zirconium acetylacetonate is an anhydrous white powder with a gravity of 1.42, and a melting point of 194°C. The typical analysis is 19.9% zirconium. Its solubility in water is 0.73 g/100 mL.

5.3.25.3 Use. Zirconium acetylacetonate is intended for use as a polymerization catalyst, a curing accelerator, and a crosslinking agent.

5.3.25.4 Safety. Zirconium acetylacetonate is burnable, and can form explosive dust mixtures in air. It can emit irritating and toxic fumes if heated to decomposition. The PEL and TLV for zirconium compounds, as Zr, are 5 mg/m^3, so breathing of dust and fumes shall be avoided. Zirconium compounds can be irritating to the eyes, skin and mucous membranes. (Refer to 4.3.1.)

5.3.25.5 Storage. Zirconium acetylacetonate shall be stored in corrosion-resistant containers in a cool, dry place. (Refer to 4.3.2.)

5.3.25.6 Disposal. In case of spills, gather up and place in containers for disposal. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

An EPA Hazardous Waste Classification is not listed in 40 CFR.

5.4 Organometallic Compounds

An organometallic compound is defined as one in which there is a bonding interaction (ionic or covalent, localized or delocalized) between one or more carbon atoms, of an organic group or molecule, and a main group, transition, lanthanide, or actinide metal atom or atoms. Organic derivatives of the metalloids (boron, silicon, germanium, arsenic and tellurium) are included, and are also termed as organometalloidal compounds.

Compounds in which carbon-containing moieties are bound to a metal via some other atom, such as oxygen, nitrogen, or sulfur, are not included in the category of organometallic compounds.

5.4.1 Aluminum Alkyls.

5.4.1.1 Name. Tri-n-Butylaluminum $Al[CH_2(CH_2)_2CH_3]_3$ FW 198.33
Aluminum tri-n-butyl CAS 1116-70-7

Source: https://assist.dla.mil -- Downloaded: 202610-26T07:47Z
Check the source to verify that this is the current version before use.

5.4.1.1.1 Technical description. Tri-n-butylaluminum is a colorless liquid with a density of 0.824 g/cm^3 at 25°C. It has a freezing point of -60°C and a boiling point of 98°C at 1 mm Hg. It is miscible with liquid hydrocarbons. It is decomposed by water, and is reactive with polar compounds including halogenated hydrocarbons. The theoretical aluminum content is 13.6 percent.

5.4.1.1.2 Specification. Manufacturer's requirements. (No Government specification.)

5.4.1.1.2.1 Requirements. Tri-n-butylaluminum is available from two manufacturers with the requirements and typical analyses shown in Tables XXXI and XXXII.

TABLE XXXI. Tri-n-butylaluminum - commercial specification requirements.

	Percent by Weight	
	Requirement	Typical Analysis
Aluminum, as Al	13.2 min	13.4
Hydride, as AlH_3	0.2 max	0.1
Tri-n-butylaluminum	95.0 min	97.0

TABLE XXXII. Tri-n-butylaluminum - commercial specification requirements.

	Percent by Weight	
	Requirement	Typical Analysis
Tri-n-butylaluminum	92.0 min	94.0
Trimethylaluminum	0.5 max	0.3
Triethylaluminum	1.8 max	0.8
Tri-n-propylaluminum	0.5 max	0.3
Triisobutylaluminum	3.0 max	1.5
$Al(C_8H_{17})_3$ isomers	3.5 max	2.2
1-Butane	1.0 max	0.6
Hydride, as AlH_3	0.8 max	0.3
Aluminum, as Al	13.4 min-13.9 max	13.6

5.4.1.1.3 Use. Tri-n-butylaluminum is used as a component of catalyst systems for olefin and diene polymerization. Other uses are as an alkylating agent for other metals and in organic synthesis, and as a reducing agent for transition metal salts.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.4.1.2 Name. Triethylaluminum $Al(C_2H_5)_3$ FW 114.16
Aluminum triethyl CAS 97-93-8

5.4.1.2.1 Technical description. Triethylaluminum (pure) is a colorless liquid with a refractive index of 1.480 at 6.5°C and a density of 0.837 g/cm^3 at 20°C. It has a freezing point of about -46°C, producing two crystalline forms. It has a boiling point of 194°C. It is miscible with liquid hydrocarbons. The compound is dimerized in the liquid state and in solution. It is decomposed by water, and is reactive with polar compounds including halogenated hydrocarbons. The theoretical aluminum content, as Al, is 23.6 percent.

5.4.1.2.2 Specification. No Government Specification.

5.4.1.2.2.1 Requirements. This covers one grade of triethylaluminum (TEA). The TEA shall be a clear liquid, free from suspended or settled solids. The chemical characteristics of the TEA shall conform to the requirements shown in Table XXXIII.

TABLE XXXIII. TEA - chemical requirements.

	Percent by Weight	
	Requirement	Typical Analysis
Soluble aluminum, as Al	21.8	23.7
Aluminum hydride equivalent, as AlH_3	----	1.2
Triethylaluminum	92.0	----

Triethylaluminum is available from two manufacturers with the requirements and typical analyses shown in Tables XXXIV and XXXV.

TABLE XXXIV. Triethylaluminum - commercial specification requirements.

	Percent by weight
Aluminum, as Al, min	23.0
n-Butyl groups (calculated as tri-n-butylaluminum), max	7.0
Hydride (calculated as AlH_3), max	0.8

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

TABLE XXXV. Triethylaluminum - commercial specification requirements.

	Percent by Weight	
	Requirement	Typical Analysis
Triethylaluminum	92.0 min	94.1
Tri-n-propylaluminum	0.7 max	0.1
Tri-n-butylaluminum	6.0 max	4.6
Triisobutylaluminum	1.0 max	0.5
Hydride, as AlH_3	2.0 max	0.6
Aluminum	23.0 min	23.3
Chloride	nil	nil

5.4.1.2.3 Use. Triethylaluminum is intended for military use in the manufacture of flame-producing munitions. Commercial uses are primarily as a component of Ziegler-type catalyst systems for the polymerization of olefins and dienes. Other uses include the production of long-chain alkyl aluminum compounds for conversion to primary alcohols.

5.4.1.3 Name. Triisobutylaluminum $Al[CH_2CH(CH_3)_2]_3$ FW 198.33
Aluminum triisobutyl CAS 100-99-2

5.4.1.3.1 Technical description. Triisobutylaluminum is a colorless liquid with a density of 0.788 g/cm^3 at 20°C. It has a freezing point of 1.0°C and a boiling point of 113.8°C at 30 mm Hg. It is miscible with liquid hydrocarbons. It is decomposed by water and is reactive with polar compounds including halogenated hydrocarbons. Triisobutylaluminum undergoes conversion to diisobutylaluminum hydride when heated above 50°C. Triisobutylaluminum exists in monomeric form because of the steric bulk of the isobutyl groups. The theoretical Al content is 13.6 percent.

5.4.1.3.2 Specification. Manufacturer's requirements. (No Government specification.)

5.4.1.3.2.1 Requirements. Triisobutylaluminum is available from two manufacturers with the requirements and typical analyses shown in Tables XXXVI and XXXVII.

Source: https://assist.dla.mil -- Downloaded: 202610-26T07:47Z
Check the source to verify that this is the currentversion before use.

TABLE XXXVI. Triisobutylaluminum - commercial specification requirements.

	Percent by Weight	
	Requirement	Typical Analysis
Aluminum, as Al	13.4 min	13.6
Hydride, as AlH_3	0.5 max	0.1
Dissolved isobutylene	2.5 max	0.2

TABLE XXXVII. Triisobutylaluminum - commercial specification requirements.

	Percent by Weight	
	Requirement	Typical Analysis
Triisobutylaluminum	95.0 min	95.5
Tri-n-butylaluminum	0.5 max	0.4
Tri-n-propylaluminum	0.5 max	0.4
Hydride, as AlH_3	0.8 max	0.5
Isobutylene	4.0 max	3.2
Aluminum	13.4 min	13.6

5.4.1.3.3 Use. Triisobutylaluminum is used as a component of catalyst systems for olefin and diene polymerization. Other uses are as a reducing agent in organic reduction reactions and as a chemical intermediate.

5.4.1.4 Name. Tri-n-Hexylaluminum $Al[CH_2(CH_2)_4CH_3]_3$ FW 282.49
Aluminum tri-n-hexyl CAS 1116-73-0

5.4.1.4.1 Technical description. Tri-n-hexylaluminum is a colorless liquid with a density of 0.837 g/cm^3 at 25°C. It has a freezing point of -87°C and a boiling point of 308.5°C. It is dimerized at 25°C but is 97% dissociated to the monomer at its boiling point. It is miscible with liquid hydrocarbons. It is decomposed by water, and is reactive with polar compounds including halogenated hydrocarbons. The theoretical aluminum content is 9.6 percent.

5.4.1.4.2 Specification. Manufacturer's requirements. (No Government specification.)

5.4.1.4.2.1 Requirements. Tri-n-hexylaluminum is available from a manufacturer with the requirements and typical analyses shown in Table XXXVIII.

Source: https://assist.dla.mil -- Downloaded: 202610-26T07:47Z
Check the source to verify that this is the currentversion before use.

TABLE XXXVIII. Tri-n-hexylaluminum - commercial specification requirements.

	Percent by Weight	
	Requirement	Typical Analysis
Tri-n-hexylaluminum	92.0 min	95.1
Aluminum as Al	9.0 min	9.5
Hydride, as AlH_3	1.0 max	0.02

5.4.1.4.3 Use. Tri-n-hexylaluminum is used as a component of catalyst systems for alkene and diene polymerization, and as a chemical intermediate.

5.4.1.5 Name. Trimethylaluminum $Al(CH_3)_3$ FW 72.09
Aluminum trimethyl CAS 75-24-1

5.4.1.5.1 Technical description. Trimethylaluminum (pure) is a colorless liquid with a refractive index of 1.432 at 12°C and a density of 0.752 g/cm^3 at 20°C. It has a freezing point of 15.4°C and a boiling point of 127°C. It is miscible with liquid hydrocarbons. The compound is dimerized in the liquid state and in solution. It is decomposed by water, and is reactive with polar compounds including halogenated hydrocarbons. The theoretical aluminum content is 37.4 percent.

5.4.1.5.2 Specification. Manufacturer's requirements. (No Government specification.)

5.4.1.5.2.1 Requirements. Trimethylaluminum is available from two manufacturers with the requirements and typical analyses shown in Tables XXXIX and XL.

TABLE XXXIX. Trimethylaluminum - commercial specification and requirements.

	Percent by Weight	
	Minimum	Maximum
Aluminum, as Al	36.5	37.4
Chloride, as Cl	—	0.1

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

TABLE XL. Trimethylaluminum - commercial specification and requirements.

	Percent by Weight	
	Requirement	Typical Analysis
Trimethylaluminum	97.0 min	99.0
Triethylaluminum	2.0 max	0.5
Tri-n-propylaluminum	0.3 max	0.0
Triisobutylaluminum	0.5 max	0.3
Tri-n-butylaluminum	0.3 max	0.1
Hydride, as AlH_3	0.5 max	0.1
Aluminum	36.3 min 37.4 max	37.1
Chloride	0.1 max	nil

5.4.1.5.3 Use. Trimethylaluminum is intended for military use in formulations for pyrophoric fuels. Commercial uses are primarily as a component of catalyst systems for the polymerization of olefins.

5.4.1.6 Name. Tri-n-Propylaluminum $Al(CH_2CH_2CH_3)_3$ FW 156.25
Aluminum tri-n-propyl CAS 102-67-0

5.4.1.6.1 Technical description. Tri-n-propylaluminum is a colorless liquid with a density of 0.824 g/cm^3 at 20°C. It has a freezing point of -60°C and a boiling point of 114°C at 20 mm Hg. It is miscible with liquid hydrocarbons. The compound is dimerized in the liquid state and in solution. It is decomposed by water, and is reactive with polar compounds, including halogenated hydrocarbons. The theoretical aluminum content is 17.4 percent.

5.4.1.6.2 Specification. Manufacturer's requirements. (No Government specification.)

5.4.1.6.2.1 Requirements. Tri-n-propylaluminum is available from two manufacturers with the requirements and typical analyses shown in Tables XLI and XLII.

TABLE XLI. Tri-n-propylaluminum - commercial specification requirements.

Aluminum, as Al, % by wt., min	16.4
Aluminum hydride equivalent, as AlH_3 % by wt., max	1.0

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

TABLE XLII. Tri-n-propylaluminum - commercial specification requirements

	Percent by Weight	
	Requirement	Typical Analysis
Tri-n-propylaluminum	92.0 min	95.2
Triethylaluminum	2.0 max	0.8
Tri-n-butylaluminum	1.0 max	0.4
Triisobutylaluminum	2.5 max	1.4
Hydride, as AlH_3	3.5 max	2.2
Aluminum	17.0 min	18.3

5.4.1.6.3 Use. Tri-n-propylaluminum is intended for military use in formulations for pyrophoric fuels. Commercial uses are as a component of catalyst systems for the polymerization of olefins, and also for use as a chemical intermediate.

5.4.1.7 Safety. Aluminum alkyls are pyrophoric liquids that flame spontaneously and give off dense smoke on exposure to air. They are reactive with water with the release of flammable and explosive vapors that can be ignited by the heat of reaction. Hydrocarbon solutions of aluminum alkyls may not be pyrophoric depending on concentration and temperature. The burning liquid can release irritating and toxic fumes and smoke. The TLV for aluminum alkyls (not otherwise classified) is 2 mg/m^3 and inhalation of fumes from burning liquid shall be avoided. Aluminum alkyls produce severe burns, predominantly thermal, on contact with skin or eyes by reaction with body moisture, so contact shall be avoided. (Refer to 4.3.1.)

5.4.1.8 Storage. Aluminum alkyls shall be stored in special containers blanketed with dry nitrogen under a slight positive pressure, in a cool, dry place. (Refer to 4.3.2.)

5.4.1.9 Disposal. Liquid spills of aluminum alkyls will ignite spontaneously. Small liquid spill fires can be controlled with dry powder extinguishers, absorbed by nonreactive dry powders and placed in sealed containers. In case of large liquid spills, the burning liquid shall be isolated by use of sandbags to prevent spreading. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

Aluminum alkyls have an EPA Hazardous Waste Classification - Ignitable, Waste No. D001; and Reactive, Waste No. D003.

5.4.2 Aluminum Alkyl Alkoxide.

Source: https://assist.dla.mil -- Downloaded: 202610-26T07:47Z
Check the source to verify that this is the current version before use.

5.4.2.1 Name. Diethylaluminum Ethoxide $Al(C_2H_5)_2OC_2H_5$ FW 130.17
Aluminum diethylethoxide CAS 1586-92-1

5.4.2.1.1 Technical description. Diethylaluminum ethoxide is a colorless liquid with a density of 0.851 g/cm^3 at 25°C. It is soluble in liquid hydrocarbons and ether. It is decomposed by water, and is reactive with polar compounds including halogenated hydrocarbons.

5.4.2.1.2 Specification. Manufacturer's requirements. (No Government specification.)

5.4.2.1.2.1 Requirements. Diethylaluminum ethoxide is available from two manufacturers with the requirements and typical analyses shown in Tables XLIII and XLIV.

TABLE XLIII. Diethylaluminum ethoxide - commercial specification requirements.

	Requirement	Theoretical
Aluminum, wt. %	19.0 to 20.6	20.7
Hydrolysis gas, mmol/g	13.6 to 15.2	15.4

TABLE XLIV. Diethylaluminum ethoxide - commercial specification requirements.

	Requirement	Analysis
Product composition, wt. %		
Aluminum	19.5 to 20.7	20.4
Ethoxide	33.4 to 36.5	35.1
Hydrolysis gas composition, mol %		
Ethane	96.0 min	97.4
n-Butane	3.8 max	1.6
Isobutane	2.5 max	0.5
Propane	0.3 max	0.1
Methane	0.4 max	0.2
Hydrogen	0.6 max	0.2

5.4.2.1.3 Use. Diethylaluminum ethoxide is used as a co-catalyst for olefin and diene polymerization, olefin isomerization, and as an alkylating agent.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.4.2.1.4 Safety. Diethylaluminum ethoxide is a pyrophoric liquid that flames spontaneously and gives off dense smoke on exposure to air. It is reactive with water with the release of flammable and explosive vapors that can be ignited by the heat of reaction. Hydrocarbon solutions of diethylaluminum ethoxide may not be pyrophoric depending on concentration and temperature. The burning liquid can release irritating and toxic fumes and smoke. There is no PEL or TLV referenced for diethylaluminum ethoxide, but the TLV, as Al, is 2 mg/m^3 for aluminim alkyls not otherwise classified. Inhalation of fumes from burning liquid shall be avoided. Diethylaluminum ethoxide produces severe burns, predominantly thermal, on contact with skin or eyes by reaction with body moisture, so contact shall be avoided. (Refer to 4.3.1.)

5.4.2.1.5 Storage. Diethylaluminum ethoxide shall be stored in special containers blanketed with dry nitrogen under a slight positive pressure, in a cool, dry place. (Refer to 4.3.2.)

5.4.2.1.6 Disposal. Liquid spills of diethylaluminum ethoxide will ignite spontaneously. Small liquid spill fires can be controlled with dry powder extinguishers, absorbed by nonreactive dry powders and placed in sealed containers. In case of large liquid spills, the burning liquid shall be isolated by use of sandbags to prevent spreading. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

Diethylaluminum ethoxide has an EPA Hazardous Waste Classification - Ignitable, Waste No. D001; and Reactive, Waste No. D003.

5.4.3 Aluminum Alkyl Halides.

5.4.3.1 Name. Diethylaluminum Chloride $Al(C_2H_5)_2Cl$ FW 120.56
Aluminum diethyl chloride CAS 96-10-6

5.4.3.1.1 Technical description. Diethylaluminum chloride is a colorless liquid with a density of 0.971 g/cm^3 at 25°C. It has a freezing point of -74°C and a boiling point of 214.1°C at 760 mm Hg. It is miscible with liquid hydrocarbons. It is decomposed by water, and is reactive with polar compounds including halogenated hydrocarbons. The theoretical composition is 22.4% Al and 29.4% Cl, and the compound is dimeric.

5.4.3.1.2 Specification. Manufacturer's requirements. (No Government specification.)

5.4.3.1.2.1 Requirements. Diethylaluminum chloride is available from two manufacturers with the requirements and typical analyses shown in Tables XLV and XLVI.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

TABLE XLV. Diethylaluminum chloride - commercial specification requirements.

	Requirement
Aluminum, wt. % Chloride/Aluminum (atom ratio) Hydrogen (in hydrolysis gas) mol %, max	21.9 to 22.4 1.00 to 1.03 0.05

TABLE XLVI. Diethylaluminum chloride - requirements and typical analysis.

	Requirement	Analysis
Product composition, wt. %		
Aluminum	21.9 to 22.4	22.1
Chloride	29.2 to 29.8	29.5
Hydrolysis gas composition, mol %		
Ethane	97.0 min	97.4
n-Butane	2.2 max	2.0
Isobutane	0.5 max	0.2
Hydrogen	0.8 max	0.4

5.4.3.1.3 Use. Diethylaluminum chloride is used as a component of catalyst systems for olefin and diene polymerizations, linear oligomerization and cyclization of unsaturated hydrocarbons, and in alkylation reactions.

5.4.3.1.4 Safety. Diethylaluminum chloride is a pyrophoric liquids that flames spontaneously and gives off dense smoke on exposure to air. It is reactive with water with the release of flammable and explosive vapors that can be ignited by the heat of reaction. Hydrocarbon solutions of diethylaluminum chloride may not be pyrophoric depending on concentration and temperature. The burning liquid can release irritating and toxic fumes and smoke. There is no PEL or TLV referenced for diethylaluminum chloride, but the TLV, as Al, is 2 mg/m^3 for aluminum alkyls not otherwise classified. Inhalation of fumes from burning liquid shall be avoided. Diethylaluminum chloride produces severe burns, predominantly thermal, on contact with skin or eyes by reaction with body moisture, so contact shall be avoided. (Refer to 4.3.1.)

5.4.3.1.5 Storage. Diethylaluminum chloride shall be stored in special containers blanketed with dry nitrogen under a slight positive pressure, in a cool, dry place. (Refer to 4.3.2.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.4.3.1.6 Disposal. Spills of diethylaluminum chloride will ignite spontaneously. Small spill fires can be controlled with dry powder extinguishers, absorbed by nonreactive dry powders and placed in sealed containers. In case of large liquid spills, the burning liquid shall be isolated by use of sandbags to prevent spreading. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

Diethylaluminum chloride has an EPA Hazardous Waste Classification - Ignitable, Waste No. D001; and Reactive, Waste No. D003.

5.4.3.2 Name. Diethylaluminum Iodide $Al(C_2H_5)_2I$ FW 212.01
Aluminum diethyl iodide CAS 2040-00-8

5.4.3.2.1 Technical description. Diethylaluminum iodide is a clear liquid with a density of 1.577 g/cm^3 at 25°C. It has a freezing point of -43.4°C and a boiling point of 262°C (extrapolated) at 760 mm Hg. It is miscible with most hydrocarbons. It is decomposed by water, and is reactive with polar compounds including halogenated hydrocarbons. The theoretical composition is 12.73% Al and 59.86% iodine, and the compound is dimeric.

5.4.3.2.2 Specification. Manufacturer's requirements. (No Government specification.)

5.4.3.2.2.1 Requirements. Diethylaluminum iodide is available from a manufacturer with the requirements and typical analysis shown in Table XLVII.

TABLE XLVII. Diethylaluminum iodide - requirements and typical analysis.

	Requirement	Analysis
Product composition, wt. %		
Aluminum	12.4 to 12.9	12.6
Iodide	59.0 to 60.0	59.2
Hydrolysis gas composition, mol %		
Ethane	96.8 min	97.8
n-Butane	2.2 max	1.3
Isobutane	0.4 max	0.1
Propane	0.4 max	0.1
Methane	0.4 max	0.2
Hydrogen	1.0 max	0.5

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.4.3.2.3 Use. Diethylaluminum iodide is used as a catalyst component for polymerization and other reactions.

5.4.3.2.4 Safety. Diethylaluminum iodide is a pyrophoric liquid that flames spontaneously and gives off dense smoke on exposure to air. It is reactive with water with the release of flammable and explosive vapors that can be ignited by the heat of reaction. Hydrocarbon solutions of diethylaluminum iodide may not be pyrophoric depending on concentration and temperature. The burning liquid can release irritating and toxic fumes and smoke. There is no PEL or TLV referenced for diethylaluminum iodide, but the TLV, as Al, is 2 mg/m^3 for aluminum alkyls not otherwise classified. Inhalation of fumes from burning liquid shall be avoided. Diethylaluminum iodide produces severe burns, predominantly thermal, on contact with skin or eyes by reaction with body moisture, so contact shall be avoided. (Refer to 4.3.1.)

5.4.3.2.5 Storage. Diethylaluminum iodide shall be stored in special containers blanketed with dry nitrogen under a slight positive pressure, in a cool, dry place. (Refer to 4.3.2.)

5.4.3.2.6 Disposal. Spills of diethylaluminum iodide will ignite spontaneously. Small spill fires can be controlled with dry powder extinguishers, absorbed by nonreactive dry powders and placed in sealed containers. In case of large liquid spills, the burning liquid shall be isolated by use of sandbags to prevent spreading. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

Diethylaluminum iodide has an EPA Hazardous Waste Classification - Ignitable, Waste No. D001; and Reactive, Waste No. D003.

5.4.3.3 Name. Diisobutylaluminum Chloride FW 176.67
Aluminum diisobutyl chloride $Al[CH_2CH(CH_3)_2]_2Cl$ CAS 1779-25-5

5.4.3.3.1 Technical description. Diisobutylaluminum chloride is a colorless liquid with a density of 0.912 g/cm^3 at 25°C. It has a freezing point of -40°C and a boiling point of 289°C at 760 mm Hg. It is miscible with most liquid hydrocarbons. It is decomposed by water, and is reactive with polar compounds including halogenated hydrocarbons. The theoretical composition is 15.3% Al and 20.1% Cl, and the compound is dimeric.

5.4.3.3.2 Specification. Manufacturer's requirements. (No Government specification.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.4.3.3.2.1 Requirements. Diisobutylaluminum chloride is available from two manufacturers with the requirements and typical analyses shown in Tables XLVIII and XLIX.

TABLE XLVIII. Diisobutylaluminum chloride - requirements and typical analysis.

	Requirement	Analysis
Aluminum, wt. %	15.2 to 15.5	15.2
Chlorine, wt. %	19.8 to 20.7	20.6
Hydrolysis gas - Isobutane, mol % min	96.0	96.5

TABLE XLIX. Diisobutylaluminum chloride - requirements and typical analysis.

	Requirement	Analysis
Product composition, wt. %		
Aluminum	15.2 to 15.5	15.4
Chloride	19.8 to 20.7	20.1
Hydrolysis gas composition, mol %		
Isobutane	96.0 min	97.4
n-Butane	0.5 max	0.3
Propane	0.6 max	0.5
Ethane	1.4 max	0.7
Methane	0.6 max	0.5
Propylene	0.2 max	0.0
Isobutylene	1.3 max	0.1
Hydrogen	1.5 max	0.5

5.4.3.3.3 Use. Diisobutylaluminum chloride is used as a catalyst component for polymerization of olefins and dienes.

5.4.3.3.4 Safety. Diisobutylaluminum chloride is a pyrophoric liquid that flames spontaneously and gives off dense smoke on exposure to air. It is reactive with water with the release of flammable and explosive vapors that can be ignited by the heat of reaction. Hydrocarbon solutions of diisobutylaluminum chloride may not be pyrophoric depending on concentration and temperature. The burning liquid can release irritating and toxic fumes and smoke. There is no PEL or TLV referenced for diisobutylaluminum chloride, but the TLV, as Al, is 2 mg/m^3 for aluminum alkyls not otherwise classified. Inhalation of

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

fumes from burning liquid shall be avoided. Diisobutylaluminum chloride produces severe burns, predominantly thermal, on contact with skin or eyes by reaction with body moisture, so contact shall be avoided. (Refer to 4.3.1.)

5.4.3.3.5 Storage. Diisobutylaluminum chloride shall be stored in special containers, blanketed with dry nitrogen under a slight positive pressure, in a cool, dry place. (Refer to 4.3.2.)

5.4.3.3.6 Disposal. Spills of diisobutylaluminum chloride will ignite spontaneously. Small spill fires can be controlled with dry powder extinguishers, absorbed by nonreactive dry powders and placed in sealed containers. In case of large liquid spills, the burning liquid shall be isolated by use of sandbags to prevent spreading. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

Diisobutylaluminum chloride has an EPA Hazardous Waste Classification - Ignitable, Waste No. D001; and Reactive, Waste No. D003.

5.4.3.4 Name. Dimethylaluminum Chloride $Al(CH_3)_2Cl$ FW 92.50
Aluminum dimethyl chloride CAS 1184-58-3

5.4.3.4.1 Technical description. Dimethylaluminum chloride is a colorless liquid with a density of 0.995 g/cm^3 at 25°C. It has a freezing point of -21°C and a boiling point of 126° to 127°C at 760 mm Hg. It is miscible with most liquid hydrocarbons. It is decomposed by water, and is reactive with polar compounds including halogenated hydrocarbons. The theoretical composition is 29.2% Al and 38.3% Cl, and the compound is dimeric.

5.4.3.4.2 Specification. Manufacturer's requirements. (No Government specification.)

5.4.3.4.2.1 Requirements. Dimethylaluminum chloride is available from two manufacturers without specification requirements.

5.4.3.4.3 Use. Dimethylaluminum chloride is used as a catalyst component for polymerization reactions and as a methylating agent.

5.4.3.4.4 Safety. Dimethylaluminum chloride is a pyrophoric liquid that flames spontaneously and gives off dense smoke on exposure to air. It is reactive with water with the release of flammable and explosive vapors that can be ignited by the heat of reaction. Hydrocarbon solutions of dimethylaluminum chloride may not be pyrophoric depending on concentration and temperature. The burning liquid can release irritating and toxic fumes

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

and smoke. There is no PEL or TLV referenced for dimethylaluminum chloride, but the TLV, as Al, is 2 mg/m^3 for aluminum alkyls not otherwise classified. Inhalation of fumes from burning liquid shall be avoided. Dimethylaluminum chloride produces severe burns, predominantly thermal, on contact with skin or eyes by reaction with body moisture, so contact shall be avoided. (Refer to 4.3.1.)

5.4.3.4.5 Storage. Dimethylaluminum chloride shall be stored in special containers blanketed with dry nitrogen under a slight positive pressure, in a cool, dry place. (Refer to 4.3.2.)

5.4.3.4.6 Disposal. Spills of dimethylaluminum chloride will ignite spontaneously. Small spill fires can be controlled with dry powder extinguishers, absorbed by nonreactive dry powders and placed in sealed containers. In case of large liquid spills, the burning liquid shall be isolated by use of sandbags to prevent spreading. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

Dimethylaluminum chloride has an EPA Hazardous Waste Classification - Ignitable, Waste No. D001; and Reactive, Waste No. D003.

5.4.3.5 Name. Ethylaluminum Dichloride $AlC_2H_5Cl_2$ FW 126.96
Aluminum ethyl dichloride CAS 563-43-9

5.4.3.5.1 Technical description. Ethylaluminum dichloride is a colorless liquid, above its freezing point, with a density of 1.227 g/cm^3 at 35°C, and its density as a solid at 25°C is 1.232 g/cm^3. It has a freezing point of 30.9°C and an extrapolated boiling point of 194°C at 760 mm Hg. It is miscible with most liquid hydrocarbons. It is decomposed by water, and is reactive with polar compounds including halogenated hydrocarbons. The theoretical composition is 21.3% Al and 55.9% Cl, and the compound is dimeric.

5.4.3.5.2 Specification. Manufacturer's requirements. (No Government specification.)

5.4.3.5.2.1 Requirements. Ethylaluminum dichloride is available from two manufacturers with the requirements and the typical analyses shown in Tables L and LI.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

TABLE L. Ethylaluminum dichloride - commercial analysis range.

	Theoretical	Analysis Range
Aluminum, wt. %	21.3	20.3 - 21.5
Chlorine, wt. %	55.9	55.2 - 56.3

TABLE LI. Ethylaluminum dichloride - requirements and typical analysis.

	Requirement	Analysis
Product composition, wt. %		
Aluminum	20.3 to 21.5	20.9
Chloride	55.2 to 56.3	56.0
Hydrolysis gas composition, mol %		
Ethane	98.0 min	99.2
Isobutane	1.0 max	0.0
n-Butane	1.5 max	0.8
Hydrogen	nil	0.0

5.4.3.5.3 Use. Ethylaluminum dichloride is used as a catalyst component for polymerization and other reactions.

5.4.3.5.4 Safety. Ethylaluminum dichloride, above 31°C, is a pyrophoric liquid that flames spontaneously and gives off dense smoke on exposure to air. It is reactive with water with the release of flammable and explosive vapors that can be ignited by the heat of reaction. Hydrocarbon solutions of ethylaluminum dichloride may not be pyrophoric depending on concentration and temperature. The burning liquid can release irritating and toxic fumes and smoke. There is no PEL or TLV referenced for ethylaluminum dichloride, but the TLV, as Al, is 2 mg/m^3 for aluminum alkyls not otherwise classified. Inhalation of fumes from burning liquid shall be avoided. Ethylaluminum dichloride produces severe burns, predominantly thermal, on contact with skin or eyes by reaction with body moisture, so contact shall be avoided. (Refer to 4.3.1.)

5.4.3.5.5 Storage. Ethylaluminum dichloride shall be stored in special containers blanketed with dry nitrogen under a slight positive pressure, in a cool, dry place. (Refer to 4.3.2.)

5.4.3.5.6 Disposal. Spills of ethylaluminum dichloride will ignite spontaneously. Small spill fires can be controlled with dry powder extinguishers, absorbed by nonreactive dry powders and placed in sealed containers. In case of large liquid spills, the burning

Source: https://assist.dla.mil -- Downloaded: 202610-26T07:47Z
Check the source to verify that this is the current version before use.

liquid shall be isolated by use of sandbags to prevent spreading. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

Ethylaluminum dichloride has an EPA Hazardous Waste Classification - Ignitable, Waste No. D001; and Reactive, Waste No. D003.

5.4.3.6 Name. Ethylaluminum Sesquichloride $Al_2(C_2H_5)_3Cl_3$ FW 247.52
Aluminum ethyl sesquichloride $(C_2H_5)_2AlCl{\cdot}Cl_2AlC_2H_5$
Triethyldialuminum trichloride CAS 12075-68-2

5.4.3.6.1 Technical description. Ethylaluminum sesquichloride is a clear liquid with a density of 1.092 g/cm³ at 25°C. It has a freezing point of -20°C and a boiling point of 204°C (extrapolated) at 760 mm Hg. It is miscible with most liquid hydrocarbons. It is decomposed by water, and is reactive with polar compounds including halogenated hydrocarbons. The theoretical composition is 21.8% Al and 43.0% Cl, and the compound is a 1:1 complex of ethylaluminum dichloride and diethylaluminum chloride.

5.4.3.6.2 Specification. Manufacturer's requirements. (No Government specification.)

5.4.3.6.2.1 Requirements. Ethylaluminum sesquichloride is available from two manufacturers with the requirements and the typical analyses shown in Tables LII and LIII.

TABLE LII. Ethylaluminum sesquichloride - commercial analysis range.

	Theoretical	Analysis Range
Aluminum, wt. %	21.8	21.4 to 22.0
Chlorine, wt. %	43.0	42.1 to 43.3

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

TABLE LIII. Ethylaluminum sesquichloride - requirements and typical analysis.

	Requirement	Analysis
Product composition, wt. %		
Aluminum	21.1 to 21.8	21.5
Chloride	42.0 to 43.5	42.9
Hydrolysis gas composition, mol %		
Ethane	98.5 min	99.5
Methane	0.2 max	0.1
Propane	0.1 max	Trace
Isobutane	0.3 max	0.1
n-Butane	1.2 max	0.2
Hydrogen	0.4 max	0.1

5.4.3.6.3 Use. Ethylaluminum sesquichloride is used as a catalyst for polymerization of olefins and for hydrogenation of aromatics.

5.4.3.6.4 Safety. Ethylaluminum sesquichloride is a pyrophoric liquid that flames spontaneously and gives off dense smoke on exposure to air. It is reactive with water with the release of flammable and explosive vapors that can be ignited by the heat of reaction. Hydrocarbon solutions of ethylaluminum sesquichloride may not be pyrophoric depending on concentration and temperature. The burning liquid can release irritating and toxic fumes and smoke. There is no PEL or TLV referenced for ethylaluminum sesquichloride, but the TLV, as Al, is 2 mg/m^3 for aluminum alkyls not otherwise classified. Inhalation of fumes from burning liquid shall be avoided. Ethylaluminum sesquichloride produces severe burns, predominantly thermal, on contact with skin or eyes by reaction with body moisture, so contact shall be avoided. (Refer to 4.3.1.)

5.4.3.6.5 Storage. Ethylaluminum sesquichloride shall be stored in special containers, blanketed with dry nitrogen under a slight positive pressure, in a cool, dry place. (Refer to 4.3.2.)

5.4.3.6.6 Disposal. Spills of ethylaluminum sesquichloride will ignite spontaneously. Small spill fires can be controlled with dry powder extinguishers, absorbed by nonreactive dry powders and placed in sealed containers. In case of large liquid spills, the burning liquid shall be isolated by use of sandbags to prevent spreading. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

Ethylaluminum sesquichloride has an EPA Hazardous Waste Classification - Ignitable, Waste No. D001; and Reactive, Waste No. D003.

5.4.3.7 Name. Isobutylaluminum Dichloride $Al[CH_2CH(CH_3)_2]Cl_2$ FW 155.00
Aluminum isobutyl dichloride CAS 1888-87-5

5.4.3.7.1 Technical description. Isobutylaluminum dichloride is a clear liquid with a density of 1.121 g/cm^3 at 30°C. It has a freezing point of -30°C. It is miscible with most liquid hydrocarbons. It is decomposed by water, and is reactive with polar compounds including halogenated hydrocarbons. The theoretical composition is 17.4% Al and 45.8% Cl, and the compound is dimeric.

5.4.3.7.2 Specification. Manufacturer's requirements. (No Government specification.)

5.4.3.7.2.1 Requirements. Isobutylaluminum dichloride is available from a manufacturer with the requirements and the typical analysis shown in Table LIV.

TABLE LIV. Isobutylaluminum dichloride - commercial analysis range.

	Theoretical	Analysis Range
Aluminum, wt. %	17.4	17.2 to 17.6
Chlorine, wt. %	45.8	45.5 to 46.2

5.4.3.7.3 Use. Isobutylaluminum dichloride is used as a catalyst for polymerization of olefins and dienes.

5.4.3.7.4 Safety. Isobutylaluminum dichloride is a pyrophoric liquid that flames spontaneously and gives off dense smoke on exposure to air. It is reactive with water with the release of flammable and explosive vapors that can be ignited by the heat of reaction. Hydrocarbon solutions of isobutylaluminum dichloride may not be pyrophoric depending on concentration and temperature. The burning liquid can release irritating and toxic fumes and smoke. There is no PEL or TLV referenced for isobutylaluminum dichloride, but the TLV, as Al, is 2 mg/m^3 for aluminum alkyls not otherwise classified. Inhalation of fumes from burning liquid shall be avoided. Isobutylaluminum dichloride produces severe burns, predominantly thermal, on contact with skin or eyes by reaction with body moisture, so contact shall be avoided. (Refer to 4.3.1.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.4.3.7.5 Storage. Isobutylaluminum dichloride shall be stored in special containers, blanketed with dry nitrogen under a slight positive pressure, in a cool, dry place. (Refer to 4.3.2.)

5.4.3.7.6 Disposal. Spills of isobutylaluminum dichloride will ignite spontaneously. Small spill fires can be controlled with dry powder extinguishers, absorbed by nonreactive dry powders and placed in sealed containers. In case of large liquid spills, the burning liquid shall be isolated by use of sandbags to prevent spreading. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

Isobutylaluminum dichloride has an EPA Hazardous Waste Classification - Ignitable, Waste No. D001; and Reactive, Waste No. D003.

5.4.3.8 Name. Isobutylaluminum Sesquichloride $Al_2[CH_2CH(CH_3)_2]_3Cl_3$
$[(CH_3)_2CHCH_2]_2AlCl{\cdot}Cl_2Al[CH_2CH(CH_3)_2]$ FW 331.67
Aluminum isobutyl sesquichloride CAS 12090-38-9
Triisobutyldialuminum trichloride

5.4.3.8.1 Technical description. Isobutylaluminum sesquichloride is a clear liquid with a density of 0.998 g/cm^3 at 23°C. It has a freezing point of -93°C and a boiling point range of 120° to 150°C at 10 mm Hg. It is miscible with most liquid hydrocarbons. It is decomposed by water, and is reactive with polar compounds including halogenated hydrocarbons. The theoretical composition is 16.3% Al and 32.0% Cl, and the compound is 1:1 complex of isobutylaluminum dichloride and diisobutylaluminum chloride.

5.4.3.8.2 Specification. Manufacturer's requirements. (No Government specification.)

5.4.3.8.2.1 Requirements. Isobutylaluminum sesquichloride is available from a manufacturer with the requirements and the typical analysis shown in Table LV.

Source: https://assist.dla.mil -- Downloaded: 202610-26T07:47Z
Check the source to verify that this is the current version before use.

TABLE LV. Isobutylaluminum sesquichloride - requirements and typical analysis.

	Requirement	Analysis
Product composition, wt. %		
Aluminum	15.8 to 16.5	16.2
Chloride	31.2 to 32.6	32.0
Hydrolysis gas composition, mol %		
Isobutane	96.0 min	98.7
n-Butane	0.6 max	0.3
Propane	0.6 max	0.2
Ethane	1.5 max	0.5
Methane	0.4 max	0.2
Isobutylene	0.5 max	0.0
Hydrogen	0.8 max	0.1

5.4.3.8.3 Use. Isobutylaluminum sesquichloride is used as a catalyst for polymerization of olefins and dienes.

5.4.3.8.4 Safety. Isobutylaluminum sesquichloride is a pyrophoric liquid that flames spontaneously and gives off dense smoke on exposure to air. It is reactive with water with the release of flammable and explosive vapors that can be ignited by the heat of reaction. Hydrocarbon solutions of isobutylaluminum sesquichloride may not be pyrophoric depending on concentration and temperature. The burning liquid can release irritating and toxic fumes and smoke. There is no PEL or TLV referenced for isobutylaluminum, but the TLV, as Al, is 2 mg/m^3 for aluminum alkyls not otherwise classified. Inhalation of fumes from burning liquid shall be avoided. Isobutylaluminum sesquichloride produces severe burns, predominantly thermal, on contact with skin or eyes by reaction with body moisture, so contact shall be avoided. (Refer to 4.3.1.)

5.4.3.8.5 Storage. Isobutylaluminum sesquichloride shall be stored in special containers, blanketed with dry nitrogen under a slight positive pressure, in a cool, dry place. (Refer to 4.3.2.)

5.4.3.8.6 Disposal. Spills of isobutylaluminum sesquichloride will ignite spontaneously. Small spill fires can be controlled with dry powder extinguishers, absorbed by nonreactive dry powders and placed in sealed containers. In case of large liquid spills, the burning liquid shall be isolated by use of sandbags to prevent spreading. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

Isobutylaluminum sesquichloride has an EPA Hazardous Waste Classification - Ignitable, Waste No. D001; and Reactive, Waste No. D003.

5.4.3.9 Name. Methylaluminum Dichloride $AlCH_3Cl_2$ FW 112.92
Aluminum methyl dichloride CAS 917-65-7

5.4.3.9.1 Technical description. Methylaluminum dichloride is a white crystalline solid with a density of 1.00 g/cm^3 at 22°C. It has a melting point of 73.6°C and a boiling point of 152°C at 760 mm Hg. It is soluble in most liquid hydrocarbons. It is decomposed by water, and is reactive with polar compounds including halogenated hydrocarbons. The theoretical composition is 23.9% Al and 62.8% Cl, and the compound is dimeric.

5.4.3.9.2 Specification. Manufacturer's requirements. (No Government specification.)

5.4.3.9.2.1 Requirements. Methylaluminum dichloride is available from two manufacturers without specification requirements.

5.4.3.9.3 Use. Methylaluminum dichloride is used as a catalyst for polymerization reactions, and as a methylating agent.

5.4.3.9.4 Safety. Methylaluminum dichloride is a pyrophoric solid that flames spontaneously and gives off dense smoke on exposure to air. It is reactive with water with the release of flammable and explosive vapors that can be ignited by the heat of reaction. Hydrocarbon solutions of methylaluminum dichloride may not be pyrophoric depending on concentration and temperature. The burning liquid can release irritating and toxic fumes and smoke. There is no PEL or TLV referenced for methylaluminum dichloride, but the TLV, as Al, is 2 mg/m^3 for aluminum alkyls not otherwise classified. Inhalation of fumes from burning liquid shall be avoided. Methylaluminum dichloride produces severe burns, predominantly thermal, on contact with skin or eyes by reaction with body moisture, so contact shall be avoided. (Refer to 4.3.1.)

5.4.3.9.5 Storage. Methylaluminum dichloride, solid or solution, shall be stored in special ,containers blanketed with dry nitrogen under a slight positive pressure, in a cool, dry place. (Refer to 4.3.2.)

5.4.3.9.6 Disposal. Spills of methylaluminum dichloride will ignite spontaneously. Small spill fires can be controlled with dry powder extinguishers, absorbed by nonreactive dry powders and placed in sealed containers. In case of large liquid spills, the burning liquid shall be isolated by use of sandbags to prevent spreading. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

Methylaluminum dichloride has an EPA Hazardous Waste Classification - Ignitable, Waste No. D001; and Reactive, Waste No. D003.

5.4.3.10 Name. Methylaluminum Sesquichloride

$Al_2(CH_3)_3Cl_3$ or $(CH_3)_2AlCl{\cdot}Cl_2AlCH_3$ FW 205.43

Aluminum methyl sesquichloride CAS 12542-85-7

Trimethyldialuminum trichloride

5.4.3.10.1 Technical description. Methylaluminum sesquichloride is a colorless liquid above its freezing point with a density of 1.163 g/cm^3 at 25°C. It has a freezing point of 22.8°C and an extrapolated boiling point of 143.7°C at 760 mm Hg. It is miscible with most liquid hydrocarbons. It is decomposed by water, and is reactive with polar compounds including halogenated compounds. The theoretical composition is 26.3% Al and 51.9% Cl, and the compound is 1:1 complex of methylaluminum dichloride and dimethylaluminum chloride.

5.4.3.10.2 Specification. Manufacturer's requirements. (No Government specification.)

5.4.3.10.2.1 Requirements. Methylaluminum sesquichloride is available from two manufacturers with the requirements and typical analyses shown in Tables LVI and LVII.

TABLE LVI. Methylaluminum sesquichloride - commercial analysis range.

	Theoretical	Analysis Range
Aluminum, wt. %	26.3	25.5 to 27.1
Chlorine, wt. %	51.9	48.0 to 52.0

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

TABLE LVII. Methylaluminum sesquichloride - requirements and typical analysis.

	Requirement	Analysis
Product composition, wt. %		
Aluminum	24.8 to 26.4	25.8
Chloride	49.5 to 52.5	51.5
Hydrolysis gas composition, mol %		
Methane	98.0 min	99.4
Ethane	2.0 max	0.4
Propane	0.3 max	0.1
Isobutane	0.5 max	0.1
n-Butane	0.3 max	0.0
Hydrogen	0.3 max	0.0

5.4.3.10.3 Use. Methylaluminum sesquichloride is used as a catalyst for polymerization of olefins and for hydrogenation of aromatics.

5.4.3.10.4 Safety. Methylaluminum sesquichloride, above 23°C, is a pyrophoric liquid that flames spontaneously and gives off dense smoke on exposure to air. It is reactive with water with the release of flammable and explosive vapors that can be ignited by the heat of reaction. Hydrocarbon solutions of methylaluminum sesquichloride may not be pyrophoric depending on concentration and temperature. The burning liquid can release irritating and toxic fumes and smoke. There is no PEL or TLV referenced for methylaluminum sesquichloride, but the TLV, as Al, is 2 mg/m^3 for aluminum alkyls not otherwise classified. Inhalation of fumes from burning liquid shall be avoided. Methylaluminum sesquichloride produces severe burns, predominantly thermal, on contact with skin or eyes by reaction with body moisture, so contact shall be avoided. (Refer to 4.3.1.)

5.4.3.10.5 Storage. Methylaluminum sesquichloride shall be stored in special containers, blanketed with dry nitrogen under a slight positive pressure, in a cool, dry place. (Refer to 4.3.2.)

5.4.3.10.6 Disposal. Spills of methylaluminum sesquichloride will ignite spontaneously. Small spill fires can be controlled with dry powder extinguishers, absorbed by nonreactive dry powders and placed in sealed containers. In case of large liquid spills, the burning liquid shall be isolated by use of sandbags to prevent spreading. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

Methylaluminum sesquichloride has an EPA Hazardous Waste Classification - Ignitable, Waste No. D001; and Reactive, Waste No. D003.

5.4.4 Aluminum Alkyl Hydrides.

5.4.4.1 Name. Diisobutylaluminum Hydride $AlH[CH_2CH(CH_3)_2]_2$ FW 142.22
Aluminum diisobutylhydride CAS 1191-15-7

5.4.4.1.1 Technical description. Diisobutylaluminum hydride is a colorless liquid with a density of 0.799 g/cm^3 at 25°C. It has a freezing point of -80°C and a boiling point of 275°C at 760 mm Hg. As a diialkylaluminum hydride, it is trimerically associated. Diisobutylaluminum hydride is miscible with liquid hydrocarbons. It is decomposed by water, and is reactive with polar compounds including halogenated hydrocarbons. The theoretical aluminum content is 19.0 percent.

5.4.4.1.2 Specification. Manufacturer's requirements. (No Government specification.)

5.4.1.1.2.1 Requirements. Diisobutylaluminum hydride is available from two manufacturers with the requirements and typical analyses shown in Tables LVIII and LVIX.

TABLE LVIII. Diisobutylaluminum - commercial specification requirements.

	Percent by Weight	
	Requirement	Typical Analysis
Aluminum, as Al	18.5 min	18.9
Triisobutylaluminum	5.5 max	3.0
Purity, as AlH $(i\text{-}C_4H_9)_2$	93.0 min	97

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

TABLE LIX. Diisobutylaluminum hydride - commerical specification requirements.

	Percent by Weight	
	Requirement	Typical Analysis
Diisobutylaluminum hydride	93.0 min	95.0
Triisobutylaluminum	5.5 max	3.5
Tri-n-butylaluminum	0.6 max	0.4
Tri-n-propylaluminum	1.5 max	0.8
Triethylaluminum	0.5 max	Trace
Methane	0.5 max	0.3
Aluminum	18.5 min	18.8

5.4.4.1.3 Use. Diisobutylaluminum hydride is used as a component of catalyst systems for olefin and diene polymerization, and as a reducing agent in organic reduction reactions.

5.4.4.1.4 Safety. Diisobutylaluminum hydride is a pyrophoric liquid that flames spontaneously and gives off dense smoke on exposure to air. It is reactive with water with the release of flammable and explosive vapors that can be ignited by the heat of reaction. Hydrocarbon solutions of diisobutylaluminum hydride may not be pyrophoric depending on concentration and temperature. The burning liquid can release irritating and toxic fumes and smoke. There is no PEL or TLV referenced for diisobutylaluminum hydride, but the TLV, as Al, is 2 mg/m^3 for aluminum alkyls not otherwise classified. Inhalation of fumes from burning liquid shall be avoided. Diisobutylaluminum hydride produces severe burns, predominantly thermal, on contact with skin or eyes by reaction with body moisture, so contact shall be avoided. (Refer to 4.3.1.)

5.4.4.1.5 Storage. Diisobutylaluminum hydride shall be stored in special containers, blanketed with dry nitrogen under a slight positive pressure, in a cool, dry place. (Refer to 4.3.2.)

5.4.4.1.6 Disposal. Liquid spills of diisobutylaluminum hydride will ignite spontaneously. Small liquid spill fires can be controlled with dry powder extinguishers, absorbed by nonreactive dry powders and placed in sealed containers. In case of large liquid spills, the burning liquid shall be isolated by use of sandbags to prevent spreading. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

Diisobutylaluminum hydride has an EPA Hazardous Waste Classification - Ignitable, Waste No. D001; and Reactive, Waste No. D003.

Source: https://assist.dla.mil -- Downloaded: 202610-26T07:47Z
Check the source to verify that this is the currentversion before use.

5.4.4.2 Name. Sodium Aluminum Diethyl Dihydride $NaAl(C_2H_5)_2H_2$
Sodium diethyldihydridoaluminate FW 110.11
Sodium diethyldihydroaluminate CAS 17836-88-3

5.4.4.2.1 Technical description. Sodium aluminum diethyl dihydride is a solid. It is soluble in aromatic hydrocarbons and ethers. It is insoluble in paraffinic hydrocarbons. It is decomposed by water and is reactive with active hydrogen or hydroxylated solvents. It does not attack halogenated compounds unless they are activated or exposed at elevated temperatures for prolonged time periods.

5.4.4.2.2 Specification. Manufacturer's requirements. (No Government specification.)

5.4.1.2.2.1 Requirements. Sodium aluminum diethyl dihydride is available from a manufacturer as a 25 wt percent solution in toluene containing 4 wt percent tetrahydrofuran, with the typical analysis shown in Table LX.

TABLE LX. Sodium aluminum diethyl dihydride solution - typical analysis.

Al. wt. %	5.9
Active hydride, meqs/g soln	4.4
Total gas evolution, mmols/g soln	8.8
Density, at 20°C, g/cm^3	0.879
Viscosity at 20°C, cp	2.08

5.4.4.2.3 Use. Sodium aluminum diethyl dihydride is used as a reducing agent for a variety of functional groups requiring an active hydrogen reducing agent, such as ketones, aldehydes, acids, esters, amides, nitriles, and nitro compounds.

5.4.4.2.4 Safety. Sodium aluminum diethyl dihydride solutions, containing concentrations of over 10 wt percent, are pyrophoric and flame spontaneously on exposure to air, giving off dense smoke. It is explosively reactive with water with the release of flammable and explosive vapors that can be ignited by the heat of reaction. The burning liquid can release irritating and toxic fumes and smoke. There is no PEL or TLV referenced for sodium aluminum diethyl dihydride, but the TLV, as Al, is 2 mg/m^3 for aluminum alkyls not otherwise classified. Inhalation of fumes from burning liquid solution shall be avoided. Sodium aluminum diethyl dihydride solution produces severe burns, predominantly thermal, on contact with skin or eyes by reaction with body moisture, so contact shall be avoided. (Refer to 4.3.1.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.4.4.2.5 Storage. Sodium aluminum diethyl dihydride solution shall be stored in special containers, blanketed with dry nitrogen under a slight positive pressure, in a cool, dry place. (Refer to 4.3.2.)

5.4.4.2.6 Disposal. Spills of sodium aluminum diethyl dihydride solutions will ignite spontaneously. Small liquid spill fires can be controlled with dry powder extinguishers, absorbed by nonreactive dry powders and placed in sealed containers for disposal. In case of large liquid spills, the burning liquid shall be isolated by use of sandbags to prevent spreading. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

Sodium aluminum diethyl dihydride has an EPA Hazardous Waste Classification - Ignitable, Waste No. D001; and Reactive, Waste No. D003.

5.4.5 Magnesium Alkyl

5.4.5.1 Name. Di-n-Hexylmagnesium $Mg[CH_2(CH_2)_4CH_3]_2$ FW 194.65
Magnesium di-n-hexyl CAS 37509-99-2

5.4.5.1.1 Technical description. Di-n-hexylmagnesium is a light green or yellow solid. It is soluble in liquid hydrocarbons. It is decomposed by water and is reactive with compounds containing active hydrogen. It reacts with oxygen to form the alkoxide. It complexes with ethers and tertiary amines.

5.4.5.1.2 Specification. Manufacturer's requirements. (No Government specification.)

5.4.5.1.2.1 Requirements. Di-n-hexylmagnesium is available from a manufacturer with the typcial analysis shown in Table LXI.

TABLE LXI. Di-n-hexylmagnesium solution - typical analysis.

$(C_6H_{13})_2Hg$, wt. %	15 to 20
Al, wt. % of contained Mg	4
Cl, wt. % of contained Mg	7

5.4.5.1.3 Use. Di-n-hexylmagnesium is used as a component of catalyst systems for olefin and diene polymerization, and as an alkylating agent.

5.4.5.1.4 Safety. Di-n-hexylmagnesium solution is pyrophoric. Its flash point is dependent on the hydrocarbon solvent, and it is either flammable, combustible or

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

burnable. It is reactive with water with the release of flammable and explosive vapors that can be ignited by the heat of reaction. The burning liquid can release irritating and toxic fumes and smoke. There is no PEL or TLV referenced for di-n-hexylmagnesium but the PEL magnesium oxide fumes is 15 mg/m^3 and the TLV is 10 mg/m^3, so inhalation of fumes from burning liquid shall be avoided. Di-n-hexylmagnesium produces severe burns, predominantly thermal, on contact with skin or eyes by reaction with body moisture, so contact shall be avoided. (Refer to 4.3.1.)

5.4.5.1.5 Storage. Di-n-hexylmagnesium shall be stored in special containers, blanketed with dry nitrogen under a slight positive pressure, in a cool, dry place. (Refer to 4.3.2.)

5.4.5.1.6 Disposal. Spills of di-n-hexylmagnesium solutions will not ignite spontaneously, and ignition shall be avoided. Small spills fire can be absorbed by nonreactive dry powders and placed in sealed containers for disposal. Large liquid spills shall be diked to prevent spreading. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

Di-n-hexylmagnesium has an EPA Hazardous Waste Classification - Ignitable, Waste No. D001; and Reactive, Waste No. D003.

5.4.6 Metallocenes

5.4.6.1 Name. 2,2-Bis(Ethylferrocenyl) Propane

$(CH_3)_2C(C_5H_4FeC_5H_4C_2H_5)_2$ FW 468.248

CAS 37206-42-1

5.4.6.1.1 Technical description. 2,2-Bis(ethylferrocenyl) propane is in the form of a liquid at 25°C. It is miscible with liquid hydrocarbons. The theoretical iron content is 23.85 percent.

5.4.6.1.2 Specification. Military, MIL-C-85493, Catalyst, Burn-Rate 2,2-Bis (Ethylferrocenyl) Propane.

5.4.6.1.2.1 Requirements. This specification covers one type of 2,2-bis (ethylferrocenyl) propane with the chemical and physical properties conforming to the requirements shown in Table LXII.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

TABLE LXII. 2,2-Bis(Ethylferrocenyl) Propane - chemical and physical requirements.

Viscosity (25°C), centistrokes, ($MM^2 \cdot S$), max	2.200
Iron content, %	
min	23.3
max	24.3
Moisture, %, max	0.10
Acidity, milliequivalent/gram, max	0.023
Insolubility in chloroform, %, max	0.1
Evaporation loss (80°C, 15 mm Hg, 22 hrs), %, max	4.0
Assay (by titration), %, min	97.5

5.4.6.1.3 Use. 2,2-Bis(ethylferrocenyl) propane is intended for military use as a burn-rate catalyst in solid rocket propellants.

5.4.6.1.4 Safety. 2,2-Bis(ethylferrocenyl) propane is a burnable liquid, and can emit irritating and toxic fumes if heated to decomposition. There is no PEL or TLV referenced for this compound; but the TLV for the parent compound, dicyclopentadienyl iron, is 10 mg/m^3, so breathing of fumes shall be avoided. It can be irritating to the eyes, skin and mucous membranes, so contact shall be avoided. (Refer to 4.3.1.)

5.4.6.1.5 Storage. 2,2-Bis(ethylferrocenyl) propane shall be stored in approved tightly sealed containers in a cool, dry place. (Refer to 4.3.2.)

5.4.6.1.6 Disposal. In case of small liquid spills, absorb by nonreactive absorbent and place in containers for disposal. In case of large liquid spills, dike to prevent spreading. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

An EPA Hazardous Waste Classification is not listed in 40 CFR.

5.4.6.2 Name. Ferrocene $C_5H_5FeC_5H_5$ FW 186.04
Dicyclopentadienyliron CAS 102-54-5

5.4.6.2.1 Technical description. Ferrocene is in the form of monoclinic crystalline yellow-orange needles with a melting point of 172.5° to 173°C. It is insoluble in water. It is soluble in methyl and ethyl alcohols, ether and benzene. The theoretical composition is 30.1% Fe, and the molecule is neutral. Ferrocene is a "sandwich"-bonded compound in which the C_5H_5 anions are planar symmetrical pentagons in shape and are staggered in configuration relative to each other. The compound is thermally stable to about 500°C. It is reactive with oxidizing agents.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.4.6.2.2 Specification. Manufacturer's requirements. (No Government specification.)

5.4.6.2.2.1 Requirements. Ferrocene is available from a manufacturer with the requirements shown in Table LXIII.

TABLE LXIII. Ferrocene (dicyclopentadienyliron) - commercial requirements.

Appearance	
Color	Orange
Form	Crystalline solid
Melting point, °C	173 to 174
Boiling point, °C	249
Iron content, as Fe	29 to 30
Toluene insolubles, %, max	0.2

5.4.6.2.3 Use. Ferrocene is intended for military use, in the form of a 10% by weight solution in xylene, as a smoke abatement additive for fuel oils. Ferrocene is also used as an intermediate for the preparation of high temperature polymers, and in the preparation of metallocenes.

5.4.6.2.4 Safety. Ferrocene is a burnable liquid that emits irritating and toxic fumes if heated to decomposition. The TLV for dicyclopentadienyliron is 10 mg/m^3, so breathing of dust and fumes shall be avoided. Ferrocene can be irritating to the eyes, skin and mucous membranes, so contact shall be avoided. (Refer to 4.3.1.)

5.4.6.2.5 Storage. Ferrocene shall be stored in tightly sealed containers in a cool, dry place. (Refer to 4.3.2.)

5.4.6.2.6 Disposal. In case of dry spills, gather up and place in containers. In case of small solution spills, absorb by nonreactive absorbents and place in containers for disposal. In case of large solution spills, dike to prevent spreading. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

An EPA Hazardous Waste Classification is not listed in 40 CFR.

5.4.6.3 Name. Methylcyclopentadienylmanganese Tricarbonyl

$CH_3C_5H_4Mn(CO)_3$ FW 218.095

CAS 12108-13-3

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.4.6.3.1 Technical description. Methylcyclopentadienylmanganese tricarbonyl is a liquid with a density of 1.3884 g/cm^3 at 20°C, a freezing point of about 1°C and a boiling point of 233°C. It is miscible with liquid hydrocarbons. It is stable in the presence of air and water. The theoretical Mn content is 25.2 percent.

5.4.6.3.2 Specification. Manufacturer's requirements. (No Government specification.)

5.4.6.3.2.1 Requirements. Methylcyclopentadienylmanganese tricarbonyl is available from a manufacturer as a clear straw colored liquid. The product shall have a minimum Mn content of 24.7 wt percent.

5.4.6.3.3 Use. Methylcyclopentadienylmanganese tricarbonyl is intended for military use as an additive for fuel oils to improve combustion efficiency. It is also used as an additive for unleaded gasoline.

5.4.6.3.4 Safety. Methylcyclopentadienylmanganese tricarbonyl is a burnable liquid that can emit irritating and toxic fumes if heated to decomposition. The compound is toxic by inhalation and skin absorption. The TLV for is 0.2 mg/m^3 including skin. Contact with eyes, skin and clothing shall be avoided. (Refer to 4.3.1.)

5.4.6.3.5 Storage. Methylcyclopentadienylmanganese tricarbonyl shall be stored in approved tightly sealed containers in a cool, dry place. (Refer to 4.3.2.)

5.4.6.3.6 Disposal. In case of small liquid spills, absorb by nonreactive absorbent and place in containers for disposal. In case of large liquid spills, dike to prevent spreading. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

An EPA Hazardous Waste Classification is not listed in 40 CFR.

5.4.7 Zinc Alkyl.

5.4.7.1 Name. Diethylzinc
Zinc diethyl

$Zn(C_2H_5)_2$

FW 123.49
CAS 557-20-0

5.4.7.1.1 Technical description. Diethylzinc is a colorless liquid with a density of 1.182 g/cm^3 at 18°C. It has a freezing point of -28°C and a boiling point of 124°C at 760 mm Hg. It is miscible with liquid hydrocarbons. It is decomposed by water, and is reactive with polar compounds including halogenated hydrocarbons.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

5.4.7.1.2 Specification. Manufacturer's requirements. (No Government specification.)

5.4.7.1.2.1 Requirements. Diethylzinc is available from a manufacturer with a mininum purity of 95 percent.

5.4.7.1.3 Use. Diethylzinc is used as a component of catalyst systems for polymerization, and also as an alkylation agent and reducing agent.

5.4.7.1.4 Safety. Diethylzinc is a pyrophoric liquid that flames spontaneously and gives off dense smoke on exposure to air. It decomposes on heating above 200°C. It is reactive with water with the release of flammable and explosive vapors that can be ignited by the heat of reaction. Hydrocarbon solutions of diethylzinc may not be pryophoric depending on concentration and temperature. The burning liquid can release irritating and toxic fumes and smoke. There is no PEL or TLV referenced for diethylzinc but the PEL and TLV for zinc oxide fumes is 5 mg/m^3, so inhalation of fumes from burning liquid shall be avoided. Diethylzinc produces severe chemical and thermal burns on contact with skin or eyes by reaction with body moisture, so contact shall be avoided. (Refer to 4.3.1.)

5.4.7.1.5 Storage. Diethylzinc shall be stored in special containers, blanketed with dry nitrogen under a slight positive pressure, in a cool, dry place. (Refer to 4.3.2.)

5.4.7.1.6 Disposal. Liquid spills of diethylzinc will ignite spontaneously. Small liquid spill fires can be controlled with dry powder extinguishers, absorbed by nonreactive dry powders and placed in sealed containers. In case of large liquid spills, the burning liquid shall be isolated by use of sandbags to prevent spreading. For appropriate procedures, contact the Installation Environmental Office, the DRMO, or Safety and Health Offices. (Refer to 4.4.)

Diethylzinc has an EPA Hazardous Waste Classification - Ignitable, Waste No. D001; and Reactive, Waste No. D003.

Source: https://assist.dla.mil -- Downloaded: 202610-26T07:47Z
Check the source to verify that this is the currentversion before use.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Subject term (key word) listing.

Aluminum acetylacetonate
Aluminum alkoxides
Aluminum alkyl alkoxide
Aluminum alkyl halides
Aluminum alkyl hydrides
Aluminum alkyls
Aluminum butoxide (n-, sec-, tert-)
Aluminum ethoxide
Aluminum isopropoxide
Aluminum stearate
Antimony alkoxides
Antimony butoxide (n-)
Antimony ethoxide
Antimony methoxide
Barium oxalate
Barium stearate
2,2-Bis(ethylferrocenyl) propane
Boron alkoxides
Boron butoxide (n-)
Boron ethoxide
Boron methoxide
Boron octoxide (n-)
Boron propoxide (n-)
Calcium oxalate
Calcium resinate
Calcium stearate
Catalyst, burn-rate
Chelate ligands
Chromic acetylacetonate
Chromium 2-ethylhexanoate
Cobaltic acetylacetonate
Cobaltous acetylacetonate
Copper acetylacetonate
Copper naphthenate
Copper 8-quinolinolate

Source: https://assist.dla.mil -- Downloaded: 2026l0-26T07:47Z
Check the source to verify that this is the currentversion before use.

Dibutyl tin acetylacetonate
Diethylaluminum chloride
Diethylaluminum ethoxide
Diethylaluminum iodide
Diethylzinc
Di-n-hexylmagnesium
Diisobutylaluminum chloride
Diisobutylaluminum hydride
Dimethylaluminum chloride
Disposal, hazardous chemicals
Ethylaluminum dichloride
Ethylaluminum sesquichloride
Exposure limits, hazardous chemicals
Ferric acetylacetonate
Ferrocene
Germanium alkoxides
Germanium butoxide (n-)
Germanium ethoxide
Germanium isopropoxide
Germanium methoxide
Isobutylaluminum dichloride
Isobutylaluminum sesquichloride
Lead 2-ethylhexanoate
Lead salicylate
Lead stearate
Lithium stearate
Magnesium acetylacetonate
Magnesium alkyl
Magnesium stearate
Manganic acetylacetonate
Manganous acetylacetonate
Metal alkoxides
Metal alkyls
Metal carboxylates
Metal chelates
Metallic soaps
Metallocene
Methylaluminum dichloride
Methylaluminum sesquichloride
Methylcyclopentadienylmanganese tricarbonyl
Nickel acetylacetonate
Organometallic compounds

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

Ruthenium acetylacetonate
Safety, hazardous chemicals
Sodium acetate
Sodium alkoxides
Sodium aluminum diethyl dihydride
Sodium butoxide (n-)
Sodium ethoxide
Sodium gluconate
Sodium methoxide
Sodium oxalate
Sodium resinate
Storage, hazardous chemicals
Strontium oxalate
Titanium alkoxides
Titanium ammonium dihydroxy lactate
Titanium butoxide (n-)
Titanium diisopropoxide acetylacetonate
Titanium diisopropoxide bis(triethanolamine)
Titanium diisopropoxide ethylacetoacetate
Titanium ethoxide
Titanium 2-ethylhexoxide
Titanium isobutoxide
Titanium isopropoxide
Titanium methoxide
Titanium potassium oxalate
Tri-n-butylaluminum
Triethylaluminum
Tri-n-hexylaluminum
Triisobutylaluminum
Trimethylaluminum
Tri-n-propylaluminum
Vanadyl acetylacetonate
Zinc acetylacetonate
Zinc alkyl
Zinc 8-quinolinolate
Zinc stearate
Zirconium acetylacetonate
Zirconium alkoxides
Zirconium butoxide (n-)
Zirconium ethoxide
Zirconium isopropoxide
Zirconium n-propoxide

Source: https://assist.dla.mil -- Downloaded: 202640-26T07:47Z
Check the source to verify that this is the currentversion before use.

6.2 **Changes from previous issue**. Asterisks or vertical lines are not used in this revision to identify changes with respect to the previous issue due to the extensiveness of the changes.

Source: https://assist.dla.mil -- Downloaded: 202640-26T07:47Z
Check the source to verify that this is the current version before use.

CONCLUDING MATERIAL

Preparing activity: Army - EA

Project Number: (6810-1322)

Custodians:

Army	EA
Navy	SH
Air Force	68

Review Activities:

Army	AR, MD, SM
DLA	DP, GS

User Activities:

Army	ME
Navy	MS, OS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T07:47Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	1. DOCUMENT NUMBER	2. DOCUMENT DATE (YYMMDD)
	MIL-STD-1445A	940921

3. DOCUMENT TITLE
METAL ORGANIC COMPOUNDS, TECHNICAL GRADE

4. NATURE OF CHANGE *(Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)*

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle Initial)	b. ORGANIZATION	
c. ADDRESS (Include Zip Code)	d. TELEPHONE (Include Area Code) (1) Commercial (2) AUTOVON (If applicable)	7. DATE SUBMITTED (YYMMDD)

8. PREPARING ACTIVITY

a. NAME	b. TELEPHONE (Include Area Code) (1) Commercial	(2) AUTOVON
U. Army Edgewood Research, Development and Engineering Center	(410) 671-3259	DSN 584-3259
c. ADDRESS (Include Zip Code) Tech Dir, U.S. Army ERDEC ATTN: SCBRD-ENE-S Aberdeen Proving Ground, MD 21010-5423	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT: Defense Quality and Standardization Office 5203 Leesburg Pike, Suite 1403, Falls Church, VA 22041-3466 Telephone (703) 756-2340 AUTOVON 289-2340	

DD Form 1426, OCT 89 *Previous editions are obsolete.* 198-290

Source: https://assist.dla.mil -- Downloaded: 202640-26T07:47Z
Check the source to verify that this is the current version before use.