P-C-436(Army-Ord)
AMENDMENT--1
2 July 1953

INTERIM FEDERAL SPECIFICATION
CLEANING COMPOUND, ALKALI-TYPE

The following changes shall be made in Specification P-C-436(Army-Ord), dated 19 February 1952:

Page 2, paragraph 3.4.1, line 5: Delete "tar".

Page 3, add new paragraph as follows:

"3.10 Surface tension.--The surface tension of a 0.05 percent solution (grams per 100 ml. of solution) of the compound in distilled water at 25°C. shall be not more than 36 dynes per centimeter when determined as specified in 4.4.6."

Page 3, paragraph 4.3.2, line 5: Delete "and asphalt."

Page 3, paragraph 4.3.2, line 7: Delete "tar" and substitute "asphalt".

Page 4, paragraph 4.4.1.1.2.2: Delete the paragraph.

Page 4, paragraph 4.4.1.1.4: Delete all references to tar in lines 4, 11, and 17.

Page 5, paragraph 4.4.1.1.5.1: Delete all references to tar in title of paragraph and lines 1 and 6.

Page 5, paragraph 4.4.1.2.2, line 7: Delete "tar".

Page 6, paragraph 4.4.1.3, sub-paragraph 4: Delete and substitute:

"4. Non-ionic surface-active agent ....."Triton X-100" manufactured by Rohm and Haas, "Igepal CA-630" manufactured by General Dyestuff Corporation or "Atlas G-1690" manufactured by Atlas Powder Company."

Page 6, paragraph 4.4.1.3, sub-paragraph 5: Delete "Santomerse #3" and substitute "Santomerse #1".

"4.4.6 Surface tension.--Dissolve 10 grams of the well mixed compound in distilled water and dilute to volume in a 2-liter volumetric flask. Take a 10-ml. aliquot of this solution and dilute to volume in a 100-ml. volumetric flask. Determine the surface tension at 25°C. using a Du Nouy tensiometer or interfacial tensiometer. A 6-cm. circumference platinum ring shall be used observing the recommended instructions of the manufacturer of the instrument. The tensiometer should be direct reading in dynes per centimeter and should be capable of reading to 0.1 dynes per cm. with a precision of 0.05 dyne per cm. Allow the solution to stand in the test vessel for 1 hour before the test is run."

Page 8, paragraph 6.3, lines 2 through 4: Delete reference to tar soil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:17Z
Check the source to verify that this is the current version before use.

(Over)

Page 8, add the following paragraph:

"6.5 Treatment of asphalt prior to soiling.--Caution should be taken against repeated heating of the entire stock of asphalt prior to spreading on the test panel. This treatment will tend to produce asphaltenes that are difficult to remove, especially if the asphalt contains hydrocarbons of an aromatic character. It is suggested that only enough asphalt be removed from the container on a spatula to soil one test panel. Soiling may be facilitated by slight heating (not over 50°C.) of both asphalt and test panel."

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:17Z
Check the source to verify that this is the current version before use.