FEDERAL SPECIFICATION SHEET

ALUMINUM ALLOY 2219, PLATE AND SHEET

This amendment, which forms part of QQ-A-250/30A, dated November 19, 1982 is approved by the Commissioner, Officer of Federal Supply and Services, Commodity Management Division (FCM), General Services Administration, for the use of all Federal Agencies.

PAGE 1

Paragraph 3.2.2.3, delete on second line, "shall be heat treatable" and substitute "shall be precipitation heat treatable".

PAGE 5

Paragraph 3.4, delete and substitute the following:

"3.4 Resistance to stress corrosion-cracking. Plate 0.750 inch and thicker, supplied in the T851 and T87 tempers or in the T351 and T37 tempers and aged to the T851 and T87 tempers shall exhibit no stress-corrosion cracking when subjected to the test specified in 4.3. Frequency of testing shall be in accordance with QQ-A-250/GEN. When specified (see 6.2), plate 0.750 inch and thicker, without prior cold work or forming, when heat treated to the T62 temper shall exhibit no stress-corrosion cracking when subjected to the test specified in 4.3 (see 6.4)."

PAGE 6

Paragraph 4.3, delete the last sentence.

Paragraph 4.4, add as follows:

"4.4 Records. It is the responsibility of the contractor that all test results be recorded, identified as to lot, and preserved after completion of the contract or purchase order. The records shall be made available to the Federal Government upon request."

FSC 9535

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:04Z
Check the source to verify that this is the current version before use.

MILITARY INTEREST:

Custodians

Army - MR
Navy - AS
Air Force - 20

Review Activities

Army - MI
Air Force - 99, 84
DLA - IS

User Activities

Navy - MC, SH

CIVIL AGENCY COORDINATING ACTIVITIES:

NASA - JFK
GSA - FSS, PCD

PREPARING ACTIVITY:

Navy - AS

DoD Project No. 9535-0364

GSA DC-8921500885

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:04Z
Check the source to verify that this is the current version before use.