CCC-C-419F
September 30, 1985
SUPERSEDING
CCC-C-419E
April 27, 1977

FEDERAL SPECIFICATION

CLOTH, DUCK, COTTON, UNBLEACHED, PLIED-YARNS ARMY AND NUMBERED

This specification is approved by the Assistant Administrator, Office of Federal Supply Service, General Services Administration, for the use of all Federal Agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers the requirements for grey (unbleached) cotton duck cloth.

1.2 Classification.

1.2.1 Types. The cloth shall be of the following types as specified (see 6.2):

Type I - Numbered duck.
Type III - Army duck.

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

Federal Specifications:

V-T-276 - Thread, Cotton
PPP-P-1135 - Packaging of Duck Fabrics (Cotton; Synthetic Fiber; Cotton-Synthetic Fiber Blends)

Federal Standards:

FED-STD-4 - Glossary of Fabric Imperfections
FED-STD-191 - Textile Test Methods
FED-STD-751 - Stitches, Seams, and Stitchings

FSC 8305

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

(Activities outside the Federal Government may obtain copies of Federal specifications, standards, and commercial item descriptions as outlined under General Information in the Index of Federal Specifications, Standards, and Commerical Item Descriptions. The Index which includes cumulative bimonthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

(Single copies of this specification and other Federal specifications and commercial item descriptions required by activities outside the Federal Government for bidding purposes are available without charge from General Services Administration Business Service Centers in Boston, MA; New York, NY; Philadelphia, PA; Washington, DC; Atlanta, GA; Chicago, IL; Kansas City, MO; Fort Worth, TX; Houston, TX; Denver, CO; San Francisco, CA; Los Angeles, CA; Seattle, WA.

(Federal Government activities may obtain copies of Federal standardization documents and the Index of Federal Specifications, Standards and Commercial Descriptions from established distribution points in their agencies.)

Military Standard:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes

(Copies of military specifications and standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

Laws and Regulations:

Rules and Regulations Under the Textile Fiber Products Identification Act

(Application for copies should be addressed to the Federal Trade Commission, Washington, DC 20580.)

(The Code of Federal Regulations (CFR) and the Federal Register (FR) are for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402. When indicated, reprints of certain regulations may be obtained from the Federal agency responsible for issuance thereof.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

2.2 Order of precedence. In the event of conflict between the text of this document and the references cited herein, the text of this document shall take precedence.

3. REQUIREMENTS

3.1 Material.

3.1.1 Yarn. The yarn shall be cotton which has been carded, drawn, and spun into singles or plied yarns as specified in tables I, II, and III.

3.2 Physical requirements. The cloth shall be as specified (see 6.2) and shall conform to the requirements specified in tables I, II, and III when tested as specified in 4.4.

3.2.1 Width. The width of the cloth shall be as specified (see 6.2). The minimum acceptable width shall be inclusive of the woven selvage when fly-shuttle looms are used or tuck-in selvages when shuttleless looms are used and exclusive of the lock-in fringed selvage when a shuttleless leno lock-in fringed selvage is used. Cut raw edges shall not be permitted. The following tolerances shall be permitted:

Width of duck in inches	Tolerance in inches
40 or less	+1/4 to -1/4
Over 40 to 51 inclusive	+3/8 to -1/4
Over 51 to 81 inclusive	+5/8 to -3/8
Over 81	+3/4 to -3/8

3.2.1.1 Shuttleless loom selvages. When the cloth is woven on shuttleless looms, the fringed selvages shall be secured by a leno lock stitch. The width of the protruding fringe shall not exceed 3/16 inch.

3.2.2 Weave. The weave shall be plain, one up and one down. The use of a fly-shuttle or a shuttleless loom is permitted.

3.3 Nonfibrous material. The cloth shall contain not more than 2.5 percent starch and protein content excluding chloroform-soluble and water-soluble material. The total sizing, finishing and other nonfibrous material content of the finished cloth shall not exceed 5.0 percent when tested as specified in 4.4.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

TABLE I. Physical requirements for type I, numbered ducks (hard texture)

Number of duck commercial designation	Weight Oz/Yd^2		Breaking strength		Air permeability Ft^3/Min/Ft^2
			Warp Pounds	Filling Pounds	
	Min	Max	Min	Min	Max
1 1/	28.7	31.6	440	370	2.0
2 1/	27.1	29.8	420	345	2.0
4 1/	23.9	26.3	375	300	2.0
6 1/	20.7	22.8	335	225	2.0
8 1/	17.6	19.4	285	190	2.0
10 2/	14.4	15.8	215	160	4.0
12 2/	11.2	13.0	195	120	4.0

1/ Plied yarns shall be used for both warp and filling.

2/ Warp yarns shall be plied; filling yards shall be singles or plied.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

TABLE II. Physical requirements for type I, numbered ducks (medium texture)

Number of duck commercial designation	Weight Oz/Yd^2		Breaking strength Warp Pounds	Breaking strength Filling Pounds	Air permeability Ft^3/Min/Ft^2
	Min	Max	Min	Min	Max
1 1/	28.7	31.6	425	345	4.0
4 1/	23.9	26.3	350	290	5.0
6 1/	20.7	22.8	305	250	4.0

1/ Plied yarns shall be used for both warp and filling.

Source: https://assist.dla.mil - Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

TABLE III. Physical requirements for type III, army duck 1/

Weight Oz/Yd^2		Breaking strength		Tearing strength		Air permeability
		Warp	Filling	Warp	Filling	
		Pounds	Pounds	Pounds	Pounds	Ft^3/Min/Ft^2
Min	Max	Min	Min	Min	Min	Max
8.25	9.25	125	120	4.0	3.0	4.0
9.85	11.00	160	110	-	-	5.0
12.30	13.50	210	130	-	-	5.0
14.80	16.30	235	175	-	-	-
18.50	20.40	315	200	-	-	-

1/ The warp yarns shall be plied and the filling yarns shall be singles or plied.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

3.4 Length and put-up. Unless otherwise specified (see 6.2), the cloth shall be furnished in continuous lengths, each not less than 40 yards, and shall be put-up on full width rolls as specified in 5.1. The maximum length of the rolls when converted to pounds shall not exceed the maximum weight specified in PPP-P-1135. For duck No. 10 and lighter in weight, pieces shall be sewn together with a butted FSa-1 type seam of FED-STD-751 using ticket No. 10, 3-ply, unbleached cotton thread conforming to type IIIA of V-T-276, and having a minimum of 6 stitches per inch. The stitching shall be placed 1/2 to 5/8 inches from the cut or raw edge of the cloth. For cloth heavier in weight than No. 10, the pieces shall be lapped and not sewn together. The number of pieces in the roll shall be indicated by stencil marking on the last 6 inches of the roll on the outer surface.

3.5 Fiber identification. Each roll shall be labeled, or ticketed, for fiber content in accordance with the Rules and Regulations Under the Textile Fiber Products Identification Act.

3.6 Face marking. The face side of the cloth shall be identified by applying a stamping on that side of the cloth with the word "FACE" at each end of the piece.

3.7 Workmanship. The cloth shall conform to the quality established by this specification. The demerit points per 100 square yards when calculated as specified in section 4 shall not exceed the established maximum point value.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the document where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Certificate of compliance. Where certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

4.2 Quality conformance inspection. Sampling for inspection shall be performed in accordance with 4.3 and 4.4. When applicable, definitions of quality assurance terms and procedures shall be in accordance with MIL-STD 105.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

4.2.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced documents unless otherwise excluded, amended, modified or qualified in this specification or applicable purchase documents.

4.3 End item examination.

4.3.1 Yard-by-yard examination. Each roll in the sample shall be examined on the face side only. When the total yardage in the roll does not exceed 100 yards, the entire yardage in the roll shall be examined. When the total yardage in the roll exceeds 100 yards, only 100 yards shall be examined. All defects, as defined in Section I of FED-STD-4, which are clearly noticeable at normal inspection distance (3 feet), shall be scored and assigned demerit points as listed in 4.3.1.1 with the following exceptions: Glossary numbers 1, 2, 3, 5, 14, 26, 27, and 29 shall not be scored unless they exceed three times the thickness of the yarn. Misdraws and reed marks shall be scored if they result in a clearly noticeable separation of warp yarns. Each knot or slub shall be scored as a defect only when it exceeds three times the normal yarn diameter. No linear yard (increments of 1 yard on the measuring device of the inspection machine) from any one roll within the sample shall be penalized more than 4 points. The sample size shall be in accordance with the following:

Lot size (yards)	Sample size (rolls)
3200 or less	8
3201 up to including 10,000	13
10,001 and over	20

The lot shall be unacceptable if the points per 100 square yards of the total yardage examined exceeds 40 points. The lot shall be unacceptable if the points per 100 square yards of two or more individual rolls exceeds 60 points. If one roll exceeds 60 points per 100 square yards, a second sample of 20 rolls shall be examined only for individual roll quality. The lot shall be unacceptable if one or more rolls in the second sample exceed 60 points per 100 square yards. Point computation for lot quality and individual roll quality shall be as follows:

$$\frac{\text{Total points scored in sample} \times 3600}{\text{Contracted width of cloth (inches)} \times \text{total yards inspected}} = \text{Points per 100 sq. yd}$$

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

4.3.1.1 Demerit points. Demerit points shall be assigned as follows:

For defects 3 inches or less in any dimension	- one point
For defects exceeding 3 inches but not exceeding 6 inches in any dimension	- two points
For defects exceeding 6 inches but not exceeding 9 inches in any dimension	- three points
For defects exceeding 9 inches in any dimension	- four points

The following defects when present shall be scored four points for each yard in which they occur:

Baggy, ridgy, or wavy cloth.
Width not within specified tolerance.
Objectionable odor.
Excessive neppiness.
Holes, cuts, or tears.
Overall uncleanliness.
Width not within specified tolerance. Fringed selvages of shuttleless loom cloth not secured by a leno lock-stitch or fringe protruding in excess of 3/16 inch.
Slack or tight selvages. (Note: To determine the presence of unacceptable selvage conditions, the following procedure shall be used: During the visual examination, the perch shall be stopped a minimum of three times for each roll in the sample, the tension removed and the finished cloth examined for selvage conditions. Suspect rolls should be removed from the perch and unrolled on the floor or table and further examined for the condition. A waviness in the selvage or significant ripples diagonally across the width of the fabric is an indication of slack or tight selvages.)

4.3.2 Length examination.

4.3.2.1 Individual rolls. During the yard-by yard examination, each roll in the sample shall be examined for length. Each defect shall be counted not more than once in each roll examined. The lot shall be unacceptable if two or more of the following defects are present:

Source: https://assist.dla.mil Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

Any length found to be more than 2 yards less than the length marked on the roll ticket.

Any piece less than 40 yards in length.

For No. 10 duck and lighter in weight:

a. Pieces not sewn together with a butted FSa-1 type seam.

b. Stitches less than the minimum specified.

c. Stitching not 1/2 to 5/8 inch from the cut or raw edge of the cloth.

For duck heavier in weight than No. 10, pieces sewn instead of lapped.

Number of pieces in roll not stenciled on last 6 inches of rolls on outer surface.

4.3.2.2 Total yardage in sample. The lot shall be unacceptable if the total of the actual lengths of rolls in the sample is less than the total of the lengths marked on the tickets. The rolls examined shall be those selected for the examination of individual rolls.

4.3.3 Roll identification examination. During the yard-by-yard examination, each roll in the sample shall be examined for labeling. The lot shall be unacceptable if two or more rolls in the sample have the face stamping missing from either or both ends, or are not labeled or ticketed in accordance with the Textile Fiber Products Identification Act.

4.3.4 Packaging inspection. The inspection shall be in accordance with PPP-P-1135.

4.4 End item testing. The cloth shall be tested for the characteristics listed in table IV. The physical and chemical values specified in section 3 apply to the results of the determinations made on a sample unit for test purposes as specified in the applicable test methods. The sample unit for testing shall be 1 1/2 yards full width of the cloth. The lot shall be unacceptable if one or more sample units fail to meet any requirements specified. All test reports shall contain the individual values utilized in expressing the final results. The sample size shall be as follows:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

Lot size (yards)	Sample size (sample units)
800 or less	2
801 up to and including 22,000	3
22,001 and over	5

TABLE IV. End item tests

Characteristic	Requirement paragraph	Test method
Yarn Ply	3.2	Visual 1/
Weight	3.2	5041
Breaking strength	3.2	5100
Tearing strength (8.25 oz)	3.2	5132
Air permeability	3.2	5450
Weave	3.2.2	Visual 1/
Starch and protein content excluding chloroform-soluble and water-soluble material	3.3	2611 2/
Total sizing, finishing, and other nonfibrous materials	3.3	2611 2/

1/ One determination shall be made from each sample unit and the results reported as "pass" or "fail."

2/ A certificate of compliance shall be submitted and will be acceptable for the stated requirement.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

5. PREPARATION FOR DELIVERY

5.1 Put-up and preservation. Put-up and preservation shall be level A or Commercial as specified (see 6.2).

5.1.1 Levels A and commercial. The cloth shall be put-up and preserved in accordance with the applicable requirements of PPP-P-1135.

5.2 Packing. Packing shall be level A, B, or Commercial as specified (see 6.2).

5.2.1 Levels A, B, and Commercial. The cloth shall be packed in accordance with the applicable requirements of PPP-P-1135.

5.3 Marking. In addition to any special marking required by the contract or purchase order, shipments shall be marked in accordance with the applicable requirements of PPP-P-1135.

6. NOTES

6.1 Intended use. The cloths are primarily intended for use in fabrication of tentage and equipage items.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in acquisition documents:

a. Title, number, and date of this specification.
b. Type and weight of cloth required. If the cloth is type I, specify number and texture (see 1.2 and 3.2).
c. Width required (see 3.2.1).
d. Length, if other than specified (see 3.4).
e. Selection of applicable levels of preservation and packing (see 5.1 and 5.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

Military Interests:

Custodians

Army - GL
Navy - NU
Air Force - 20

Review activities

Army - MD, EA
Navy - MC
Air Force - 99, 82
DPSC - CT

User activities

Army - AR, AT, ME, MI
Navy - YD
Air Force - 45

Civil Agency Coordination Activity:

GSA - FSS

Preparing Activity:

Army - GL

Project No. 8305-0026

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
CCC-C-419F	Cloth, Duck, Cotton, Unbleached, Plied-Yarns Army and Numbered

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ USER
	☐ MANUFACTURER
	☐ OTHER *(Specify)*: _____

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

NATICK OP, L ADF 84

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE ARMY
US Army Natick Research and Development Center
Natick, Massachusetts 01760

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300
STRNC-ES

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 12062 WASHINGTON D. C.
POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
US Army Natick Research and Development Center
ATTN: STRNC-ES
Natick, MA 01760

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.