CCC-C-425c
May 15, 1967
SUPERSEDING
Fed. Spec. CCC-C-425b
February 8, 1966

FEDERAL SPECIFICATION

CLOTH, BIRDSEYE AND GAUZE: COTTON

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers the requirements for two types of cotton cloth.

1.2 Classification.

1.2.1 Types and classes. The cloth shall be of the following types and classes as specified (see 6.2):

Type I - Birdseye.

Class 1 - Daiper cloth (bleached).
Class 2 - Coverall cloth (bleached).
Class 3 - Coverall cloth (dyed).

Type II - Gauze - double layer.

2. APPLICABLE DOCUMENTS

2.1 The following specifications and standards, of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

Federal Specifications:

CCC-T-191 - Textile Test Methods.

PPP-P-1134 - Packaging and Packing of Cotton and Cotton-Synthetic Fiber Blend Fabrics (Excluding Duck Fabrics).

Federal Standard:

Fed. Std. No. 4 - Glossary of Fabric Imperfections.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, D.C. 20402.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Washington, D.C., Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, Los Angeles, and Seattle, Wash.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standard:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

2.2 Other publications. The following publication forms a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

Rules and Regulations Under the Textile Fiber Products Identification Act.

(Copies may be obtained free of charge from the Federal Trade Commission, Washington, D. C. 20580.)

3. REQUIREMENTS

3.1 Standard sample. When a standard sample is available, the finished cloth shall match the standard sample for shade and shall be equal to or better than the standard sample with respect to all characteristics for which the standard sample is referenced (see 6.4).

3.2 Material.

3.2.1 Cotton. The cotton yarn shall be made from clean cotton and shall be carded, drawn, and spun.

3.3 Color.

3.3.1 Bleached. The color for type I, classes 1 and 2 and type II cloth shall be chemically bleached to match the available standard sample (see 6.4). An optical brightener or tinting compound may be used unless otherwise specified. The bleached finished cloth shall not discolor to a degree greater than that shown by the standard sample when tested as specified in 4.4. When no standard sample is available, the discoloration shall be not less than "fair" when tested as specified in 4.4.

3.3.2 Dyed. The color for type I, class 3 cloth shall be OG-107 or as specified (see 6.2 and 6.5). The use of sulfur dyes and dyes containing elementary sulfur or compounds capable of oxidation to sulfuric acid is prohibited. The dyed and finished cloth shall contain no more labile sulfur than that shown by the standard sample when tested as specified in 4.4.

3.3.3 Matching. The color shall match the available standard sample under natural (north sky) daylight or artificial daylight having a color temperature of 7500° Kelvin and shall be a good approximation to the standard sample under incandescent lamplight at 2800° Kelvin.

3.3.4 Colorfastness. The dyed cloth shall show colorfastness to combined laundering and bleaching, perspiration, crocking, and light equal to or better than the standard sample. When no standard sample is established or when the standard sample is not a reference for colorfastness, the dyed cloth shall show "good" colorfastness to combined laundering and bleaching, perspiration, and light, and no more crocking than Munsell Neutral Value 8.5 when tested as specified in 4.4.

3.4 Physical requirements. The finished cloth shall conform to the requirements specified in table I or table II when tested as specified in 4.4.

TABLE I. Physical requirements - type I, birdseye

Class	Weight per square yard (ounces)		Width (inches (including selvage)		Yarns per inch (minimum)		Breaking strength (pounds) minimum	
	Min.	Max.	Min.	Max.	Warp	Filling	Warp	Filling
1	4.0	------	26-1/2	27-1/2	60	48	40	60
2	3.4	3.8	as specified		60	46	40	60
3	3.7	4.2	as specified		60	46	40	60

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

TABLE II. Physical requirements - type II, gauze

Weight 1/ (oz/sq.yd.)	Width (including selvages) inches		Yarns per inch (sum of warp and filling) 2/	Breaking strength (pounds) minimum	
Minimum	Min.	Max.	Minimum	Warp	Filling
3.35	39-1/2	40-1/2	74	45	25

1/ Utilizing two plys of panel.

2/ Determined on single ply of panel, but both single panels shall conform to this requirement.

3.4.1 Weave.

3.4.1.1 Type I, classes 1, 2, and 3. The cloth shall be a single layer cloth in a birdseye weave.

3.4.1.2 Type II. Type II cloth shall be a double layer gauze cloth woven in a plain interlocking-type weave. The combining, or interlocking, of the double layer to form a single layer shall be throughout the length of the cloth and at regular intervals filling-wise to form pinking bars.

3.4.1.2.1 Pinking bar. A filling-wise bar (pinking bar) 1-1/2 ± 1/2 inches wide shall be woven into the cloth at regular intervals so as to form panels of the double layer (2-ply cloth). The 1-1/2 inch pinking bars shall be made by weaving the warps of the 2-ply cloth to form a single layer cloth.

3.4.1.2.2 Panels. The panels of 2-ply cloth formed by the pinking bars shall measure 19 ± 1/2 inch in length from inside of pinking bar to inside of pinking bar.

3.4.1.2.3 Folding stripes. The supplier may, at his option, insert folding stripes. If folding stripes are used, one stripe consisting of four ends weaving as one in a group of 3 or 4 shall be positioned 13-1/2 ± 1/2 inch from one selvage. Another stripe shall be positioned 8 ± 1/2 inch from the opposite selvage. The folding stripes shall become part of the single layer pinking bars at point of intersection.

3.5 Shrinkage. The sum of the warp and filling residual shrinkage for type I, class 1, or type II cloth shall not exceed 20 percent when tested as specified in 4.4. The residual shrinkage for type I, classes 2 and 3 cloth shall not exceed 2.0 percent in the warp and filling directions when tested as specified in 4.4.

3.6 Absorbency. Type I, class 1 and type II cloth shall show a minimum absorption of 80 percent when tested as specified in 4.4. Type I, classes 2 and 3 cloth shall show a minimum absorption of 65 percent when tested as specified in 4.4.

3.7 Finish.

3.7.1 Nonfibrous materials. The starch and protein content including chloroform-soluble and water-soluble material of the finished cloth shall not exceed 2.0 percent when tested as specified in 4.4 except that the determination for type I, class 3 shall be prior to dyeing.

3.8 Length and put-up. Unless otherwise specified (see 6.2), the cloth shall be furnished in continuous lengths, each not less than 40 yards (see 6.7). Each length shall be put up on full width rolls as specified in PPP-P-1134.

3.8.1 Pieces. Pieces of type II cloth shall begin and end with a pinked edge located in the middle of the pinking bar.

3.9 Fiber identification. Each roll shall be labeled, ticketed, or invoiced for fiber content in accordance with the Rules and Regulations Under the Textile Fiber Products Identification Act.

3.10 Workmanship. The finished cloth shall conform to the quality established by this specification. The demerit points per 100 square yards, when calculated as specified in section 4, shall not exceed the established maximum point value.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.1.1 Certificate of compliance. Where certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

4.2 Inspection. Inspection shall be in accordance with the provisions set forth in MIL-STD-105, except where otherwise indicated.

4.2.1 Component and material inspection. In accordance with 4.1 above, components and materials shall be tested in accordance with all the requirements of referenced specifications, drawings and standards unless otherwise excluded, amended, modified or qualified in this specification or applicable procurement documents.

4.2.2 Yard-by-yard examination. The required yardage of each piece shall be examined on the face side only except that on type II the sides shall be alternated with each piece so that all defects, as defined in section I of Fed. Std. No. 4, which are clearly noticeable at normal inspection distance (3 feet) shall be scored and assigned demerit points as listed in 4.2.2.1 with the following exceptions: coarse yarns and jerked-in filling, glossary numbers 2, 3, and 26 will not be scored as defects. Only those slubs and knots which exceed the maximum acceptable limits shown for each in figure 1 shall be scored. No linear yard (increments of 1 yard on the measuring device of the inspection machine) shall be penalized more than four points. The sample unit for this examination shall be one linear yard. The sample size shall be 750 linear yards, regardless of lot size. The sample yardage shall be examined from 25 pieces taken from 25 containers. An approximately equal number of yards shall be examined in each piece of the sample. The lot shall be unacceptable if the points per hundred square yards exceed the following values:

45.00 points for type I, classes 1 and 2; and type II cloth.
40.00 points for type I, class 3 cloth.

Point computation shall be as follows:

$$\frac{\text{Total points scored in sample size} \times 3600}{\text{Contracted width of cloth (inches)} \times 750} = \text{Points per 100 square yards}$$

4.2.2.1 Demerit points. Demerit points shall be assigned as follows:

For defects up to 3 inches in any dimension	- one point
For defects exceeding 3 inches, but not exceeding 6 inches in any dimension	- two points
For defects exceeding 6 inches, but not exceeding 9 inches in any dimension	- three points
For defects exceeding 9 inches in any dimension	- four points

Note: The following defects, when present, shall be scored four points for each yard in which they occur:

Selvage curled, folded, rolled, or slack continuously or intermittently throughout the piece.

Over-all uncleanliness, objectionable odor.

Uneven weaving throughout the piece.

Not bleached white (type I, classes 1 and 2, and type II).

Poor dye penetration, mottled, streaky, or cloudy (type I, class 3).

Width not within specified tolerance.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

Length of panels not within specified tolerance (type II).

Width of pinking bar not within tolerance (type II).

Folding stripes, if present, not in specified locations (type II).

4.2.3 Examination for length.

4.2.3.1 Individual pieces. During the yard-by-yard examination, each piece in the sample shall be examined for length. Any length found to be less than the minimum specified or more than two yards less than the length marked on the ticket shall be considered a defect with respect to length. For type II, any piece which does not begin or end with a pinked edge in the middle of the pinking bar shall also be considered a defect. The lot shall be unacceptable if two or more pieces in the sample are defective in respect to length.

4.2.3.2 Total yardage in sample. The lot shall be unacceptable if the total of the actual length of pieces in the sample is less than the total of the lengths marked on the tickets.

4.2.4 Examination for noncompliance with the Textile Fiber Products Identification Act. During the yard-by-yard examination, each piece in the sample shall be examined for conformance to the Textile Fiber Products Identification Act. Each piece not labeled in accordance with this act shall be considered a defect. The lot shall be unacceptable if two or more of these defects occur.

4.3 Examination of preparation for delivery requirements. An examination shall be made in accordance with the provisions of PPP-P-1134 to determine that packaging, packing, and marking requirements of section 5 of this specification are complied with.

4.4 Testing of the end item. The methods of testing specified in CCC-T-191, wherever applicable, and as listed in table III, shall be followed. Except as otherwise indicated, the physical and chemical values specified in section 3 apply to the average of the determinations made on a sample unit for test purposes as specified in the applicable test methods. The sample unit shall be 3 continuous yards, full width, of the finished cloth. The lot shall be unacceptable if one or more sample units fail to meet any test requirements specified. All test reports shall contain the individual values utilized in expressing the final results. The sample size (number of sample units) shall be in accordance with the following:

Lot size (yards)	Sample size
800 or less	2
801 up to and including 22,000	3
22,001 and over	5

TABLE III. Test methods

Characteristic	Requirement paragraph	Test method
Material, cotton	3.2.1	1/
Discoloration	3.3.1	5660 2/ 3/
Sulfur content	3.3.2	2020
Colorfastness to		
Combined laundering and bleaching	3.3.4	5605
Perspiration	3.3.4	5680
Light	3.3.4	5660
Crocking	3.3.4	5651
Weight	3.4	5041 4/

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

TABLE III. Test methods (cont'd.)

Characteristic	Requirement paragraph	Test method
Yarns per inch:		
Warp	3.4	5050 5/
Filling	3.4	5050 5/
Breaking strength:		
Warp	3.4	5100 6/
Filling	3.4	5100 6/
Weave	3.4.1	Visual 3/
Shrinkage in laundering:		
Warp	3.5	5550 7/
Filling	3.5	5550 7/
Absorbency	3.6	5502
Nonfibrous materials	3.7.1	2611

1/ A certificate of compliance is required and will be acceptable for the requirements specified.

2/ Method 5660 shall be used, except that exposure of the specimen and standard sample shall be for 20 standard fading hours. Any specimen showing discoloration less than or equal to that of the standard sample shall be rated "satisfactory". Any specimen showing discoloration greater than that of the standard sample shall be rated "unsatisfactory". When no standard sample is available, the discoloration of the specimen shall be rated "fair" when there is an appreciable but not objectionable change in color.

3/ One determination shall be made from each sample unit and the results reported as "pass" or "fail".

4/ For type II - determination to be made on the two layers of body cloth and should not include folding stripes if present.

5/ For type II - determination to be made on single layer of panel, specimens shall be sampled from both layers and must meet the requirement. The specimens should not include folding stripes if present.

6/ For type II - determination to be made of double layer body cloth (not single ply). All tests must be clear of, and must not include the pinking bars or folding stripes, if present.

7/ The specimens of type II cloth shall be a complete diaper, double layer, and shall be cut the width of the cloth through the middle of the respective pinking bars, leaving a pinked edge. The samples shall be dried prior to pressing.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A or C as specified (see 6.2 and 6.2.1).

5.1.1 Levels A and C. The cloth, put up on rolls, shall be packaged in accordance with the applicable requirements of PPP-P-1134.

5.2 Packing. Packing shall be level A, B or C as specified (see 6.2 and 6.2.1).

5.2.1 Levels A, B and C. Cloth of one type only shall be packed in accordance with the applicable requirements of PPP-P-1134.

5.3 Marking. In addition to any special marking required by the contract or order, shipments shall be marked in accordance with the applicable requirements of PPP-P-1134.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

6. NOTES

6.1 Intended use. The cloths covered by this specification are intended for the following:

(a) Type I, class 1 cloth and type II cloth are intended for use in the fabrication of infant diapers.

(b) Type I, classes 2 and 3 cloths are intended for use in the fabrication of coveralls, cooling, toxicological agents protective and rocket fuel handlers. Class 2 is used by the Air Force and class 3 is used by the Army.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

(a) Title, number, and date of this specification.
(b) Type and class of cloth required (see 1.2.1).
(c) Color of cloth required (see 3.3.2).
(d) Width required (see 3.4).
(e) Minimum length, if other than specified (see 3.8).
(f) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).

6.2.1 In the preparation of contracts or orders, it must be noted that various options, choices, and alternatives, as indicated in PPP-P-1134, may be exercised in the preparation for delivery of cloth.

6.3 Level B packaging and packing should be used by ordering agencies only when shipment is known to be made to a holding supply depot or warehouse from which partial shipments will be made to ultimate consumers.

6.4 Standard sample. For access to standard sample, address the procuring office issuing the invitation for bids.

6.5 Dyestuff formulation.

6.5.1 Olive Green 107. A suggested but not mandatory dyestuff formulation for Olive Green 107 (OG 107) is as follows:

New color index

Vat Black 25, CI 69525

Vat Green 3, CI 69500

Vat Green 8, CI 71050

Shadded with either or both of the following:

Vat Brown 3, CI 69015

Vat Yellow of suitable fastness

The redness of shade should result from the predominant use of the main colors specified and not from the shading colors.

6.6 It is to be noted that some of the referenced test methods, new and revised, are contained in Int. Amendment-5 of CCC-T-191b.

6.7 For GSA procurement, rolls or bolts shall be 40 yards in length with a tolerance of within plus or minus 2 yards.

MILITARY INTEREST:

Custodians:

Army-GL
Navy-SA
Air Force-82

Preparing activity:

Army-GL

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

Review activities:

Army-MD
Navy-SA
Air Force-82,85

User activity:


DSA-DM

Civil agencies interest:


COM-NBS
GSA-FSS
HEW
INT
VA-DMS

Review and user information is current as of the date of this document. For future coordination of changes to this document, draft circulation should be based on the information in the current Federal Supply Classification Listing of DOD Documents.

Slub



Slub (Loose, Thick)



Lump or Knot (Fuzz)




Figure 1. Limits of acceptability

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents referenced herein.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

"to detach this form, cut along this line"

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 119-R004

INSTRUCTIONS

This sheet is to be filled out by personnel either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity.

SPECIFICATION

Cloth, Birdseye and Gauze: Cotton CCC-C-425c

ORGANIZATION	CITY AND STATE

CONTRACT NO.	QUANTITY OF ITEMS PROCURED	DOLLAR AMOUNT
		$

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO IF "YES", IN WHAT WAY?

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity)*	DATE

DD FORM 1 OCT 64 1426

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE ARMY
U. S. Army Natick Laboratories
Natick, Massachusetts 01760

POSTAGE AND FEES PAID
DEPARTMENT OF THE ARMY

OFFICIAL BUSINESS

Commanding General
U. S. Army Natick Laboratories
ATTN: AMXRES-QS
Natick, Massachusetts 01760

FOLD

"to detach this form cut along this line"

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.