CCC-C-435
MAY 24, 1957
SUPERSEDING
Fed. Spec. CCC–S–276
February 5, 1935

FEDERAL SPECIFICATION

CLOTH, COTTON, SHEETING (LAUNDRY COVER CLOTH)

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope.—This specification covers the requirements of unbleached, laundry, cotton sheeting used as surface covering on flatwork ironers.

1.2 Classification.

1.2.1 *Type and classes.*—The cotton cloth sheeting covered by this specification shall be of one type and two classes as specified (see 6.1):

Class 1.—72 inches wide.

Class 2.—90 inches wide.

2. APPLICABLE SPECIFICATIONS AND STANDARDS

2.1 The following specifications and standards, of the issues in effect on date of invitation for bids, form a part of this specification:

Federal Specifications:

CCC–T–191—Textile Test Methods.

PPP–P–31 — Preservation, Packaging, Packing, and Marking of Material; and Shipping Instructions (Domestic Shipment and Storage).

Federal Standards:

No. 4—Glossary of Fabric Imperfections.

No. 102—Preservation, Packaging, and Packing Levels.

(Activities outside the Federal Government may obtain copies of Federal Specifications and Standards as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington 25, D. C.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, Los Angeles, Seattle, and Washington, D. C.

(Federal Government activities may obtain copies of Federal Specifications and Standards and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Specification:

MIL–P–12438—Packaging and Packing of Cotton Fabrics (except Cotton Duck).

Military Standards:

MIL–STD–105 — Sampling Procedures and Tables for Inspection by Attributes and Appendix Thereto.

MIL–STD–129—Marking for Shipment and Storage.

(Copies of Military specifications and standards required by contractors in connection with specific procurement functions should be obtained from the procuring agency or as directed by the contracting officer.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

3. REQUIREMENTS

3.1 Material.—The cotton used in the manufacture of the yarn shall be of suitable length of staple and grade to meet the requirements of this specification. The cotton shall be thoroughly cleaned, carded, drawn, evenly spun and twisted into a 2-ply yarn for both the warp and filling.

3.2 Color.—The cloth shall be unbleached.

3.3 Physical requirements.—The finished cloth shall conform to the requirements shown in table I.

TABLE I.—*Physical requirements*

Weight per square yard	Yarns per inch (minimum)		Breaking Strength (grab method) (minimum)	
	warp 2 ply	filling, 2 ply	warp	filling
Ounces			*Pounds*	*Pounds*
6.9 min.... 7.3 max.	56	58	85	100

3.4 Width Tolerance.—The width tolerance for the specified classes shall be as follows:

Class 1—plus 1½ inches, minus ¾ inch.

Class 2—plus 1¾ inches, minus 1 inch.

3.5 Weave.—The weave shall be plain.

3.6 Nonfibrous material.—The cloth shall contain not more than 5.0 percent total nonfibrous material when tested as specified in 4.4.

3.7 Length.—The cloth shall be furnished in either bolts or rolls, and shall be in one continuous piece of not less than 50 yards unless otherwise specified.

3.8 Tickets.—Each bolt or roll shall have a ticket attached to the selvage at one end with not finer than five-fold cotton string doubled to not less than 8 inches long. The ticket shall be made of cardboard not less than 0.020 inch in thickness and the color shall be white or light in intensity to permit easy reading of printed or penciled markings. The finish on the cardboard shall be suitable for pencil markings. The ticket shall have a reinforced eyelet for attaching the tying cord and shall be legibly printed with water-insoluble ink. Unless otherwise specified, the ticket shall contain the following information and in addition, the ticket shall have sufficient blank space at the bottom for the inspector's stamp:

Nomenclature
Class_____. Width_____
Stock number
Contractor's name
Contract number and date
Contractor's piece number
Specification number and date
Name of contracting office
Gross yards
Net yards

3.9 Workmanship.—The finished cloth shall be clean, evenly woven and shall conform to the quality and grade of product established by this specification. The occurrence of defects shall not exceed the applicable acceptance quality levels.

4. SAMPLING, INSPECTION, AND TEST PROCEDURES

4.1 General.—The sampling, inspection and testing provisions contained in this section are applicable to inspection. Sampling, inspection and testing for components or materials described shall be in accordance with this specification and with subsidiary specifications referenced herein to the extent applicable, except that this specification shall govern in the event of conflict.

4.2 Pre-acceptance inspection.—Not required.

4.3 Inspection for acceptance.—Except when otherwise specified by Civilian Government agencies, inspection shall be in accordance with the provisions of Military Standard MIL–STD–105. When MIL–STD–105 specifies

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

an action by the Government, it shall, at the option of the Government, be performed either by the Government or by the contractor under the supervision of the Government inspector.

4.3.1 *Inspection of the end item.*—Defects found during this examination shall be classified in accordance with list shown in 4.3.1.1, 4.3.1.2 and 4.3.1.3. The Government reserves the right to require examination for any defect not included herein and to classify such defects in accordance with the definitions contained in Military Standard MIL–STD–105 and Appendix.

4.3.1.1 *Yard by yard examination.*—The defects listed shall be counted regardless of their proximity to each other, except where two or more defects represent a single local condition of the cloth, in which case only the more serious defect shall be counted. A continuous defect shall be counted as one defect for each warpwise yard or fraction thereof in which it occurs. The unit of product for this examination shall be 1 linear yard.

Glossary No. Fed. Std. No. 4	Defect	Classification	
		Major	Minor
90, 91, 92, 55, 56	Hole, cut, tear or break—any including selvage.	X	
78	Smash, any	X	
11, 33	Broken or missing yarns:		
	Three or more contiguous, regardless of length.	X	
	Two contiguous, 2 inches or more missing.	X	
	Two contiguous, less than 2 inches missing or single, 2 inches or more missing.		X
9	Fine filling bar or light place—Clearly noticeable.	X	
9, 12, 35	Open place, crack or hitch-back—opening at widest point four or more filling yarn diameters or sequence of opening resulting in a weak place.	X	
13, 14	Floats or skips, multiple, ½ inch or more in combined warp and filling direction.	X	
	Multiple, less than ½ inch in combined warp and filling directions, or single floating over 2 inches or more.		X
1, 2, 4, 10, 26	Heavy filling bar, heavy place, coarse or additional yarns, clearly noticeable.		X
3, 5, 27, 77	Slough-off, jerked in filling, slubs, slugs, gouts in either direction, three or more times the thickness of normal yarns.		X
6, 7, 28, 29	Knots, oversize or kinks, multiple.		X
48	Selvage curled, folded or rolled.		X
51	Selvage scalloped — more than ½ inch from edge of cloth.		X
93	Baggy, ridgy or wavy cloth, clearly noticeable.	X	
89	Tender or weak place	X	
79	Abrasion mark, clearly noticeable, but not resulting in a weak place.		X
59, 61	Crease or wrinkle, embedded, clearly noticeable.		X
83	Trash, any noticeable accumulation.		X
74, 75, 76	Spot, stain or streak—clearly noticeable.	X	

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

4.3.1.2 *Overall examination.*—The unit of product for this examination shall be one piece of cloth.

Defects

Overall uncleanness.
Objectionable odor.
Uneven weaving, clearly noticeable.
Width less than specified.
Selvage curled, folded, rolled, tight or slack, continuously or intermittently throughout the piece.

4.3.1.3 *Examination for length of individual pieces.*—The piece shall be examined for gross length. Any gross length found to be less than the specified minimum length, or any gross length found to be more than 2 yards below the gross length marked on the piece ticket shall be considered as a defect with respect to length. The unit of product for this examination shall be one piece.

4.3.1.4 *Total yardage in sample.*—The lot shall be unacceptable if the total of the actual gross lengths of pieces in the sample is less than the total of the gross lengths marked on piece tickets.

4.3.1.5 *Acceptable quality levels.*—Acceptable quality levels shall be as follows:

a. For yard by yard examination (4.3.1.1)—1.5 major defects and 6.5 total defects per 100 units (yards).

b. For overall examination (4.3.1.2) 1.0 defects per 100 units (pieces)

c. Examination for length of individual pieces (4.3.1.3) 1.0 defects per 100 units (pieces)

4.3.1.6 *Inspection levels.*

a. Yard by yard examination (4.3.1.1)—Level III of table III of Military Standard MIL–STD–105. The lot size shall be expressed in units of 1 yard each. An approximately equal number of yards shall be examined from each piece in the sample. The number of pieces to be drawn shall be computed as follows:

$$\frac{\text{Yards in sample}}{35}$$

b. Overall examination (4.3.1.2).—The pieces examined shall be those selected for yard by yard examination.

c. Examination for length of individual pieces (4.3.1.3).—The pieces examined shall be those selected for yard-by-yard examination.

4.4 Testing of the end item.—The methods of testing specified in Federal Specification CCC–T–191, wherever applicable, and as listed in table II shall be followed. The physical and chemical values specified in section 3 apply to the average of the determinations made on a unit of product for test purposes as specified in the applicable test method. Unless otherwise specified by civilian agencies, the acceptable quality level for each characteristic shall be 6.5 and the inspection level shall be L-1, table VII of Appendix to Military Standard MIL–STD–105. The unit of product shall be 1 continuous yard, full width of the finished cloth.

TABLE II.—*Test Methods*

Characteristic	Test Method
Weave	Visual
Yarns per inch	5050
Yarn ply	Visual
Weight per square yard	5041
Breaking strength	5100
Non fibrous material[1]	2611

[1] The specimen shall be spot-tested for starch and protein prior to proceeding with paragraph 4.4 of test method. If negative, procedure in paragraph 4.4 shall be omitted.

5. PREPARATION FOR DELIVERY

5.1 Packaging.—(For definitions and levels see 6.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

5.1.1 *Level A.*—The cloth shall be packaged in accordance with the applicable requirements of Military Specification MIL–P–12438.

5.1.2 *Level C.*—The cloth shall be packaged in accordance with the manufacturer's normal practice.

5.2 **Packing.**—(For definitions and levels see 6.2).

5.2.1 *Level A.*—The cloth of one class only, packaged as specified in 5.1.1, shall be packed in accordance with the applicable requirements for overseas shipment of Military Specification MIL–P–12438.

5.2.2 *Level B.*—The cloth of one class only, packaged as specified in 5.1.1, shall be packed in accordance with the applicable requirements for domestic shipment of Military Specification MIL–P–12438.

5.2.3 *Level C.*—The cloth of one class only, packaged as specified in 5.1.2, shall be packed in a manner acceptable to common carriers for safe transportation to point of destination specified in shipping instructions at the lowest transportation rate for such supplies.

5.3 **Marking.**

5.3.1 *Civilian agencies.* — Shipments shall be marked in accordance with the applicable requirements of Federal Specification PPP–P–31.

5.3.2 *Military agencies.*—Shipments shall be marked in accordance with the applicable requirements of Military Specification MIL–P–12438.

6. NOTES

6.1 **Ordering data.**—Procurement documents should specify the following:

a. Title, number, and date of this specification.
b. Class of cloth required (see 1.2).
c. Any exception to length of pieces (see 3.7).
d. Any exception to ticket information (see 3.8).
e. Any exceptions by Civilian Gov. agencies to use of Military Standard MIL–STD–105 (see 4.3).
f. Any exceptions by Civilian Gov. agencies to acceptable quality level (see 4.4).
g. Whether the cloth is to be packaged and packed for level A, B, or C.

6.2 Federal Standard No. 102 shall be referred to for definitions and applications of the various levels of packaging protection for supplies and equipment.

6.3 **Transportation description.**—The transportation description applicable to this item is:

Cotton piece goods, in the original piece (Sheeting).
Carload minimum weight — any quantity.
Cotton piece goods, not otherwise indexed.
Truckload minimum weight — any quantity.

Notice. — When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility, nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded by implication or otherwise, as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

MILITARY INTERESTS:
Army—Q
Navy—S
Air Force.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.