CCC-C-435c
August 18, 1966

SUPERSEDING
Fed. Spec. CCC-C-435b
November 1, 1962
(See section 6)

FEDERAL SPECIFICATION

CLOTH, SHEETING, COTTON (LAUNDRY COVER CLOTH)

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 This specification covers the requirements for one type of unbleached, laundry, cotton sheeting (see 6.3).

2. APPLICABLE DOCUMENTS

2.1 Specifications and standards. The following specifications and standards, of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

Federal Specifications:

CCC-T-191—Textile Test Methods.
PPP-P-51—Packaging, Packing, and Marking of Textile Fabrics (Woolens, Worsteds, Cottons, Silks, and Synthetics).

Federal Standard:

Fed. Std. No. 4—Glossary of Fabric Imperfections.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, D.C. 20402.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Washington, D.C., Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, Los Angeles, and Seattle, Wash.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standard:

MIL-STD-105—Sampling Procedures and Tables for Inspection by Attributes.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publication. The following document forms a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation of bids or request for proposal shall apply.

Rules and Regulations Under the Textile Fiber Products Identification Act.

(Copies may be obtained without charge from the Federal Trade Commission, Washington, D.C., 20580.)

3. REQUIREMENTS

3.1 Material.

3.1.1 *Yarn.* The yarn shall be made from cotton which has been cleaned, carded, drawn, and spun (see 4.4).

3.2 Color. The cloth shall be unbleached.

3.3 Physical requirements. The finished

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

cloth shall conform to the requirements shown in table I when tested as specified in 4.4.

TABLE I. *Physical requirements*

Weight per square yard (minimum)	Yarns per inch (minimum)		Breaking strength (minimum)	
	Warp	Filling	Warp	Filling
Ounces			*Pounds*	*Pounds*
6.9	56	52	85	100

3.3.1 *Weave.* The weave shall be plain.

3.3.2 *Width.* The width shall be as specified (see 6.2), and shall be the minimum acceptable width inclusive of selvages.

3.4 **Nonfibrous material.** The starch and protein content including chloroform-soluble and water-soluble material of the finished cloth shall not exceed 13.0 percent when tested as specified in 4.4.

3.5 **Length and put-up.** Unless otherwise specified (see 6.2), the cloth shall be furnished in continuous lengths, each not less than 40 yards. Each length shall be put up in folded pieces or rolls as specified in PPP-P-51.

3.6 **Fiber identification.** Each piece or roll of cloth shall be labeled, ticketed, or invoiced for fiber content in accordance with the Rules and Regulations Under the Textile Fiber Products Identification Act.

3.7 **Workmanship.** The finished cloth shall conform to the quality established by this specification. The points per 100 square yards, when calculated as specified in section 4, shall not exceed the established maximum point value.

4. QUALITY ASSURANCE PROVISIONS

4.1 **Responsibility for inspection.** Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.2 **Examination of the end item.** Examination of the end item shall be in accordance with the provisions of MIL-STD-105 and 4.2.1 through 4.2.3.

4.2.1 *Yard-by-yard examination.* The required yardage of each piece or roll shall be examined on the face side, and all defects as defined in section I of Fed. Std. No. 4, which are clearly noticeable at normal inspection distance (3 feet) shall be scored and assigned demerit points as listed in 4.2.1.1, except that only those slubs and knots which exceed the maximum acceptable limits shown for each in figure 1 shall be scored. None of the 30 continuous linear yards, (folded yards, or increments of one yard on the measuring device of the inspection machine) selected for examination from any one piece within the sample, shall be penalized more than four points. The sample unit for this examination shall be one linear yard. The sample size shall be 750 yards, regardless of lot size. The sample yardage shall be examined from 25 pieces or rolls taken from 25 containers. An approximately equal number of yards shall be examined in each piece or roll of the sample. The lot shall be unacceptable if the points per hundred square yards exceed 35.0 points. Point computation shall be as follows:

$$\frac{\text{Total points scored in sample size} \times 3600}{\text{Sample size (yards)} \times \text{contracted width of material (inches)}} = \text{Points per 100 square yards}$$

4.2.1.1 *Demerit points.* Demerit points shall be assigned as follows:

For defects 3 inches or less in any dimension	—one point.
For defects exceeding 3 inches but not exceeding 6 inches in any dimension	—two points

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

For defects exceeding 6 inches, but not exceeding 9 inches in any dimension —three points.
For defects exceeding 9 inches in any dimension —four points.

The following defects, when present, shall be scored four points for each yard in which they occur:

Baggy, ridgy, or wavy cloth.
Objectionable odor.
Color not as specified.
Width less than specified.

4.2.2 *Examination for length.*

4.2.2.1 *Individual pieces or rolls.* During the yard-by-yard examination, each piece or roll in the sample shall be examined for length. Any length found to be less than the minimum specified or more than two yards less than the length marked on the ticket shall be considered a defect with respect to length. The lot shall be unacceptable if two or more pieces or rolls in the sample are defective in respect to length.

4.2.2.2 *Total yardage in sample.* The lot shall be unacceptable if the total of the actual lengths of pieces or rolls in the sample is less than the total of the lengths marked on the tickets.

4.2.3 *Examination for noncompliance with the Rules and Regulations Under the Textile Fiber Products Identification Act.* During the yard-by-yard examination, each piece or roll in the sample shall be examined for conformance to the Rules and Regulations Under the Textile Fiber Products Identification Act. Each piece or roll not labeled in accordance with this act shall be a defect. The lot shall be unacceptable if two or more of these defects occur.

4.3 **Examination of preparation for delivery requirements.** An examination shall be made in accordance with the provisions of PPP-P-51 to determine that packaging, packing, and marking requirements of section 5 of this specification are complied with.

4.4 **Testing methods.** The methods of testing specified in CCC-T-191, wherever applicable, and as listed in table III shall be followed. Except as otherwise indicated, the physical and chemical values specified in section 3 apply to the average of the determinations made on a sample unit for test purposes as specified in the applicable test method. All test reports shall contain the individual values utilized in expressing the final results. The sample unit shall be 1 continuous yard, full width of the finished cloth. The sample size shall be as shown in table II. The lot size shall be expressed in units of 1 yard. The lot shall be unacceptable if one or more units fail to meet any requirement specified.

TABLE II. *Sampling for testing*

Lot size (yards)	Sample size
800 or less	2
801 up to and including 22,000	3
22,001 and over	5

TABLE III. *Methods of testing*

Characteristic	Requirement paragraph	Test method
Material (yarn)	3.1.1	[1]
Weave	3.3.1	Visual[2]
Yarns per inch	3.3	5050
Weight	3.3	5041
Breaking strength	3.3	5100
Nonfibrous material	3.4	2611

[1] The supplier shall submit a certificate of compliance for this characteristic. When required, the certificate shall be accompanied by actual test, inspection, or other verifiable quality data.

[2] One determination shall be made on each sample unit and the result reported as "pass" or "fail."

5. PREPARATION FOR DELIVERY

5.1 **Packaging.** Packaging shall be level A or C, as specified (see 6.2 and 6.2.1).

5.1.1 *Levels A and C.* The cloth, put up as specified, shall be packaged in accordance with the applicable requirements for class 3 fabrics of PPP-P-51.

5.2 **Packing.** Packing shall be level A, B, or C, as specified (see 6.2 and 6.2.1).

5.2.1 *Levels A, B, and C.* The cloth shall

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

be packed in accordance with the applicable requirements of PPP-P-51.

5.3 Marking. In addition to any special marking required by the contract or order, shipments shall be marked in accordance with the applicable requirements of PPP-P-51.

6. NOTES

6.1 Intended use. The cloth covered by this specification is intended for use as surface covering on flatwork ironers.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

(*a*) Title, number, and date of this specification.
(*b*) Width of cloth required (see 3.3.2).
(*c*) Length required if other than specified (see 3.5).
(*d*) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).

6.2.1 In the preparation of contracts or orders, it must be noted that various options, choices, and alternatives as indicated in PPP-P-51 may be exercised in the preparation for delivery of this commodity.

6.3 Supersession data. Comparison of classes as pertains to CCC-C-435b and CCC-C-435c is as follows:

CCC-C-435b	CCC-C-435c
Class 1	Deleted[1]
Class 2	Deleted[1]

[1] The minimum width inclusive of selvage is now as specified (see 3.3.2).

MILITARY CUSTODIANS:

Army—GL
Navy—SA
Air Force—11

Review activities:

Navy—SA, MC
Air Force—11, 67

User activity:

Navy—CG


Preparing activity:

Army—GL


Review and user information is current as of the date of this document. For future coordination of changes to this document, draft circulation should be based on the information in the current Federal Supply Classification Listing Of DOD Standardization Documents.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

Slub



Slub (Loose, Thick)



Lump or Knot (Fuzz)




FIGURE 1. (Limits of acceptability)

Orders for this publication are to be placed with acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents referenced herein.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 119-R004

INSTRUCTIONS

This sheet is to be filled out by personnel either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity.

SPECIFICATION
Cloth, Sheeting, Cotton (Laundry Cover Cloth) CCC-C-435c

ORGANIZATION	CITY AND STATE

CONTRACT NO.	QUANTITY OF ITEMS PROCURED	DOLLAR AMOUNT
		$

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO IF "YES", IN WHAT WAY?

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity)*	DATE

DD FORM 1 OCT 64 1426

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE ARMY
U. S. Army Natick Laboratories
Natick, Massachusetts 01762

POSTAGE AND FEES PAID
DEPARTMENT OF THE ARMY

OFFICIAL BUSINESS

Commanding General
U. S. Army Natick Laboratories
ATTN: AMXRE-SS
Natick, Massachusetts 01762

FOLD

"To detach, bend cut along this line"

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.