CCC-C-435D
August 24, 1971
SUPERSEDING
Fed. Spec. CCC-C-435C
August 18, 1966

# FEDERAL SPECIFICATION

## CLOTH, SHEETING, COTTON (LAUNDRY COVER CLOTH)

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE

1.1 This specification covers the requirements for one type of unbleached, laundry, cotton sheeting.

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

Federal Specification:

PPP-P-1134 - Packaging and Packing of Cotton and Cotton-Synthetic Fiber Blend Fabrics (Excluding Duck Fabrics).

Federal Standards:

Fed. Std. No. 4 - Glossary of Fabric Imperfections.
Fed. Std. No. 191 - Textile Test Methods.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, D. C. 20402.

FSC 8305

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers, at the General Services Administration Regional Offices in Boston, New York, Washington, D.C., Atlanta, Chicago, Kansas City, Mo., Ft. Worth, Denver, San Francisco, Los Angeles, and Seattle, Washington.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standard:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publication. The following document forms a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply:

Rules and Regulations Under the Textile
Fiber Products Identification Act.

(Copies may be obtained without charge from the Federal Trade Commission, Washington, D.C., 20580.)

3. REQUIREMENTS

3.1 Material.

3.1.1 Yarn. The yarn shall be made from cotton which has been carded, drawn, and spun (see 4.4).

3.2 Color. The cloth shall be unbleached.

3.3 Physical requirements. The finished cloth shall conform to the requirements shown in table I when tested as specified in 4.4.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

TABLE I. Physical requirements

| Weight per square yard (minimum) | Yarns per inch (minimum) | | Breaking strength (minimum) | |
|---|---|---|---|---|
| | Warp | Filling | Warp | Filling |
| Ounces | | | Pounds | Pounds |
| 6.9 | 56 | 52 | 85 | 100 |

3.3.1 Weave. The weave shall be plain.

3.3.2 Width. The width shall be as specified (see 6.2), and shall be the minimum acceptable width inclusive of selvages.

3.4 Nonfibrous material. The starch and protein content including chloroform-soluble and water-soluble material of the finished cloth shall not exceed 13.0 percent when tested as specified in 4.4.

3.5 pH. The pH value of the water extract of the finished cloth shall be not less than 5.0 nor more than 8.5 when tested as specified in 4.4.

3.6 Length and put-up. Unless otherwise specified (see 6.2), the cloth shall be furnished in continuous lengths, each not less than 40 yards. The cloth shall be put up in folded pieces or rolls as specified in PPP-P-1134.

3.7 Fiber identification. Each piece or roll of cloth shall be labeled, ticketed, or invoiced for fiber content in accordance with the Rules and Regulations Under the Textile Fiber Products Identification Act.

3.8 Face identification.- The face side of the cloth shall be identified by applying a stamping on that side of the cloth with the word "Face" at each end of the folded piece or roll.

3.9 Workmanship. The finished cloth shall conform to the quality established by this specification. The demerit points per 100 square yards, when calculated as specified in section 4, shall not exceed the established maximum point value.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.1.1 Certificate of compliance. Where certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

4.2 Inspection. Sampling for inspection shall be performed in accordance with MIL-STD-105, except where otherwise indicated hereinafter.

4.2.1 Component and material inspection. In accordance with 4.1 above, components and materials shall be tested in accordance with all the requirements of referenced specifications, drawings, and standards unless otherwise excluded, amended, modified or qualified in this specification or applicable purchase documents.

4.2.2 Examination of the end item. The examination of the end item shall be in accordance with 4.2.2.1 through 4.2.2.4.

4.2.2.1 Yard-by-yard examination. Each folded piece or roll in the sample shall be examined on the face side only. When the total yardage in the folded piece or roll does not exceed 100 yards, the entire yardage in the folded piece or roll shall be examined. When the total yardage in the folded piece or roll exceeds 100 yards, only 100 yards shall be examined. All defects, as defined in Section I of Fed. Std. No. 4, which are clearly noticeable at normal inspection distance (3 feet) shall be scored and assigned demerit points as listed in 4.2.2.1.1 except that only those slubs and knots which exceed the limits shown on figure 1 of Fed. Std. No. 4 shall be scored. No linear yard from any one folded piece or roll within the sample shall be penalized more than 4 points. The sample size shall be 20 folded pieces or rolls selected from 20 containers. The lot shall be unacceptable if the points per 100 square yards of the total yardage examined exceeds 35 points. The lot shall be unacceptable if the points per 100 square yards of two or more individual folded pieces or rolls exceeds 53 points. If the folded piece or one roll exceeds 53 points per 100 square yards, a second sample of 20 folded pieces or rolls shall be examined only for



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

individual folded piece or roll quality examination. The lot shall be unacceptable if one or more folded pieces or rolls in the second sample exceeds 53 points per 100 square yards. Point computation for lot quality and individual folded piece or roll quality shall be as follows:

$$\frac{\text{Total points scored in sample} \times 3600}{\text{Contracted width of cloth (inches)} \times \text{total yards inspected}} = \text{Points per 100 square yards}$$

4.2.2.1.1 Demerit points. Demerit points shall be assigned as follows:

| | |
|---|---|
| For defects 3 inches or less in any dimension | - one point. |
| For defects exceeding 3 inches but not exceeding 6 inches in any dimension | - two points. |
| For defects exceeding 6 inches, but not exceeding 9 inches in any dimension | - three points |
| For defects exceeding 9 inches in any dimension | - four points |

The following defects, when present, shall be scored four points for each yard in which they occur:

Baggy, ridgy, or wavy cloth.
Overall uncleanness.
Color not as specified.
Width less than specified.

4.2.2.2 Examination for length.

4.2.2.2.1 Individual folded pieces or rolls. During the yard-by-yard examination, each folded piece or roll in the sample shall be examined for length. Any length found to be less than the minimum specified or more than two yards less than the length marked on the ticket shall be considered a defect with respect to length. The lot shall be unacceptable if two or more folded pieces or rolls in the sample are defective in respect to length.

4.2.2.3 Total yardage in sample. The lot shall be unacceptable if the total of the actual lengths of folded pieces or rolls in the sample is less than the total of the lengths marked on the tickets.

4.2.2.4 Examination for compliance with the Rules and Regulations Under the Textile Fiber Products Identification Act and face marking. During the yard-by-yard examination, each folded piece or roll in the sample shall be examined for defects listed below. The lot shall be unacceptable if two or more of the following defects are present in the sample:



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

Not labeled, ticketed, or invoiced in accordance with the Rules and Regulations Under the Textile Fiber Products Identification Act.

"Face" stamping missing from either or both ends.

"Face" stamping on wrong side.

4.3 Examination of preparation for delivery requirements. An examination shall be made in accordance with the provisions of PPP-P-1134 to determine whether packaging, packing, and marking comply with the section 5 requirements.

4.4 Testing of the end item. The methods of testing specified in Fed. Std. No. 191 wherever applicable, and as listed in table III shall be followed. Except as otherwise indicated, the physical and chemical values specified in section 3 apply to the average of the determinations made on a sample unit for test purposes as specified in the applicable test method. All test reports shall contain the individual values utilized in expressing the final results. The sample unit shall be 1 continuous yard, full width of the finished cloth. The sample size shall be as shown in table II. The lot size shall be expressed in units of 1 yard. The lot shall be acceptable if one or more units fail to meet any requirement specified.

TABLE II. Sample size

| Lot size (yards) | Sample size |
|---|---|
| 800 or less | 2 |
| 801 up to and including 22,000 | 3 |
| 22,001 and over | 5 |

TABLE III. Test methods

| Characteristic | Requirement paragraph | Test method |
|---|---|---|
| Material (yarn) | 3.1.1 | 1200 1/ |
| Weave | 3.3.1 | Visual 2/ |
| Yarns per inch | 3.3 | 5050 |
| Weight | 3.3 | 5041 |
| Breaking strength | 3.3 | 5100 |
| Nonfibrous material | 3.4 | 2611 |
| pH | 3.5 | 2811 |

1/ Unless otherwise specified, a certificate of compliance shall be submitted and will be acceptable for the stated requirement.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

2/ One determination shall be made on each sample unit and the result reported as "pass" or "fail".

5. PREPARATION FOR DELIVERY

5.1 Put-up and packaging. Put-up and packaging shall be level A or C as specified (see 6.2).

5.1.1 Levels A and C. The cloth shall be put-up and packaged in accordance with the applicable requirements of PPP-P-1134.

5.2 Packing. Packing shall be level A, B, or C, as specified (see 6.2).

5.2.1 Levels A, B, and C. The cloth shall be packed in accordance with the applicable requirements of PPP-P-1134.

5.3 Marking. In addition to any special marking required by the contract or order, shipments shall be marked in accordance with the applicable requirements of PPP-P-1134.

6. NOTES

6.1 Intended use. The cloth covered by this specification is intended for use as surface covering on flatwork ironers.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

(a) Title, number, and date of this specification.
(b) Width of cloth required (see 3.3.2).
(c) Length required if other than specified (see 3.5).
(d) Selection of applicable levels of put-up, packaging and packing (see 5.1 and 5.2).



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

MILITARY CUSTODIANS:

Army - GL
Navy - SA
Air Force - 11

Review activities:

Air Force - 45, 82

User activity:

Navy - CG

Preparing activity:

Army - GL

CIVIL AGENCIES INTEREST:

AGR
COM-NBS
GSA-FSS
HEW
VA

---

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents referenced herein. Price 15 cents each.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

# SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 22-R255

INSTRUCTIONS: This sheet is to be filled out by personnel, either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments and suggestions submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or serve to amend contractual requirements.

SPECIFICATION

Cloth, Sheeting, Cotton (Laundry Cover Cloth) CCC-C-435D

ORGANIZATION

CITY AND STATE

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO *(If "yes", in what way?)*

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity - Optional)*

DATE

DD FORM 1 JAN 66 1426

REPLACES EDITION OF 1 OCT 64 WHICH MAY BE USED.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE ARMY
U. S. Army Natick Laboratories
Natick, Massachusetts 01760

POSTAGE AND FEES PAID
DEPARTMENT OF THE ARMY

U.S.MAIL

OFFICIAL BUSINESS

Commanding General
U. S. Army Natick Laboratories
ATTN: AMXRES-EQS
Natick, Massachusetts 01760

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.