CCC-C-444a
SEPTEMBER 23, 1960
SUPERSEDING
Fed. Spec. CCC-C-444
April 8, 1958

FEDERAL SPECIFICATION

# CLOTH, COTTON, JEAN, (BLEACHED)

*This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.*

## 1. SCOPE AND CLASSIFICATION

**1.1 Scope.**—This specification covers the requirements for bleached cotton jean cloth. (See 6.1.)

**1.2 Classification.**

1.2.1 *Type.* — The jean cloth covered by this specification shall be of one type.

## 2. APPLICABLE SPECIFICATIONS, STANDARDS, AND OTHER PUBLICATIONS

**2.1 Specifications and standards.**—The following specifications and standards, of the issues in effect on date of invitation for bids, form a part of this specification to the extent specified herein.

*Federal Specifications:*

CCC–T–191 — Textile Test Methods.
PPP–P–51 — Packaging, Packing and Marking of Textile Fabrics (Woolens, Worsteds, Cottons, Silks and Synthetics).

*Federal Standards:*

Fed. Std. No. 4 — Glossary of Fabric Imperfections.
Fed. Std. No. 102 — Preservation, Packaging, and Packing Levels.
Fed. Std. No. 123—Marking for Domestic Shipment (Civilian Agencies).

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications, Standards, and Handbooks and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington 25, D. C.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, Los Angeles, Seattle, and Washington, D. C.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications, Standards, and Handbooks from established distribution points in their agencies.)

*Military Standards:*

MIL–STD–105 — Sampling Procedures and Tables for Inspection by Attributes.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

**2.2 Other publications.** — The following document forms a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids shall apply.

Textile Fiber Products Identification Act.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

(Copies may be obtained, free of charge, from the Federal Trade Commission, Washinton 25, D. C.)

## 3. REQUIREMENTS

### 3.1 Material.

**3.1.1** *Yarn.* — The cotton used in the manufacture of the yarn shall be cleaned, carded, drawn and evenly spun.

**3.2 Physical requirements.** — The finished fabric shall conform to the requirements shown in table I when tested as specified in 4.4.

**3.2.1** *Width.* — The width shall be as specified and shall be the minimum acceptable width inclusive of selvages (see 6.2).

**3.3 Finish.** — The cloth shall be closely singed, desized, and bleached. Residual size, finishing, or nonfibrous material shall not exceed 2 percent when tested as specified in 4.4.

**3.4 Shrinkage.**—The cloth shall be preshrunk and shall not shrink more than 1 percent in either the direction of the warp or filling when tested as specified in 4.4. The preshrinking process used shall not be identified on the cloth, the ticket, or on the package.

**3.5 Length.**—Unless otherwise specified, the cloth shall be in one continuous length of not less than 50 yards and shall be put up in folded pieces as specified in Federal Specification PPP–P–51.

**3.6 Labeling.**—Each piece, or roll, shall be labeled, ticketed, or invoiced in accordance with the Rules and Regulations of the Textile Fiber Products Identification Act dated March 3, 1960.

**3.7 Workmanship.** — The cloth shall conform to the quality and grade of product established by this specification, and the occurrence of defects shall not exceed the levels set by the applicable acceptable quality levels.

## 4. SAMPLING, INSPECTION, AND TEST PROCEDURES

**4.1 Contractor's inspection responsibility.** —Unless otherwise specified, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own or any other inspection facilities and services acceptable to the Government. Inspection records of the examination and tests shall be kept complete and available to the Government as specified in the contract order. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

**4.2 Examination of the end item.**—Except when otherwise specified by Civil Govern-

TABLE I.—*Physical requirements*

| Weight per square yard Minimum | Yarns per inch (Minimum) | | Breaking strength (grab method) (Minimum) | | Weave |
|---|---|---|---|---|---|
| | Warp | Filling | Warp | Filling | |
| *Ounces* | | | *Pounds* | *Pounds* | |
| 4.7 | 98 | 60 | 85 | 48 | $\frac{2}{1}$ twill |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

ment agenies, inspection shall be in accordance with the provisions of Military Standard MIL–STD–105 except where otherwise indicated. Defects found during the examination shall be classified in accordance with list shown in 4.2.1, 4.2.2, and 4.2.3.

4.2.1 *Yard-by-yard examination.* — The required yardage of each piece shall be inspected on the face and visual defects classified as listed. The defects found shall be counted regardless of their proximity to each other except where two or more defects represent a single local condition of the cloth, in which case only the more serious defect shall be counted. A continuous defect shall be counted as one defect for each warpwise yard or fraction therof in which it occurs. The unit of product shall be 1 linear yard. The acceptable quality level (AQL) shall be 1.5 major and 6.5 total defects per hundred units. The sample size shall be based upon inspection level II of Military Standard MIL–STD–105. The lot size shall be expressed in units of 1 yard each. The number of pieces from which the sample is to be selected shall be in accordance with table II of this specification. An approximately equal number of yards shall be examined in each piece of the sample.

4.2.2 *Overall examination.* — Each defect listed shall be counted not more than once in each piece examined. The unit of product for this examination shall be one piece. The sample size (number of pieces selected as sample) for this examination and the acceptance number (number of defects acceptable) shall be as shown in table II. The examination shall be conducted for the defects listed below:

*Defects*

Width less than specified.
Selvage curled, doubled, folded, or rolled extending continuously or intermittently throughout the piece.
Uneven weaving throughout the piece, clearly noticeable.
Not fully bleached.
Objectionable odor.
Overall uncleanness.

| Glossary No. of Fed. Std. No. 4 | Defects | Classification | |
|---|---|---|---|
| | | Major | Minor |
| | *General defects:* (Defect not restricted to a direction and defects applicable to both warp and filling) | | |
| 90, 91, 92 | Any hole, cut or tear, three or more yarns ruptured in adjoining points | X | |
| 78 | Any smash | X | |
| 79 | Any abrasion mark or chafe resulting in a thin or weak place, clearly noticeable[1] | X | |
| 74, 75, 76 | Any spot, stain, or streak clearly noticeable[1] more than ½ inch in combined length and width direction | | X |
| 11, 33 | Two or more contiguous yarns, broken or missing for 3 inches or more in length | X | |
| | Two or more contiguous yarns broken or missing for less than 3 inches in length | | X |
| 5, 27 | Any slub, slug or bunch, three or more times the thickness of the normal yarn diameter and 1½ inch or more in length | X | |
| | Any slub, slug or bunch, three or more times the thickness of the normal yarn diameter and more than ¾ inch but less than 1½ inch in length | | X |
| | Any slub, slug or bunch, thicker than the normal yarn diameter but less than three times the thickness and 1½ inch or more in length | | X |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

| Glossary No. of Fed. Std. No. 4 | Defects | Classification | |
|---|---|---|---|
| | | Major | Minor |
| 13, 34 | Multiple floats or skips ¾ inch or more in combined warp and filling directions | X | |
| | Multiple floats or skips less than ¾ inch in combined warp and filling directions | | X |
| | Single, more than 4 inches in length | | X |
| 15, 37 | Tight yarn causing waviness in adjoining area | | X |
| | *Warpwise defects:* (Defects restricted to the warpwise direction) | | |
| 35 | Hitchbacks, clearly noticeable[1], distorted area 2 inches or more in combined direction | | X |
| | *Fillingwise defects:* (Defects restricted to the fillingwise direction) | | |
| 2, 9 | Fine or heavy filling bar, light or heavy place, clearly noticeable[1] | X | |
| 4, 10 | Double pick or mispick, clearly noticeable[1] | | X |
| 3 | Jerked in filling more than 1/16 inch in thickness and 4 inches or more in length | X | |
| | Jerked in filling more than 1/16 inch in thickness and more than 2 inches but less than 4 inches in length | | X |
| 12 | Crack, opening at widest point 1/8 inch or more | X | |
| | Crack, opening at widest point less than 1/8 inch | | X |
| 22 | Finger mark or pressure mark, clearly noticeable[1], and extending over one inch | | X |
| | *Selvage defects:* (Defects restricted to the selvage) | | |
| 49, 50 | Tight or slack selvage, resulting in pronounced slackness or waviness in adjoining cloth | X | |
| 51 | Scalloped selvage, deepest indentation more than ½ inch | | X |
| 55, 56 | Cut, broken or torn selvage | X | |
| | *Finishing defects:* (Defects restricted to the finishing operations) | | |
| 57 | Finishing mark, clearly noticeable[1] | | X |
| 59, 61 | Crease or wrinkle, hard embedded | | X |
| 69, 70 | Dye stain or streak, clearly noticeable[1] | | X |

[1] Clearly noticeable at normal inspection distance—approximately three feet.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

TABLE II.—*Sample size*

| Lot size in yards | Sample size in pieces | Acceptable number |
|---|---|---|
| Up to 1,300[1] | 3 | 0 |
| 1,301 to 3,200 | 5 | 0 |
| 3,201 to 8,000 | 7 | 0 |
| 8,001 to 22,000 | 10 | 0 |
| 22,001 to 110,000 | 15 | 1 |
| 110,001 and over | 25 | 1 |

[1] If a lot contains fewer than three pieces, each piece in the lot shall be examined.

4.2.3 *Examination for length.*

4.2.3.1 *Individual pieces.* — The piece shall be examined for gross length. Any gross length found to be less than the minimum specified, or more than 2 yards below the gross length marked on the ticket, shall be considered a defect with respect to length. The unit of product for this examination shall be one piece. The number of pieces selected as the sample (sample size) for this examination and the acceptance number shall be as specified in table II.

4.2.3.2 *Total yardage in sample.* — The lot shall be unacceptable if the total of the actual gross lengths of the pieces in the sample is less than the total of the gross lengths marked on the tickets.

**4.3 Examination of preparation for delivery requirements.**—An examination will be made to determine that packaging, packing and marking requirements of Section 5 of this specification are complied with. Defects will be scored in accordance with the list below. The sample unit shall be one shipping container fully packed, selected just prior to the closing operation. Defects of closure listed below will be examined on shipping containers fully prepared for delivery. The lot size shall be the number of containers in the inspection lot. The inspection level shall be L–4 and the AQL shall be 4.0 defects per hundred units.

| Examine | Defect |
|---|---|
| Marking (exterior and interior) | Omitted, incorrect, illegible, of improper size, location, sequence, or method of application. |
| Materials | Any component missing. |
| | Any component damaged, affecting serviceability. |
| Workmanship | Inadequate application of components, such as: Incomplete closure of case liners, container flaps, loose strapping, inadequate stapling. |
| | Bulging or distortion of containers. |
| Weight | Gross weight exceeds requirement. |

**4.4 Testing of the end item.**—The methods of testing specified in Federal Specification CCC–T–191, wherever applicable, and as listed in table III shall be followed. When the data in the "number of determinations per sample unit" and the "results reported as" columns are not specified in the table, they shall be as required by the referenced test method. The physical and chemical values specified in Section 3 apply to the average of the determinations made on a unit of product for test purposes as specified in the applicable test method. The unit of product shall be 3½ yards, full width, of the finished cloth. The lot shall be unacceptable if one or more units fail to meet any requirement specified. The sample size shall be as follows:

| *Lot size (yards)* | *Sample size* |
|---|---|
| 800 or less | 2 |
| 801 to 22,000 | 3 |
| 22,001 and over | 5 |

## 5. PREPARATION FOR DELIVERY

(Federal Standard No. 102 shall be referred to for definitions and application of the various levels of packaging and packing protection for Civil agency procurements.)

**5.1 Packaging.**—Packaging shall be level A, B, or C as specified (see 6.2 and 6.3).



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

5.1.1 *Levels A, B, and C.* — The cloth shall be flat folded and packaged in accordance with the applicable requirements for class 3 fabrics of Federal Specification PPP–P–51.

5.2 **Packing.**—Packing shall be level A, B, or C as specified (see 6.2 and 6.3).

5.2.1 *Levels A, B, and C.* — The cloth shall be packed in accordance with the applicable requirements of Federal Specification PPP–P–51.

5.3 **Marking.**—In addition to any special marking required by the contract or order, shipments shall be marked in accordance with the applicable requirements of Federal Specification PPP–P–51.

## 6. NOTES

6.1 **Intended use.**—The cloth, cotton, jean covered by this specification is intended for use in the manufacture of clothing and equipage items.

6.2 **Ordering data.**—Purchasers should exercise any desired options offered herein, and procurement documents should specify the following:

(*a*) Title, number and date of this specification.

(*b*) Width of cloth required (see 3.2.1).

TABLE III.—*Test methods*

| Characteristics | Requirement reference | Test method | Number of determinations | Results reported as |
|---|---|---|---|---|
| Fiber identification | 3.1.1 | 1200 | | |
| Weight | Table I | 5041 | | |
| Weave | Table I | Visual | 1 | Pass or fail |
| Yarns per inch: | | | | |
| Warp | Table I | 5050 | | |
| Filling | Table I | 5050 | | |
| Breaking strength: | | | | |
| Warp | Table I | 5100 | | |
| Filling | Table I | 5100 | | |
| Nonfibrous material[1] | 3.3 | 2611 | | |
| Shrinkage[2] | 3.4 | 5550 | | |

[1] The nonfibrous content shall be determined in accordance with method specified and shall be calculated from the following formula:

$$\text{Nonfibrous content, percent} = \frac{O-S}{O} \times 100$$

[2] The three specimens shall be selected from the cloth (unit of product) as follows: One specimen from each side of the cloth within three inches of selvage and one specimen from the center of the cloth. No two specimens shall contain the same filling yarns.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

(*c*) Selection of applicable levels of packaging and packing, (see 5.1, 5.2 and 6.3).

6.3 In the preparation of contracts or orders, it must be noted that various options, choices and alternatives, as indicated in Federal Specification PPP–P–51, may be exercised in the preparation for delivery of this commodity.

6.4 **Transportation description.** — Transportation descriptions and minimum weights applicable to this commodity are:

*Rail:*

Cotton piece goods in the original piece. Carload minimum weight, any quantity.

*Motor:*

Cotton piece goods, not otherwise indexed, in the original piece.

Motor volume minimum weight, any quantity.

6.5 **Level B.**—Level B packaging and packing should be used by ordering agencies only when shipment is known to be made to a holding supply depot or warehouse from which partial shipments will be made to ultimate consumers.

**Notice. — When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded, by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.**

**MILITARY INTERESTS:**
**Army—M Q**
**Navy—S MC**
**Air Force—WADC**



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.